



RUST SCAT®

WB ACRYLIC INTERIOR/EXTERIOR ENAMEL
GLOSS C80

Features

- Durable Multi-Purpose Waterborne Enamel
- Excellent Color and Gloss Retention
- Fast Dry
- Superior Leveling
- Suitable for use on USDA inspected facilities

General Description

Rust Scat® Gloss Acrylic Enamel is an interior-exterior finish, which is suitable for coating primed metal, wood or masonry surfaces. It is water thinned so it poses no fire hazard. The acrylic resin provides excellent color and gloss retention as well as tenacious adhesion properties.

Recommended For

A durable waterborne coating for use on wood, metal, masonry and drywall in commercial, institutional, industrial and residential applications. Not recommended for unprimed wood and metal, immersion service or high corrosion areas.

Limitations

- Rust Inhibitive when used with Rust Inhibitive Primer
- Apply at temperatures between 50 °F (10 °C) and 100 °F (37.7 °C)
- Not intended for immersion service.
- Not intended as a house paint on wood siding

Product Information

Colors — Standard:
White (1)

— Tint Bases:
Pastel Base (32), Tint Base (33), Deep Base (34), Accent Base (36)

Tint with Universal Colorants only

— Special Colors:
Contact your retailer.

Certifications & Qualifications:

Suitable for use on USDA inspected facilities
Eligible for LEED® v4 Credit
Qualifies for CHPS low emitting credit
(Collaborative for High Performance Schools)
CDPH v1 Emission Certified

| VOC REGION | COMPLIANT |
|------------|-----------|
| FEDERAL | YES |
| OTC | YES |
| OTCII | YES |
| CARB | YES |
| CARB07 | YES |
| UTAH | YES |
| AZMC | YES |
| SCAQMD | NO |

Technical Assistance:

Available through your local authorized independent retailer.
For the location of the retailer nearest you, call 1-866-708-9180 or visit www.coronadopaint.com

| Technical Data | White | | | | |
|--|--|-------------|----------------|-------------|----------------|
| Vehicle Type | Acrylic | | | | |
| Pigment Type | Titanium Dioxide | | | | |
| Volume Solids | 39 ± 1.0% | | | | |
| Coverage per Gallon at Recommended Film Thickness | 350 – 450 Sq. Ft. | | | | |
| Recommended Film Thickness | <table border="0"> <tr> <td>– Wet</td> <td>3.6 - 4.6 mils</td> </tr> <tr> <td>– Dry</td> <td>1.4 - 1.7 mils</td> </tr> </table> | – Wet | 3.6 - 4.6 mils | – Dry | 1.4 - 1.7 mils |
| – Wet | 3.6 - 4.6 mils | | | | |
| – Dry | 1.4 - 1.7 mils | | | | |
| Depending on surface texture and porosity. Be sure to estimate the right amount of paint for the job. This will ensure color uniformity and minimize the disposal of excess paint. | | | | | |
| Dry Time @ 77 °F (25 °C) @ 50% RH | <table border="0"> <tr> <td>– Tack Free</td> <td>30 Minutes</td> </tr> <tr> <td>– To Recoat</td> <td>2 Hours</td> </tr> </table> | – Tack Free | 30 Minutes | – To Recoat | 2 Hours |
| – Tack Free | 30 Minutes | | | | |
| – To Recoat | 2 Hours | | | | |
| High humidity and cool temperatures will result in longer dry, recoat and service times. | | | | | |
| Dries By | Coalescence | | | | |
| Viscosity | 92 – 97 KU | | | | |
| Flash Point | 200 °F or greater (TT-P-141, Method 4293) | | | | |
| Gloss / Sheen | Gloss (70 – 80 @ 60°) | | | | |
| Surface Temperature at Application | <table border="0"> <tr> <td>– Min.</td> <td>50 °F</td> </tr> <tr> <td>– Max.</td> <td>100 °F</td> </tr> </table> | – Min. | 50 °F | – Max. | 100 °F |
| – Min. | 50 °F | | | | |
| – Max. | 100 °F | | | | |
| Thin With | Clean Water | | | | |
| Clean Up Thinner | Warm Soapy Water | | | | |
| Weight Per Gallon | 10.3 lbs | | | | |
| Storage Temperature | <table border="0"> <tr> <td>– Min.</td> <td>45 °F</td> </tr> <tr> <td>– Max.</td> <td>95 °F</td> </tr> </table> | – Min. | 45 °F | – Max. | 95 °F |
| – Min. | 45 °F | | | | |
| – Max. | 95 °F | | | | |

Volatile Organic Compounds (VOC)

96 Grams/Liter 0.80 Lbs./Gallon

Rust Scat® WB Acrylic Interior/Exterior Enamel Gloss C80

Surface Preparation

Surfaces to be painted must be clean, dry, and free of dirt, dust, grease, oil, soap, wax, scaling paint, water soluble materials and mildew. Remove any peeling or scaling paint, and sand these areas to feather edges smooth with adjacent surfaces. Glossy areas should be dulled. Drywall surfaces must be free of sanding dust. Spot prime before and after filling nail holes, cracks, and other surface imperfections.

New plaster or masonry surfaces must be allowed to cure (30 days) before applying base coat. Cured plaster should be hard, have a slight sheen and maximum pH of 10; soft, porous or powdery plaster indicates improper cure. Knife off any protrusions and prime plaster before and after applying patching compound. Poured or pre-cast concrete with a very smooth surface should be etched or abraded to promote adhesion, after removing all form release agents and curing compounds. Remove any powder or loose particles.

Difficult Substrates: Insl-x® offers a variety of specialty primers for use over difficult substrates such as plaster, bleeding woods, grease stains, crayon markings, hard glossy surfaces, galvanized metal or other substrates where paint adhesion or stain suppression is a particular problem. Your dealer can recommend the right problem-solving primer for your special needs.

WARNING! If you scrape, sand, or remove old paint, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Informational Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead

Primer System

New surfaces should be fully primed, and previously painted surfaces may be primed or spot primed as necessary.

Wood and Engineered Wood Products:

Primer: All-Purpose Interior Alkyd Primer (Insl-x® Prime Lock™ Plus) or All-Purpose Interior Acrylic Primer (Super Kote 5000® 40-11)

Finish: 1 or 2 coats of Rust Scat® WB Acrylic Enamel Gloss (C80)

Bleeding Type Woods, (Redwood and Cedar):

Primer: All-Purpose Interior Alkyd Primer (Insl-x® Prime Lock™ Plus)

Finish: 1 or 2 coats of Rust Scat® WB Acrylic Enamel Gloss (C80)

Drywall:

Primer: All-Purpose Interior Acrylic Primer (Super Kote 5000® 40-11)

Finish: 1 or 2 coats of Rust Scat® WB Acrylic Enamel Gloss (C80)

Plaster:

Primer: All-Purpose Interior Acrylic Primer (Super Kote 5000® 40-11)

Finish: 1 or 2 coats of Rust Scat® WB Acrylic Enamel Gloss (C80)

Masonry; Rough or Pitted Masonry:

Primer: Masonry Latex Block Filler (Super Kote 5000® 958)

Finish: 1 or 2 coats of Rust Scat® WB Acrylic Enamel Gloss (C80)

Masonry; Smooth Poured or Pre-cast Concrete:

Primer: All-Purpose Interior Acrylic Primer (Super Kote 5000® 40-11)

Finish: 1 or 2 coats of Rust Scat® WB Acrylic Enamel Gloss (C80)

Ferrous Metal (Steel & Iron):

Primer: Acrylic Metal Primer (Rust Scat® 36 Primer) or Alkyd Metal Primer (Rust Scat® 35 Primer)

Finish: 1 or 2 coats of Rust Scat® WB Acrylic Enamel Gloss (C80)

Hard glossy alkyd surfaces: Abrasion by sanding provides to optimum adhesion.

Non-Ferrous Metal (Galvanized & Aluminum): All new metal surfaces must be thoroughly cleaned with an Oil & Grease Emulsifier to remove contaminants. New shiny non-ferrous metal surfaces that will be subject to abrasion should be dulled with very fine sandpaper or a synthetic steel wool pad to promote adhesion.

Primer: Acrylic Metal Primer (Rust Scat® 36 Primer)

Finish: 1 or 2 coats of Rust Scat® WB Acrylic Enamel Gloss (C80)

Repaint, All Substrates: Prime bare areas with the primer recommended for the substrate above.

Application

Stir thoroughly. Make sure that no pigment remains on the bottom of the can and that the entire contents are fluid and free of lumps. Apply by brush, roller or spray. You may thin product with water sparingly to achieve the desired consistency. Apply at temperatures between 50 °F and 100 °F (10 °C – 37.7 °C).

Do not apply if temperature is within 5° of dew point or if rain is expected within 12 hours.

Clean Up

Clean up with warm, soapy water followed by a clean water rinse.

USE COMPLETELY OR DISPOSE OF PROPERLY. Dry empty containers may be recycled in a can recycling program. **Local disposal requirements vary; consult your sanitation department or state-designated environmental agency on disposal options.**

Environmental Health & Safety Information

WARNING!

Possible birth defect hazard. Contains, Trimethylolpropane, which may cause birth defects based on animal data.

Use only with adequate ventilation. Do not breathe vapors, spray mist or sanding dust. Ensure fresh air entry during application and drying. Avoid contact with eyes and prolonged or repeated contact with skin. Avoid exposure to dust and spray mist by wearing a NIOSH approved respirator during application, sanding and clean up. Follow respirator manufacturer's directions for respirator use. Close container after each use. Wash thoroughly after handling.



WARNING: Cancer and Reproductive Harm—
www.P65warnings.ca.gov

FIRST AID: In case of eye contact, flush immediately with plenty of water for at least 15 minutes; for skin, wash thoroughly with soap and water. If symptoms persist, seek medical attention. If you experience difficulty breathing, leave the area to obtain fresh air. If continued difficulty is experienced, get medical attention immediately.

IN CASE OF SPILL – Absorb with inert material and dispose of as specified under “Clean Up”.

**KEEP OUT OF REACH OF CHILDREN
PROTECT FROM FREEZING**

**Refer to Safety Data Sheet for
additional health and safety information.**