



SUPER KOTE® 1000

LATEX FLAT 88 LINE

Features

- Latex Flat Paint
- Water Clean Up
- Fast Dry
- Resists Spattering

General Description

This Latex Flat Coating is designed to provide good dry hide and an excellent flat finish when applied to properly prepared surfaces. It is easy to apply and exhibits good touchup properties.

Recommended For

Flat finish for properly prepared interior walls. Has good dry hide and good touch up. It is ideal for rental properties.

Limitations

- Apply when surface temperature is above 50 °F (10 °C).
- Not for use in high-abuse areas that are frequently washed or scrubbed

Product Information

Colors — Standard: White (1)	Technical Data \diamond White						
— Tint Bases: N/A	Vehicle Type Latex						
— Special Colors: Contact your dealer.	Pigment Type Titanium Dioxide						
Certifications & Qualifications: VOC compliant in all regulated areas The products supported by this data sheet contain a maximum of 50 grams per liter VOC/VOS (0.42 lbs. /gal.) excluding water & exempt solvents.	Volume Solids 30 \pm 1.0%						
	Coverage per Gallon at Recommended Film Thickness 300 – 400 Sq. Ft.						
Technical Assistance: Available through your local authorized independent dealer. For the location of the dealer nearest you, call 1-866-708-9180, or visit www.coronadopaint.com	<table border="0" style="width: 100%;"> <tr> <td style="width: 60%;">Recommended Film Thickness</td> <td style="width: 20%; text-align: center;">– Wet</td> <td style="width: 20%; text-align: right;">3 – 4 mils</td> </tr> <tr> <td></td> <td style="text-align: center;">– Dry</td> <td style="text-align: right;">0.9 – 1.2 mils</td> </tr> </table>	Recommended Film Thickness	– Wet	3 – 4 mils		– Dry	0.9 – 1.2 mils
	Recommended Film Thickness	– Wet	3 – 4 mils				
		– Dry	0.9 – 1.2 mils				
	Depending on surface texture and porosity. Be sure to estimate the right amount of paint for the job. This will ensure color uniformity and minimize the disposal of excess paint.						
	<table border="0" style="width: 100%;"> <tr> <td style="width: 60%;">Dry Time @ 77 °F (25 °C) @ 50% RH</td> <td style="width: 20%; text-align: center;">– Tack Free</td> <td style="width: 20%; text-align: right;">30 Minutes</td> </tr> <tr> <td></td> <td style="text-align: center;">– To Recoat</td> <td style="text-align: right;">4 Hours</td> </tr> </table>	Dry Time @ 77 °F (25 °C) @ 50% RH	– Tack Free	30 Minutes		– To Recoat	4 Hours
	Dry Time @ 77 °F (25 °C) @ 50% RH	– Tack Free	30 Minutes				
		– To Recoat	4 Hours				
	High humidity and cool temperatures will result in longer dry, recoat and service times.						
	Dries By Coalescence						
	Viscosity 110 – 115 KU						
Flash Point N/A							
Gloss / Sheen Flat (1.5 – 2.5 @ 85°)							
<table border="0" style="width: 100%;"> <tr> <td style="width: 60%;">Surface Temperature at Application</td> <td style="width: 20%; text-align: center;">– Min.</td> <td style="width: 20%; text-align: right;">50 °F</td> </tr> <tr> <td></td> <td style="text-align: center;">– Max.</td> <td style="text-align: right;">90 °F</td> </tr> </table>	Surface Temperature at Application	– Min.	50 °F		– Max.	90 °F	
Surface Temperature at Application	– Min.	50 °F					
	– Max.	90 °F					
Thin With Clean Water							
Clean Up Thinner Warm Soapy Water							
Weight Per Gallon 11.1 lbs.							
<table border="0" style="width: 100%;"> <tr> <td style="width: 60%;">Storage Temperature</td> <td style="width: 20%; text-align: center;">– Min.</td> <td style="width: 20%; text-align: right;">40 °F</td> </tr> <tr> <td></td> <td style="text-align: center;">– Max.</td> <td style="text-align: right;">90 °F</td> </tr> </table>	Storage Temperature	– Min.	40 °F		– Max.	90 °F	
Storage Temperature	– Min.	40 °F					
	– Max.	90 °F					
Volatile Organic Compounds (VOC) 31.2 Grams/Liter 0.26 Lbs./Gallon							

\diamond Reported values are for White.

Surface Preparation

Surfaces to be painted must be clean, dry, and free of dirt, dust, grease, oil, soap, wax, peeling or flaking paint, water soluble materials and mildew. Remove any peeling or flaking paint, and sand these areas to feather edges smooth with adjacent surfaces. Glossy areas should be dulled. Drywall surfaces must be free of sanding dust. Spot prime before and after filling nail holes, cracks, and other surface imperfections.

New plaster or masonry surfaces must be allowed to cure (30 days) before applying base coat. Cured plaster should be hard, have a slight sheen and maximum pH of 10; soft, porous or powdery plaster indicates improper cure.

Primers: New surfaces should be fully primed. Previously painted surfaces should be primed or spot primed as necessary. There are a number of specialty primers available in our family of brands that can be used on difficult substrates such as bleeding woods, hard glossy surfaces, or other substrates where paint adhesion or stain blocking is a problem. Your dealer can recommend the right problem solving primer necessary to meet your needs.

WARNING! If you scrape, sand, or remove old paint, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead.

Application

Stir product with a circular, lifting motion before you begin to paint. Super Kote® 1000 Latex Flat may be applied by brush, roller or spray techniques, at a rate of application not to exceed 400 square feet per gallon. Surface texture and porosity will affect actual yield. For best brush application results, use a quality synthetic filament brush. For roller application use a ¼" or 3/8" nap cover for smooth surfaces, a ½" nap cover for semi-rough surfaces, and a ¾" nap cover for rough surfaces. May be reduced with clean water up to 15% for spray application.

Airless Spray

Tip size and atomization pressures will vary with type of equipment, viscosity and temperature. A tip size of .017 to .021 will provide the most satisfactory spray pattern.

Clean Up

Clean up with warm, soapy water.

USE COMPLETELY OR DISPOSE OF PROPERLY. Dry empty containers may be recycled in a can recycling program. **Local disposal requirements vary; consult your sanitation department or state-designated environmental agency on disposal options.**

Environmental Health & Safety Information

Use only with adequate ventilation. Do not breathe spray mist or sanding dust. Ensure fresh air entry during application and drying. Avoid contact with eyes and prolonged or repeated contact with skin. Avoid exposure to dust and spray mist by wearing a NIOSH approved respirator during application, sanding and clean up. Follow respirator manufacturer's directions for respirator use. Close container after each use. Wash thoroughly after handling.



WARNING Cancer and Reproductive Harm—
www.P65warnings.ca.gov

FIRST AID: In case of eye contact, flush immediately with plenty of water for at least 15 minutes; for skin, wash thoroughly with soap and water. If symptoms persist, seek medical attention. If you experience difficulty breathing, leave the area to obtain fresh air. If continued difficulty is experienced, get medical attention immediately.

IN CASE OF SPILL – Absorb with inert material and dispose of as specified under "Clean Up".

**KEEP OUT OF REACH OF CHILDREN
PROTECT FROM FREEZING**

**Refer to Safety Data Sheet for
additional health and safety information.**