



SUPER KOTE® 1000

LATEX PRIMER 88-11

Features

- Latex Flat Primer
- Water Clean Up
- Fast Dry
- Resists Spattering

General Description

An economical and fast drying latex primer - sealer for interior dry wall and cured plaster. Is easy to apply and quick drying.

Recommended For

Flat finish for properly prepared interior walls. It is ideal for rental properties.

Limitations

- Apply when surface temperature is above 50 °F (10 °C).
- Not for use in high-abuse areas that are frequently washed or scrubbed.

Product Information

Colors — Standard: White (11)	Technical Data White																										
— Tint Bases: N/A	<table border="1"> <tr> <td>Vehicle Type</td> <td>Vinyl Acrylic</td> </tr> <tr> <td>Pigment Type</td> <td>Titanium Dioxide</td> </tr> <tr> <td>Volume Solids</td> <td>29.4 ± 1.0%</td> </tr> <tr> <td>Coverage per Gallon at Recommended Film Thickness</td> <td>300 – 400 Sq. Ft.</td> </tr> <tr> <td>Recommended Film Thickness</td> <td> <table border="1"> <tr> <td>– Wet</td> <td>3.0 to 4.0 mils</td> </tr> <tr> <td>– Dry</td> <td>0.9 to 1.2 mils</td> </tr> </table> </td> </tr> </table>	Vehicle Type	Vinyl Acrylic	Pigment Type	Titanium Dioxide	Volume Solids	29.4 ± 1.0%	Coverage per Gallon at Recommended Film Thickness	300 – 400 Sq. Ft.	Recommended Film Thickness	<table border="1"> <tr> <td>– Wet</td> <td>3.0 to 4.0 mils</td> </tr> <tr> <td>– Dry</td> <td>0.9 to 1.2 mils</td> </tr> </table>	– Wet	3.0 to 4.0 mils	– Dry	0.9 to 1.2 mils												
Vehicle Type	Vinyl Acrylic																										
Pigment Type	Titanium Dioxide																										
Volume Solids	29.4 ± 1.0%																										
Coverage per Gallon at Recommended Film Thickness	300 – 400 Sq. Ft.																										
Recommended Film Thickness	<table border="1"> <tr> <td>– Wet</td> <td>3.0 to 4.0 mils</td> </tr> <tr> <td>– Dry</td> <td>0.9 to 1.2 mils</td> </tr> </table>	– Wet	3.0 to 4.0 mils	– Dry	0.9 to 1.2 mils																						
– Wet	3.0 to 4.0 mils																										
– Dry	0.9 to 1.2 mils																										
— Special Colors: Contact your dealer.	Depending on surface texture and porosity. Be sure to estimate the right amount of paint for the job. This will ensure color uniformity and minimize the disposal of excess paint.																										
Certifications & Qualifications: VOC compliant in all regulated areas The products supported by this data sheet contain a maximum of 50 grams per liter VOC/VOS (0.42 lbs. /gal.) excluding water and exempt solvents. This product meets the qualifications for LEED (Leadership in Energy and Environmental Design) projects as a flat coating.	<table border="1"> <tr> <td>Dry Time @ 77 °F (25 °C) @ 50% RH</td> <td> <table border="1"> <tr> <td>– Tack Free</td> <td>30 Minutes</td> </tr> <tr> <td>– To Recoat</td> <td>4 Hours</td> </tr> </table> </td> </tr> </table>	Dry Time @ 77 °F (25 °C) @ 50% RH	<table border="1"> <tr> <td>– Tack Free</td> <td>30 Minutes</td> </tr> <tr> <td>– To Recoat</td> <td>4 Hours</td> </tr> </table>	– Tack Free	30 Minutes	– To Recoat	4 Hours																				
Dry Time @ 77 °F (25 °C) @ 50% RH	<table border="1"> <tr> <td>– Tack Free</td> <td>30 Minutes</td> </tr> <tr> <td>– To Recoat</td> <td>4 Hours</td> </tr> </table>	– Tack Free	30 Minutes	– To Recoat	4 Hours																						
– Tack Free	30 Minutes																										
– To Recoat	4 Hours																										
Technical Assistance: Available through your local authorized independent dealer. For the location of the dealer nearest you, call 1-866-708-9180, or visit www.coronadopaint.com	High humidity and cool temperatures will result in longer dry, recoat and service times. <table border="1"> <tr> <td>Dries By</td> <td>Coalescence</td> </tr> <tr> <td>Viscosity</td> <td>110 – 115 KU</td> </tr> <tr> <td>Flash Point</td> <td>N/A</td> </tr> <tr> <td>Gloss / Sheen</td> <td>Flat (0 – 2.5 @ 85°)</td> </tr> <tr> <td>Surface Temperature at Application</td> <td> <table border="1"> <tr> <td>– Min.</td> <td>50 °F</td> </tr> <tr> <td>– Max.</td> <td>90 °F</td> </tr> </table> </td> </tr> <tr> <td>Thin With</td> <td>Clean Water</td> </tr> <tr> <td>Clean Up Thinner</td> <td>Warm Soapy Water</td> </tr> <tr> <td>Weight Per Gallon</td> <td>11.03 lbs.</td> </tr> <tr> <td>Storage Temperature</td> <td> <table border="1"> <tr> <td>– Min.</td> <td>45 °F</td> </tr> <tr> <td>– Max.</td> <td>95 °F</td> </tr> </table> </td> </tr> </table> <p style="text-align: center;">Volatile Organic Compounds (VOC)</p> <p style="text-align: center;">43.5 Grams/Liter 0.36 Lbs./Gallon</p>	Dries By	Coalescence	Viscosity	110 – 115 KU	Flash Point	N/A	Gloss / Sheen	Flat (0 – 2.5 @ 85°)	Surface Temperature at Application	<table border="1"> <tr> <td>– Min.</td> <td>50 °F</td> </tr> <tr> <td>– Max.</td> <td>90 °F</td> </tr> </table>	– Min.	50 °F	– Max.	90 °F	Thin With	Clean Water	Clean Up Thinner	Warm Soapy Water	Weight Per Gallon	11.03 lbs.	Storage Temperature	<table border="1"> <tr> <td>– Min.</td> <td>45 °F</td> </tr> <tr> <td>– Max.</td> <td>95 °F</td> </tr> </table>	– Min.	45 °F	– Max.	95 °F
Dries By	Coalescence																										
Viscosity	110 – 115 KU																										
Flash Point	N/A																										
Gloss / Sheen	Flat (0 – 2.5 @ 85°)																										
Surface Temperature at Application	<table border="1"> <tr> <td>– Min.</td> <td>50 °F</td> </tr> <tr> <td>– Max.</td> <td>90 °F</td> </tr> </table>	– Min.	50 °F	– Max.	90 °F																						
– Min.	50 °F																										
– Max.	90 °F																										
Thin With	Clean Water																										
Clean Up Thinner	Warm Soapy Water																										
Weight Per Gallon	11.03 lbs.																										
Storage Temperature	<table border="1"> <tr> <td>– Min.</td> <td>45 °F</td> </tr> <tr> <td>– Max.</td> <td>95 °F</td> </tr> </table>	– Min.	45 °F	– Max.	95 °F																						
– Min.	45 °F																										
– Max.	95 °F																										

◇ Reported values are for White. Contact dealer for values of other bases or colors.

Surface Preparation

Previously Painted Surfaces: Surfaces to be painted must be clean, dry, and free of dirt, dust, grease, oil, soap, wax, peeling or flaking paint, water soluble materials and mildew. Remove any peeling or flaking paint, and sand these areas to feather edges smooth with adjacent surfaces. Spot Prime before and after filling nail holes, cracks, and other surface imperfections. Glossy areas should be dulled. Drywall surfaces must be free of sanding dust.

New plaster or masonry surfaces must be allowed to cure (30 days) before applying base coat. Cured plaster should be hard, have a slight sheen and maximum pH of 10; soft, porous or powdery plaster indicates improper cure.

Primers: New surfaces should be fully primed. Previously painted surfaces should be primed or spot primed as necessary. There are a number of specialty primers available in our family of brands that can be used on difficult substrates such as bleeding woods, hard glossy surfaces, or other substrates where paint adhesion or stain blocking is a problem. Your dealer can recommend the right problem solving primer necessary to meet your needs.

WARNING! If you scrape, sand, or remove old paint, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead.

Application

Stir product with a circular, lifting motion before you begin to paint. Super Kote® 1000 Latex Primer may be applied by brush, roller, pad or spray techniques, at a rate of application not to exceed 400 square feet per gallon. Surface texture and porosity will affect actual yield. For best brush application results, use a quality synthetic filament brush. For roller application use a 1/4" or 3/8" nap cover for smooth surfaces, a 1/2" nap cover for semi-rough surfaces, and a 3/4" nap cover for rough surfaces. May be reduced with clean water up to 15% for spray application.

Airless Spray

Tip size and atomization pressures will vary with type of equipment, viscosity and temperature. A tip size of .017 to .021 will provide the most satisfactory spray pattern.

Clean Up

Clean up with warm, soapy water.

USE COMPLETELY OR DISPOSE OF PROPERLY. Dry, empty containers may be recycled in a can recycling program. **Local disposal requirements vary; consult your sanitation department or state-designated environmental agency on disposal options.**

Environmental Health & Safety Information

Use only with adequate ventilation. Do not breathe spray mist or sanding dust. Ensure fresh air entry during application and drying. Avoid contact with eyes and prolonged or repeated contact with skin. Avoid exposure to dust and spray mist by wearing a NIOSH approved respirator during application, sanding and clean up. Follow respirator manufacturer's directions for respirator use. Close container after each use. Wash thoroughly after handling



WARNING Cancer and Reproductive Harm—
www.P65warnings.ca.gov

FIRST AID: In case of eye contact, flush immediately with plenty of water for at least 15 minutes; for skin, wash thoroughly with soap and water. If symptoms persist, seek medical attention. If you experience difficulty breathing, leave the area to obtain fresh air. If continued difficulty is experienced, get medical attention immediately.

IN CASE OF SPILL – Absorb with inert material and dispose of as specified under "Clean Up".

**KEEP OUT OF REACH OF CHILDREN
PROTECT FROM FREEZING**

**Refer to Safety Data Sheet for
additional health and safety information.**