



EXTERIOR STAIN ACRYLIC SOLID STAIN N089

Features

- Beautiful rustic matte finish
- Suitable for use on properly cured stucco, masonry, manufactured and fiber-cement siding
- Specially formulated to resist mildew growth on the coating
- Offers excellent color retention and fast dry

General Description

A premium product which masks the grain of the wood without obscuring its texture. This durable finish protects and enhances the appearance of new or previously stained smooth or rough siding, manufactured hardboard and fiber-cement siding, shakes, trim, railings, fencing, stucco and masonry.

Recommended For

Residential or commercial applications where a premium quality finish is desired. Use on new or previously stained smooth or rough siding, manufactured hardboard and fiber-cement siding, shakes, trim, railings, fencing, stucco and masonry.

Limitations

- Do not apply when air and surface temperatures are below 40°F (4.4°C).
- Do not apply to surfaces such as outdoor furniture or decks
- Do not paint vinyl siding darker than the original color

Product Information

Colors: —Standard:

White (01)

—Tint Bases:

Benjamin Moore® Color Preview® bases 1B, 2B, 3B, & 4B

—Special Colors:

Contact your Benjamin Moore representative

Certification:

VOC compliant in all regulated areas.

Master Painters Institute MPI #16

Technical Assistance

Available through your local authorized Benjamin Moore® retailer. For the location of the retailer nearest you, call 1-800-826-2623, see www.benjaminmoore.com, or consult your local Yellow Pages

Technical Data[◇]

Vehicle Type	100% Acrylic Latex
Pigment Type	Titanium Dioxide
Volume Solids	32%

Coverage per Gallon at Recommended Film Thickness	200 – 400 Sq. Ft.
Recommended Film Thickness	– Wet 5.3 mils – Dry 1.7 mils

Depending on surface texture and porosity. Be sure to estimate the right amount of paint for the job. This will ensure color uniformity and minimize the disposal of excess paint.

Dry Time @ 77°F	– To Touch	1 Hour
(25°C) @ 50% RH	– To Recoat	3 – 4 Hours

High humidity and cool temperatures will result in longer dry, recoat and service times.

Dries By	Evaporation, Coalescence
----------	--------------------------

Viscosity	108 ± 2 KU
-----------	------------

Flash Point	None
-------------	------

Gloss / Sheen	Flat (1-5 @ 85°)
---------------	------------------

Surface Temperature at Application	– Min. 40°F – Max. 90°F
------------------------------------	----------------------------

Thin With	See Chart
-----------	-----------

Clean Up Thinner	Clean Water
------------------	-------------

Weight Per Gallon	11.43 lbs
-------------------	-----------

Storage Temperature	– Min. 40°F – Max. 90°F
---------------------	----------------------------

Volatile Organic Compounds (VOC)

72.2 Grams/Liter .61 lbs./Gallon

[◇] Reported values are for Pastel Base. Contact Benjamin Moore for values of other bases or colors..

Surface Preparation

Surfaces to be stained must be clean, dry and free of dirt, mildew, oil or grease. Remove contaminants or chalky residue from weathered painted surfaces by washing with Benjamin Moore® Clean Multi-Purpose Cleaner (318). Excessive chalk must be removed by power wash equipment. **Note:** Smooth planed clapboards or siding must be sanded thoroughly or treated with Benjamin Moore® Brighten Brightener & Neutralizer (317) to break the “mill glaze” to allow proper penetration and adhesion.

Mildew: Stains from mildew must be removed by cleaning with Benjamin Moore® Clean (318) prior to coating the surface.

Painted Surfaces: Remove old scaling or peeling coatings by scraping, wire brushing and sanding. Glossy surfaces must be dulled by sanding. Un-weathered areas such as eaves, ceilings, or overhangs must be washed with a detergent solution and/or rinsed with a strong stream from a garden hose to remove surface salts that can interfere with proper adhesion.

Caution: Refer to the 317 and 318 technical data and material safety data sheets for instructions on their proper use and handling.

WARNING! If you scrape, sand or remove old paint, you may release lead dust. **LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE.** Wear a NIOSH-approved respirator to control lead exposure. Carefully clean up with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead.

Primer/Finish Systems

Previously Stained, Painted, or Sealed Wood:

Primer: No priming necessary.

Finish: 1 or 2 coats Benjamin Moore® Acrylic Solid Siding Stain.

New Wood or Properly Prepared Weathered Wood:

Primer: Priming usually unnecessary. If light shades are applied to wood with high tannin levels, such as redwood and cedar, 1 coat of Benjamin Moore® Premium Exterior Stain Alkyd Primer (366) should be used before top coating to prevent bleeding. If unsure, test a small area prior to staining.

Finish: 2 coats Benjamin Moore® Acrylic Solid Siding Stain.

Stucco and Masonry:

Primer: No priming necessary if the surface is in good condition. Loose, sandy masonry should be hosed down thoroughly to remove surface particles, allowed to dry and primed with Super Spec® Masonry Interior / Exterior 100% Acrylic Masonry Sealer (N/066). New masonry must be cured unless primed with Super Spec® Masonry Interior / Exterior 100% Acrylic Masonry Sealer (N/066).

Finish: 1 or 2 coats Benjamin Moore® Acrylic Solid Siding Stain

Repaint, All Substrates: Prime bare areas with the primer recommended for the substrate above.

Application

Mixing of paint: Immediately prior to use, the paint should be mixed thoroughly even though it has been shaken mechanically by the retailer. Preferred application method is by brushing. Roller application should be done only on rough or textured surfaces. To minimize lapping, always maintain a wet edge. On horizontal siding apply the stain on a section of 2 or 3 boards completely across the house. Lower the ladder and continue in the same manner until the side is completed. Vertical siding is coated using the same principle from top to bottom. Never stop staining in mid-wall; continue until a natural break is reached, such as a window. Refrain from staining in direct hot sun. Do not apply when air and surface temperatures are below 40°F (4.4°C), nor over damp surfaces or during threatening weather.

This product can also be sprayed. The Chart below is for general application guidance.

Thinning/Cleaning

Conditioning with Benjamin Moore® 518 Extender may be necessary under certain conditions to adjust open time or spray characteristics. The chart below is for general guidance		
	Mild conditions	Severe conditions
	Humid (RH> 50%) with no direct sunlight & with little to no wind	Dry (RH<50%), in direct sunlight, or windy conditions
Brush: Nylon / Polyester	No thinning necessary	Add 518 Extender or water: Max of 8 fl. oz. to a gallon of paint Never add other paints or solvents.
Roller: Aura® Roller Cover		
Spray: Airless Pressure: 1,500 -25,00 psi Tip: 0.013-0.017		

Cleanup: Wash painting tools in warm soapy water immediately after use. Spray equipment should be given a final rinse with mineral spirits to prevent rusting.

USE COMPLETELY OR DISPOSE OF PROPERLY. Dry, empty containers may be recycled in a can recycling program. **Local disposal requirements vary; consult your sanitation department or state-designated environmental agency on disposal options.**

Environmental, Health & Safety Information

Use only with adequate ventilation. Do not breathe spray mist or sanding dust. Ensure fresh air entry during application and drying. Avoid contact with eyes and prolonged or repeated contact with skin. Avoid exposure to dust and spray mist by wearing a NIOSH approved respirator during application, sanding and clean up. Follow respirator manufacturer’s directions for respirator use. Close container after each use. Wash thoroughly after handling.

WARNING: This product contains a chemical known to the state of California to cause cancer and birth defects, or other reproductive harm.

FIRST AID: In case of eye contact, flush immediately with plenty of water for at least 15 minutes; for skin, wash thoroughly with soap and water. If symptoms persist, seek medical attention. If you experience difficulty breathing, leave the area to obtain fresh air. If continued difficulty is experienced, get medical attention immediately.

IN CASE OF SPILL – Absorb with inert material and dispose of as specified under **Thinning/Cleanup**.

**KEEP OUT OF REACH OF CHILDREN
PROTECT FROM FREEZING**

Refer to Material Safety Data Sheet for additional health and safety information.