



LATEX FLOOR & PATIO LOW SHEEN ENAMEL N122

Features

- Resistant to soaps and detergents, grease and oil
- Exhibits a smooth, uniform appearance
- One coat covers most previously painted surfaces that are in fair to good condition
- Easy to apply

Recommended For

Residential or commercial applications where a premium quality finish is desired. For interior and exterior use on unpainted concrete (new or old) and previously finished wood or concrete floors. Particularly recommended for basements, porches, patios, breezeways, showrooms, and light industrial applications.

General Description

A premium quality, quick-drying, epoxy-modified acrylic low sheen latex floor enamel. One coat covers most previously painted surfaces that are in fair to good condition.

Limitations

- Many tires contain compounds which may attack latex paints, resulting in loss of adhesion and film pickup.

CAUTION: All floor coatings may become slippery when wet. Where non-skid characteristics are desired, use an appropriate anti-slip aggregate.

Product Information

Colors — Standard:	Technical Data [◇]	Pastel Base				
White (01), Country Redwood (23), Green (40), Rich Brown (60), Light Gray (70), Deck Gray (71) & Platinum Gray (74)	Vehicle Type	Epoxy Modified Acrylic Latex				
— Tint Bases: Benjamin Moore [®] Gennex [®] Bases 1X, 2X, 3X, & 4X	Pigment Type	Titanium Dioxide				
— Special Colors: Contact your Benjamin Moore representative.	Volume Solids	35%				
Certifications & Qualifications: VOC compliant in all regulated areas Qualifies for LEED [®] v4 Credit Qualifies for CHPS low emitting credit (Collaborative for High Performance Schools) CDPH v1 Emission Certified	Coverage per Gallon at Recommended Film Thickness	500 – 600 Sq. Ft. (46.4 – 55.7 sq. m)				
Technical Assistance Available through your local authorized independent Benjamin Moore retailer. For the location of the retailer nearest you, call 1-866-708-9180 or visit www.benjaminmoore.com	Recommended Film Thickness	<table border="1"> <tr> <td>– Wet</td> <td>2.9 mils</td> </tr> <tr> <td>– Dry</td> <td>1.0 mils</td> </tr> </table>	– Wet	2.9 mils	– Dry	1.0 mils
– Wet	2.9 mils					
– Dry	1.0 mils					
	Depending on surface texture and porosity. Be sure to estimate the right amount of paint for the job. This will ensure color uniformity and minimize the disposal of excess paint.					
	Dry Time @ 77 °F (25 °C) @ 50% RH	<table border="1"> <tr> <td>– To Touch</td> <td>1 Hour</td> </tr> <tr> <td>– To Recoat</td> <td>4 Hours</td> </tr> </table>	– To Touch	1 Hour	– To Recoat	4 Hours
– To Touch	1 Hour					
– To Recoat	4 Hours					
	High humidity and cool temperatures will result in longer dry, recoat and service times. Withstands light traffic after overnight dry.					
	Dries By	Evaporation, Coalescence				
	Viscosity	78 ± 2 KU				
	Flash Point	None				
	Gloss / Sheen	Satin (10 - 25 @ 60°)				
	Surface Temperature at Application	<table border="1"> <tr> <td>– Min.</td> <td>50 °F (10 °C)</td> </tr> <tr> <td>– Max.</td> <td>90 °F (32 °C)</td> </tr> </table>	– Min.	50 °F (10 °C)	– Max.	90 °F (32 °C)
– Min.	50 °F (10 °C)					
– Max.	90 °F (32 °C)					
	Thin With	See Chart				
	Clean Up Thinner	Clean Water				
	Weight Per Gallon	11.0 lbs				
	Storage Temperature	<table border="1"> <tr> <td>– Min.</td> <td>40 °F (4 °C)</td> </tr> <tr> <td>– Max.</td> <td>90 °F (32 °C)</td> </tr> </table>	– Min.	40 °F (4 °C)	– Max.	90 °F (32 °C)
– Min.	40 °F (4 °C)					
– Max.	90 °F (32 °C)					
	Volatile Organic Compounds (VOC)					
	45 Grams/Liter	.38 Lbs./Gallon				

[◇] Reported values are for Pastel Base. Contact Benjamin Moore for values of other bases or colors.

Latex Floor and Patio Low Sheen Enamel N122

Surface Preparation

Surfaces to be painted must be clean, dry, and free of dirt, dust, grease, oil, soap, wax, scaling paint, water soluble materials, and mildew. Remove any peeling or scaling paint and sand these areas to feather edges smooth with adjacent surfaces. Glossy areas should be dulled.

New masonry surfaces must be allowed to cure 30 days and then be cleaned to removing all form release agents and curing compounds before applying the base coat. Poured or pre-cast concrete with a smooth surface should be etched with a Concrete Pretreatment & Etch or a 10% muriatic acid solution to promote adhesion. Remove any powder or loose particles before applying the base coat.

Difficult Substrates: Benjamin Moore offers a variety of specialty primers for use over difficult substrates such as bleeding woods, grease stains, crayon markings, hard glossy surfaces, galvanized metal or other substrates where paint adhesion or stain suppression is a particular problem. Your Benjamin Moore® retailer can recommend the right problem-solving primer for your special needs.

WARNING! If you scrape, sand, or remove old paint, you may release lead dust. **LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE.** Wear a NIOSH approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Informational Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead.

Primer/Finish Systems

New surfaces should be fully primed, and previously painted surfaces may be primed or spot primed as necessary. For best hiding results, tint the primer to the approximate shade of the finish coat, especially when a significant color change is desired. **Special Note:** Certain custom colors require a Deep Color Base Primer tinted to a special prescription formula to achieve the desired color. Consult your retailer.

Unpainted Concrete:

Primer: Self Priming – Apply a thin first coat of Latex Floor & Patio Low Sheen Enamel N122 and allow to dry for a minimum of 4 hours
Finish: 1-2 coats Latex Floor & Patio Low Sheen Enamel (N122)

Previously Painted Wood and Concrete:

Primer/Finish: 1-2 coats Latex Floor & Patio Low Sheen Enamel (N122)

Wood and Engineered Wood Products:

Primer: Fresh Start® Multi-Purpose Latex Primer (N023) or Fresh Start® High-Hiding All Purpose Primer (046)
Finish: 1-2 coats Latex Floor & Patio Low Sheen Enamel (N122)

Bleeding Type Woods, (Redwood and Cedar):

Primer: Fresh Start® Multi-Purpose Oil Based Primer (024) or 1-2 coats of Fresh Start® High-Hiding All Purpose Primer (046) may be used
Finish: 1-2 coats Latex Floor & Patio Low Sheen Enamel (N122)

Repaint, All Substrates: Prime bare areas with the primer recommended for the substrate above.

Application

Mixing of Paint: Stir thoroughly before and occasionally during use. Apply with a quality synthetic brush, short or medium nap roller or spray. Do not apply when air and surface temperatures are below 50°F (10°C).

Thinning/Clean Up

Conditioning with Benjamin Moore® 518 Extender may be necessary under certain conditions to adjust open time or spray characteristics. The chart below is for general guidance		
	Mild conditions	Severe conditions
	Humid (RH> 50%) with no direct sunlight & with little to no wind	Dry (RH<50%), in direct sunlight, or windy conditions
Brush: Nylon / Polyester	No thinning necessary	Add 518 Extender or water: Max of 8 fl. oz. to a gallon of paint Never add other paints or solvents.
Roller: Premium Quality 3/8" roller cover		
Spray: Airless Pressure: 1500 - 2500 psi Tip: 0.013-0.015		

Clean Up: Wash painting tools in warm soapy water immediately after use. Spray equipment should be given a final rinse with mineral spirits to prevent rusting if compliant with local requirements.

Environmental, Health & Safety Information

Caution: All floor coatings may become slippery when wet. Where non-skid characteristics are desired, a small amount of clean sand may be added. Stir often during application.

Use only with adequate ventilation. Do not breathe spray mist or sanding dust. Ensure fresh air entry during application and drying. Avoid contact with eyes and prolonged or repeated contact with skin. Avoid exposure to dust and spray mist by wearing a NIOSH approved respirator during application, sanding and clean up. Follow respirator manufacturer's directions for respirator use. Close container after each use. Wash thoroughly after handling.



WARNING Cancer and Reproductive Harm—
www.P65warnings.ca.gov

FIRST AID: In case of eye contact, flush immediately with plenty of water for at least 15 minutes; for skin, wash thoroughly with soap and water. If symptoms persist, seek medical attention. If you experience difficulty breathing, leave the area to obtain fresh air. If continued difficulty is experienced, get medical attention immediately.

IN CASE OF SPILL: Absorb with inert material and dispose of as specified under **Thinning/Clean up**.

**KEEP OUT OF REACH OF CHILDREN
PROTECT FROM FREEZING**

**Refer to Safety Data Sheet for additional health
and safety information.**