



LATEX FLOOR & PATIO

LOW SHEEN ENAMEL

F122

Features

- Resistant to soaps and detergents, grease and oil
- Exhibits a smooth, uniform appearance
- One coat covers most previously painted surfaces that are in fair to good condition
- Easy to apply

Recommended For

Residential or commercial applications where a premium quality finish is desired. For interior and exterior use on unpainted concrete (new or old) and previously finished wood or concrete floors. Particularly recommended for basements, porches, patios, breezeways, showrooms, and light industrial applications.

General Description

A premium quality, quick-drying, epoxy-modified acrylic low sheen latex floor enamel. One coat covers most previously painted surfaces that are in fair to good condition.

Limitations

- Many tires contain compounds which may attack latex paints, resulting in loss of adhesion and film pickup.

Product Information

<p>Colours — Standard: White (01), Platinum Grey (74)</p> <p>— Tint Bases: Benjamin Moore® Gennex® Bases 1X, 2X, 3X, & 4X</p> <p>— Special Colours: Contact your Benjamin Moore representative.</p> <p>Certifications & Qualifications: VOC compliant in all regulated areas</p> <p>Qualifies for LEED® v4 Credit Qualifies for CHPS low emitting credit (Collaborative for High Performance Schools) CDPH v1 Emission Certified</p> <p>CUSTOMER INFORMATION CENTRE: 1-800-361-5898, info@benjaminmoore.ca, www.benjaminmoore.ca</p>	<table border="1"> <thead> <tr> <th colspan="2">Technical Data[∆]</th> <th>Base 1</th> </tr> </thead> <tbody> <tr> <td>Vehicle Type</td> <td colspan="2">Epoxy Modified Acrylic Latex</td> </tr> <tr> <td>Pigment Type</td> <td colspan="2">Titanium Dioxide</td> </tr> <tr> <td>Volume Solids</td> <td colspan="2">37 ± 2%</td> </tr> <tr> <td>Coverage per 3.79 L at</td> <td colspan="2">46.4 – 55.7 sq. m</td> </tr> <tr> <td>Recommended Film Thickness</td> <td colspan="2">(500 – 600 Sq. Ft.)</td> </tr> <tr> <td rowspan="2">Recommended Film Thickness</td> <td>– Wet</td> <td>2.7 – 3.2 mils</td> </tr> <tr> <td>– Dry</td> <td>1.0 – 1.2 mils</td> </tr> <tr> <td colspan="3">Depending on surface texture and porosity. Be sure to estimate the right amount of paint for the job. This will ensure colour uniformity and minimize the disposal of excess paint.</td> </tr> <tr> <td rowspan="2">Dry Time @ 25 °C (77 °F) @ 50% RH</td> <td>– To Touch</td> <td>1 Hour</td> </tr> <tr> <td>– To Recoat</td> <td>4 Hours</td> </tr> <tr> <td colspan="3">High humidity and cool temperatures will result in longer dry, recoat and service times. Withstands light traffic after overnight dry.</td> </tr> <tr> <td>Dries By</td> <td colspan="2">Evaporation, Coalescence</td> </tr> <tr> <td>Viscosity</td> <td colspan="2">78 ± 2 KU</td> </tr> <tr> <td>Flash Point</td> <td colspan="2">None</td> </tr> <tr> <td>Gloss / Sheen</td> <td colspan="2">Satin (10 – 25 @ 60°)</td> </tr> <tr> <td rowspan="2">Surface Temperature at Application</td> <td>– Min.</td> <td>10 °C (50 °F)</td> </tr> <tr> <td>– Max.</td> <td>32 °C (90 °F)</td> </tr> <tr> <td>Thin With</td> <td colspan="2">See Chart</td> </tr> <tr> <td>Clean Up Thinner</td> <td colspan="2">Clean Water</td> </tr> <tr> <td>Weight Per 3.79 L</td> <td colspan="2">5 kg (11.0 lbs.)</td> </tr> <tr> <td rowspan="2">Storage Temperature</td> <td>– Min.</td> <td>4 °C (40 °F)</td> </tr> <tr> <td>– Max.</td> <td>32 °C (90 °F)</td> </tr> <tr> <td colspan="3" style="text-align: center;">Volatile Organic Compounds (VOC)</td> </tr> <tr> <td colspan="3" style="text-align: center;">45 Grams/Litre</td> </tr> </tbody> </table>	Technical Data [∆]		Base 1	Vehicle Type	Epoxy Modified Acrylic Latex		Pigment Type	Titanium Dioxide		Volume Solids	37 ± 2%		Coverage per 3.79 L at	46.4 – 55.7 sq. m		Recommended Film Thickness	(500 – 600 Sq. Ft.)		Recommended Film Thickness	– Wet	2.7 – 3.2 mils	– Dry	1.0 – 1.2 mils	Depending on surface texture and porosity. Be sure to estimate the right amount of paint for the job. This will ensure colour uniformity and minimize the disposal of excess paint.			Dry Time @ 25 °C (77 °F) @ 50% RH	– To Touch	1 Hour	– To Recoat	4 Hours	High humidity and cool temperatures will result in longer dry, recoat and service times. Withstands light traffic after overnight dry.			Dries By	Evaporation, Coalescence		Viscosity	78 ± 2 KU		Flash Point	None		Gloss / Sheen	Satin (10 – 25 @ 60°)		Surface Temperature at Application	– Min.	10 °C (50 °F)	– Max.	32 °C (90 °F)	Thin With	See Chart		Clean Up Thinner	Clean Water		Weight Per 3.79 L	5 kg (11.0 lbs.)		Storage Temperature	– Min.	4 °C (40 °F)	– Max.	32 °C (90 °F)	Volatile Organic Compounds (VOC)			45 Grams/Litre		
Technical Data [∆]		Base 1																																																																						
Vehicle Type	Epoxy Modified Acrylic Latex																																																																							
Pigment Type	Titanium Dioxide																																																																							
Volume Solids	37 ± 2%																																																																							
Coverage per 3.79 L at	46.4 – 55.7 sq. m																																																																							
Recommended Film Thickness	(500 – 600 Sq. Ft.)																																																																							
Recommended Film Thickness	– Wet	2.7 – 3.2 mils																																																																						
	– Dry	1.0 – 1.2 mils																																																																						
Depending on surface texture and porosity. Be sure to estimate the right amount of paint for the job. This will ensure colour uniformity and minimize the disposal of excess paint.																																																																								
Dry Time @ 25 °C (77 °F) @ 50% RH	– To Touch	1 Hour																																																																						
	– To Recoat	4 Hours																																																																						
High humidity and cool temperatures will result in longer dry, recoat and service times. Withstands light traffic after overnight dry.																																																																								
Dries By	Evaporation, Coalescence																																																																							
Viscosity	78 ± 2 KU																																																																							
Flash Point	None																																																																							
Gloss / Sheen	Satin (10 – 25 @ 60°)																																																																							
Surface Temperature at Application	– Min.	10 °C (50 °F)																																																																						
	– Max.	32 °C (90 °F)																																																																						
Thin With	See Chart																																																																							
Clean Up Thinner	Clean Water																																																																							
Weight Per 3.79 L	5 kg (11.0 lbs.)																																																																							
Storage Temperature	– Min.	4 °C (40 °F)																																																																						
	– Max.	32 °C (90 °F)																																																																						
Volatile Organic Compounds (VOC)																																																																								
45 Grams/Litre																																																																								

Latex Floor and Patio Low Sheen Enamel F122

Surface Preparation

Surfaces to be painted must be clean, dry, and free of dirt, dust, grease, oil, soap, wax, scaling paint, water soluble materials, and mildew. Remove any peeling or scaling paint and sand these areas to feather edges smooth with adjacent surfaces. Glossy areas should be dulled.

New masonry surfaces must be allowed to cure 30 days and then be cleaned to removing all form release agents and curing compounds before applying the base coat. Poured or pre-cast concrete with a smooth surface should be etched with a Concrete Pretreatment & Etch or a 10% muriatic acid solution to promote adhesion. Remove any powder or loose particles before applying the base coat.

Difficult Substrates: Benjamin Moore offers a variety of specialty primers for use over difficult substrates such as bleeding woods, grease stains, crayon markings, hard glossy surfaces, galvanized metal or other substrates where paint adhesion or stain suppression is a particular problem. Your Benjamin Moore® retailer can recommend the right problem-solving primer for your special needs.

WARNING! If you scrape, sand, or remove old paint, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by logging onto Health Canada @ <https://www.canada.ca/en/health-canada/services/environmental-workplace-health/environmental-contaminants/lead/lead-information-package-some-commonly-asked-questions-about-lead-human-health.html>

Primer/Finish Systems

New surfaces should be fully primed, and previously painted surfaces may be primed or spot primed as necessary. For best hiding results, tint the primer to the approximate shade of the finish coat, especially when a significant colour change is desired.

Special Note: Certain custom colours require a Deep Colour Base Primer tinted to a special prescription formula to achieve the desired colour. Consult your retailer.

Unpainted Concrete:

Primer: Self Priming – Apply a thin first coat of Latex Floor & Patio Low Sheen Enamel F122 and allow to dry for a minimum of 4 hours

Finish: 1-2 coats Latex Floor & Patio Low Sheen Enamel (F122)

Previously Painted Wood and Concrete:

Primer/Finish: 1-2 coats Latex Floor & Patio Low Sheen Enamel (F122)

Wood and Engineered Wood Products:

Primer: Fresh Start® High-Hiding All Purpose Primer (K046)

Finish: 1-2 coats Latex Floor & Patio Low Sheen Enamel (F122)

Bleeding Type Woods, (Redwood and Cedar):

Primer: Fresh Start® Undecoater and Primer/Sealer (K032), Fresh Start® Deck & Siding Primer (K094) or 1-2 coats of Fresh Start® High-Hiding All Purpose Primer (K046) may be used

Finish: 1-2 coats Latex Floor & Patio Low Sheen Enamel (F122)

Repaint, All Substrates: Prime bare areas with the primer recommended for the substrate above.

Application

Mixing of Paint: Stir thoroughly before and occasionally during use. Apply with a quality synthetic brush, short or medium nap roller or spray. Do not apply when air and surface temperatures are below 10°C (50°F).

This product can also be sprayed.

Spray, Airless

Pressure: 1,500-2,500 psi; Tip: 0.013-0.015

Thinning/Clean Up

Conditioning with Benjamin Moore® K518 Extender may be necessary under certain conditions to adjust open time or spray characteristics.

Add K518 Extender or water - Max of 236 mL to 3.79 L of paint
Never add other paints or solvents.

Clean Up: Wash painting tools in warm soapy water immediately after use. Spray equipment should be given a final rinse with mineral spirits to prevent rusting.

Environmental Health & Safety Information

Use only in a well ventilated area. Keep container closed when not in use. In case of spillage, absorb with inert material and dispose of in accordance with local regulations. Wash thoroughly after handling.

Caution: All floor coatings may become slippery when wet. Where non-skid characteristics are desired, use an appropriate anti-slip aggregate.

WARNING: This product contains isothiazolinone compounds at levels of <0.1%. These substances are biocides commonly found in most paints and a variety of personal care products as a preservative. Certain individuals may be sensitive or allergic to these substances, even at low levels.

**KEEP OUT OF REACH OF CHILDREN
PROTECT FROM FREEZING**

**Refer to Safety Data Sheet for additional health
and safety information.**