



# ELASTITE™

20 MIL 100% ACRYLIC WATERPROOF COATING

## 162 LINE

### Features

- Acrylic Elastomeric Coating
- Keeps Damaging Water Out
- 200% Elongation Rating
- Flexible down to -18 °C (0 °F)

### General Description

Elastite™ 162 20 Mil 100% Acrylic Elastomeric Waterproof Coating is a new technology elastomeric membrane coating designed to keep damaging water out of commercial and residential structures. When properly applied, this product will stop wind driven rain from entering the structure through the coating film, yet is permeable enough to allow moisture vapor to escape. This product remains flexible down to -18 °C (0 °F), keeping a continuous membrane wrapped around a building, even if small cracks form in the substrate. It cures harder than traditional elastomeric coatings on the outermost surface, giving this product much better resistance to dirt accumulation versus traditional elastomerics, yet it remains flexible underneath the surface to bridge cracks and move with the building.

### Recommended For

Masonry, Wood, Metal. Apply at 20 mil wet.

### Limitations

- Apply only if temperatures are between 7.22°C (45°F) and 35°C (95°F), and in humidities less than 90%.
- Do not apply if ambient & substrate temperatures are within 5 degrees of the dew point and falling.
- Do not apply if rain is expected within 12 hours.

### Product Information

Colours — Standard:	Technical Data◇	White
White Can be tinted with up to 60 ml Universal Colorant per 3.79 L	Vehicle Type	Acrylic
	Pigment Type	Titanium Dioxide
	Volume Solids	54 ± 1.0%
	Coverage per 3.79 L at	7 - 7,9 sq. m
	Recommended Film Thickness	(75 - 85 Sq. Ft.)
	Recommended Film Thickness	- Wet 19 - 21 mil - Dry 10.2 - 11.3 mil
	Depending on surface texture and porosity. Be sure to estimate the right amount of paint for the job. This will ensure colour uniformity and minimize the disposal of excess paint.	
	Dry Time @ 25°C (77°F) @ 50% RH	- Tack Free 2 Hours - To Recoat 6 Hours
	High humidity and cool temperatures will result in longer dry, recoat and service times.	
	Dries By	Evaporation
	Viscosity	130 – 135 KU
	Flash Point	93.3 °C (200 °F or greater) (TT-P-141, Method 4293)
	Gloss / Sheen	Flat 3 - 10 Units @ 85°
	Surface Temperature at Application	- Min. 7.22°C (45°F) - Max. 35°C (95°F)
	Thin With	Clean Water
	Clean Up Thinner	Warm Soapy Water
	Weight Per 3.79 L	12.0 lbs.
	Storage Temperature	- Min. 7.22°C (45°F) - Max. 35°C (95°F)
	<b>Volatile Organic Compounds (VOC)</b> 47 Grams/Liter 0.39 Lbs./3.79 L	
<b>Colours — Standard:</b> White Can be tinted with up to 60 ml Universal Colorant per 3.79 L		
<b>— Tint Bases:</b> N/A		
<b>— Special Colours:</b> Contact your dealer.		
<b>Certification:</b>  The products supported by this data sheet contain a maximum of 50 grams per liter VOC/VOS (0.42 lbs/3.79 L) excluding water & exempt solvents. This product is compliant under the Ozone Transport Commission regulations as a Flat Coating. Meets Performance Requirements of TT-C-555B ASTM D-2370 - 200% Elongation @10 mil DFT ASTM D 1653-93 Perm Ratings 14 Perms @ 10 mil DFT ASTM D-1604 Resistance to Wind Driven Rain – Passes		
<b>Technical Assistance:</b> Available through your local authorized independent dealer. For the location of the dealer nearest you, call 1-800-225-5554 or visit <a href="http://www.coronadopaint.ca">www.coronadopaint.ca</a>		

◇ Reported values are for White. Contact dealer for values of other bases or colours.

## Elastite™ 20 Mil 100% Acrylic Waterproof Coating 162 Line

### Surface Preparation

The surface to be coated must be clean and free of dirt, efflorescence, chalk, form release agents, oil, mildew, rust, flaking paint or any other surface contaminant that could affect proper adhesion. Dirt, mildew, chalk and efflorescence should be removed by power washing. Form release agents, oil and grease should be cleaned by using an Oil & Grease Emulsifier, following all label directions. Rust must be removed by abrasive blasting, conscientious power tool cleaning or vigorous hand tool cleaning. Remove loose paint to tight adhering edges. Glossy surfaces must be dulled by lightly sanding. Any exposed substrate should be primed with the appropriate primer. All cracks and voids must be filled with an appropriate caulk or patching compound.

**PRIMING:** (Recommended for new and previously coated surfaces; use appropriate primer listed below):

Masonry - 48 Line or 1066 Line.

Ferrous Metal - Apply DTM Primer or Acrylic Primer 36-11

Galvanized Metal - Apply DTM Primer or Grip & Seal 116-11

Wood - Apply Acrylic Primer

**WARNING!** If you scrape, sand, or remove old paint, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by logging onto Health Canada @ [http://www.hc-sc.gc.ca/ewh-semt/contaminants/lead-plomb/asked\\_questions-questions\\_posees-eng.php](http://www.hc-sc.gc.ca/ewh-semt/contaminants/lead-plomb/asked_questions-questions_posees-eng.php)

### Application

Stir product thoroughly before you begin to paint. Coronado® Elastite™ 162 20 Mil 100% Acrylic Elastomeric Waterproof Coating should be applied by airless spray or by heavy nap roller cover. If applying by airless spray, back roll to force material into voids and to even out film. If applying by roller, use a 19 mm à 38 mm (3/4" to 1 1/2") nap cover, depending on surface texture. Roller application will create a slight stippled effect to the finish. This "Crows Feet" effect is normal and should be seen if the product is applied at the proper spread rate by roller. Elastite™ 162 should be applied at an average rate of 7,4 square metres per 3.79 L (20 mil WFT). Monitor application rates periodically to assure proper film thickness is being achieved. **Best waterproofing results will be obtained by applying two coats** and will only be achieved if used in conjunction with proper sealants around windows, doors, changes of angle and junction of dissimilar materials.

\*Brush application should be limited to "cutting in", touch ups or application to small tight areas.

Do not apply if rain is threatening. Apply only if temperatures are between 7.22 °C (45 °F) and 35 °C (95 °F), and in humidities less than 90%. Do not apply if ambient and substrate temperatures are within 5 degrees of the dew point and falling.

### Clean up

Clean all tools and equipment with warm, soapy water followed by a clean water rinse.

**MILDEW:** Mildew is a natural phenomenon over which we have no control and although every effort is made to make this paint a mildew resistant coating, we cannot assume responsibility for the formation of this fungus on the paint film. Prior to painting any mildewed surface, thoroughly remove the mildew by scrubbing with a solution of one part household bleach mixed with three parts water. Rinse well with clean water following bleach wash. Follow bleach manufacturer's instructions for safe handling and use of bleach solution.

### Environmental Health & Safety Information

Use only in a well ventilated area. Keep container closed when not in use. In case of spillage, absorb with inert material and dispose of in accordance with local regulations. Wash thoroughly after handling.

**KEEP OUT OF REACH OF CHILDREN  
PROTECT FROM FREEZING**

**Refer to Safety Data Sheet for  
additional health and safety information.**