



SUPER SPEC[®]

ALKYD CALCIMINE RECOATER

306

Features

- Features a uniform, glare-free finish
- Provides a highly serviceable film
- Superior leveling and hiding qualities
- Superb problem-solver coating that excels over difficult recoat surfaces
- Self-priming over calcimine coatings

Recommended For

For commercial and residential applications. Specifically formulated for recoating surfaces previously painted with calcimine material

General Description

A premium quality, high hiding, alkyd flat paint specifically designed for recoating surfaces previously painted with calcimine material. Covers most wall, ceiling, and trim surfaces in one coat.

Limitations

- Do not apply when air and surface temperatures are below 50 °F (10 °C)

Product Information

<p>Colors — Standard: White (01)</p> <p>May be tinted with up to 2.0 fl. oz. of Benjamin Moore[®] Color Preview[®] colorants per gallon.)</p>	<table border="1"> <thead> <tr> <th colspan="2">Technical Data[◇]</th> <th>Pastel Base</th> </tr> </thead> <tbody> <tr> <td>Vehicle Type</td> <td></td> <td>Alkyd</td> </tr> <tr> <td>Pigment Type</td> <td></td> <td>Titanium Dioxide</td> </tr> <tr> <td>Volume Solids</td> <td></td> <td>48%</td> </tr> <tr> <td>Coverage per Gallon at Recommended Film Thickness</td> <td></td> <td>400 – 450 Sq. Ft.</td> </tr> <tr> <td>Recommended Film Thickness</td> <td>– Wet</td> <td>3.8 mils</td> </tr> <tr> <td></td> <td>– Dry</td> <td>1.8 mils</td> </tr> <tr> <td colspan="3">Depending on surface texture and porosity. Be sure to estimate the right amount of paint for the job. This will ensure color uniformity and minimize the disposal of excess paint.</td> </tr> <tr> <td>Dry Time @ 77 °F (25 °C) @ 50% RH</td> <td>– To Touch</td> <td>4 - 6 Hours</td> </tr> <tr> <td></td> <td>– To Recoat</td> <td>12 Hours</td> </tr> <tr> <td colspan="3">Painted surfaces can be washed after two weeks. High humidity and cool temperatures will result in longer dry, recoat and service times.</td> </tr> <tr> <td>Dries By</td> <td></td> <td>Oxidation</td> </tr> <tr> <td>Viscosity</td> <td></td> <td>103 ± 3 KU</td> </tr> <tr> <td>Flash Point</td> <td></td> <td>Combustible</td> </tr> <tr> <td>Gloss / Sheen</td> <td></td> <td>Flat</td> </tr> <tr> <td>Surface Temperature at Application</td> <td>– Min.</td> <td>50 °F</td> </tr> <tr> <td></td> <td>– Max</td> <td>90 °F</td> </tr> <tr> <td>Thin With</td> <td></td> <td>Do Not Thin</td> </tr> <tr> <td>Clean Up Thinner</td> <td></td> <td>Mineral Spirits</td> </tr> <tr> <td>Weight Per Gallon</td> <td></td> <td>13.3 lbs</td> </tr> <tr> <td>Storage Temperature</td> <td>– Min.</td> <td>40 °F</td> </tr> <tr> <td></td> <td>– Max</td> <td>90 °F</td> </tr> <tr> <td colspan="3" style="text-align: center;">Volatile Organic Compounds (VOC)</td> </tr> <tr> <td colspan="3" style="text-align: center;">440.7 Grams/Liter 3.67 Lbs./Gallon</td> </tr> </tbody> </table>	Technical Data [◇]		Pastel Base	Vehicle Type		Alkyd	Pigment Type		Titanium Dioxide	Volume Solids		48%	Coverage per Gallon at Recommended Film Thickness		400 – 450 Sq. Ft.	Recommended Film Thickness	– Wet	3.8 mils		– Dry	1.8 mils	Depending on surface texture and porosity. Be sure to estimate the right amount of paint for the job. This will ensure color uniformity and minimize the disposal of excess paint.			Dry Time @ 77 °F (25 °C) @ 50% RH	– To Touch	4 - 6 Hours		– To Recoat	12 Hours	Painted surfaces can be washed after two weeks. High humidity and cool temperatures will result in longer dry, recoat and service times.			Dries By		Oxidation	Viscosity		103 ± 3 KU	Flash Point		Combustible	Gloss / Sheen		Flat	Surface Temperature at Application	– Min.	50 °F		– Max	90 °F	Thin With		Do Not Thin	Clean Up Thinner		Mineral Spirits	Weight Per Gallon		13.3 lbs	Storage Temperature	– Min.	40 °F		– Max	90 °F	Volatile Organic Compounds (VOC)			440.7 Grams/Liter 3.67 Lbs./Gallon		
Technical Data [◇]		Pastel Base																																																																							
Vehicle Type		Alkyd																																																																							
Pigment Type		Titanium Dioxide																																																																							
Volume Solids		48%																																																																							
Coverage per Gallon at Recommended Film Thickness		400 – 450 Sq. Ft.																																																																							
Recommended Film Thickness	– Wet	3.8 mils																																																																							
	– Dry	1.8 mils																																																																							
Depending on surface texture and porosity. Be sure to estimate the right amount of paint for the job. This will ensure color uniformity and minimize the disposal of excess paint.																																																																									
Dry Time @ 77 °F (25 °C) @ 50% RH	– To Touch	4 - 6 Hours																																																																							
	– To Recoat	12 Hours																																																																							
Painted surfaces can be washed after two weeks. High humidity and cool temperatures will result in longer dry, recoat and service times.																																																																									
Dries By		Oxidation																																																																							
Viscosity		103 ± 3 KU																																																																							
Flash Point		Combustible																																																																							
Gloss / Sheen		Flat																																																																							
Surface Temperature at Application	– Min.	50 °F																																																																							
	– Max	90 °F																																																																							
Thin With		Do Not Thin																																																																							
Clean Up Thinner		Mineral Spirits																																																																							
Weight Per Gallon		13.3 lbs																																																																							
Storage Temperature	– Min.	40 °F																																																																							
	– Max	90 °F																																																																							
Volatile Organic Compounds (VOC)																																																																									
440.7 Grams/Liter 3.67 Lbs./Gallon																																																																									
<p>— Tint Bases: Benjamin Moore[®] Color Preview[®] Pastel Base 1B</p>																																																																									
<p>— Special Colors: Contact your Benjamin Moore representative</p>																																																																									
<p>Certifications & Qualifications: Master Painters Institute MPI # 49</p> <table border="1" data-bbox="657 1113 941 1386"> <thead> <tr> <th>VOC REGION</th> <th>COMPLIANT</th> </tr> </thead> <tbody> <tr> <td>FEDERAL</td> <td>YES</td> </tr> <tr> <td>OTC</td> <td>YES</td> </tr> <tr> <td>OTCII</td> <td>YES</td> </tr> <tr> <td>CARB</td> <td>NO</td> </tr> <tr> <td>CARB07</td> <td>NO</td> </tr> <tr> <td>UTAH</td> <td>YES</td> </tr> <tr> <td>AZMC</td> <td>NO</td> </tr> <tr> <td>SCAQMD</td> <td>NO</td> </tr> </tbody> </table>	VOC REGION	COMPLIANT	FEDERAL	YES	OTC	YES	OTCII	YES	CARB	NO	CARB07	NO	UTAH	YES	AZMC	NO	SCAQMD	NO																																																							
VOC REGION	COMPLIANT																																																																								
FEDERAL	YES																																																																								
OTC	YES																																																																								
OTCII	YES																																																																								
CARB	NO																																																																								
CARB07	NO																																																																								
UTAH	YES																																																																								
AZMC	NO																																																																								
SCAQMD	NO																																																																								
<p>Technical Assistance Available through your local authorized independent Benjamin Moore retailer. For the location of the retailer nearest you, call 1-866-708-9180 or visit www.benjaminmoore.com</p>																																																																									

[◇]Reported values are for Pastel Base. Contact Benjamin Moore for values of other bases or color.

Surface Preparation

Surfaces to be painted must be clean, dry, and free of dirt, dust, grease, oil, soap, wax, scaling paint, water soluble materials, and mildew. Remove any peeling or scaling paint and sand these areas to feather edges smooth with adjacent surfaces. Glossy areas should be dulled. Drywall surfaces must be free of sanding dust.

New plaster or masonry surfaces must be allowed to cure (30 – 60 days) before applying base coat. Cured plaster should be hard, have a slight sheen and maximum pH of 10; soft, porous or powdery plaster indicates improper cure. Never sand a plaster surface; knife off any protrusions and prime plaster before and after applying patching compound. Poured or pre-cast concrete with a very smooth surface should be etched or abraded to promote adhesion, after removing all form release agents and curing compounds. Remove any powder or loose particles before priming.

Difficult Substrates: Benjamin Moore & Co. offers a number of specialty primers for use over difficult substrates such as bleeding woods, grease, crayon markings, hard glossy surfaces, galvanized metal, or other substrates where paint adhesion or stain suppression is a particular problem. Your Benjamin® retailer can recommend the right problem-solving primer for your special needs.

WARNING! If you scrape, sand or remove old paint, you may release lead dust. **LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE.** Wear a NIOSH approved respirator to control lead exposure. Carefully clean up with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead.

Primer/Finish Systems

Note: All alkyd-based enamels experience a certain amount of yellowing. This effect is accelerated in dark or poorly ventilated areas.

This product is sold only for the repainting of surfaces previously painted with calcimine material. For new surfaces or surfaces previously painted with non-calcimine coatings, a variety of Benjamin Moore® interior products are available. Consult your Benjamin Moore® retailer for recommendations.

Mixing of Paint: Stir thoroughly before and occasionally during use. Apply with a quality china bristle brush, or all purpose synthetic brush, short nap roller, or airless spray.

Do not apply when air and surface temperatures are below 50 °F (10 °C). **Spray, Airless:** Fluid Pressure — 1,500 to 2,000 PSI; Tip: .013 - .017 Orifice

Thinning/Cleaning

Do not thin. Clean up with mineral spirits

Clean up: Clean brushes, rollers and other painting tools in warm soapy water after use. Spray equipment should be given a final rinse with mineral spirits to prevent rusting.

USE COMPLETELY OR DISPOSE OF PROPERLY. Dry empty containers may be recycled in a can recycling program. **Local disposal requirements vary; consult your sanitation department or state-designated environmental agency on disposal options.**

Environmental, Health & Safety Information

WARNING! COMBUSTIBLE LIQUID AND VAPOR

Contains Stoddard Solvent and Crystalline Silica

VAPOR HARMFUL. CAUSES EYE, SKIN, NOSE, AND THROAT IRRITATION

NOTICE: Repeated and prolonged exposure to solvents may lead to permanent brain and nervous system damage. Eye watering, headaches, nausea, dizziness and loss of coordination are signs that solvent levels are too high. Intentional misuse by deliberately concentrating and inhaling the contents may be harmful or fatal. **Crystalline Silica** can cause cancer when in the respirable form (spray mist or sanding dust).

Keep away from heat and flame. **Use only with adequate ventilation.** Do not breathe vapors, spray mist or sanding dust. Avoid contact with eyes and prolonged or repeated contact with skin. Wear eye protection and gloves. To avoid breathing vapors or spray mist, open window and doors or use other means to ensure fresh air entry during application and drying. If you experience eye watering, headaches or dizziness, increase fresh air or wear a properly fitted vapor/particulate respirator approved by NIOSH for use with paints or leave the area. In all cases follow respirator manufacturer's directions for respirator use. Close container after each use.



WARNING Cancer and Reproductive Harm—
www.P65warnings.ca.gov

FIRST AID: If affected by inhalation of vapors or spray mist, remove to fresh air. In case of eye contact, flush immediately with plenty of water for at least 15 minutes and call a physician; for skin, wash thoroughly with soap and water. In case of ingestion - DO NOT INDUCE VOMITING, get medical help immediately.

IN CASE OF: FIRE – Use foam, CO2, dry chemical, or water fog.
SPILL – Absorb with inert material and dispose of as specified under **Thinning/Cleanup**.

**KEEP OUT OF REACH OF CHILDREN
PROTECT FROM FREEZING**

**Refer to Safety Data Sheet for additional
health and safety information.**