

Features

- Pearl finish provides high durability and pearl like finish
- Spatter resistant
- Easy application properties
- Provides a mildew resistant coating

• Easy touch up

- Great for high use or commercial surfaces
- Painted surfaces can be washed after two weeks
- Self priming on most surfaces

REGAL[®] CLASSIC PREMIUM INTERIOR 100% ACRYLIC PEARL FINISH N310

General Description

Regal[®] Classic Pearl is a premium quality proprietary acrylic pearl finish with unique properties. Its high-hiding pearl lustre finish provides an elegant look to walls, ceilings, trim, doors, and cabinets. Regal[®] Classic Pearl is easy-to-use, spatter resistant and fast drying. Its durable satin like finish is ideal for any interior application.

Limitations

 Do not apply when air and surface temperatures are below 50 °F (10 °C)

ight amount of paint for the job. ninimize the disposal of excess pa Dry Time @ 77 °F 25 °C) @ 50% RH Painted surfaces can be washed	- Wet 3.8 m - Dry 1.3 m nd porosity. Be sure to estimate to this will ensure color uniformity a point. - To Touch 1 Ho - To Recoat 2 - 3 Hou after two weeks. High humidity a nger dry, recoat and service times. Evaporation, Coalescen		
Pigment Type /olume Solids Coverage per Gallon at Recommended Film Thickness Recommended Film Thickness Depending on surface texture ar ght amount of paint for the job. ninimize the disposal of excess pain Dry Time @ 77 °F 25 °C) @ 50% RH Painted surfaces can be washed ool temperatures will result in Ion Dries By	Titanium Dioxi Titanium Dioxi 37.9 ss 400 – 450 Sq. 1 — Wet - Wet - Met - M		
/olume Solids Coverage per Gallon at Recommended Film Thickness Recommended Film Thickness Depending on surface texture ar ight amount of paint for the job. ninimize the disposal of excess paint Dry Time @ 77 °F 25 °C) @ 50% RH Painted surfaces can be washed ool temperatures will result in Ion Dries By	37.9 $58 400 - 450 ext{ Sq.}$ $\frac{- \text{ Wet} 3.8 \text{ m}}{- \text{ Dry} 1.3 \text{ m}}$ $\frac{- \text{ Wet} 3.8 \text{ m}}{- \text{ Dry} 1.3 \text{ m}}$ $\frac{- \text{ Tory} 1.3 \text{ m}}{- \text{ Jry} 1.3 \text{ m}}$ $\frac{- \text{ To Touch} 1 \text{ Hc}}{- \text{ To Recoat} 2 - 3 \text{ Hou}}$ $\frac{- \text{ To Recoat} 2 - 3 \text{ Hou}}{- \text{ after two weeks. High humidity a mger dry, recoat and service times.}}$ $Evaporation, Coalescent$		
Coverage per Gallon at Recommended Film Thicknes Recommended Film Thickness Depending on surface texture ar ight amount of paint for the job. ninimize the disposal of excess part Dry Time @ 77 °F 25 °C) @ 50% RH Painted surfaces can be washed ool temperatures will result in Ion Dries By	$\begin{array}{c c} & 400-450 \text{ Sq. I} \\ \hline - \text{ Wet} & 3.8 \text{ m} \\ \hline - \text{ Dry} & 1.3 \text{ m} \\ \hline \text{ ory} & 1.3 \text{ m} \\ \hline \text{ nd porosity. Be sure to estimate t} \\ \hline \text{ This will ensure color uniformity a baint.} \\ \hline \hline - \text{ To Touch} & 1 \text{ Hc} \\ \hline - \text{ To Recoat} & 2-3 \text{ Hou} \\ \hline \text{ after two weeks. High humidity a nger dry, recoat and service times.} \\ \hline \hline \text{ Evaporation, Coalescen} \end{array}$		
Recommended Film Thickness Recommended Film Thickness Depending on surface texture ar- ight amount of paint for the job. ninimize the disposal of excess paint Dry Time @ 77 °F 25 °C) @ 50% RH Painted surfaces can be washed ool temperatures will result in Ion Dries By	- Wet 3.8 m - Dry 1.3 m Ind porosity. Be sure to estimate to this will ensure color uniformity a baint. - To Touch 1 Hc - To Recoat 2 - 3 Hou after two weeks. High humidity a nger dry, recoat and service times. Evaporation, Coalescen		
Thickness Depending on surface texture arright amount of paint for the job. ninimize the disposal of excess painting of t	- Dry 1.3 m Ind porosity. Be sure to estimate to this will ensure color uniformity a baint. - To Touch - To Recoat 2 - 3 Hou d after two weeks. High humidity a nger dry, recoat and service times. Evaporation, Coalescen		
Depending on surface texture ar ight amount of paint for the job. ninimize the disposal of excess pain Dry Time @ 77 °F 25 °C) @ 50% RH Painted surfaces can be washed ool temperatures will result in lon Dries By	Ind porosity. Be sure to estimate to the sum of the sum o		
ight amount of paint for the job. ninimize the disposal of excess pa Dry Time @ 77 °F 25 °C) @ 50% RH Painted surfaces can be washed ool temperatures will result in Ion Dries By	This will ensure color uniformity a baint. - To Touch 1 Hc - To Recoat 2 - 3 Hou d after two weeks. High humidity a nger dry, recoat and service times. Evaporation, Coalescen		
25 °C) @ 50% RH Painted surfaces can be washed ool temperatures will result in Ion Dries By	- To Recoat 2 - 3 Hou d after two weeks. High humidity a nger dry, recoat and service times. Evaporation, Coalescen		
Painted surfaces can be washed ool temperatures will result in lon Dries By	after two weeks. High humidity a nger dry, recoat and service times. Evaporation, Coalescen		
ool temperatures will result in lon Dries By	nger dry, recoat and service times. Evaporation, Coalescen		
Dries By	Evaporation, Coalescen		
,	•		
riscosity			
Viscosity 94 ± 2 KI Flash Point Non Gloss / Sheen Pearl (12-25 @ 60°			
		Surface Temperature	– Min. 50
		t Application	– Max. 90
Thin With	See Ch		
Clean Up Thinner	Clean Wat		
Veight Per Gallon	10.7		
	– Min. 40		
Storage Temperature	– Max. 90		
Volatile Organic	c Compounds (VOC)		
	urface Temperature t Application hin With Clean Up Thinner Veight Per Gallon torage Temperature Volatile Organic		

 $\Diamond \mbox{Reported values are for Pastel Base. Contact Benjamin Moore & Co. for values of other bases or colors.$

Recommended For Recommended for use on new or previously painted wallboard, plaster, masonry, and primed or previously painted wood and metal. It is ideal for areas where a durable film is required as it

can withstand repeated washings and mild scrubbing.

Surface Preparation

Surfaces to be painted must be clean, dry, and free of dirt, dust, grease, oil, soap, wax, scaling paint, water soluble materials, and mildew. Remove any peeling or scaling paint and sand these areas to feather edges smooth with adjacent surfaces. Glossy areas should be dulled. Drywall surfaces must be free of sanding dust.

New plaster or masonry surfaces must be allowed to cure 30 days before applying base coat. Cured plaster should be hard, have a slight sheen and maximum PH of 10; soft, porous or powdery plaster indicates improper cure. Never sand a plaster surface; knife off any protrusions and prime plaster before and after applying patching compound.

Poured or pre-cast concrete with a very smooth surface should be etched or abraded to promote adhesion, after removing all form release agents and curing compounds. Remove any powder or loose particles before priming. Wood substrates must be thoroughly dry.

Difficult Substrates: Benjamin Moore & Co. offers a variety of specialty primers for use over difficult substrates such as bleeding woods, grease stains, crayon markings, hard glossy surfaces, galvanized metal or other substrates where paint adhesion or stain suppression is a particular problem. Your Benjamin Moore[®] retailer can recommend the right problem-solving primer for your special needs.

WARNING! If you scrape, sand or remove old paint, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH approved respirator to control lead exposure. Carefully clean up with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead.

Primer/Finish Systems

Regal[®] Classic Finish is self priming on most surfaces. On bare substrates two coats are required; previously painted surfaces can be finished with 1 or 2 coats. While the high quality of our products sometimes makes one-coat coverage achievable, Benjamin Moore recommends two coats of this product to achieve full color development and to maximize paint film performance. **Special Note**: Certain deep custom colors may require a Deep Base Primer tinted to a special prescription formula to achieve the desired color. Consult your retailer.

Wood, and engineered wood products:

Primer: Regal[®] Classic Premium Interior Latex Primer (N216), Fresh Start[®] All-Purpose 100% Alkyd Primer (024) or Fresh Start[®] Alkyd Enamel Underbody (217)

Finish: 1 or 2 coats Regal® Classic Premium Interior 100% Acrylic Pearl Finish (N310)

Bleeding woods; like redwood or cedar: Fresh Start[®] All-Purpose Alkyd Primer (024), Alkyd Enamel Underbody (217) or Fresh Start[®] High-Hiding All Purpose Primer (046)

Finish: 1 or 2 coats Regal[®] Classic Premium Interior 100% Acrylic Pearl Finish (N310)

Drywall:

Primer/Finish: 1 or 2 coats of Regal® Classic Premium Interior 100% Acrylic Pearl Finish (N310)

Plaster:

Primer/Finish: 1 or 2 coats of Regal® Classic Premium Interior 100% Acrylic Pearl Finish (N310)

Rough or Pitted Masonry:

Primer: Ultra Spec[®] Masonry Interior/Exterior Hi-Build Block Filler (571)

Finish: 1 or 2 coats Regal $^{\odot}$ Classic Premium Interior 100% Acrylic Pearl Finish (N310)

Smooth Poured or Pre-cast Concrete:

Primer/Finish: 1 or 2 coats of Regal[®] Classic Premium Interior 100% Acrylic Pearl Finish (N310)

Ferrous Metal (Steel and Iron):

Primer: Ultra Spec[®] HP Acrylic Metal Primer (HP04) or Super Spec HP[®] Alkyl Metal Primer (P06)

Finish: 1or 2 coats Regal® Classic Premium Interior 100% Acrylic Pearl Finish (N310)

Non-Ferrous Metal (Galvanized & Aluminum): All new metal surfaces must be thoroughly cleaned with Corotech[®] Oil & Grease Emulsifier (V600) to remove contaminants. New shiny non-ferrous metal surfaces that will be subject to abrasion should be dulled with very fine sandpaper or a synthetic steel wool pad to promote adhesion

Primer: Not required on properly prepared surfaces Finish: 1 or 2 coats Regal[®] Classic Premium Interior 100% Acrylic Pearl Finish (N310)

Repaint, All Substrates: Prime bare areas with the primer recommended for the substrate above.

Application

Mixing of Paint: Stir thoroughly before and during use. Apply one or two coats. For best results, use a premium Benjamin Moore[®] customblended nylon/polyester brush, premium Benjamin Moore[®] roller, or a similar product. Apply paint generously from unpainted area into wet area. This product can also be sprayed.

Thinning / Clean Up

Conditioning with Benjamin Moore® 518 Extender may be necessary under certain conditions to adjust open time or spray characteristics. The chart below is for general guidance			
	Mild conditions	Severe Conditions	
	Humid (RH> 50%) with	Dry (RH<50%), in	
	no direct sunlight & with	direct sunlight,	
	little to no wind	or windy conditions	
Brush: Nylon / Polyester		Add 518 Extender or	
Roller:		water:	
Premium Quality Nylon/Polyester	No thinning necessary	Max of 8 fl. oz. to a gallon of paint	
Spray: Airless		gailori or paint	
Pressure: 1500 -2500 psi Tip: 0.011-0.015		Never add other paints or solvents.	

Wash painting tools in warm soapy water immediately after use. Spray equipment should be given a final rinse with mineral spirits to prevent rusting.

USE COMPLETELY OR DISPOSE OF PROPERLY. Dry empty containers may be recycled in a can recycling program. Local disposal requirements vary; consult your sanitation department or state-designated environmental agency on disposal options.

Environmental Health & Safety Information

Use only with adequate ventilation. Do not breathe spray mist or sanding dust. Ensure fresh air entry during application and drying. Avoid contact with eyes and prolonged or repeated contact with skin. Avoid exposure to dust and spray mist by wearing a NIOSH approved respirator during application, sanding and clean up. Follow respirator manufacturer's directions for respirator use. Close container after each use. Wash thoroughly after handling.

WARNING Cancer and Reproductive Harmwww.P65warnings.ca.gov

FIRST AID: In case of eye contact, flush immediately with plenty of water for at least 15 minutes; for skin, wash thoroughly with soap and water. If symptoms persist, seek medical attention. If you experience difficulty breathing, leave the area to obtain fresh air. If continued difficulty is experienced, get medical attention immediately.

IN CASE OF SPILL – Absorb with inert material and dispose of as specified under "Clean Up"

KEEP OUT OF REACH OF CHILDREN PROTECT FROM FREEZING

Refer to Safety Data Sheet for additional health and safety information.

Benjamin Moore & Co., 101 Paragon Drive, Montvale, NJ 07645 Tel: (201) 573-9600 Fax: (201) 573-9046 www.benjaminmoore.com M72 N310 US 080718 Benjamin Moore, Color Preview, Fresh Start, Regal, Super Spec HP, Ultra Spec and the triangle "M" symbol are registered trademarks of Benjamin Moore & Co. © 2006, 2018 Benjamin Moore & Co. All other trademarks are registered trademarks of their respective owners. All rights reserved