



STAYS CLEAR[®]

ACRYLIC POLYURETHANE LOW LUSTRE

F423

Features

- Does not yellow like solvent based varnishes & polyurethanes.
- Tintable to many decorative shades.
- Quick dry and re-coat.
- Soap and water clean up.

Recommended For

- For commercial and residential applications
- Applicable for new or previously painted, stained, or varnished interior wood surfaces.

General Description

A premium quality product that combines the attributes of acrylic and polyurethane resins to produce a durable clear finish that dries quickly with very little odour. Provides excellent resistance to damage caused by abrasion, household chemicals, and water, alcohol or food stains. For use on new or previously painted, stained or varnished interior wood surfaces, including floors. May also be used as a protective clear coating over decorative faux finishes on any substrate.

Limitations

- Do not apply when air and surface temperatures are below 10 °C (50 °F)
- For use on wood substrates or as a protective topcoat for decorative Faux finishes only

Product Information

<p>Colours — Standard: Clear (00)</p> <p>(May be tinted with up to 2.0 fl. oz. Benjamin Moore[®] Colour Preview[®] or Gennex[®] colorants per 3.79 L.)</p>	<table border="1"> <thead> <tr> <th colspan="2">Technical Data[◇]</th> <th>Low Lustre</th> </tr> </thead> <tbody> <tr> <td>Vehicle Type</td> <td colspan="2">Acrylic Polyurethane</td> </tr> <tr> <td>Pigment Type</td> <td colspan="2">None</td> </tr> <tr> <td>Volume Solids</td> <td colspan="2">36%</td> </tr> <tr> <td>Coverage per 3.79 L at</td> <td colspan="2">32.5 – 41.8 sq. m.</td> </tr> <tr> <td>Recommended Film Thickness</td> <td colspan="2">(350 – 450 sq. ft.)</td> </tr> <tr> <td rowspan="2">Recommended Film Thickness</td> <td>– Wet</td> <td>4.0 mils</td> </tr> <tr> <td>– Dry</td> <td>1.4 mils</td> </tr> </tbody> </table>	Technical Data [◇]		Low Lustre	Vehicle Type	Acrylic Polyurethane		Pigment Type	None		Volume Solids	36%		Coverage per 3.79 L at	32.5 – 41.8 sq. m.		Recommended Film Thickness	(350 – 450 sq. ft.)		Recommended Film Thickness	– Wet	4.0 mils	– Dry	1.4 mils
Technical Data [◇]		Low Lustre																						
Vehicle Type	Acrylic Polyurethane																							
Pigment Type	None																							
Volume Solids	36%																							
Coverage per 3.79 L at	32.5 – 41.8 sq. m.																							
Recommended Film Thickness	(350 – 450 sq. ft.)																							
Recommended Film Thickness	– Wet	4.0 mils																						
	– Dry	1.4 mils																						
<p>— Tint Bases: Not available</p>	<p>Depending on surface texture and porosity. Be sure to estimate the right amount of paint for the job. This will ensure color uniformity and minimize the disposal of excess paint.</p>																							
<p>— Special Colours: Not available</p>	<table border="1"> <tbody> <tr> <td rowspan="2">Dry Time @ 25 °C (77 °F) @ 50% RH</td> <td>– To Touch</td> <td>1 Hour</td> </tr> <tr> <td>– To Recoat</td> <td>2-3 Hours</td> </tr> </tbody> </table>	Dry Time @ 25 °C (77 °F) @ 50% RH	– To Touch	1 Hour	– To Recoat	2-3 Hours																		
Dry Time @ 25 °C (77 °F) @ 50% RH	– To Touch		1 Hour																					
	– To Recoat	2-3 Hours																						
<p>Certifications & Qualifications:</p> <p>Qualifies for LEED[®] v4 Credit Qualifies for CHPS low emitting credit (Collaborative for High Performance Schools) CDPH v1 Emission Certified Class A (0-25) over non-combustible surfaces when tested in accordance with ASTM E-84 Master Painters Institute MPI # 121</p>	<p>Painted surfaces can be washed after two weeks. High humidity and cool temperatures will result in longer dry, recoat and service times. Allow final coat to harden 24 hours before subjecting to normal floor traffic.</p> <table border="1"> <tbody> <tr> <td>Dries By</td> <td colspan="2">Evaporation, Coalescence</td> </tr> <tr> <td>Viscosity</td> <td colspan="2">72 ± 2 KU</td> </tr> <tr> <td>Flash Point</td> <td colspan="2">None</td> </tr> <tr> <td>Gloss / Sheen</td> <td colspan="2">Low Lustre (35-45 @ 60°)</td> </tr> <tr> <td rowspan="2">Surface Temperature at Application</td> <td>– Min.</td> <td>10 °C (50 °F)</td> </tr> <tr> <td>– Max</td> <td>32 °C (90 °F)</td> </tr> </tbody> </table>	Dries By	Evaporation, Coalescence		Viscosity	72 ± 2 KU		Flash Point	None		Gloss / Sheen	Low Lustre (35-45 @ 60°)		Surface Temperature at Application	– Min.	10 °C (50 °F)	– Max	32 °C (90 °F)						
Dries By	Evaporation, Coalescence																							
Viscosity	72 ± 2 KU																							
Flash Point	None																							
Gloss / Sheen	Low Lustre (35-45 @ 60°)																							
Surface Temperature at Application	– Min.	10 °C (50 °F)																						
	– Max	32 °C (90 °F)																						
<p>CUSTOMER SERVICE INFORMATION CENTRE: 1-800-361-5898, info@benjaminmoore.ca, www.benjaminmoore.ca</p>	<table border="1"> <tbody> <tr> <td>Thin With</td> <td colspan="2">Clean Water</td> </tr> <tr> <td>Clean Up Thinner</td> <td colspan="2">Clean Water</td> </tr> <tr> <td>Weight Per 3.79 L</td> <td colspan="2">3.9 kg (8.8 lbs)</td> </tr> <tr> <td rowspan="2">Storage Temperature</td> <td>– Min.</td> <td>4.4 °C (40 °F)</td> </tr> <tr> <td>– Max</td> <td>32 °C (90 °F)</td> </tr> </tbody> </table> <p>Volatile Organic Compounds (VOC)</p> <p>271 Grams/Liter 1.03 kg/3.79 L</p>	Thin With	Clean Water		Clean Up Thinner	Clean Water		Weight Per 3.79 L	3.9 kg (8.8 lbs)		Storage Temperature	– Min.	4.4 °C (40 °F)	– Max	32 °C (90 °F)									
Thin With	Clean Water																							
Clean Up Thinner	Clean Water																							
Weight Per 3.79 L	3.9 kg (8.8 lbs)																							
Storage Temperature	– Min.	4.4 °C (40 °F)																						
	– Max	32 °C (90 °F)																						

◇ Reported values are for Low Lustre.

Stays Clear® Acrylic Polyurethane Low Lustre F423

Surface Preparation

Surfaces to be finished must be free from wax, dirt, grease, dust, and other contaminants. Glossy surfaces must be dulled with sandpaper or synthetic steel wool. **Do not use steel wool loose fibres will cause rusting in the finish coat.**

Note: The application of this or any clear acrylic finish over fresh alkyd coatings may cause yellowing of the basecoat.

WARNING! If you scrape, sand, or remove old paint, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by logging onto Health Canada @ <https://www.canada.ca/en/health-canada/services/environmental-workplace-health/environmental-contaminants/lead/lead-information-package-some-commonly-asked-questions-about-lead-human-health.html>

Primer/Finish Systems

Raw Wood: New interior wood must be sanded smooth. Use fine sandpaper following the grain of the wood to achieve a smooth finish. Stays Clear® may be used as both the sealer and finish on raw wood. Allow sufficient dry time before sanding lightly and applying topcoats.

Sealer: 1 coat Stays Clear® Acrylic Polyurethane

Finish: 1-2 or more coats Stays Clear® Acrylic Polyurethane

Old Finishes: Do not apply over sealers containing silicones, wax, or stearate. Remove old finishes which are chipping, peeling, or in otherwise poor condition. Remove any and all old finishes containing wax or stearate. Other finishes in good condition must be sanded lightly with fine sandpaper until smooth. Surfaces requiring complete restoration must have the finish removed by either power sanding or use of paint and varnish remover, then treated as new surface.

One-Day Finishing (Floors): Apply in thin, even coats following grain of wood. For 3 coat/1-day application, allow at least 3 hours dry time between coats. Sand lightly with fine sandpaper between applications. If sandpaper gums when sanding, insufficient drying time has been allowed between coats. Optimal conditions are 15.6 °C – 26.7 °C (60 °F to 80 °F) and 30% to 60% relative humidity. After final coat has been applied, avoid heavy traffic on floors during the initial 24 hours. In addition, care should be taken during first week after application, especially when replacing furniture.

Application

Stir thoroughly before and occasionally during use to ensure a uniform sheen.

Brush: Apply as received in the container with a good quality synthetic brush or painting pad. Apply along grain of the wood in thin, even, uniform coats. Keep a wet-edge during application and avoid working back into partially dry areas.

Roller: Large smooth surfaces can be coated using a short-nap roller in thin, even, uniform coats. Keep a wet-edge during application and avoid working back into partially dry areas.

Spray, Airless: Fluid Pressure —1,500 to 2,000 PSI;

Tip —.011 - .015 Orifice;

Allow a minimum of 2-3 hours dry; then sand lightly with the grain, before recoating. For optimal performance a minimum of two coats are required for furniture or trim.

Thinning/Cleanup

Do not thin; thinning will reduce the sealing ability of this product. Do not add other paints or solvents. Wash painting tools in warm soapy water immediately after use. Spray equipment should be given a final rinse with mineral spirits to prevent rusting.

USE COMPLETELY OR DISPOSE OF PROPERLY. Dry empty containers may be recycled in a can recycling program. Local disposal requirements vary; consult your sanitation department or state-designated environmental agency on disposal options.

Environmental, Health & Safety Information

Use only in a well ventilated area. Keep container closed when not in use. In case of spillage, absorb with inert material and dispose of in accordance with local regulations. Wash thoroughly after handling.

**KEEP OUT OF REACH OF CHILDREN
PROTECT FROM FREEZING**

**Refer to Safety Data Sheet for additional
health and safety information.**