



ULTRA SPEC[®] EXT LOW LUSTRE FINISH K455

Features

- A quality acrylic latex low lustre finish
- Provides a breathable surface for maximum durability
- Low temperature application down to 4.4 °C (40 °F)
- Blister resistant
- Excellent hiding
- Resistant to peeling and cracking
- Specially formulated to resist mildew growth on the paint film.
- Fast, simple clean up with warm soapy water
- Excellent colour retention
- Low VOC

Recommended For

Recommended for wood, hardboard, vinyl, aluminum and fibre cement sidings; unglazed brick, concrete, stucco, cinder block, and primed metal.

General Description

A professional quality 100% acrylic exterior low lustre finish. Designed for application to a wide variety of exterior surfaces as well as features excellent hiding, film durability and colour retention. Fast-dry formula allows for quick recoating as well as low temperature application. Easy soap and water cleanup.

Limitations

- Do not apply when air and surface temperatures are below 4.4 °C (40 °F).
- Do not paint vinyl siding or trim darker than the original colour
- Not for interior use

Product Information

<p>Colours — Standard: White (01)</p> <p>(May be tinted with up to 60 ml of Benjamin Moore[®] Gennex[®] colorants per 3.79 L.)</p>	<p>Technical Data Pastel Base</p>							
<p>— Tint Bases: Benjamin Moore[®] Gennex[®] bases 1X, 2X, 3X, 4X</p>	<p>Vehicle Type 100% Acrylic</p>							
<p>— Special Colours: Contact your Benjamin Moore Representative</p>	<p>Pigment Type Titanium Dioxide</p>							
<p>Certifications & Qualifications: VOC compliant in all regulated areas</p> <p>Master Painters Institute MPI # 214</p> <p>Passes ASTM D6904 Wind Driven Rain Resistance: Over one coat of Masonry Sealer</p>	<p>Volume Solids 34%</p>							
<p>Customer Information Centre: 1-800-361-5898, info@benjaminmoore.ca, www.benjaminmoore.ca.</p>	<p>Coverage per 3.79 L at Recommended Film Thickness 32.5-44.1 sq. m. (350 – 475 Sq. Ft.)</p>							
	<table border="0"> <tr> <td>Recommended Film Thickness</td> <td>– Wet</td> <td>3.9 mils</td> </tr> <tr> <td></td> <td>– Dry</td> <td>1.3 mils</td> </tr> </table>		Recommended Film Thickness	– Wet	3.9 mils		– Dry	1.3 mils
Recommended Film Thickness	– Wet	3.9 mils						
	– Dry	1.3 mils						
	<p>Depending on surface texture and porosity. Be sure to estimate the right amount of paint for the job. This will ensure colour uniformity and minimize the disposal of excess paint.</p>							
	<table border="0"> <tr> <td>Dry Time @ 25 °C (77 °F) @ 50% RH</td> <td>– To Touch</td> <td>1 Hour</td> </tr> <tr> <td></td> <td>– To Recoat</td> <td>4 Hours</td> </tr> </table>		Dry Time @ 25 °C (77 °F) @ 50% RH	– To Touch	1 Hour		– To Recoat	4 Hours
Dry Time @ 25 °C (77 °F) @ 50% RH	– To Touch	1 Hour						
	– To Recoat	4 Hours						
	<p>High humidity and cool temperatures will result in longer dry, recoat and service times.</p>							
	<p>Dries By Evaporation, Coalescence</p>							
	<p>Viscosity 105 ± 2 KU</p>							
	<p>Flash Point None</p>							
	<p>Gloss / Sheen Low Lustre (7 - 12 @ 60°)</p>							
	<table border="0"> <tr> <td>Surface Temperature at Application</td> <td>– Min.</td> <td>4.4 °C (40 °F)</td> </tr> <tr> <td></td> <td>– Max.</td> <td>32.2 °C (90 °F)</td> </tr> </table>		Surface Temperature at Application	– Min.	4.4 °C (40 °F)		– Max.	32.2 °C (90 °F)
Surface Temperature at Application	– Min.	4.4 °C (40 °F)						
	– Max.	32.2 °C (90 °F)						
	<p>Thin With See Chart</p>							
	<p>Clean Up Thinner Clean Water</p>							
	<p>Weight Per 3.79 L 4.9 kg (10.9 lbs)</p>							
	<table border="0"> <tr> <td>Storage Temperature</td> <td>– Min.</td> <td>4.4 °C (40 °F)</td> </tr> <tr> <td></td> <td>– Max.</td> <td>35 °C (95 °F)</td> </tr> </table>		Storage Temperature	– Min.	4.4 °C (40 °F)		– Max.	35 °C (95 °F)
Storage Temperature	– Min.	4.4 °C (40 °F)						
	– Max.	35 °C (95 °F)						
	<p style="text-align: center;">Volatile Organic Compounds (VOC)</p> <p style="text-align: center;">48 Grams/Litre</p>							

∅Reported values are for Pastel Base. Contact Benjamin Moore for values of other bases or colours.

Surface Preparation

Surfaces must be clean, dry and free of oil, grease, wax, rust, mildew, chalk and loose or scaling paint. Cement based water proofing paints should be removed. Glossy surfaces must be dulled. Un-weathered areas such as eaves, porch ceilings, overhangs and protected wall areas should be washed with a Benjamin Moore® Clean (K318) and rinsed with a strong stream of water from a garden hose or power washer to remove contaminants that can interfere with proper adhesion. Stains from mildew must be removed by cleaning with Benjamin Moore® Clean (K318) prior to coating the surface. **Caution:** Refer to the (K318) Clean technical data and material safety data sheets for instructions on its proper use and handling.

All new masonry surfaces must be power washed or brushed thoroughly with stiff fibre bristles to remove loose particles. New masonry substrates must be allowed to cure for 30 days before priming or painting. Poured or pre-cast concrete with a very smooth surface should be etched or abraded to promote adhesion, after removing all form release agents and curing compounds.

Difficult Substrates: Benjamin Moore offers a number of specialty primers for use over difficult substrates such as bleeding woods, grease stains, crayon markings, hard glossy surfaces, or other substrates where paint adhesion or stain suppression is a particular problem. Your Benjamin Moore® retailer can recommend the right problem-solving primer for your special needs.

WARNING! If you scrape, sand, or remove old paint, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by logging onto Health Canada @ <https://www.canada.ca/en/health-canada/services/environmental-workplace-health/environmental-contaminants/lead/lead-information-package-some-commonly-asked-questions-about-lead-human-health.html>

Primer/Finish Systems

New surfaces should be fully primed, and previously painted surfaces may be primed or spot primed as necessary. For best hiding results, tint the primer to the approximate shade of the finish coat, especially when a significant colour change is desired. **Special Note:** Certain custom colours require a Deep Colour Base Primer tinted to a special prescription formula to achieve the desired colour. Consult your retailer.

Wood and engineered wood products:

Primer: Ultra Spec® EXT latex Primer (K558), Fresh Start® Multi-Purpose Latex Primer (F023) or Fresh Start® Exterior Wood Primer (K094)

Finish: 1 or 2 coats Ultra Spec® EXT Low Lustre Finish (K455)

Bleeding Type Woods, (Redwood and Cedar):

Primer: Fresh Start® Exterior Wood Primer (K094), Fresh Start® Multi-Purpose Oil Based Primer (F024) or 1-2 coats of Fresh Start® High-Hiding All Purpose Primer (K046) may be used

Finish: 1 or 2 coats Ultra Spec® EXT Low Lustre Finish (K455)

Hardboard Siding, Bare or Factory Primed:

Primer: Ultra Spec® EXT latex Primer (K558)

Finish: 1 or 2 coats Ultra Spec® EXT Low Lustre Finish (K455)

Vinyl Siding & Vinyl Composite

Note: Do not paint vinyl siding or trim darker than the original colour.

Primer: Fresh Start® Multi-Purpose Latex Primer (F023)

Finish: 1 or 2 coats Ultra Spec® EXT Low Lustre Finish (K455)

Rough or Pitted Masonry:

Primer: Ultra Spec® Hi-Build Masonry Block Filler (K571)

Finish: 1 or 2 coats Ultra Spec® EXT Low Lustre Finish (K455)

Poured or Pre-cast Concrete and Fibre Cement Siding:

Primer: Ultra Spec® EXT latex Primer (K558) or Fresh Start® Multi-Purpose Latex Primer (F023)

Finish: 1 or 2 coats Ultra Spec® EXT Low Lustre Finish (K455)

Ferrous Metal (Steel and Iron):

Primer: Ultra Spec® HP Acrylic Metal Primer (FP04) or Super Spec HP® Alkyd Metal Primer (KP06)

Finish: 1 or 2 coats Ultra Spec® EXT Low Lustre Finish (K455)

Non-Ferrous Metal (Galvanized & Aluminum): All new metal surfaces must be thoroughly cleaned with Corotech® Oil & Grease Emulsifier (V600) to remove contaminants. New shiny non-ferrous metal surfaces that will be subject to abrasion should be dulled with very fine sandpaper or a synthetic steel wool pad to promote adhesion.

Primer: Ultra Spec® HP Acrylic Metal Primer (FP04)

Finish: 1 or 2 Ultra Spec® EXT Low Lustre Finish (K455)

Repaint, All Substrates: Prime bare areas with the primer recommended for the substrate above.

Application

Stir thoroughly before and during use. Apply one or two coats. **Paint Application:** For best results, use a premium Benjamin Moore® custom-blended nylon/polyester brush, premium Benjamin Moore® roller, or a similar product. Apply paint generously from unpainted area into wet area. This product can also be sprayed.

Conditioning with Benjamin Moore® K518 Extender may be necessary under certain conditions to adjust open time or spray characteristics.		
The chart below is for general guidance		
	Mild conditions	Severe Conditions
	Humid (RH> 50%) with no direct sunlight & with little to no wind	Dry (RH<50%), in direct sunlight, or windy conditions
Brush: Nylon / Polyester	No thinning necessary	Add K518 Extender or water:
Roller: Premium Quality		Max of 240 ml (8 fl. oz.) to a 3.79 L of paint
Spray: Airless Pressure: 1,500 – 2,500 psi Tip: .013 - .017		Never add other paints or solvents.

Thinning/Clean up

Cleanup: Clean up with warm soapy water. Spray equipment should be given a final rinse with mineral spirits to prevent rusting.

Environmental Health & Safety Information

Use only in a well ventilated area. Keep container closed when not in use. In case of spillage, absorb with inert material and dispose of in accordance with local regulations. Wash thoroughly after handling.

WARNING: This product contains isothiazolinone compounds at levels of <0.1%. These substances are biocides commonly found in most paints and a variety of personal care products as a preservative. Certain individuals may be sensitive or allergic to these substances, even at low levels.

**KEEP OUT OF REACH OF CHILDREN
PROTECT FROM FREEZING**

**Refer to Safety Data Sheet for additional
health and safety information.**