

Washable

Quick dry

levelling

credit

Easy application

Superior flow and

Soap and water clean up

Qualifies for LEED® v4

٠

Features

- Zero VOC
- Low odour
- Excellent hiding
- · Great touch up
- Spatter resistant
- Decorative and uniform low sheen eggshell finish

Recommended For

Interior wall and ceiling surfaces in commercial and institutional environments where a washable Low Sheen Eggshell Finish is desired. For use on primed or previously painted drywall, plaster, wood, metal and wallpapered surfaces.

ULTRA SPEC[®] 500 INTERIOR LOW SHEEN EGGSHELL K537

General Description

A professional-quality interior waterborne low sheen eggshell finish based on a proprietary cross-linking acrylic resin that tints on the Gennex[®] zero VOC colorant system. This waterborne interior Low Sheen Eggshell Finish provides the wash ability of a semi-gloss in a softer sheen. The product qualifies for LEED[®] v4 credit and passes the most stringent environmental standards in any colour. Because[®] 500 finishes are available in any colour without an increase in VOC.

Limitations

 Do not apply when air and surface temperatures are below 10 °C (50 °F)

Product Information						
Colours — Standard:			Technical Data◊	White		
White (01)			Vehicle Type	Acrylic Copolyme		
— Tint Bases: Benjamin Moore [®] Gennex [®] bases 0X, 1X, 2X, 3X & 4X			Pigment Type	Titanium Dioxide		
			Volume Solids	42 ± 2 %		
— Special Colours:				Coverage per 3.79 L at32.5 - 37.1 sq. m.Recommended Film Thickness350 - 400 sq. ft.		
Contact your Benjamin Moore® representative			Recommended Film Thickness	– Wet 4.3 mile		
Certifications & Qualifications:				– Dry 1.8 mils		
VOC compliant in all regulated areas Zero VOC				Depending on surface texture and porosity. Be sure to estimate the right amount of paint for the job. This will ensure colour uniformity and minimize the disposal of excess paint.		
Class A (0-25) over non-combustible surfaces when tested in accordance with ASTM E-84				Dry Time @ 25 °C (77 °F) @ 50 % RH	– To Touch 2 Hours	
Master Painters Institute MPI # 44, 44 X-Green, 144, 144 X-Green [™]			– To Recoat 2 – 3 Hours			
Master Painters Institute High Performance # 138, 138 X-Green [™]				Painted surfaces can be washed after two weeks. High humidity and cool temperatures will result in longer dry, recoat and service times.		
Cradle to Cradle			Dries By	Coalescence		
Certified [™] Silver				Viscosity	93 ± 5 Kl	
				Flash Point	N/A	
	Benjamin Moore's Green Promise® designation is our				Low Sheen (15 – 20 @ 85°	
company's assurance that this product meets – and often exceeds – rigorous environmental and				Surface Temperature at Application	– Min. 10 °C (50 °F	
performance criteria regarding VOCs, emissions, application, washability, scrubbability and packaging, while also delivering the premium levels of performance you expect from Benjamin Moore.			– Max. 32.2 °C (90 °F			
			Thin With	See Char		
			Clean Up Thinner	Clean Wate		
		Qualifies for CHPS		Weight Per 3.79 L	5.28 kg (11.7 lbs	
Eligible for LEED [®] v4 Credit	CDPH v1 Emissions Certified	low emitting credit (Collaborative for High Performance Schools)	VOC (in any colour)	Storage Temperature	– Min. 4.4 °C (40 °F	
					– Max. 32.2 °C (90 °F	
YES	YES	YES	<50 g/L	Volatile Organi	ic Compounds (VOC)	
This Benjamin Moore product has been tested by independent third parties and meets or exceeds the published chemical restriction and performance criteria of the						
Green Seal™ GS-11 2015 standard				0 g/L		
Customer Information Centre: 1-800-361-5898, info@benjaminmoore.ca, www.benjaminmoore.ca				Zero VOC post tint (any base and any colour)		

 $\Diamond \mbox{Reported values are for White. Contact Benjamin Moore for values of other bases or colour$

Surface Preparation

Surfaces to be painted must be clean, dry, and free of dirt, dust, grease, oil, soap, wax, scaling paint, water-soluble materials, and mildew. Remove any peeling or scaling paint and sand these areas to feather edges smooth with adjacent surfaces. Glossy areas should be dulled. Drywall surfaces must be free of sanding dust.

New plaster or masonry surfaces must be allowed to cure 30 days before applying base coat. Cured plaster should be hard, have a slight sheen and maximum PH of 10; soft, porous or powdery plaster indicates improper cure. Never sand a plaster surface; knife off any protrusions and prime plaster before and after applying patching compound. Poured or pre-cast concrete with a very smooth surface should be etched or abraded to promote adhesion, after removing all form release agents and curing compounds. Remove any powder or loose particles before priming. Wood substrates must be thoroughly dry.

Difficult Substrates: Benjamin Moore offers a variety of specialty primers for use over difficult substrates such as bleeding woods, grease stains, crayon markings, hard glossy surfaces, galvanized metal or other substrates where paint adhesion or stain suppression is a particular problem. Your Benjamin Moore[®] retailer can recommend the right problem-solving primer for your special needs.

WARNING! If you scrape, sand, or remove old paint, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by logging onto Health Canada @ https://www.canada.ca/en/health-canada/services/environmental-workplace-health/environmental-contaminants/lead/lead-information-package-some-commonly-asked-questions-about-lead-human-health.html

Primer/Finish Systems

New surfaces should be fully primed, and previously painted surfaces may be primed or spot primed as necessary. For best hiding results, tint the primer to the approximate shade of the finish coat, especially when a significant colour change is desired. **Special Note:** Certain custom colours require a Deep Colour Base Primer tinted to a special prescription formula to achieve the desired colour. Consult your retailer.

Wood and Engineered Wood Products

Primer: Ultra Spec[®] 500 Interior Latex Primer (K534) or Fresh Start[®] All-Purpose Alkyd Primer (F024)

Finish: 1 or 2 coats Ultra Spec[®] 500 Interior Low Sheen Eggshell Finish (K537)

Drywall

Primer: Ultra Spec® 500 Interior Latex Primer (K534)

Finish: 1 or 2 coats Ultra Spec[®] 500 Interior Low Sheen Eggshell Finish (K537)

Plaster (Cured)

Primer: Ultra Spec[®] 500 Interior Latex Primer (K534) or Fresh Start[®] Multi-Purpose Latex Primer (F023)

Finish: 1 or 2 coats Ultra Spec® 500 Interior Low Sheen Eggshell Finish (K537)

Rough or Pitted Masonry

Primer: Ultra Spec[®] Masonry Interior/Exterior Hi-Build Block Filler (K571)

Finish: 1 or 2 coats Ultra Spec[®] 500 Interior Low Sheen Eggshell Finish (K537)

Smooth Poured or Precast Concrete

Primer: Ultra Spec[®] 500 Interior Latex Primer (K534) or Fresh Start[®] Multi-Purpose Latex Primer (F023)

Finish: 1 or 2 coats Ultra Spec[®] 500 Interior Low Sheen Eggshell Finish (K537)

Ferrous Metal (Steel and Iron)

Primer: Ultra Spec[®] HP Acrylic Metal Primer (FP04) or Super Spec HP[®] Alkyd Metal Primer (KP06) **Finish:** 1 or 2 coats Ultra Spec[®] 500 Interior Low Sheen Eggshell Finish (K537)

Non-Ferrous Metal (Galvanized & Aluminum)

All new metal surfaces must be thoroughly cleaned with Corotech[®] Oil & Grease Emulsifier (V600) to remove contaminants. New shiny non-ferrous metal surfaces that will be subject to abrasion should be dulled with very fine sandpaper or a synthetic steel wool pad to promote adhesion.

Primer: Ultra Spec[®] HP Acrylic Metal Primer (FP04) Finish: 1 or 2 coats Ultra Spec[®] 500 Interior Low Sheen Eggshell Finish (K537)

Repaint, All Substrates: Prime bare areas with the primer recommended for the substrate above.

Application

Stir thoroughly before use. Apply one or two coats. For best results, use a Benjamin Moore[®] Professional custom-blended nylon/ polyester brush, Benjamin Moore[®] Professional roller, or a similar product. This product can also be sprayed.

Thinning/Clean Up

Conditioning with Benjamin Moore® K518 Extender may be necessary under certain conditions to adjust open time or spray characteristics. The chart below is for general guidance						
	Mild conditions	Severe conditions				
	Humid (RH> 50 %) with no direct sunlight & with little to no wind	Dry (RH<50 %), in direct sunlight, or windy conditions				
Brush: Nylon / Polyester Roller: Premium Quality 10 mm roller cover	No thinning necessary	Add K518 Extender or water: Max of 236 ml to a 3.79 L of paint				
Spray: Airless Pressure: 1,500–2,500 psi Tip: 0.013-0.017		Never add other paints or solvents.				

Thinning is unnecessary, but if required to obtain desired application properties, a small amount of clean water may be added. Never add other paints or solvents.

Clean Up: Use soap and water. Spray equipment should be given a final rinse with mineral spirits to prevent corrosion.

Environmental Health & Safety Information

Use only in a well ventilated area. Keep container closed when not in use. In case of spillage, absorb with inert material and dispose of in accordance with local regulations. Wash thoroughly after handling.

KEEP OUT OF REACH OF CHILDREN PROTECT FROM FREEZING

Refer to Safety Data Sheet for additional health and safety information.

Benjamin Moore & Co., Ltd. 8775 Keele St., Concord, ON L4K 2N1 1-800-361-5898 <u>www.benjaminmoore.ca</u> M72 K537 CE 041320 Benjamin Moore, Fresh Start, Gennex, Green Promise, Super Spec HP, Ultra Spec and the triangle "M" symbol are registered trademarks of Benjamin Moore & Co., Ltd. Cradle to Cradle Certified is a certification mark licensed by the Cradle to Cradle Products Innovation Institute. All other marks belong to their respective owners. © 2015, 2020 Benjamin Moore & Co., Ltd. All rights Reserved.