

Features

- Zero VOC
- Low odour
- Excellent hiding
- Spatter resistant
- Decorative and uniform semialoss finish

Customer Information Centre:

1-800-361-5898, info@benjaminmoore.ca, www.benjaminmoore.ca

- Quick dry
- Easy application
- Soap and water clean up
- MPI Approved
- Washable
- Eligible for LEED® v4 credit

Interior door, trim, cabinet, wall and ceiling surfaces in commercial and

ULTRA SPEC® 500 INTERIOR SEMI-GLOSS FINISH K539

General Description

A professional-quality interior waterborne semi-gloss finish based on a proprietary cross-linking acrylic resin that tints on the Gennex® zero VOC colorant system. This waterborne interior semi-gloss has excellent stain release so it washes clean easily. The product is eligible for LEED® v4 credit and passes the most stringent environmental standards in any colour. Because it tints on our Gennex® waterborne colorant system all Ultra Spec® 500 finishes are available in any colour without an increase in VOC.

Limitations

• Do not apply when air and surface temperatures are below 10 °C (50 °F)

Product Information White Colours — Standard: Technical Data◊ White (01) Vehicle Type Acrylic Copolymer Titanium Dioxide - Tint Bases: Pigment Type Benjamin Moore® Gennex® bases 1X, 2X, 3X & 4X Volume Solids 41 ± 2% 32.5 - 37.1 sq. m. Coverage per 3.79 L at — Special Colours: Recommended Film Thickness (350 - 400 sq. ft.) Contact your Benjamin Moore representative – Wet Recommended Film 4.3 mils Thickness Dry 1.8 mils **Certifications & Qualifications:** VOC compliant in all regulated areas Depending on surface texture and porosity. Be sure to estimate the right amount of paint for the job. This will ensure colour uniformity Zero VOC and minimize the disposal of excess paint. Class A (0-25) over non-combustible surfaces when tested in accordance with Dry Time @ 25 °C - To Touch 2 Hours ASTM F-84 (77 °F) @ 50% RH - To Recoat 4 Hours Master Painters Institute MPI # 43, 43 X-Green[™], 146, 146 X-Green[™] Master Painters Institute High Performance # 140, 140 X-Green™ Painted surfaces can be washed after two weeks. High humidity and cool temperatures will result in longer dry, recoat and service times. Benjamin Moore's Green Promise® designation is our Dries By Coalescence company's assurance that this product meets - and often exceeds - rigorous environmental and Viscosity $93 \pm 3 \, KU$ performance criteria regarding VOCs, emissions, Flash Point N/A application, washability, scrubbability and packaging, Gloss / Sheen Semi-Gloss (20 - 35 @ 60°) while also delivering the premium levels of performance you expect from Benjamin Moore. - Min. 10 °C (50 °F) Surface Temperature at Application - Max. 32.2 °C (90 °F) **Qualifies for CHPS** Eligible for CDPH v1 VOC low emitting credit Thin With See Chart LEED® v4 Credit **Emissions Certified** (in any colour) (Collaborative for High Clean Up Thinner Clean Water Performance Schools) Weight Per 3.79 L 5.1 kg (11.2 lbs) YES This Benjamin Moore product has been tested by independent third parties and meets or 4.4 °C (40 °F) - Min. Storage Temperature exceeds the published chemical restriction and performance criteria of the - Max. 32.2 °C (90 °F) Green Seal™ GS-11 2015 standard

Volatile Organic Compounds (VOC)

0 g/L

Zero VOC post tint (any base and any colour)

values of other bases or colour.

Recommended For

institutional environments where a washable semi-gloss finish is desired. For use on primed or previously painted drywall, plaster, wood, metal and wallpapered surfaces.

♦Reported values are for White. Contact Benjamin Moore for

Surface Preparation

Surfaces to be painted must be clean, dry, and free of dirt, dust, grease, oil, soap, wax, scaling paint, water-soluble materials, and mildew. Remove any peeling or scaling paint and sand these areas to feather edges smooth with adjacent surfaces. Glossy areas should be dulled. Drywall surfaces must be free of sanding dust.

New plaster or masonry surfaces must be allowed to cure 30 days before applying base coat. Cured plaster should be hard, have a slight sheen and maximum PH of 10; soft, porous or powdery plaster indicates improper cure. Never sand a plaster surface; knife off any protrusions and prime plaster before and after applying patching compound. Poured or pre-cast concrete with a very smooth surface should be etched or abraded to promote adhesion, after removing all form release agents and curing compounds. Remove any powder or loose particles before priming. Wood substrates must be thoroughly dry.

Difficult Substrates: Benjamin Moore offers a variety of specialty primers for use over difficult substrates such as bleeding woods, grease stains, crayon markings, hard glossy surfaces, galvanized metal or other substrates where paint adhesion or stain suppression is a particular problem. Your Benjamin Moore® retailer can recommend the right problem-solving primer for your special needs.

WARNING! If you scrape, sand, or remove old paint, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by logging onto Health Canada @ https://www.canada.ca/en/health-canada/services/environmental-workplace-health/environmental-contaminants/lead/lead-information-package-some-commonly-asked-questions-about-lead-human-health.html

Primer/Finish Systems

New surfaces should be fully primed, and previously painted surfaces may be primed or spot primed as necessary. For best hiding results, tint the primer to the approximate shade of the finish coat, especially when a significant colour change is desired. **Special Note**: Certain custom colours require a Deep Colour Base Primer tinted to a special prescription formula to achieve the desired colour. Consult your retailer.

Wood, and engineered wood products

Primer: Ultra Spec[®] 500 Interior Latex Primer (K534) or Fresh Start[®] All-Purpose Alkyd Primer (F024)

Finish: 1 or 2 coats Ultra Spec® 500 Interior Semi-Gloss Finish (K539)

Drywall

Primer: Ultra Spec® 500 Interior Latex Primer (K534) or Fresh Start®

Multi-Purpose Latex Primer (F023)

Finish: 1 or 2 coats Ultra Spec® 500 Interior Semi-Gloss Finish (K539)

Plaster (Cured)

Primer: Ultra Spec® 500 Interior Latex Primer (K534) or Fresh Start®

Multi-Purpose Latex Primer (F023)

Finish: 1 or 2 coats Ultra Spec® 500 Interior Semi-Gloss Finish (K539)

Rough or Pitted Masonry

Primer: Ultra Spec® Masonry Interior/Exterior Hi-Build Block Filler (K571) Finish: 1 or 2 coats Ultra Spec® 500 Interior Semi-Gloss Finish (K539)

Smooth Poured or Precast Concrete

Primer: Ultra Spec® 500 Interior Latex Primer (K534) or Fresh Start®

Multi-Purpose Latex Primer (F023)

Finish: 1 or 2 coats Ultra Spec® 500 Interior Semi-Gloss Finish (K539)

Ferrous Metal (Steel and Iron)

Primer: Ultra Spec® HP Acrylic Metal Primer (FP04) or Super Spec HP®

Alkyd Metal Primer (KP06)

Finish: 1 or 2 coats Ultra Spec® 500 Interior Semi-Gloss Finish (K539)

Non-Ferrous Metal (Galvanized & Aluminum)

All new metal surfaces must be thoroughly cleaned with Corotech® Oil & Grease Emulsifier (V600) to remove contaminants. New shiny nonferrous metal surfaces that will be subject to abrasion should be dulled with very fine sandpaper or a synthetic steel wool pad to promote adhesion.

Primer: Ultra Spec® HP Acrylic Metal Primer (FP04)

Finish: 1 or 2 coats Ultra Spec® 500 Interior Semi-Gloss Finish (K539)

Repaint, All Substrates: Prime bare areas with the primer

recommended for the substrate above.

Application

Stir thoroughly before use. Apply one or two coats. For best results, use a Benjamin Moore® Professional custom-blended nylon/polyester brush, Benjamin Moore® Professional roller, or a similar product. This product can also be sprayed.

Conditioning with Denismin Moore® VE40 Extender may be personal.		
Conditioning with Benjamin Moore® K518 Extender may be necessary under certain conditions to adjust open time or spray characteristics.		
The chart below is for general guidance		
	Mild conditions	Severe conditions
	Humid (RH> 50%) with no	Dry (RH<50%), in
	direct sunlight & with little to	direct sunlight, or
	no wind	windy conditions
Brush:		
Nylon /		
Polyester		Add K518 Extender
Roller:		or water:
Premium		
Quality	No thinning	Max of 236 ml to a
10 mm roller	necessary	3.79 L of paint
cover	,	·
Spray: Airless		Never add other
Pressure:		paints or solvents.
1,500-2,500 psi		-
Tip: 0.013-0.017		

Thinning/Clean Up

Thinning is unnecessary, but if required to obtain desired application properties, a small amount of clean water may be added. Never add other paints or solvents.

Clean up: Use soap and water. Spray equipment should be given a final rinse with mineral spirits to prevent corrosion.

USE COMPLETELY OR DISPOSE OF PROPERLY. Dry empty containers may be recycled in a can recycling program. Local disposal requirements vary; consult your sanitation department or state-designated environmental agency on disposal options.

Environmental Health & Safety Information

May cause allergic skin reaction.

Do not get on skin or clothing.

Use only in a well ventilated area. Keep container closed when not in use. In case of spillage, absorb with inert material and dispose of in accordance with local regulations. Wash thoroughly after handling.

WARNING: This product contains isothiazolinone compounds at levels of <0.1%. These substances are biocides commonly found in most paints and a variety of personal care products as a preservative. Certain individuals may be sensitive or allergic to these substances, even at low levels.

KEEP OUT OF REACH OF CHILDREN PROTECT FROM FREEZING

Refer to Safety Data Sheet for additional health and safety information.