



ben[®]
100% ACRYLIC EXTERIOR
FLAT FINISH K541

Features

- Low temperature application down to 4.4 °C (40 °F)
- Resistant to peeling and cracking
- Excellent hide and colour retention
- Blister resistant
- Resists new mildew formation
- Soap and water clean-up
- 25 Year warranty

Recommended For

For exterior surfaces such as new or previously painted wood, hardboard siding, cured masonry, and unglazed brick.

General Description

A premium quality 100% acrylic latex flat house paint designed for application to a wide variety of exterior surfaces such as wood, hardboard, vinyl and aluminum siding, shingles, unglazed brick, concrete, stucco, cinder block, and primed metal. Provides a breathable surface for maximum durability.

Limitations

- Do not apply when air and surface temperatures are below 4.4 °C (40 °F).
- Not for interior use

Product Information

<p>Colours — Standard: White (01)</p> <p>(May be tinted with up to 60 ml of Benjamin Moore[®] Gennex[®] colorants per 3.79L.)</p>	<p>Technical Data[∅]</p>	<p>Pastel Base</p>						
<p>— Tint Bases: Benjamin Moore[®] Gennex[®] bases 1X, 2X, 3X & 4X</p>	<table border="1"> <tr> <td>Vehicle Type</td> <td>100% Acrylic Latex</td> </tr> <tr> <td>Pigment Type</td> <td>Titanium Dioxide</td> </tr> <tr> <td>Volume Solids</td> <td>34.5%</td> </tr> </table>	Vehicle Type	100% Acrylic Latex	Pigment Type	Titanium Dioxide	Volume Solids	34.5%	
Vehicle Type	100% Acrylic Latex							
Pigment Type	Titanium Dioxide							
Volume Solids	34.5%							
<p>— Special Colours: Contact your Benjamin Moore representative</p>	<table border="1"> <tr> <td>Coverage per 3.79 L at Recommended Film Thickness</td> <td>32.5 – 44.1 sq. m. (350-475 sq. ft.)</td> </tr> <tr> <td>Recommended Film Thickness</td> <td>– Wet 3.8 mils – Dry 1.3 mils</td> </tr> </table>	Coverage per 3.79 L at Recommended Film Thickness	32.5 – 44.1 sq. m. (350-475 sq. ft.)	Recommended Film Thickness	– Wet 3.8 mils – Dry 1.3 mils			
Coverage per 3.79 L at Recommended Film Thickness	32.5 – 44.1 sq. m. (350-475 sq. ft.)							
Recommended Film Thickness	– Wet 3.8 mils – Dry 1.3 mils							
<p>Certifications & Qualifications: VOC compliant in all regulated areas</p> <p>Master Painters Institute MPI # 10 Water vapor permeance ASTM D1653: 47 perms Wind driven rain ASTM D6904 (1 coat masonry primer/1 coat K541)</p>	<p>Depending on surface texture and porosity. Be sure to estimate the right amount of paint for the job. This will ensure colour uniformity and minimize the disposal of excess paint.</p>							
<p>Customer Service Information Centre: 1-800-361-5898, info@benjaminmoore.ca, www.benjaminmoore.ca.</p>	<table border="1"> <tr> <td>Dry Time @ 25 °C (77 °F) @ 50% RH</td> <td>– To Touch 1 Hour – To Recoat 4 Hours</td> </tr> </table> <p>High humidity and cool temperatures will result in longer dry, recoat and service times.</p>	Dry Time @ 25 °C (77 °F) @ 50% RH	– To Touch 1 Hour – To Recoat 4 Hours					
Dry Time @ 25 °C (77 °F) @ 50% RH	– To Touch 1 Hour – To Recoat 4 Hours							
	<p>Dries By Evaporation, Coalescence</p>							
	<p>Viscosity (Zahn 2) 105 ± 3 KU</p>							
	<p>Flash Point N/A</p>							
	<p>Gloss / Sheen Flat (0.5 – 2.5 @ 85°)</p>							
	<table border="1"> <tr> <td>Surface Temperature at Application</td> <td>– Min. 4.4 °C (40 °F) – Max. 32.2 °C (90 °F)</td> </tr> </table>	Surface Temperature at Application	– Min. 4.4 °C (40 °F) – Max. 32.2 °C (90 °F)					
Surface Temperature at Application	– Min. 4.4 °C (40 °F) – Max. 32.2 °C (90 °F)							
	<p>Thin With See Chart</p>							
	<p>Clean Up Thinner Clean Water</p>							
	<p>Weight Per 3.79 L 5 kg (11 lbs)</p>							
	<table border="1"> <tr> <td>Storage Temperature</td> <td>– Min. 4.4 °C (40 °F) – Max. 35 °C (95 °F)</td> </tr> </table>	Storage Temperature	– Min. 4.4 °C (40 °F) – Max. 35 °C (95 °F)					
Storage Temperature	– Min. 4.4 °C (40 °F) – Max. 35 °C (95 °F)							
	<p>Volatile Organic Compounds (VOC)</p> <p>44 g/L</p>							

[∅]Reported values are for Pastel Base. Contact Benjamin Moore for values of other bases or colours.

Surface Preparation

Surfaces must be clean, dry and free of oil, grease, wax, rust, mildew, chalk and loose or scaling paint. Cement based water proofing paints should be removed. Glossy surfaces must be dulled. Un-weathered areas such as eaves, porch ceilings, overhangs and protected wall areas should be washed with a Benjamin Moore® Clean (K318) and rinsed with a strong stream of water from a garden hose or power washer to remove contaminants that can interfere with proper adhesion. Stains from mildew must be removed by cleaning with Benjamin Moore® Clean (K318) prior to coating the surface. **Caution:** Refer to the (K318) Clean technical data and material safety data sheets for instructions on its proper use and handling.

All masonry surfaces must be power washed or brushed thoroughly with stiff fibre bristles to remove loose particles. New masonry substrates must be allowed to cure for 30 days before priming or painting. Poured or pre-cast concrete with a very smooth surface should be etched or abraded to promote adhesion, after removing all form release agents and curing compounds.

Difficult Substrates: Benjamin Moore offers a number of specialty primers for use over difficult substrates such as bleeding woods, grease stains, crayon markings, hard glossy surfaces, or other substrates where paint adhesion or stain suppression is a particular problem. Your Benjamin Moore retailer can recommend the right problem-solving primer for your special needs.

WARNING! If you scrape, sand, or remove old paint, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by logging onto Health Canada @ <https://www.canada.ca/en/health-canada/services/environmental-workplace-health/environmental-contaminants/lead/lead-information-package-some-commonly-asked-questions-about-lead-human-health.html>.

Primer/Finish Systems

New surfaces should be fully primed, and previously painted surfaces may be primed or spot primed as necessary. For best hiding results, tint the primer to the approximate shade of the finish coat, especially when a significant colour change is desired. **Special Note:** Certain custom colours require a Deep Colour Base Primer tinted to a special prescription formula to achieve the desired colour. Consult your retailer.

Wood and engineered wood products:

Primer: Fresh Start® High-Hiding All Purpose Primer (K046) or Fresh Start® Multi-Purpose Latex Primer (F023)

Finish: 1 or 2 coats of ben® Exterior 100% Acrylic Flat Finish (K541)

Bleeding Type Woods, (Redwood and Cedar):

Primer: Fresh Start® Exterior Wood Primer (K094) or 1-2 coats of

Fresh Start® High-Hiding All Purpose Primer (K046) may be used

Finish: 1 or 2 coats of ben® Exterior 100% Acrylic Flat Finish (K541)

Hardboard Siding, Bare or Factory Primed:

Primer: Fresh Start® High-Hiding All Purpose Primer (K046) or

Fresh Start® Multi-Purpose Latex Primer (F023)

Finish: 1 or 2 coats of ben® Exterior 100% Acrylic Flat Finish (K541)

Vinyl & Vinyl Composite Siding:

Note: Do not paint vinyl siding or trim darker than the original colour.

Primer: Fresh Start® Multi-Purpose Latex Primer (F023)

Finish: 1 or 2 coats of ben® Exterior 100% Acrylic Flat Finish (K541)

Rough or Pitted Masonry:

Primer: Ultra Spec® Masonry Interior/Exterior Hi-Build Block Filler (K571)

Finish: 1 or 2 coats of ben® Exterior 100% Acrylic Flat Finish (K541)

Poured or Pre-cast Concrete and Fibre Cement Siding:

Primer: Fresh Start® Multi-Purpose Latex Primer (F023)

Finish: 1 or 2 coats of ben® Exterior 100% Acrylic Flat Finish (K541)

Ferrous Metal (Steel and Iron):

Primer: Ultra Spec® HP Acrylic Metal Primer (FP04) or Super Spec HP® Alkyd Metal Primer (KP06)

Finish: 1 or 2 coats of ben® Exterior 100% Acrylic Flat Finish (K541)

Non-Ferrous Metal (Galvanized & Aluminum): All new metal surfaces must be thoroughly cleaned with Corotech® Oil & Grease Emulsifier (V600) to remove contaminants. New shiny non-ferrous metal surfaces that will be subject to abrasion should be dulled with very fine sandpaper or a synthetic steel wool pad to promote adhesion

Primer: No primer needed

Finish: 1 or 2 coats of ben® Exterior 100% Acrylic Flat Finish (K541)

Repaint, All Substrates: Prime bare areas with the primer recommended for the substrate above.

Application

Stir thoroughly before and during use. Apply one or two coats.

Paint Application: For best results, use a premium Benjamin Moore® custom-blended nylon/polyester brush, premium Benjamin Moore® roller, or a similar product. Apply paint generously from unpainted area into wet area. This product can also be sprayed. Refer to the chart below for application recommendations.

Thinning/Clean up

Conditioning with Benjamin Moore® K518 Extender may be necessary under certain conditions to adjust open time or spray characteristics. The chart below is for general guidance		
	Mild conditions	Severe conditions
	Humid (RH> 50%) with no direct sunlight & with little to no wind	Dry (RH<50%), in direct sunlight, or windy conditions
Brush: Nylon / Polyester	No thinning necessary	Add K518 Extender or water: Max of 236 ml to a 3.79 L Never add other paints or solvents.
Roller: Premium Quality		
Spray: Airless Pressure: 1,500 -2,500 psi Tip: 0.013-0.017		

Clean Up: Clean up with warm soapy water. Spray equipment should be given a final rinse with mineral spirits to prevent rusting.

Environmental Health & Safety Information

May cause allergic skin reaction.

Do not get on skin or clothing.

Use only in a well ventilated area. Keep container closed when not in use. In case of spillage, absorb with inert material and dispose of in accordance with local regulations. Wash thoroughly after handling.

**KEEP OUT OF REACH OF CHILDREN
PROTECT FROM FREEZING**

**Refer to Safety Data Sheet for additional
health and safety information.**