

Features

- Low temperature application down to 1.7 °C (35 °F)
- Resistant to peeling and cracking
- Excellent hide and colour retention
- Rlister resistant
- Resists new mildew formation
- Soap and water clean-up
- 25 Year warranty

Recommended For

For exterior surfaces such as new or previously painted wood, hardboard siding, cured masonry, and unglazed brick.

100% ACRYLIC EXTERIOR FLAT FINISH K541

General Description

A premium qaulity100% acrylic latex flat house paint designed for application to a wide variety of exterior surfaces such as wood, hardboard, vinyl and aluminum siding, shingles, unglazed brick, concrete, stucco, cinder block, and primed metal. Provides a breathable surface for maximum durability.

Limitations

Do not apply when air and surface temperatures are below 1.7 °C (35 °F).

Pastel Base

100% Acrylic Latex

Titanium Dioxide

32.5 - 44.1 sq. m.

(350 - 475 sq. ft.)

Evaporation, Coalescence

Flat (0.5 - 2.5 @ 85°)

34.5%

3.8 mils

1.3 mils

1 Hour

4 Hours

105 ± 3 KU

1.7 °C (35 °F)

See Chart

Clean Water

5 kg (11 lbs)

4.4 °C (40 °F)

35 °C (95 °F)

37.7 °C (100 °F)

N/A

Not for interior use **Product Information** Colours — Standard: Technical Data◊ White (01) Vehicle Type Pigment Type (May be tinted with up to 60 ml of Benjamin Moore® Gennex® colorants per 3.79L.) Volume Solids - Tint Bases: Coverage per 3.79 L at Recommended Film Thickness Benjamin Moore® Gennex® bases 1X, 2X, 3X & 4X Recommended Film Wet — Special Colours: **Thickness** - Drv Contact your Benjamin Moore representative Depending on surface texture and porosity. Be sure to estimate the right amount of paint for the job. This will ensure colour uniformity **Certifications & Qualifications:** and minimize the disposal of excess paint. VOC compliant in all regulated areas Dry Time @ 25 °C To Touch Master Painters Institute MPI # 10 (77 °F) @ 50% RH - To Recoat Water vapor permeance ASTM D1653: 47 perms High humidity and cool temperatures will result in longer dry, recoat and service times Wind driven rain ASTM D6904 (1 coat masonry primer/1 coat K541) Dries By Early Rain Resistance: 1 ½ - 2 hours after application over wood, primed surfaces or previously painted surfaces (25 °C / 50% RH) Viscosity (Zahn 2) - Other surfaces such as hardboard or vinyl may require a longer dry time Flash Point Passes ASTM D3273 / D3274 Mildew, Mould Resistance Tests Gloss / Sheen (no growth) - Min. Surface Temperature at Application - Max 25 YEAR WARRANTY: Benjamin Moore & Co., Limited warrants that this product when used in accordance with the label instructions, will not: 1. blister from properly Thin With prepared and primed surfaces, 2. peel from properly prepared and primed surfaces, and 3. wear down or weather to expose the previously painted surface. This warranty Clean Up Thinner shall be effective for 25 years and is made to the original residential consumer paint purchaser. This warranty is non-transferable. If this product fails to perform as Weight Per 3.79 L explained above when used according to label instructions within the warranty period, - Min. Benjamin Moore & Co., Limited will, upon presentation of proof of purchase (original Storage Temperature sales receipt), provide an equivalent or comparable product at no charge. Since we Max.

Volatile Organic Compounds (VOC)

44 g/L

Customer Service Information Centre:

have other rights, which vary from province to province.

1-800-361-5898, info@benjaminmoore.ca, www.benjaminmoore.ca.

have no control over surface preparation or application, THIS LIMITED WARRANTY DOES NOT INCLUDE THE COST OF LABOUR FOR APPLICATION OF PAINT. BENJAMIN MOORE SHALL IN NO EVENT BE LIABLE FOR INDIRECT, SPECIAL, INCIDENTAL OR CONSEQUENTIAL DAMAGES. SOME PROVINCES DO NOT

ALLOW THE EXCLUSION OF INCIDENTAL OR CONSEQUENTIAL DAMAGES, SO THE LIMITATIONS OR EXCLUSIONS CONTAINED IN THE ABOVE WARRANTY

MAY NOT APPLY TO YOU. This warranty gives you specific legal rights; you may also

◊Reported values are for Pastel Base. Contact Benjamin Moore for values of other bases or colours.

Surface Preparation

Surfaces must be clean, dry and free of oil, grease, wax, rust, mildew, chalk and loose or scaling paint. Cement based water proofing paints should be removed. Glossy surfaces must be dulled. Un-weathered areas such as eaves, porch ceilings, overhangs and protected wall areas should be washed with a Benjamin Moore® Clean (K318) and rinsed with a strong stream of water from a garden hose or power washer to remove contaminants that can interfere with proper adhesion. Stains from mildew must be removed by cleaning with Benjamin Moore® Clean (K318) prior to coating the surface. Caution: Refer to the (K318) Clean technical data and material safety data sheets for instructions on its proper use and handling.

All masonry surfaces must be power washed or brushed thoroughly with stiff fibre bristles to remove loose particles. New masonry substrates must be allowed to cure for 30 days before priming or painting. Poured or pre-cast concrete with a very smooth surface should be etched or abraded to promote adhesion, after removing all form release agents and curing compounds.

Difficult Substrates: Benjamin Moore offers a number of specialty primers for use over difficult substrates such as bleeding woods, grease stains, crayon markings, hard glossy surfaces, or other substrates where paint adhesion or stain suppression is a particular problem. Your Benjamin Moore retailer can recommend the right problem-solving primer for your special needs.

WARNING! If you scrape, sand, or remove old paint, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by logging onto Health Canada

@ https://www.canada.ca/en/health-canada/services/environmentalworkplace-health/environmental-contaminants/lead/lead-informationpackage-some-commonly-asked-questions-about-lead-humanhealth.html.

Primer/Finish Systems

New surfaces should be fully primed, and previously painted surfaces may be primed or spot primed as necessary. For best hiding results, tint the primer to the approximate shade of the finish coat, especially when a significant colour change is desired. Special Note: Certain custom colours require a Deep Colour Base Primer tinted to a special prescription formula to achieve the desired colour. Consult your retailer.

Wood and engineered wood products:

Primer: Fresh Start® High-Hiding All Purpose Primer (K046) or

Fresh Start® Multi-Purpose Latex Primer (F023)

Finish: 1 or 2 coats of ben® Exterior 100% Acrylic Flat Finish (K541)

Bleeding Type Woods, (Redwood and Cedar):

Primer: Fresh Start® Exterior Wood Primer (K094) or 1-2 coats of Fresh Start® High-Hiding All Purpose Primer (K046) may be used Finish: 1 or 2 coats of ben® Exterior 100% Acrylic Flat Finish (K541)

Hardboard Siding, Bare or Factory Primed:

Primer: Fresh Start® High-Hiding All Purpose Primer (K046) or

Fresh Start® Multi-Purpose Latex Primer (F023)

Finish: 1 or 2 coats of ben® Exterior 100% Acrylic Flat Finish (K541)

Vinyl & Vinyl Composite Siding:

In most cases, a primer is not necessary. Only areas of pitted and porous vinyl siding must be primed. In these cases, we recommend Fresh Start® High-Hiding All Purpose Primer (K046), or Fresh Start® Multi-Purpose Latex Primer (F023).

Colours that are safe for use on vinyl siding - Do not paint vinyl with any colour darker than the original colour or having a Light Reflective Value (LRV) of less than 55 unless it is in the Benjamin Moore approved Colours for Vinyl palette and comports with the specific vinyl manufacturer guidelines when making the colour selection and painting. Otherwise, the colour will absorb more heat, possibly causing the siding to warp, resulting in additional repairs and expenses.

Rough or Pitted Masonry:

Primer: Ultra Spec® Masonry Interior/Exterior Hi-Build Block Filler (K571) Finish: 1 or 2 coats of ben® Exterior 100% Acrylic Flat Finish (K541)

Poured or Pre-cast Concrete and Fibre Cement Siding: Primer: Fresh Start® Multi-Purpose Latex Primer (F023)

Finish: 1 or 2 coats of ben® Exterior 100% Acrylic Flat Finish (K541)

Ferrous Metal (Steel and Iron):

Primer: Ultra Spec® HP Acrylic Metal Primer (FP04) or Super Spec HP®

Alkvd Metal Primer (KP06)

Finish: 1 or 2 coats of ben® Exterior 100% Acrylic Flat Finish (K541)

Non-Ferrous Metal (Galvanized & Aluminum): All new metal surfaces must be thoroughly cleaned with Corotech® Oil & Grease Emulsifier (V600) to remove contaminants. New shiny non-ferrous metal surfaces that will be subject to abrasion should be dulled with very fine sandpaper or a synthetic steel wool pad to promote adhesion

Primer: No primer needed

Finish: 1 or 2 coats of ben® Exterior 100% Acrylic Flat Finish (K541)

Repaint, All Substrates: Prime bare areas with the primer recommended for the substrate above.

Application

Stir thoroughly before and during use. Apply one or two coats. Paint Application: For best results, use a premium Benjamin Moore® custom-blended nylon/polyester brush, premium Benjamin Moore® roller, or a similar product. Apply paint generously from unpainted area into wet area. This product can also be sprayed. Refer to the chart below for application recommendations.

Thinning/Clean up

Conditioning with Benjamin Moore® K518 Extender may be necessary under certain conditions to adjust open time or spray characteristics. The chart below is for general guidance Mild conditions Severe conditions Humid (RH> 50%) with no Dry (RH<50%), in direct sunlight & with little to direct sunlight, or windy conditions no wind Brush: Nylon / Add K518 Extender Polyester or water: Roller: No thinning Max of 236 ml to a Premium Quality necessary 3.79 L Spray: Airless Never add other Pressure: paints or solvents. 1,500 -2,500 psi

Clean Up: Clean up with warm soapy water. Spray equipment should be given a final rinse with mineral spirits to prevent rusting.

Environmental Health & Safety Information

May cause allergic skin reaction. Do not get on skin or clothing.

Tip: 0.013-0.017

Use only in a well ventilated area. Keep container closed when not in use. In case of spillage, absorb with inert material and dispose of in accordance with local regulations. Wash thoroughly after handling.

WARNING: This product contains isothiazolinone compounds at levels of <0.1%. These substances are biocides commonly found in most paints and a variety of personal care products as a preservative. Certain individuals may be sensitive or allergic to these substances. even at low levels.

KEEP OUT OF REACH OF CHILDREN PROTECT FROM FREEZING

Refer to Safety Data Sheet for additional health and safety information.