

# **ULTRA SPEC®**

ACRYLIC SELF-SEALING LOW LUSTRE-EGGSHELL K581

## **Features**

- · Self-sealing
- Excellent hiding
- · Great touch up
- Spatter resistant
- Low sheen finish
- · High build formula
- Quick dry
- · Easy application
- Soap and water cleanup

# **General Description**

An acrylic blended Low Lustre-Eggshell latex designed for application to a wide variety of interior surfaces such as walls and ceilings. The high build formula allows the product to be used as a sealer and finish. This highly durable, low sheen finish enamel has excellent hiding and touch up along with easy application and soap and water clean up.

## **Recommended For**

For interior walls and ceilings. Ideal for new or previously painted drywall, and masonry as well as primed or previously painted plaster, wood and metal.

## Limitations

 Do not apply when air and surface temperatures are below 10 °C (50 °F).

| Product Inform  | nation  |                          |                                   |  |
|---|---|--------------------------|-----------------------------------|--|
| Colours — Standard:   | Technical Data◊   |                          | Tintable White                    |  |
| Tintable White (01)   | Vehicle Type  | A                        | Acrylic Blended Latex             |  |
| (May be tinted with up to 60 ml of Benjamin Moore® Gennex® colorants per 3.79 L)  — Tint Bases:   | Pigment Type  | Titanium Dioxide         |                                   |  |
|   | Volume Solids   | 40.5%                    |                                   |  |
|   | Coverage per 3.79 L at<br>Recommended Film Th   |                          |                                   |  |
| Benjamin Moore® Gennex® Bases 2X, and 3X.   | Recommended Film Thickness  | – Wet<br>– Dry           | 3.6 – 4.0 mils<br>1.4 – 1.6 mils  |  |
| — Special Colours: Contact your Benjamin Moore representative   | Depending on surface texture and porosity. Be sure to estimate the right amount of paint for the job. This will ensure colour uniformity and minimize the disposal of excess paint. |                          |                                   |  |
|   | Dry Time @ 25 °C<br>(77 °F) @ 50% RH  | – To Touch               |                                   |  |
| Certifications & Qualifications:  |   | – To Reco                | I I I I I I I I                   |  |
| Eligible for LEED® v4 Credit  | Painted surfaces can be washed after two weeks. High humidity and cool temperatures will result in longer dry, recoat and service times.  |                          |                                   |  |
| Qualifies for CHPS low emitting credit (Collaborative for High Performance Schools) CDPH v1 Emission Certified Master Painters Institute MPI # 53 | Dries By  | Evaporation, Coalescence |                                   |  |
|   | Viscosity   | 96 ± 3 KU                |                                   |  |
|   | Flash Point   |                          | N/A                               |  |
|   | Gloss / Sheen   | (4 – 7 @ 85°) (3 @ 60°)  |                                   |  |
|   | Surface Temperature at Application  | – Min.<br>– Max          | 10 °C (50 °F)<br>32.2 °C (90 °F)  |  |
|   | Thin With   |                          | Clean Water                       |  |
| Customer Information Centre: 1-800-361-5898, info@benjaminmoore.com, www.benjaminmoore.ca   | Clean Up Thinner  |                          | Clean Water                       |  |
|   | Weight Per 3.79 L   |                          | 5.1 kg (11.2 lbs)                 |  |
|   | Storage Temperature   | – Min.<br>– Max          | 4.4 °C (40 °F)<br>32.2 °C (90 °F) |  |
|   | Volatile Organic Compounds (VOC)  47 g/L  |                          |                                   |  |

## **Surface Preparation**

Surfaces to be painted must be clean, dry, and free of dirt, dust, grease, oil, soap, wax, scaling paint, water-soluble materials, and mildew. Remove any peeling or scaling paint and sand these areas to feather edges smooth with adjacent surfaces. Glossy areas should be dulled. Drywall surfaces must be free of sanding dust.

New plaster or masonry surfaces must be allowed to cure (30 days) before applying base coat. Cured plaster should be hard, have a slight sheen and maximum pH of 10; soft, porous or powdery plaster indicates improper cure. Never sand a plaster surface; knife off any protrusions and prime plaster before and after applying patching compound. Poured or pre-cast concrete with a very smooth surface should be etched or abraded to promote adhesion, after removing all form release agents and curing compounds. Remove any powder or loose particles before priming.

**Difficult Substrates:** Benjamin Moore offers a variety of specialty primers for use over difficult substrates such as plaster, bleeding woods, grease stains, crayon markings, hard glossy surfaces, galvanized metal or other substrates where paint adhesion or stain suppression is a particular problem. Your Benjamin Moore retailer can recommend the right problem-solving primer for your special needs

WARNING! If you scrape, sand, or remove old paint, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by logging onto Health Canada @ <a href="https://www.canada.ca/en/health-canada/services/environmental-workplace-health/environmental-contaminants/lead/lead-information-package-some-commonly-asked-questions-about-lead-human-health.html">https://www.canada.ca/en/health-contaminants/lead/lead-information-package-some-commonly-asked-questions-about-lead-human-health.html</a>

# **Primer/Finish Systems**

Ultra Spec® Acrylic Self-Sealing Low Lustre-Eggshell K581 is self-priming in most situations. **Special Note:** Certain custom colours require a Deep Colour Base Primer tinted to a special prescription formula to achieve the desired colour. Consult your retailer.

## Wood and engineered wood products

Primer: Ultra Spec® 500 Interior Latex Primer (K534) or Fresh

Start® High-Hiding All Purpose Primer (K046)

Finish: 1 or 2 coats of Ultra Spec® Acrylic Self-Sealing Low Lustre-Eggshell (K581)

# Bleeding Type Woods (Redwood and Cedar)

Primer: Fresh Start® Undercoater and Primer/Sealer (K032) or

Fresh Start® High-Hiding All Purpose Primer (K046)

Finish: 1 or 2 coats of Ultra Spec® Acrylic Self-Sealing Low Lustre-Eggshell (K581)

# Drywall

**Primer/Finish:** 1 or 2 coats of Ultra Spec<sup>®</sup> Acrylic Self-Sealing Low Lustre-Eggshell (K581)

#### Plaster

**Primer:** Fresh Start® High-Hiding All Purpose Primer (K046) **Finish:** 1 or 2 coats of Ultra Spec® Acrylic Self-Sealing Low Lustre-Eggshell (K581)

#### **Rough or Pitted Masonry**

Primer: Ultra Spec® Hi-Build Masonry Block Filler (K571)

Finish: 1 or 2 coats of Ultra Spec® Acrylic Self-Sealing Low Lustre-

Eggshell(K581)

## **Smooth Poured or Pre-cast Concrete**

Primer/Finish: 1 or 2 coats of Ultra Spec® Acrylic Self-Sealing Low

Lustre-Eggshell (K581)

#### Ferrous Metal (Steel and Iron)

Primer: Ultra Spec® HP Acrylic Metal Primer (FP04) or Super

Spec HP® Alkyd Metal Primer (KP06)

Finish: 1 or 2 coats of Ultra Spec® Acrylic Self-Sealing Low

Lustre-Eggshell (K581)

#### Non-Ferrous Metal (Galvanized & Aluminum)

All new metal surfaces must be thoroughly cleaned with Corotech® Oil & Grease Emulsifier (V600) to remove contaminants. New shiny non-ferrous metal surfaces that will be subject to abrasion should be dulled with very fine sandpaper or a synthetic steel wool pad to promote adhesion.

**Primer/Finish:** 1 or 2 coats of Ultra Spec® Acrylic Self-Sealing Low Lustre-Eggshell (K581)

**Repaint, All Substrates:** Prime bare areas with the primer recommended for the substrate above.

## **Application**

**Mixing of Paint:** Stir thoroughly before and during use. Apply one or two coats. **Paint Application:** For best results, use a premium Benjamin Moore® custom-blended nylon/polyester brush, premium Benjamin Moore® roller, or a similar product. Apply paint generously from unpainted area into wet area. This product can also be sprayed.

**Spray, Airless:** Fluid Pressure — 1,500 or 2,500 PSI; Tip — .013 - .017 Orifice

# Thinning/Clean up

Thinning is unnecessary, but if required to obtain desired application properties, a small amount of clean water may be added. Never add other paints or solvents.

Wash painting tools in warm soapy water immediately after use. Spray equipment should be given a final rinse with mineral spirits to prevent rusting.

# **Environmental Health & Safety Information**

**Use only in a well ventilated area**. Keep container closed when not in use. In case of spillage, absorb with inert material and dispose of in accordance with local regulations. Wash thoroughly after handling.

# KEEP OUT OF REACH OF CHILDREN PROTECT FROM FREEZING

Refer to Safety Data Sheet for additional health and safety information.