



AURA[®]

WATERBORNE EXTERIOR PAINT

SATIN FINISH 631

Features

- Extreme hide, never more than two coats in any color
- Color lock technology and extreme UV resistance
- Low temperature application
- Superior adhesion
- Delivers a high-build paint film for excellent durability
- Soap and water clean up
- Fast dry and re-coat times
- Resistant to fading, cracking, peeling, chalking, blistering, dirt pick-up
- Provides a mildew resistant film
- Self priming in most situations
- Vapor permeable

Recommended For

Recommended for exterior use on wood, fiber cement board, hard board, vinyl and aluminum siding, shakes, unglazed brick, concrete, stucco, cinder block and primed metal.

General Description

A super premium quality, 100% acrylic exterior satin latex finish. This product combines the advantages of our latest resin technology and our proprietary Gennex[®] colorant system to provide the ultimate exterior coating. This high solids formula is suitable for a variety of exterior surfaces and can be applied as low as 40 °F.

Limitations

- Do not apply when air and surface temperatures are below 40 °F (4.4 °C).
- For Wind-Driven Rain over smooth and stable masonry only (non-elastomeric use). Follow primer/finish instructions.

Product Information

Colors — Standard:

White (01)

— Tint Bases:

Benjamin Moore[®] Gennex[®] bases 1X, 2X, 3X & 4X

— Special Colors:

Contact your Benjamin Moore[®] representative

Certifications & Qualifications:

VOC compliant in all regulated areas

The following results are based on independent, third-party laboratory testing:

- Passes Wind Driven Rain Test (1.3 oz) ASTM D6904 (TT-C-555B)
1 coat Ultra Spec[®] Acrylic Masonry Sealer 608 @ 4 mils WFT
2 coats Aura[®] Exterior Paint Satin Finish 631 each @ 1.85 DFT
- Passes Alkali Resistance Test ASTM D1308 (24 hrs. no effect)
1 coat Ultra Spec[®] Acrylic Masonry Sealer 608 @ 4 mils WFT
1 coats Aura[®] Exterior Paint Satin Finish 631 each @ 1.85 DFT
- Passes Conical Mandrel Flexibility Test ASTM D522 (no cracking)
1 coat Aura[®] Exterior Paint Satin Finish 631 @ 1.6 DFT
- Passes Mildew, Mold Resistance Test ASTM D3273 (no growth)
- Passes Mildew Resistance Test ASTM D3274 (no growth).
- ASTM D1653 Water Vapor Transmission Properties
60.2 perms @ 2.0 mils DFT
- ASTM D2370 Tensile Properties: Peak Tensile Strength, psi 406
Elongation at Break, percent 380

Technical Assistance

Available through your local authorized independent Benjamin Moore retailer. For the location of the retailer nearest you, call 1-866-708-9180 or visit www.benjaminmoore.com

Technical Data[◇]

Technical Data [◇]		Pastel Base
Vehicle Type	Proprietary 100% Acrylic	
Pigment Type	Titanium Dioxide	
Volume Solids	40.4%	
Coverage per Gallon at Recommended Film Thickness	250 – 350 sq. ft. (23.2 – 32.5 sq. m.)	
Recommended Film Thickness	– Wet	4.6 – 6.4 mils
	– Dry	1.9 – 2.6 mils
High Build System Coverage: 160 – 265 sq. ft. 6-10 mils wet film thickness		
Depending on surface texture and porosity. Be sure to estimate the right amount of paint for the job. This will ensure color uniformity and minimize the disposal of excess paint.		
Dry Time @ 77 °F (25 °C) @ 50% RH	– To Touch	1 Hour
	– To Recoat	4 Hours
High humidity and cool temperatures will result in longer dry, recoat and service times		
Dries By	Evaporation, Coalescence	
Viscosity	102 ± 2 KU	
Flash Point	None	
Gloss / Sheen	Satin (35 - 50 @ 60°)	
Surface Temperature at Application	– Min.	40 °F (4.4 °C)
	– Max	100 °F (37.7 °C)
Thin With	See Chart	
Clean Up Thinner	Clean Water	
Weight Per Gallon	11.2 lbs	
Storage Temperature	– Min.	40 °F (4.4 °C)
	– Max	90 °F (32 °C)

Volatile Organic Compounds (VOC)

45.2 Grams / Liter 0.38 lbs. / Gallon

[◇]Reported values are for Pastel Base. Contact Benjamin Moore for values of other bases or colors.

Surface Preparation

Surfaces must be clean and free of grease, wax, and mildew. Remove any chalk and loose or scaling paint. If previously coated with cement-base waterproofing paints, clean by sandblasting. Glossy surfaces must be dulled. Un-weathered areas such as eaves, ceilings, and overhangs should be washed with a detergent solution and/or rinsed with a strong stream of water from a garden hose to remove contaminants that can interfere with proper adhesion. Stains from mildew must be removed by cleaning with Benjamin Moore® Clean (N318) prior to coating the surface. **Caution:** Refer to the (N318) Clean technical data and material safety data sheets for instructions on its proper use and handling. For metal surfaces, remove rust. Wipe down with paint thinner to remove surface oils.

Difficult Substrates: Benjamin Moore® offers a number of specialty primers for use over difficult substrates such as bleeding woods, grease stains, crayon markings, hard glossy surfaces, or other substrates where paint adhesion or stain suppression is a particular problem. Your Benjamin Moore® retailer can recommend the right problem-solving primer for your special needs.

WARNING! If you scrape, sand, or remove old paint, you may release lead dust. **LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE.** Wear a NIOSH approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Informational Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead

Primer/Finish Systems

Aura® Waterborne Exterior Satin Finish is self priming on most properly prepared substrates, including: wood, fiber cement board, hardboard, nonferrous metals and cured masonry surfaces. On bare substrates two coats are required; previously painted surfaces can be finished with 1 or 2 coats. **Special Note:** For certain deep colors, Aura® Color Foundation must be used to achieve maximum hide and the desired topcoat color. Consult your retailer.

Wood And Engineered Wood Products:

Primer: No primer needed

Finish: 2 coats Aura® Waterborne Exterior Paint Satin Finish (631)

Bleeding Type Woods, (Redwood and Cedar):

Primer: Fresh Start® Exterior Wood Primer (094) or 1-2 coats of Fresh Start® High-Hiding All Purpose Primer (046) may be used

Finish: 1 or 2 coats Aura® Waterborne Exterior Paint Satin Finish (631)

Hardboard Siding, Bare or Factory Primed:

Primer: No primer needed

Finish: 1 or 2 coats Aura® Waterborne Exterior Paint Satin Finish (631)

Vinyl Siding & Vinyl Composite

Note: Do not paint vinyl siding or trim darker than the original color

Primer: Fresh Start® High-Hiding All Purpose Primer (046)

Finish: 1 or 2 coats Aura® Waterborne Exterior Paint Satin Finish (631)

Rough or Pitted Masonry: Poured and precast concrete and block construction should be allowed to cure for at least 30 days. New masonry only needs to be cured for 7 days when using Ultra Spec® Masonry Interior / Exterior 100% Acrylic Masonry Sealer (608). All surfaces must be thoroughly brushed with stiff fiber bristles to remove loose particles.

Primer: Ultra Spec® Masonry Interior/Exterior Hi-Build Block Filler (571)

Finish: 1 or 2 coats Aura® Waterborne Exterior Paint Satin Finish (631)

Poured or Pre-cast Concrete and Fiber Cement Siding:

Primer: No primer needed

Finish: 1 or 2 coats Aura® Waterborne Exterior Paint Satin Finish (631)

Masonry, Weathered and Unpainted, Soft with Age (Including Unglazed Brick): Remove any loose, sandy masonry by dry brushing.

Primer: Ultra Spec® Masonry Interior / Exterior 100% Acrylic Masonry Sealer (608)

Finish: 1 or 2 coats Aura® Waterborne Exterior Paint Satin Finish (631)

Ferrous Metal (Steel and Iron):

Primer: Ultra Spec® HP Acrylic Metal Primer (HP04) or Super Spec HP® Alkyd Metal Primer (P06)

Finish: 1 or 2 coats Aura® Waterborne Exterior Paint Satin Finish (631)

Non-Ferrous Metal (Galvanized & Aluminum):

All new metal surfaces must be thoroughly cleaned with Corotech®

Oil & Grease Emulsifier (V600) to remove contaminants. New shiny non-ferrous metal surfaces that will be subject to abrasion should be dulled with very fine sandpaper or a synthetic steel wool pad to promote adhesion

Primer: Not required on properly prepared surfaces

Finish: 1 or 2 coats Aura® Waterborne Exterior Paint Satin Finish (631)

Repaint, All Substrates: Prime bare areas with the primer recommended for the substrate above.

Application

Use the same application techniques as you would for any low-VOC compliant coating. Use a Benjamin Moore® Premium roller or Premium extra firm nylon polyester brush for best results. Aura® paint features excellent flow and leveling; it's not necessary to over brush to smooth out brush marks. Aura® dries faster than other acrylic paints; avoid lap marks by not painting in direct sunlight and by coating sections of the surface either down or across the structure to natural breaks, maintaining a wet edge. If your edge begins to dry or you see that you missed a spot and the paint is already setting up, allow it to dry completely before touching up that area. This product can also be sprayed.

Thinning/Clean Up

Conditioning with Benjamin Moore® 518 Extender may be necessary under certain conditions to adjust open time or spray characteristics. The chart below is for general guidance		
	Mild conditions	Severe conditions
	Humid (RH> 50%) with no direct sunlight & with little to no wind	Dry (RH<50%), in direct sunlight, or windy conditions
Brush: Nylon / Polyester	No thinning necessary	Add 518 Extender or water: Max of 8 fl. oz. to a gallon paint Never add other paints or solvents.
Roller: Aura® Roller Cover		
Spray: Airless Pressure: 2000-3000 psi Tip: 0.015-0.017		
* Under normal application conditions AURA® may be sprayed to achieve a high build one coat system over properly prepared substrates that are in good condition. Refer to Surface Preparation / Priming Sections for appropriate priming and preparation information. High Build System Coverage: 160 – 265 sq. ft. 6-10 mils wet film thickness.		

Clean Up: Wash painting tools in warm soapy water immediately after use. Spray equipment should be given a final rinse with mineral spirits to prevent rusting.

USE COMPLETELY OR DISPOSE OF PROPERLY. Dry, empty containers may be recycled in a can recycling program. **Local disposal requirements vary; consult your sanitation department or state-designated environmental agency on disposal options.**

Environmental Health & Safety Information

WARNING!

Possible birth defect hazard. Contains, Carbamic acid, 1H-benzimidazol-2-yl-, methyl ester, which may cause birth defects based on animal data.

Use only with adequate ventilation. Do not breathe vapors, spray mist or sanding dust. Ensure fresh air entry during application and drying. Avoid contact with eyes and prolonged or repeated contact with skin. May cause allergic skin reaction. Avoid exposure to dust and spray mist by wearing a NIOSH approved respirator during application, sanding and clean up. Follow respirator manufacturer's directions for respirator use. Close container after each use. Wash thoroughly after handling.



WARNING Cancer and Reproductive Harm—
www.P65warnings.ca.gov

FIRST AID: In case of eye contact, flush immediately with plenty of water for at least 15 minutes; for skin, wash thoroughly with soap and water. If symptoms persist, seek medical attention. If you experience difficulty breathing, leave the area to obtain fresh air. If continued difficulty is experienced, get medical attention immediately.

IN CASE OF SPILL – Absorb with inert material and dispose of as specified under **Thinning/Clean Up**.

**KEEP OUT OF REACH OF CHILDREN
PROTECT FROM FREEZING**

Refer to Safety Data Sheet for additional health and safety information.