

WATERBORNE EXTERIOR PAINT **LOW LUSTRE FINISH 634**

Features

- · Extreme hide it covers dark colors and imperfections in less coats
- Low temperature application
- Superior adhesion
- Delivers a high-build paint film for excellent durability
- Color Lock® technology and extreme UV resistance
- Soap and water clean up Fast dry and re-coat times
- Resistant to fading, cracking, peeling, chalking blistering, dirt pick-up
- Provides a mildew resistant
- Self priming in most situations
- Vapor permeable

General Description

A super premium quality, 100% acrylic exterior low lustre latex finish. This product combines the advantages of our latest resin technology and our proprietary Gennex® colorant system to provide the ultimate exterior coating. This high solids formula is suitable for a variety of exterior surfaces and can be applied as low as 40 °F (4.4 °C). Aura® Waterborne Exterior Low Lustre Finish is suitable for wind driven rain when applied according to recommendations.

Recommended For

Recommended for exterior use on wood, fiber cement board, hard board, vinyl and aluminum siding, shakes, unglazed brick, concrete, stucco,

Limitations

- Do not apply when air and surface temperatures are below 40 °F (4.4 °C)
- For Wind-Driven Rain over smooth and stable masonry only (nonelastomeric use). Follow primer/finish instructions

cinder block and primed metal.	• F
Product Info	
Colors — Standard: White (01)	
— Tint Bases:	
Benjamin Moore® Gennex® bases 1X, 2X, 3X & 4X	
— Special Colors:	
Contact your Benjamin Moore representative.	
Certifications & Qualifications:	
VOC compliant in all regulated areas	
Master Painters Institute MPI # 15, 315	
The following results are based on independent, third-party laboratory testing - Passes Wind Driven Rain Test (3.0 oz) ASTM D6904 1 coat Ultra Spec® Acrylic Masonry Sealer 608 @ 4 mils WFT 1 or 2 coats Aura® Exterior Paint Low Lustre Finish 634 each @ 2.8 DFT - Passes Alkali Resistance Test (no effect) ASTM D1308 1 coat Ultra Spec® Acrylic Masonry Sealer 608 @ 4 mils WFT 1 or 2 coats Aura® Exterior Paint Low Lustre Finish 634 @ 2.8 DFT - Passes Conical Mandrel Flexibility Test (no cracking) ASTM D522 1 coat Aura® Exterior Paint Low Lustre Finish 634 @ 2.8 DFT - Passes Mildew, Mold Resistance Test (no growth) ASTM D3273/D3274 1 coat Aura® Exterior Paint Low Lustre Finish 634 @ 2.8 DFT - ASTM D1653 – Water Vapor Transmission Properties Topcoat 63401, one-coat at 250 ft²/gal (2.8-mils DFT)-25.7 perms - ASTM D2370 Tensile Properties Peak Tensile Strength, psi 255 - Elongation at Break, 120%	
LIFETIME LIMITED WARRANTY: Benjamin Moore & Co. warrants that this prodused in accordance with the label instructions, will not: 1. blister from properly and primed surfaces, 2. peel from properly prepared and primed surfaces, and down or weather to expose the previously painted surface. This warranty shall be for so long as you reside in your home and is made to the original residential opaint purchaser. This warranty is non-transferable. If this product fails to peexplained above when used according to label instructions within the warrant Benjamin Moore & Co. will, upon presentation of proof of purchase (original sales provide an equivalent or comparable product at no charge. Since we have no co surface preparation or application, THIS LIFETIME LIMITED WARRANTY DC INCLUDE THE COST OF LABOR FOR APPLICATION OF PAINT. BENJAMIN	prepared d 3. wear e effective consumer erform as ty period, s receipt), ntrol over DES NOT

Colors — Standard:	Technical Data	Base 1
White (01)	Vehicle Type	Proprietary 100% Acrylic
— Tint Bases:	Pigment Type	Titanium Dioxide
Benjamin Moore® Gennex® bases 1X, 2X, 3X & 4X	Volume Solids	42.7%
— Special Colors: Contact your Benjamin Moore representative.	Coverage per Gallon at Recommended Film Thic	ckness 250 – 350 Sq. Ft.
Certifications & Qualifications:	Recommended Film Thickness	− Wet 4.6 − 6.4 mils − Dry 2.0 − 2.8 mils
VOC compliant in all regulated areas Master Painters Institute MPI # 15, 315	High Build System Covera	
The following results are based on independent, third-party laboratory testing: - Passes Wind Driven Rain Test (3.0 oz) ASTM D6904 1 coat Ultra Spec® Acrylic Masonry Sealer 608 @ 4 mils WFT	Depending on surface texture and porosity. Be sure to estimate the right amount of paint for the job. This will ensure color uniformity and minimize the disposal of excess paint	
1 or 2 coats Aura® Exterior Paint Low Lustre Finish 634 each @ 2.8 DFT - Passes Alkali Resistance Test (no effect) ASTM D1308 1 coat Ultra Spec® Acrylic Masonry Sealer 608 @ 4 mils WFT	Dry Time @ 77°F (25°C) @ 50% RH	- To Touch 1 Hour - To Recoat 4 Hours
1 or 2 coats Aura® Exterior Paint Low Lustre Finish 634 @ 2.8 DFT - Passes Conical Mandrel Flexibility Test (no cracking) ASTM D522 1 coat Aura® Exterior Paint Low Lustre Finish 634 @ 2.8 DFT	Painted surfaces can be washed after two weeks. High humidity and cool temperatures will result in longer dry, recoat and service times	
 Passes Mildew, Mold Resistance Test (no growth) ASTM D3273/D3274 1 coat Aura® Exterior Paint Low Lustre Finish 634 @ 2.8 DFT ASTM D1653 – Water Vapor Transmission Properties Topcoat 63401, one-coat at 250 ft²/gal (2.8-mils DFT)-25.7 perms 	Dries By	Evaporation, Coalescence
	Viscosity	102 ± 2 KU
- ASTM D2370 Tensile Properties	Flash Point	None
Peak Tensile Strength, psi 255 - Elongation at Break, 120%	Gloss / Sheen	Low Lustre (9 – 14 @ 60°)
LIFETIME LIMITED WARRANTY: Benjamin Moore & Co. warrants that this product when used in accordance with the label instructions, will not: 1. blister from properly prepared and primed surfaces, 2. peel from properly prepared and primed surfaces, and 3. wear down or weather to expose the previously painted surface. This warranty shall be effective	Surface Temperature at Application	- Min. 40 °F (4.4 °C) - Max 100 °F (37.7 °C)
for so long as you reside in your home and is made to the original residential consumer	Thin With	See Chart
paint purchaser. This warranty is non-transferable. If this product fails to perform as explained above when used according to label instructions within the warranty period, Benjamin Moore & Co. will, upon presentation of proof of purchase (original sales receipt), provide an equivalent or comparable product at no charge. Since we have no control over	Clean Up Thinner	Clean Water
	Weight Per Gallon	11.5 lbs
surface preparation or application, THIS LIFETIME LIMITED WARRANTY DOES NOT		– Min. 40 °F (4.4 °C)
NCLUDE THE COST OF LABOR FOR APPLICATION OF PAINT. BENJAMIN MOORE Storage Temperatur SHALL IN NO EVENT BE LIABLE FOR INDIRECT, SPECIAL, INCIDENTAL OR	Storage Temperature	– Max 90 °F (32 °C)
CONSEQUENTIAL DAMAGES. SOME STATES DO NOT ALLOW THE EXCLUSION OF INCIDENTAL OR CONSEQUENTIAL DAMAGES, SO THE LIMITATIONS OR		

Technical Assistance

state to state.

Available through your local authorized independent Benjamin Moore retailer. For the location of the retailer nearest you, call 1-866-708-9180 or visit www.benjaminmoore.com

EXCLUSIONS CONTAINED IN THE ABOVE WARRANTY MAY NOT APPLY TO YOU.

This warranty gives you specific legal rights; you may also have other rights which vary

Volatile Organic Compounds (VOC)

46.6 Grams / Liter 0.39 LBS / Gallon

Surface Preparation

Surfaces must be clean and free of grease, wax, and mildew. Remove any chalk and loose or scaling paint. If previously coated with cement-base waterproofing paints, clean by sandblasting. Glossy surfaces must be dulled. Un-weathered areas such as eaves, ceilings, and overhangs should be washed with a detergent solution and/or rinsed with a strong stream of water from a garden hose to remove contaminants that can interfere with proper adhesion. Stains from mildew must be removed by cleaning with Benjamin Moore® Clean (N318) prior to coating the surface. Caution: Refer to the (N318) Clean technical data and material safety data sheets for instructions on its proper use and handling. For metal surfaces, remove rust. Wipe down with paint thinner to remove surface oils.

Difficult Substrates: Benjamin Moore offers a number of specialty primers for use over difficult substrates such as bleeding woods, grease stains, crayon markings, hard glossy surfaces, or other substrates where paint adhesion or stain suppression is a particular problem. Your Benjamin Moore® retailer can recommend the right problem-solving primer for your

WARNING! If you scrape, sand or remove old paint, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH-approved respirator to control lead exposure. Carefully clean up with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead.

Primer/Finish Systems

Aura® Waterborne Exterior Low Lustre Finish is self priming on most properly prepared substrates, including: wood, fiber cement board, hardboard, nonferrous metals and cured masonry surfaces. On bare substrates two coats are required; previously painted surfaces can be finished with 1 or 2 coats. Special Note: For certain deep colors, Aura® Color Foundation must be used to achieve maximum hide and the desired topcoat color. Consult your retailer.

Wood and engineered wood products:

Primer: No primer needed

Finish: 2 coats Aura® Waterborne Exterior Low Lustre Finish (634)

Bleeding Type Woods, (Redwood and Cedar):

Primer: Fresh Start® Exterior Wood Primer (094) or 1-2 coats of Fresh Start®

High-Hiding All Purpose Primer (046) may be used

Finish: 2 coats Aura® Waterborne Exterior Low Lustre Finish (634)

Hardboard Siding, Bare or Factory Primed:

Primer: No primer needed

Finish: 1 or 2 coats Aura® Waterborne Exterior Low Lustre Finish (634)

Vinyl Siding & Vinyl Composite

In most cases, a primer is not necessary. Only areas of pitted and porous vinyl siding must be primed. In these cases, we recommend Fresh Start® High-Hiding All Purpose Primer (046), or Fresh Start® Multi-Purpose Latex Primer (N023).

Colors that are safe for use on vinyl siding - Do not paint vinyl with any color darker than the original color or having a Light Reflective Value (LRV) of less than 55 unless it is in the Benjamin Moore approved Colors for Vinyl palette and comports with the specific vinyl manufacturer guidelines when making the color selection and painting. Otherwise, the color will absorb more heat, possibly causing the siding to warp, resulting in additional repairs

Rough or Pitted Masonry: Poured and precast concrete and block construction should be allowed to sure for at least 30 days. New masonry only needs to be cured for 7 days when using Ultra Spec® Masonry Interior / Exterior 100% Acrylic Masonry Sealer (608). All surfaces must be thoroughly brushed with stiff fiber bristles to remove loose particles.

Primer: Ultra Spec® Masonry Interior/Exterior Hi-Build Block Filler (571) Finish: 2 coats Aura® Waterborne Exterior Low Lustre Finish (634)

Poured or Pre-cast Concrete and Fiber Cement Siding:

Primer: No primer needed

Finish: 1 or 2 coats Aura® Waterborne Exterior Low Lustre Finish (634)

Masonry, Weathered and Unpainted, Soft with Age (Including Unglazed Brick): Remove any loose, sandy masonry by dry brushing.

Primer: Ultra Spec® Masonry Interior / Exterior 100% Acrylic Masonry Sealer (608)

Finish: 1 or 2 coats Aura® Waterborne Exterior Low Lustre Finish (634)

Ferrous Metal (Steel and Iron):

Primer: Ultra Spec® HP Acrylic Metal Primer (HP04) or Super Spec HP® Alkyd Metal Primer (P06)

Finish: 1 or 2 coats Aura® Waterborne Exterior Low Lustre Finish (634) Non-Ferrous Metal (Galvanized & Aluminum): All new metal surfaces must be thoroughly cleaned with Corotech® Oil & Grease Emulsifier (V600) to remove contaminants. New shiny non-ferrous metal surfaces that will be subject to abrasion should be dulled with very fine sandpaper or a synthetic steel wool pad to promote adhesion

Primer: Not required on properly prepared surfaces

Finish: 1 or 2 coats Aura® Waterborne Exterior Low Lustre Finish (634)

Repaint, All Substrates: Prime bare areas with the primer recommended for the substrate above.

Application

Use the same application techniques as you would for any low-VOC compliant coating. Use a Benjamin Moore® Premium roller or Premium extra firm nylon polyester brush for best results. Aura® paint features excellent flow and leveling; it's not necessary to over brush to smooth out brush marks. Aura® dries faster than other acrylic paints; avoid lap marks by not painting in direct sunlight and by coating sections of the surface either down or across the structure to natural breaks, maintaining a wet edge. If your edge begins to dry or you see that you missed a spot and the paint is already setting up, allow it to dry completely before touching up that area.

This product can also be sprayed; refer to the chart below.

Thinning/Cleanup

Conditioning with Benjamin Moore® 518 Extender may be necessary under certain conditions to adjust open time or spray characteristics.

The chart below is for general guidance

The chart below is for general guidance			
	Mild conditions	Severe conditions	
	Humid (RH> 50%) with no	Dry (RH<50%), in	
	direct sunlight & with little	direct sunlight,	
	to no wind	or windy conditions	
Brush : Nylon / Polyester		Add 518 Extender or water:	
Roller: Aura® Roller Cover	No thinning	Max of 8 fl. oz. to a	
Spray: Airless Pressure:	necessary	gallon of paint	
2000 -3000 psi Tip: 0.015-0.017		Never add other paints or solvents.	

* Under normal application conditions AURA® may be sprayed to achieve a high build one coat system over properly prepared substrates that are in good condition. Refer to Surface Preparation / Priming Sections for appropriate priming and preparation information. High Build System Coverage: 160 - 265 sq. ft. 6-10 mils wet film thickness.

Cleanup: Wash painting tools in warm soapy water immediately after use. Spray equipment should be given a final rinse with mineral spirits to prevent

USE COMPLETELY OR DISPOSE OF PROPERLY. Dry, empty containers may be recycled in a can recycling program. Local disposal requirements vary; consult your sanitation department or state-designated environmental agency on disposal options.

Environmental Health & Safety Information

WARNING!

Possible birth defect hazard. Contains, Carbamic acid, 1Hbenzimidazol-2-yl-, methyl ester, which may cause birth defects based on

Use only with adequate ventilation. Do not breathe vapors, spray mist or sanding dust. Ensure fresh air entry during application and drying. Avoid contact with eyes and prolonged or repeated contact with skin. May cause allergic skin reaction. Avoid exposure to dust and spray mist by wearing a NIOSH approved respirator during application, sanding and clean up. Follow respirator manufacturer's directions for respirator use. Close container after each use. Wash thoroughly after handling.

WARNING: Cancer and Reproductive Harm-

www.P65warnings.ca.gov

WARNING: This product contains isothiazolinone compounds at levels of <0.1%. These substances are biocides commonly found in most paints and a variety of personal care products as a preservative. Certain individuals may be sensitive or allergic to these substances, even at low levels.

FIRST AID: In case of eye contact, flush immediately with plenty of water for at least 15 minutes; for skin, wash thoroughly with soap and water. If symptoms persist, seek medical attention. If you experience difficulty breathing, leave the area to obtain fresh air. If continued difficulty is experienced, get medical attention immediately.

IN CASE OF SPILL - Absorb with inert material and dispose of as specified under Thinning/Cleanup.

KEEP OUT OF REACH OF CHILDREN PROTECT FROM FREEZING

Refer to Safety Data Sheet for additional health and safety information.