

Features

- Uniform Flat Finish
- Good Touch Up
- Good Dry Hide
- Resists Spattering

General Description

An easy to apply fast-drying vinyl acrylic primer/finish for use on properly prepared interior drywall and thoroughly cured plaster.

Recommended For

New interior drywall for walls and ceilings, and thoroughly cured plaster. It is ideal for new residential and commercial construction, as well as rental properties.

Limitations

- Apply when surface temperature is above 10 °C (50 °F).
- Not for use in high-abuse areas that are frequently washed or scrubbed.

Product Information

<p>Colours — Standard: White (11)</p> <p>Up to 60 mL of Benjamin Moore Gennex[®], Colour Preview[®] or Universal colorant may be added per gallon.</p> <hr/> <p style="text-align: center;">— Tint Bases:</p> <p>N/A</p> <hr/> <p style="text-align: center;">— Special Colours:</p> <p>Contact your dealer.</p> <hr/> <p>Certifications & Qualifications:</p> <p>Qualifies for LEED[®] v4 Credit Qualifies for CHPS low emitting credit (Collaborative for High Performance Schools) CDPH v1 Emission Certified The products supported by this data sheet</p> <hr/> <p>Technical Assistance: Available through your local authorized independent retailer. For the location of the retailer nearest you, call 1-800-361-5898 or visit www.coronadopaint.ca</p>	<table style="width: 100%; border-collapse: collapse;"> <thead> <tr> <th style="text-align: left;">Technical Data</th> <th style="text-align: right;">White</th> </tr> </thead> <tbody> <tr> <td>Vehicle Type</td> <td style="text-align: right;">Vinyl Acrylic</td> </tr> <tr> <td>Pigment Type</td> <td style="text-align: right;">Titanium Dioxide</td> </tr> <tr> <td>Volume Solids</td> <td style="text-align: right;">30 ± 1.0%</td> </tr> <tr> <td>Coverage per 3.79 L. at Recommended Film Thickness</td> <td style="text-align: right;">27.9 – 37.2 sq. m. (300 – 400 sq. ft.)</td> </tr> <tr> <td>Recommended Film Thickness</td> <td style="text-align: right;"> <table style="width: 100%; border-collapse: collapse;"> <tr> <td style="width: 50%; border-bottom: 1px solid black;">– Wet</td> <td style="width: 50%; text-align: right;">4.0 – 5.3 mils</td> </tr> <tr> <td style="border-bottom: 1px solid black;">– Dry</td> <td style="text-align: right;">1.2 – 1.6 mils</td> </tr> </table> </td> </tr> <tr> <td colspan="2">Depending on surface texture and porosity. Be sure to estimate the right amount of paint for the job. This will ensure colour uniformity and minimize the disposal of excess paint.</td> </tr> <tr> <td>Dry Time @ 25 °C (77 °F) @ 50% RH</td> <td style="text-align: right;"> <table style="width: 100%; border-collapse: collapse;"> <tr> <td style="width: 50%; border-bottom: 1px solid black;">– Tack Free</td> <td style="width: 50%; text-align: right;">30 Minutes</td> </tr> <tr> <td style="border-bottom: 1px solid black;">– To Recoat</td> <td style="text-align: right;">4 Hours</td> </tr> </table> </td> </tr> <tr> <td colspan="2">High humidity and cool temperatures will result in longer dry, recoat and service times.</td> </tr> <tr> <td>Dries By</td> <td style="text-align: right;">Evaporation, Coalescence</td> </tr> <tr> <td>Viscosity</td> <td style="text-align: right;">112 ± 3 KU</td> </tr> <tr> <td>Flash Point</td> <td style="text-align: right;">N/A</td> </tr> <tr> <td>Gloss / Sheen</td> <td style="text-align: right;">Flat (1 – 3.0 @ 85°)</td> </tr> <tr> <td>Surface Temperature at Application</td> <td style="text-align: right;"> <table style="width: 100%; border-collapse: collapse;"> <tr> <td style="width: 50%; border-bottom: 1px solid black;">– Min.</td> <td style="width: 50%; text-align: right;">10 °C (50 °F)</td> </tr> <tr> <td style="border-bottom: 1px solid black;">– Max.</td> <td style="text-align: right;">32 °C (90 °F)</td> </tr> </table> </td> </tr> <tr> <td>Thin With</td> <td style="text-align: right;">Clean Water</td> </tr> <tr> <td>Clean Up Thinner</td> <td style="text-align: right;">Clean Water</td> </tr> <tr> <td>Weight Per 3.79 L.</td> <td style="text-align: right;">4.9 kg (10.9 lbs.)</td> </tr> <tr> <td>Storage Temperature</td> <td style="text-align: right;"> <table style="width: 100%; border-collapse: collapse;"> <tr> <td style="width: 50%; border-bottom: 1px solid black;">– Min.</td> <td style="width: 50%; text-align: right;">4.4 °C (40 °F)</td> </tr> <tr> <td style="border-bottom: 1px solid black;">– Max.</td> <td style="text-align: right;">35 °C (95 °F)</td> </tr> </table> </td> </tr> <tr> <td colspan="2" style="text-align: center;">Volatile Organic Compounds (VOC)</td> </tr> <tr> <td colspan="2" style="text-align: center;">19.3 Grams/Litre</td> </tr> </tbody> </table>	Technical Data	White	Vehicle Type	Vinyl Acrylic	Pigment Type	Titanium Dioxide	Volume Solids	30 ± 1.0%	Coverage per 3.79 L. at Recommended Film Thickness	27.9 – 37.2 sq. m. (300 – 400 sq. ft.)	Recommended Film Thickness	<table style="width: 100%; border-collapse: collapse;"> <tr> <td style="width: 50%; border-bottom: 1px solid black;">– Wet</td> <td style="width: 50%; text-align: right;">4.0 – 5.3 mils</td> </tr> <tr> <td style="border-bottom: 1px solid black;">– Dry</td> <td style="text-align: right;">1.2 – 1.6 mils</td> </tr> </table>	– Wet	4.0 – 5.3 mils	– Dry	1.2 – 1.6 mils	Depending on surface texture and porosity. Be sure to estimate the right amount of paint for the job. This will ensure colour uniformity and minimize the disposal of excess paint.		Dry Time @ 25 °C (77 °F) @ 50% RH	<table style="width: 100%; border-collapse: collapse;"> <tr> <td style="width: 50%; border-bottom: 1px solid black;">– Tack Free</td> <td style="width: 50%; text-align: right;">30 Minutes</td> </tr> <tr> <td style="border-bottom: 1px solid black;">– To Recoat</td> <td style="text-align: right;">4 Hours</td> </tr> </table>	– Tack Free	30 Minutes	– To Recoat	4 Hours	High humidity and cool temperatures will result in longer dry, recoat and service times.		Dries By	Evaporation, Coalescence	Viscosity	112 ± 3 KU	Flash Point	N/A	Gloss / Sheen	Flat (1 – 3.0 @ 85°)	Surface Temperature at Application	<table style="width: 100%; border-collapse: collapse;"> <tr> <td style="width: 50%; border-bottom: 1px solid black;">– Min.</td> <td style="width: 50%; text-align: right;">10 °C (50 °F)</td> </tr> <tr> <td style="border-bottom: 1px solid black;">– Max.</td> <td style="text-align: right;">32 °C (90 °F)</td> </tr> </table>	– Min.	10 °C (50 °F)	– Max.	32 °C (90 °F)	Thin With	Clean Water	Clean Up Thinner	Clean Water	Weight Per 3.79 L.	4.9 kg (10.9 lbs.)	Storage Temperature	<table style="width: 100%; border-collapse: collapse;"> <tr> <td style="width: 50%; border-bottom: 1px solid black;">– Min.</td> <td style="width: 50%; text-align: right;">4.4 °C (40 °F)</td> </tr> <tr> <td style="border-bottom: 1px solid black;">– Max.</td> <td style="text-align: right;">35 °C (95 °F)</td> </tr> </table>	– Min.	4.4 °C (40 °F)	– Max.	35 °C (95 °F)	Volatile Organic Compounds (VOC)		19.3 Grams/Litre	
Technical Data	White																																																								
Vehicle Type	Vinyl Acrylic																																																								
Pigment Type	Titanium Dioxide																																																								
Volume Solids	30 ± 1.0%																																																								
Coverage per 3.79 L. at Recommended Film Thickness	27.9 – 37.2 sq. m. (300 – 400 sq. ft.)																																																								
Recommended Film Thickness	<table style="width: 100%; border-collapse: collapse;"> <tr> <td style="width: 50%; border-bottom: 1px solid black;">– Wet</td> <td style="width: 50%; text-align: right;">4.0 – 5.3 mils</td> </tr> <tr> <td style="border-bottom: 1px solid black;">– Dry</td> <td style="text-align: right;">1.2 – 1.6 mils</td> </tr> </table>	– Wet	4.0 – 5.3 mils	– Dry	1.2 – 1.6 mils																																																				
– Wet	4.0 – 5.3 mils																																																								
– Dry	1.2 – 1.6 mils																																																								
Depending on surface texture and porosity. Be sure to estimate the right amount of paint for the job. This will ensure colour uniformity and minimize the disposal of excess paint.																																																									
Dry Time @ 25 °C (77 °F) @ 50% RH	<table style="width: 100%; border-collapse: collapse;"> <tr> <td style="width: 50%; border-bottom: 1px solid black;">– Tack Free</td> <td style="width: 50%; text-align: right;">30 Minutes</td> </tr> <tr> <td style="border-bottom: 1px solid black;">– To Recoat</td> <td style="text-align: right;">4 Hours</td> </tr> </table>	– Tack Free	30 Minutes	– To Recoat	4 Hours																																																				
– Tack Free	30 Minutes																																																								
– To Recoat	4 Hours																																																								
High humidity and cool temperatures will result in longer dry, recoat and service times.																																																									
Dries By	Evaporation, Coalescence																																																								
Viscosity	112 ± 3 KU																																																								
Flash Point	N/A																																																								
Gloss / Sheen	Flat (1 – 3.0 @ 85°)																																																								
Surface Temperature at Application	<table style="width: 100%; border-collapse: collapse;"> <tr> <td style="width: 50%; border-bottom: 1px solid black;">– Min.</td> <td style="width: 50%; text-align: right;">10 °C (50 °F)</td> </tr> <tr> <td style="border-bottom: 1px solid black;">– Max.</td> <td style="text-align: right;">32 °C (90 °F)</td> </tr> </table>	– Min.	10 °C (50 °F)	– Max.	32 °C (90 °F)																																																				
– Min.	10 °C (50 °F)																																																								
– Max.	32 °C (90 °F)																																																								
Thin With	Clean Water																																																								
Clean Up Thinner	Clean Water																																																								
Weight Per 3.79 L.	4.9 kg (10.9 lbs.)																																																								
Storage Temperature	<table style="width: 100%; border-collapse: collapse;"> <tr> <td style="width: 50%; border-bottom: 1px solid black;">– Min.</td> <td style="width: 50%; text-align: right;">4.4 °C (40 °F)</td> </tr> <tr> <td style="border-bottom: 1px solid black;">– Max.</td> <td style="text-align: right;">35 °C (95 °F)</td> </tr> </table>	– Min.	4.4 °C (40 °F)	– Max.	35 °C (95 °F)																																																				
– Min.	4.4 °C (40 °F)																																																								
– Max.	35 °C (95 °F)																																																								
Volatile Organic Compounds (VOC)																																																									
19.3 Grams/Litre																																																									

Surface Preparation

Surfaces to be primed must be clean, dry, and free of dirt, dust, grease, oil, soap, wax, peeling or flaking paint, water soluble materials and mildew. Drywall surfaces must be free of sanding dust.

New plaster or masonry surfaces must be allowed to cure (30 days) before applying base coat. Cured plaster should be hard, have a slight sheen and pH less than 9; soft, porous or powdery plaster indicates improper cure.

Difficult Substrates: Your retailer offers specialty primers for use over difficult substrates such as bleeding woods, grease stains, crayon markings, hard glossy surfaces, galvanized metal or other substrates where paint adhesion or stain suppression is a particular problem. Your retailer can recommend the right problem solving primer for your special needs

WARNING! If you scrape, sand, or remove old paint, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by logging onto Health Canada @ <https://www.canada.ca/en/health-canada/services/environmental-workplace-health/environmental-contaminants/lead/lead-information-package-some-commonly-asked-questions-about-lead-human-health.html>

Application

Stir product with a circular, lifting motion before you begin to paint. Coronado® PVA Primer / Finish may be applied by brush, roller, pad or spray, at a rate of application not to exceed 37.2 sq. m. (400 sq. ft.) per 3.79 L. Surface texture and porosity will affect actual yield. For best brush application results, use a quality synthetic filament brush. For roller application use a 9.5 mm nap cover for smooth surfaces, a 12.7 mm nap cover for semi-rough surfaces, and a 19 mm nap cover for rough surfaces. May be reduced with clean water up to 15% for spray application.

For use as a primer, apply one coat allowing 4 hours to dry before applying 1-2 finish coats. For use as a primer and finish, apply 2 coats allowing 4 hours to dry between each coat.

Airless Spray

Fluid Pressure — 1,500 to 3,000 PSI
Tip — .013-.017 Orifice

Clean Up

Clean up with warm, soapy water.

Environmental Health & Safety Information

Use only in a well ventilated area. Keep container closed when not in use. In case of spillage, absorb with inert material and dispose of in accordance with local regulations. Wash thoroughly after handling.

WARNING: This product contains isothiazolinone compounds at levels of <0.1%. These substances are biocides commonly found in most paints and a variety of personal care products as a preservative. Certain individuals may be sensitive or allergic to these substances, even at low levels.

**KEEP OUT OF REACH OF CHILDREN
PROTECT FROM FREEZING**

**Refer to Safety Data Sheet for
additional health and safety information.**