

CRYLI COTE[®]

100% ACRYLIC EXTERIOR PAINT FLAT N10

Features

- 100% Acrylic
- Durable finish that resists fading
- Self-priming on many surfaces
- Protects against cracking & peeling
- Provides a mildew-resistant coating

Recommended For

For exterior wood, masonry, hardboard and metal in commercial, institutional and residential applications. Use on exterior siding, foundations, fascia, shutters or retaining walls. Designed as a self-priming system on non-bleeding woods, smooth poured or pre-cast masonry and clean, properly prepared galvanized metal surfaces.

General Description

A 100% Acrylic Exterior Paint which provides lasting service over new or previously painted surfaces in good condition. This paint will provide a durable and protective finish on any properly prepared and primed exterior surface.

Limitations

- Do not apply when air and surface temperatures are below 40 °F (4.4 °C).
- Not for interior use

Product Information

<p>Colors — Standard: Tintable White (1)</p> <p style="text-align: center;">— Tint Bases: Tint Base (33), Accent Base (36)</p> <p>Tint with Benjamin Moore[®] Gennex[®] colorant only</p> <p style="text-align: center;">— Special Colors: Contact your dealer</p> <p>Certifications & Qualifications: VOC compliant in all regulated areas</p> <p>The products supported by this data sheet contain a maximum of 50 grams per liter VOC/VOS (0.42 lbs. /gal.) excluding water & exempt solvents. Master Painters Institute MPI # 10</p> <p>Technical Assistance: Available through your local authorized independent dealer. For the location of the dealer nearest you, call 1-866-708-9180, or visit www.coronadopaint.com</p>	<table style="width: 100%; border-collapse: collapse;"> <thead> <tr> <th style="text-align: left; border-bottom: 1px solid black;">Technical Data[◇]</th> <th style="text-align: left; border-bottom: 1px solid black;">Tintable White</th> </tr> </thead> <tbody> <tr> <td>Vehicle Type</td> <td>100% Acrylic</td> </tr> <tr> <td>Pigment Type</td> <td>Titanium Dioxide</td> </tr> <tr> <td>Volume Solids</td> <td>38 ± 1.0%</td> </tr> <tr> <td>Coverage per Gallon at Recommended Film Thickness</td> <td>350 – 450 Sq. Ft.</td> </tr> <tr> <td>Recommended Film Thickness</td> <td> <table style="width: 100%; border-collapse: collapse;"> <tr> <td style="width: 50%; border-bottom: 1px solid black;">– Wet</td> <td style="width: 50%; text-align: right;">3.7 – 4.5 mils</td> </tr> <tr> <td style="border-bottom: 1px solid black;">– Dry</td> <td style="text-align: right;">1.4 – 1.7 mils</td> </tr> </table> </td> </tr> <tr> <td colspan="2">Depending on surface texture and porosity. Be sure to estimate the right amount of paint for the job. This will ensure color uniformity and minimize the disposal of excess paint.</td> </tr> <tr> <td>Dry Time @ 77 °F (25 °C) @ 50% RH</td> <td> <table style="width: 100%; border-collapse: collapse;"> <tr> <td style="width: 50%; border-bottom: 1px solid black;">– Tack Free</td> <td style="width: 50%; text-align: right;">1 Hour</td> </tr> <tr> <td style="border-bottom: 1px solid black;">– To Recoat</td> <td style="text-align: right;">4 Hours</td> </tr> </table> </td> </tr> <tr> <td colspan="2">High humidity and cool temperatures will result in longer dry, recoat and service times.</td> </tr> <tr> <td>Dries By</td> <td>Evaporation, Coalescence</td> </tr> <tr> <td>Viscosity</td> <td>97 – 103 KU</td> </tr> <tr> <td>Flash Point</td> <td>N/A</td> </tr> <tr> <td>Gloss / Sheen</td> <td>Flat (0.5 – 3.5 @ 85°)</td> </tr> <tr> <td>Surface Temperature at Application</td> <td> <table style="width: 100%; border-collapse: collapse;"> <tr> <td style="width: 50%; border-bottom: 1px solid black;">– Min.</td> <td style="width: 50%; text-align: right;">40 °F</td> </tr> <tr> <td style="border-bottom: 1px solid black;">– Max.</td> <td style="text-align: right;">100 °F</td> </tr> </table> </td> </tr> <tr> <td>Thin With</td> <td>Clean Water</td> </tr> <tr> <td>Clean Up Thinner</td> <td>Warm Soapy Water</td> </tr> <tr> <td>Weight Per Gallon</td> <td>11.3 lbs.</td> </tr> <tr> <td>Storage Temperature</td> <td> <table style="width: 100%; border-collapse: collapse;"> <tr> <td style="width: 50%; border-bottom: 1px solid black;">– Min.</td> <td style="width: 50%; text-align: right;">40 °F</td> </tr> <tr> <td style="border-bottom: 1px solid black;">– Max.</td> <td style="text-align: right;">90 °F</td> </tr> </table> </td> </tr> <tr> <td colspan="2" style="text-align: center; padding: 10px 0;">Volatile Organic Compounds (VOC)</td> </tr> <tr> <td colspan="2" style="text-align: center; padding: 5px 0;">46.1 Grams/Liter 0.38 Lbs./Gallon</td> </tr> </tbody> </table>	Technical Data [◇]	Tintable White	Vehicle Type	100% Acrylic	Pigment Type	Titanium Dioxide	Volume Solids	38 ± 1.0%	Coverage per Gallon at Recommended Film Thickness	350 – 450 Sq. Ft.	Recommended Film Thickness	<table style="width: 100%; border-collapse: collapse;"> <tr> <td style="width: 50%; border-bottom: 1px solid black;">– Wet</td> <td style="width: 50%; text-align: right;">3.7 – 4.5 mils</td> </tr> <tr> <td style="border-bottom: 1px solid black;">– Dry</td> <td style="text-align: right;">1.4 – 1.7 mils</td> </tr> </table>	– Wet	3.7 – 4.5 mils	– Dry	1.4 – 1.7 mils	Depending on surface texture and porosity. Be sure to estimate the right amount of paint for the job. This will ensure color uniformity and minimize the disposal of excess paint.		Dry Time @ 77 °F (25 °C) @ 50% RH	<table style="width: 100%; border-collapse: collapse;"> <tr> <td style="width: 50%; border-bottom: 1px solid black;">– Tack Free</td> <td style="width: 50%; text-align: right;">1 Hour</td> </tr> <tr> <td style="border-bottom: 1px solid black;">– To Recoat</td> <td style="text-align: right;">4 Hours</td> </tr> </table>	– Tack Free	1 Hour	– To Recoat	4 Hours	High humidity and cool temperatures will result in longer dry, recoat and service times.		Dries By	Evaporation, Coalescence	Viscosity	97 – 103 KU	Flash Point	N/A	Gloss / Sheen	Flat (0.5 – 3.5 @ 85°)	Surface Temperature at Application	<table style="width: 100%; border-collapse: collapse;"> <tr> <td style="width: 50%; border-bottom: 1px solid black;">– Min.</td> <td style="width: 50%; text-align: right;">40 °F</td> </tr> <tr> <td style="border-bottom: 1px solid black;">– Max.</td> <td style="text-align: right;">100 °F</td> </tr> </table>	– Min.	40 °F	– Max.	100 °F	Thin With	Clean Water	Clean Up Thinner	Warm Soapy Water	Weight Per Gallon	11.3 lbs.	Storage Temperature	<table style="width: 100%; border-collapse: collapse;"> <tr> <td style="width: 50%; border-bottom: 1px solid black;">– Min.</td> <td style="width: 50%; text-align: right;">40 °F</td> </tr> <tr> <td style="border-bottom: 1px solid black;">– Max.</td> <td style="text-align: right;">90 °F</td> </tr> </table>	– Min.	40 °F	– Max.	90 °F	Volatile Organic Compounds (VOC)		46.1 Grams/Liter 0.38 Lbs./Gallon	
Technical Data [◇]	Tintable White																																																								
Vehicle Type	100% Acrylic																																																								
Pigment Type	Titanium Dioxide																																																								
Volume Solids	38 ± 1.0%																																																								
Coverage per Gallon at Recommended Film Thickness	350 – 450 Sq. Ft.																																																								
Recommended Film Thickness	<table style="width: 100%; border-collapse: collapse;"> <tr> <td style="width: 50%; border-bottom: 1px solid black;">– Wet</td> <td style="width: 50%; text-align: right;">3.7 – 4.5 mils</td> </tr> <tr> <td style="border-bottom: 1px solid black;">– Dry</td> <td style="text-align: right;">1.4 – 1.7 mils</td> </tr> </table>	– Wet	3.7 – 4.5 mils	– Dry	1.4 – 1.7 mils																																																				
– Wet	3.7 – 4.5 mils																																																								
– Dry	1.4 – 1.7 mils																																																								
Depending on surface texture and porosity. Be sure to estimate the right amount of paint for the job. This will ensure color uniformity and minimize the disposal of excess paint.																																																									
Dry Time @ 77 °F (25 °C) @ 50% RH	<table style="width: 100%; border-collapse: collapse;"> <tr> <td style="width: 50%; border-bottom: 1px solid black;">– Tack Free</td> <td style="width: 50%; text-align: right;">1 Hour</td> </tr> <tr> <td style="border-bottom: 1px solid black;">– To Recoat</td> <td style="text-align: right;">4 Hours</td> </tr> </table>	– Tack Free	1 Hour	– To Recoat	4 Hours																																																				
– Tack Free	1 Hour																																																								
– To Recoat	4 Hours																																																								
High humidity and cool temperatures will result in longer dry, recoat and service times.																																																									
Dries By	Evaporation, Coalescence																																																								
Viscosity	97 – 103 KU																																																								
Flash Point	N/A																																																								
Gloss / Sheen	Flat (0.5 – 3.5 @ 85°)																																																								
Surface Temperature at Application	<table style="width: 100%; border-collapse: collapse;"> <tr> <td style="width: 50%; border-bottom: 1px solid black;">– Min.</td> <td style="width: 50%; text-align: right;">40 °F</td> </tr> <tr> <td style="border-bottom: 1px solid black;">– Max.</td> <td style="text-align: right;">100 °F</td> </tr> </table>	– Min.	40 °F	– Max.	100 °F																																																				
– Min.	40 °F																																																								
– Max.	100 °F																																																								
Thin With	Clean Water																																																								
Clean Up Thinner	Warm Soapy Water																																																								
Weight Per Gallon	11.3 lbs.																																																								
Storage Temperature	<table style="width: 100%; border-collapse: collapse;"> <tr> <td style="width: 50%; border-bottom: 1px solid black;">– Min.</td> <td style="width: 50%; text-align: right;">40 °F</td> </tr> <tr> <td style="border-bottom: 1px solid black;">– Max.</td> <td style="text-align: right;">90 °F</td> </tr> </table>	– Min.	40 °F	– Max.	90 °F																																																				
– Min.	40 °F																																																								
– Max.	90 °F																																																								
Volatile Organic Compounds (VOC)																																																									
46.1 Grams/Liter 0.38 Lbs./Gallon																																																									

Cryli Cote® 100% Acrylic Flat Exterior Paint Flat N10

Surface Preparation

Surfaces must be clean, dry and free of grease, wax, and mildew. Remove any chalk and loose or scaling paint. If previously coated with cement-base waterproofing paints, clean by sandblasting. Glossy surfaces must be dulled. Un-weathered areas such as eaves, ceilings, and overhangs should be washed with a detergent solution and/or rinsed with a strong stream of water from a garden hose to remove contaminants that can interfere with proper adhesion. Stains from mildew must be removed by cleaning with an anti-mildew wash prior to coating the surface.

Caution: Refer to the detergent solution's data and material safety data sheet for instructions on its proper use and handling. For metal surfaces, remove all active rust. Wipe down with paint thinner to remove surface oils.

All new masonry substrates must be allowed to cure for 30 days before priming or painting.

Priming

Wood – Non-bleeding: Apply 1-2 coats of Cryli Cote®

Wood – Bleeding: Prime redwood, cedar and other bleeding woods with a stain blocking primer

Galvanized and Aluminum: New galvanized metal surfaces must be thoroughly cleaned with an Oil & Grease Emulsifier to remove contaminants. Apply 1-2 coats of Cryli Cote®

Ferrous Metal: Apply a rust-inhibitive metal primer.

Masonry: Apply 1-2 coats of Cryli Cote®

WARNING! If you scrape, sand, or remove old paint, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Informational Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead.

WARRANTY: Manufacturer warrants that this product when used in accordance with the label instructions will not: 1. blister from properly prepared and primed surfaces, 2. peel from properly prepared and primed surfaces, and 3. wear down or weather to expose the previously painted surface. This warranty shall be effective for 20 years and is made to the original residential consumer paint purchaser. This warranty is non-transferable. If this product fails to perform as explained above when used according to label instructions within the warranty period, Manufacturer will, upon presentation of proof of purchase (original sales receipt), provide an equivalent or comparable product at no charge. Since we have no control over surface preparation or application, THIS LIMITED WARRANTY DOES NOT INCLUDE THE COST OF LABOR FOR APPLICATION OF PAINT. MANUFACTURER SHALL IN NO EVENT BE LIABLE FOR INDIRECT, SPECIAL, INCIDENTAL OR CONSEQUENTIAL DAMAGES. SOME STATES DO NOT ALLOW THE EXCLUSION OF INCIDENTAL OR CONSEQUENTIAL DAMAGES, SO THE LIMITATIONS OR EXCLUSIONS CONTAINED IN THE ABOVE WARRANTY MAY NOT APPLY TO YOU. This warranty gives you specific legal rights; you may also have other rights which vary state to state.

Application

Stir product with a circular, lifting motion before you begin to paint. Cryli Cote® may be applied by brush, spray or roller, at a rate of application not to exceed 450 square feet per gallon. Surface texture and porosity will affect actual yield. For best brush application results, use a quality synthetic filament brush. For roller application, use a 3/8" or 1/2" nap cover for smooth surfaces, a 3/4" nap cover for semi-rough surfaces and a 1" or 1 1/2" nap cover for rough surfaces. For spray application, thin with clean water, up to 20% reduction if necessary. Do not apply when surface or air temperatures are below 40 °F. Do not apply to hot surfaces or in direct sunlight. Do not apply if rain is threatening.

Clean Up

Clean up with warm, soapy water followed by a clean water rinse.

USE COMPLETELY OR DISPOSE OF PROPERLY. Dry empty containers may be recycled in a can recycling program. **Local disposal requirements vary; consult your sanitation department or state-designated environmental agency on disposal options.**

Environmental Health & Safety Information

WARNING!

Possible birth defect hazard. Contains, **Carbamic acid, 1H-benzimidazol-2-yl-, methyl ester**, which may cause birth defects based on animal data.

Use only with adequate ventilation. Do not breathe vapors, spray mist or sanding dust. Ensure fresh air entry during application and drying. Avoid contact with eyes and prolonged or repeated contact with skin. Avoid exposure to dust and spray mist by wearing a NIOSH approved respirator during application, sanding and clean up. Follow respirator manufacturer's directions for respirator use. Close container after each use. Wash thoroughly after handling.



WARNING: Cancer and Reproductive Harm—
www.P65warnings.ca.gov

WARNING: This product contains isothiazolinone compounds at levels of <0.1%. These substances are biocides commonly found in most paints and a variety of personal care products as a preservative. Certain individuals may be sensitive or allergic to these substances, even at low levels.

FIRST AID: In case of eye contact, flush immediately with plenty of water for at least 15 minutes; for skin, wash thoroughly with soap and water. If symptoms persist, seek medical attention. If you experience difficulty breathing, leave the area to obtain fresh air. If continued difficulty is experienced, get medical attention immediately.

IN CASE OF SPILL – Absorb with inert material and dispose of as specified under "Clean up".

**KEEP OUT OF REACH OF CHILDREN
PROTECT FROM FREEZING**

**Refer to Safety Data Sheet for
additional health and safety information.**