

Features

- Formula is ready to use for spraying out of the can
- Reduce cost of masking & covering
- Suitable for use in USDA inspected facilities
- Recoat in 4 hours
- Waterborne product with soap and water cleanup

Recommended For

- For spray application to interior ceilings, walls and structural members in commercial, residential and institutional buildings.
- Properly prepared galvanized metal

General Description

Super Kote 5000[®] Latex Dry Falls are formulated for spray application to interior ceilings, walls and structural members in commercial and institutional buildings. The overspray dries to a dust before reaching the floor. This feature reduces the cost of masking and covering procedures.

Limitations

- May be applied when surface and air temperatures are between 50 °F and 90 °F (10 °C – 32.2 °C).
- Spray application only.

Product Information

<p>Colors — Standard: White (1)</p> <p>— Tint Bases: N/A</p> <p>— Special Colors: Contact your dealer.</p> <p>Certification & Qualifications:</p> <p>The products supported by this data sheet contain a maximum of 150 grams per liter VOC/VOS (1.25 lbs. /gal.) excluding water and exempt solvents.</p> <p>This product meets the qualifications for LEED (Leadership in Energy and Environmental Design) projects.</p> <p>Master Painters Institute MPI # 226</p>	<p>Technical Data White</p> <table style="width: 100%; border-collapse: collapse;"> <tr> <td>Vehicle Type</td> <td style="text-align: right;">Acrylic</td> </tr> <tr> <td>Pigment Type</td> <td style="text-align: right;">Titanium Dioxide</td> </tr> <tr> <td>Volume Solids</td> <td style="text-align: right;">35.8 ± 2%</td> </tr> <tr> <td>Coverage per Gallon at Recommended Film Thickness</td> <td style="text-align: right;">400 – 500 sq. ft.</td> </tr> <tr> <td>Recommended Film Thickness</td> <td style="text-align: right;">– Wet 3.4 – 4.3 mils – Dry 1.2 – 1.5 mils</td> </tr> </table> <p>Depending on surface texture and porosity. Be sure to estimate the right amount of paint for the job. This will ensure color uniformity and minimize the disposal of excess paint.</p> <table style="width: 100%; border-collapse: collapse;"> <tr> <td>Dry Time @ 77 °F</td> <td style="text-align: right;">– Tack Free 1 Hour</td> </tr> <tr> <td>(25 °C) @ 50% RH</td> <td style="text-align: right;">– To Recoat 4 Hours</td> </tr> </table> <p>High humidity and cool temperatures will result in longer dry, recoat and service times.</p> <table style="width: 100%; border-collapse: collapse;"> <tr> <td>Dries By</td> <td style="text-align: right;">Evaporation</td> </tr> <tr> <td>Viscosity</td> <td style="text-align: right;">75 ± 4 KU</td> </tr> <tr> <td>Flash Point</td> <td style="text-align: right;">200 °F or greater (TT-P-141, Method 4293)</td> </tr> <tr> <td>Gloss / Sheen</td> <td style="text-align: right;">30 – 40 @ 60°</td> </tr> <tr> <td>Surface Temperature at Application</td> <td style="text-align: right;">– Min. 50 °F – Max. 90 °F</td> </tr> <tr> <td>Thin With</td> <td style="text-align: right;">Not Recommended</td> </tr> <tr> <td>Clean Up Thinner</td> <td style="text-align: right;">Warm, Soapy Water</td> </tr> <tr> <td>Weight Per Gallon</td> <td style="text-align: right;">10.3 lbs.</td> </tr> <tr> <td>Storage Temperature</td> <td style="text-align: right;">– Min. 50 °F – Max. 90 °F</td> </tr> </table> <p style="text-align: center;">Volatile Organic Compounds (VOC)</p> <p style="text-align: center;">68 Grams/Liter 0.62 lbs./Gallon</p>	Vehicle Type	Acrylic	Pigment Type	Titanium Dioxide	Volume Solids	35.8 ± 2%	Coverage per Gallon at Recommended Film Thickness	400 – 500 sq. ft.	Recommended Film Thickness	– Wet 3.4 – 4.3 mils – Dry 1.2 – 1.5 mils	Dry Time @ 77 °F	– Tack Free 1 Hour	(25 °C) @ 50% RH	– To Recoat 4 Hours	Dries By	Evaporation	Viscosity	75 ± 4 KU	Flash Point	200 °F or greater (TT-P-141, Method 4293)	Gloss / Sheen	30 – 40 @ 60°	Surface Temperature at Application	– Min. 50 °F – Max. 90 °F	Thin With	Not Recommended	Clean Up Thinner	Warm, Soapy Water	Weight Per Gallon	10.3 lbs.	Storage Temperature	– Min. 50 °F – Max. 90 °F
Vehicle Type	Acrylic																																
Pigment Type	Titanium Dioxide																																
Volume Solids	35.8 ± 2%																																
Coverage per Gallon at Recommended Film Thickness	400 – 500 sq. ft.																																
Recommended Film Thickness	– Wet 3.4 – 4.3 mils – Dry 1.2 – 1.5 mils																																
Dry Time @ 77 °F	– Tack Free 1 Hour																																
(25 °C) @ 50% RH	– To Recoat 4 Hours																																
Dries By	Evaporation																																
Viscosity	75 ± 4 KU																																
Flash Point	200 °F or greater (TT-P-141, Method 4293)																																
Gloss / Sheen	30 – 40 @ 60°																																
Surface Temperature at Application	– Min. 50 °F – Max. 90 °F																																
Thin With	Not Recommended																																
Clean Up Thinner	Warm, Soapy Water																																
Weight Per Gallon	10.3 lbs.																																
Storage Temperature	– Min. 50 °F – Max. 90 °F																																

Technical Assistance:

Available through your local authorized independent dealer. For the location of the dealer nearest you, call 1-866-708-9180, or visit www.coronadopaint.com

Surface Preparation

Surface to be painted must be clean and free of dirt, chalk, mildew, wax, grease, rust or loose flaking paint. Dirt and chalk should be removed by power washing or hand scrubbing with an abrasive cleanser and water, followed by a clean water rinse. Mildew must be removed by washing the surface with a solution of one part household bleach mixed with six parts water. Rinse well with clean water following wash. Wax should be removed by solvent cleaning. Grease and oil should be cleaned using an Oil & Grease Emulsifier. Rust must be removed by blasting, hand sanding vigorously or by conscientious power tool cleaning. Remove loose, flaking paint by scraping. Feather sand rough edges to insure a smooth finish coat. Glossy surfaces must be dulled by lightly sanding. Remove sanding dust before paint application. Any exposed substrate should be spot primed with the appropriate primer.

Priming:

Ferrous Metal – Use an acrylic or alkyd rust preventive metal primer.

Non-ferrous and galvanized metals, aluminum – Use an acrylic metal primer.

Wood – Use a latex or alkyd undercoat.

Drywall/Plaster – Use an Interior acrylic primer.

Concrete – Use an acrylic primer or block filler.

There are a number of specialty primers available in our family of brands that can be used on difficult substrates such as bleeding woods, hard glossy surfaces, or other substrates where paint adhesion or stain blocking is a problem. Your dealer can recommend the right problem solving primer necessary to meet your needs.

WARNING! If you scrape, sand, or remove old paint, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Informational Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead.

Application

Stir product thoroughly prior to painting. Apply by airless spray tip size .013 - .019 @ 1800 - 3000 PSI at a rate up to 400 – 500 square feet per gallon. Changes in relative humidity will cause significant differences in the distance required for dry fall characteristics. At 50% relative humidity, the product will dry fall at 8 feet. However, at 90% humidity, as much as 15 feet will be necessary for overspray to dry. Do not apply when temperature is below 50 °F. Thinning is not generally necessary. If required, use clean water sparingly.

NOTE: Adding water will affect the dry fall characteristics of this product by extending the drop distance necessary for overspray to dry.

Clean Up

Clean up with warm, soapy water.

USE COMPLETELY OR DISPOSE OF PROPERLY. Dry empty containers may be recycled in a can recycling program. **Local disposal requirements vary; consult your sanitation department or state-designated environmental agency on disposal options.**

Environmental, Health & Safety Information

Use only with adequate ventilation. Do not breathe spray mist or sanding dust. Ensure fresh air entry during application and drying. Avoid contact with eyes and prolonged or repeated contact with skin. Avoid exposure to dust and spray mist by wearing a NIOSH approved respirator during application, sanding and clean up. Follow respirator manufacturer's directions for respirator use. Close container after each use. Wash thoroughly after handling.



WARNING: This product can expose you to chemicals including Crystalline Silica, which are known to the State of California to cause cancer, and Ethylene glycol, which are known to the State of California to cause birth defects or other reproductive harm. For more information go to www.P65warnings.ca.gov

FIRST AID: In case of eye contact, flush immediately with plenty of water for at least 15 minutes; for skin, wash thoroughly with soap and water. If symptoms persist, seek medical attention. If you experience difficulty breathing, leave the area to obtain fresh air. If continued difficulty is experienced, get medical attention immediately.

IN CASE OF SPILL – Absorb with inert material and dispose of as specified under "Clean Up".

**KEEP OUT OF REACH OF CHILDREN
PROTECT FROM FREEZING**

**Refer to Safety Data Sheet for
additional health and safety information.**