



# SUPER KOTE 5000 ACRYLIC LATEX ENAMEL SATIN FINISH 1160

## Features

- Premium commercial acrylic latex designed for the professional painter
- No spatter and good flow & levelling provide fast production
- Professional satin finish withstands washing and scrubbing
- Soap and water clean up
- Low VOC

## General Description

Super Kote 5000 Acrylic Satin Enamel is suited for wall and trim applications in kitchens, bathrooms, family rooms, hallways and bedrooms where routine cleaning is needed. Fast dry and a pleasant satin sheen make it an ideal finish for residential or commercial jobs.

## Recommended For

Interior drywall, plaster, wood, metal, masonry and stucco in commercial, institutional and residential applications. Ideal for wall and trim where routine cleaning is needed.

## Limitations

- May be applied when surface and air temperatures are between 10 °C and 32.2 °C (50 °F and 90 °F).

## Product Information

Product Information																																																																									
<b>Colours — Standard:</b> White	<b>Technical Data<sup>◇</sup></b> <table border="1"> <thead> <tr> <th colspan="2"></th> <th>White</th> </tr> </thead> <tbody> <tr> <td>Vehicle Type</td> <td></td> <td>Vinyl Acrylic</td> </tr> <tr> <td>Pigment Type</td> <td></td> <td>Titanium Dioxide</td> </tr> <tr> <td>Volume Solids</td> <td></td> <td>33 ± 1.0%</td> </tr> <tr> <td>Coverage per 3.79 L at Recommended Film Thickness</td> <td></td> <td>32.5 – 41.8 sq. m. (350 – 450 sq. ft.)</td> </tr> <tr> <td>Recommended Film Thickness</td> <td>– Wet</td> <td>3.6 - 4.6 mils</td> </tr> <tr> <td></td> <td>– Dry</td> <td>1.2 - 1.5 mils</td> </tr> <tr> <td colspan="3">Depending on surface texture and porosity. Be sure to estimate the right amount of paint for the job. This will ensure colour uniformity and minimize the disposal of excess paint.</td> </tr> <tr> <td>Dry Time @ 25 °C (77 °F) @ 50% RH</td> <td>– Tack Free</td> <td>30 Minutes</td> </tr> <tr> <td></td> <td>– To Recoat</td> <td>4 Hours</td> </tr> <tr> <td colspan="3">High humidity and cool temperatures will result in longer dry, recoat and service times.</td> </tr> <tr> <td>Dries By</td> <td></td> <td>Evaporation</td> </tr> <tr> <td>Viscosity</td> <td></td> <td>90 – 95 KU</td> </tr> <tr> <td>Flash Point</td> <td></td> <td>N/A</td> </tr> <tr> <td>Gloss / Sheen</td> <td></td> <td>Satin 20-25units @ 15.6 °C (60 °F)</td> </tr> <tr> <td>Surface Temperature at Application</td> <td>– Min.</td> <td>10 °C (50 °F)</td> </tr> <tr> <td></td> <td>– Max.</td> <td>32.2 °C (90 °F)</td> </tr> <tr> <td>Thin With</td> <td></td> <td>Clean Water</td> </tr> <tr> <td>Clean Up Thinner</td> <td></td> <td>Warm, Soapy Water</td> </tr> <tr> <td>Weight Per 3.79 L</td> <td></td> <td>4.8 kg (10.6 lbs)</td> </tr> <tr> <td>Storage Temperature</td> <td>– Min.</td> <td>7.2 °C (45 °F)</td> </tr> <tr> <td></td> <td>– Max.</td> <td>32.2 °C (90 °F)</td> </tr> <tr> <td colspan="3" style="text-align: center;"><b>Volatile Organic Compounds (VOC)</b></td> </tr> <tr> <td></td> <td>95 Grams/Litre</td> <td>0.36 kg (0.79 Lbs.)/3.79 L</td> </tr> </tbody> </table>			White	Vehicle Type		Vinyl Acrylic	Pigment Type		Titanium Dioxide	Volume Solids		33 ± 1.0%	Coverage per 3.79 L at Recommended Film Thickness		32.5 – 41.8 sq. m. (350 – 450 sq. ft.)	Recommended Film Thickness	– Wet	3.6 - 4.6 mils		– Dry	1.2 - 1.5 mils	Depending on surface texture and porosity. Be sure to estimate the right amount of paint for the job. This will ensure colour uniformity and minimize the disposal of excess paint.			Dry Time @ 25 °C (77 °F) @ 50% RH	– Tack Free	30 Minutes		– To Recoat	4 Hours	High humidity and cool temperatures will result in longer dry, recoat and service times.			Dries By		Evaporation	Viscosity		90 – 95 KU	Flash Point		N/A	Gloss / Sheen		Satin 20-25units @ 15.6 °C (60 °F)	Surface Temperature at Application	– Min.	10 °C (50 °F)		– Max.	32.2 °C (90 °F)	Thin With		Clean Water	Clean Up Thinner		Warm, Soapy Water	Weight Per 3.79 L		4.8 kg (10.6 lbs)	Storage Temperature	– Min.	7.2 °C (45 °F)		– Max.	32.2 °C (90 °F)	<b>Volatile Organic Compounds (VOC)</b>				95 Grams/Litre	0.36 kg (0.79 Lbs.)/3.79 L
		White																																																																							
Vehicle Type		Vinyl Acrylic																																																																							
Pigment Type		Titanium Dioxide																																																																							
Volume Solids		33 ± 1.0%																																																																							
Coverage per 3.79 L at Recommended Film Thickness		32.5 – 41.8 sq. m. (350 – 450 sq. ft.)																																																																							
Recommended Film Thickness	– Wet	3.6 - 4.6 mils																																																																							
	– Dry	1.2 - 1.5 mils																																																																							
Depending on surface texture and porosity. Be sure to estimate the right amount of paint for the job. This will ensure colour uniformity and minimize the disposal of excess paint.																																																																									
Dry Time @ 25 °C (77 °F) @ 50% RH	– Tack Free	30 Minutes																																																																							
	– To Recoat	4 Hours																																																																							
High humidity and cool temperatures will result in longer dry, recoat and service times.																																																																									
Dries By		Evaporation																																																																							
Viscosity		90 – 95 KU																																																																							
Flash Point		N/A																																																																							
Gloss / Sheen		Satin 20-25units @ 15.6 °C (60 °F)																																																																							
Surface Temperature at Application	– Min.	10 °C (50 °F)																																																																							
	– Max.	32.2 °C (90 °F)																																																																							
Thin With		Clean Water																																																																							
Clean Up Thinner		Warm, Soapy Water																																																																							
Weight Per 3.79 L		4.8 kg (10.6 lbs)																																																																							
Storage Temperature	– Min.	7.2 °C (45 °F)																																																																							
	– Max.	32.2 °C (90 °F)																																																																							
<b>Volatile Organic Compounds (VOC)</b>																																																																									
	95 Grams/Litre	0.36 kg (0.79 Lbs.)/3.79 L																																																																							
<b>— Tint Bases:</b> 1160-33, Tint Base																																																																									
<b>— Special Colours:</b> Contact your dealer.																																																																									
<b>Certifications &amp; Qualifications :</b>  The products supported by this data sheet contain a maximum of 100 grams per litre VOC / VOS (0.83 lbs/gal.) excluding water & exempt solvents  This product is compliant as a Non-Flat Coating.  This product is certified under MPI #43.  This product meets the qualifications for LEED (Leadership in Energy and Environmental Design) projects as a non-flat coating.  This product has been approved by CFIA (Canadian Food Inspection Agency) for use in Food Processing Facilities.																																																																									
<b>Technical Assistance:</b> Available through your local authorized independent dealer. For the location of the dealer nearest you, call 1-800-361-5898 or visit <a href="http://www.coronadopaint.ca">www.coronadopaint.ca</a> .																																																																									

<sup>◇</sup> Reported values are for White. Contact dealer for values of other bases or colours.

## Super Kote 5000 Acrylic Latex Enamel Satin Finish 1160

### Surface Preparation

Surfaces to be painted must be clean, dry, and free of dirt, dust, grease, oil, soap, wax, scaling paint, water soluble materials and mildew. Remove any peeling or scaling paint, and sand these areas to feather edges smooth with adjacent surfaces. Glossy areas should be dulled. Drywall surfaces must be free of sanding dust. Spot prime before and after filling nail holes, cracks, and other surface imperfections.

New plaster or masonry surfaces must be allowed to cure (30 days) before applying base coat. Cured plaster should be hard, have a slight sheen and maximum pH of 10; soft, porous or powdery plaster indicates improper cure. Knife off any protrusions and prime plaster before and after applying patching compound. Remove any powder or loose particles.

**Primers:** New surfaces should be fully primed. Previously painted surfaces should be primed or spot primed as necessary. There are a number of specialty primers available in our family of brands that can be used on difficult substrates such as bleeding woods, hard glossy surfaces, or other substrates where paint adhesion or stain blocking is a problem. Your dealer can recommend the right problem solving primer necessary to meet your needs.

**WARNING!** If you scrape, sand, or remove old paint, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by logging onto Health Canada @ <https://www.canada.ca/en/health-canada/services/environmental-workplace-health/environmental-contaminants/lead/lead-information-package-some-commonly-asked-questions-about-lead-human-health.html>

### Application

Stir product with a circular, lifting motion before you begin to paint. Super Kote 5000 Acrylic Latex Satin Enamel may be applied by brush, roller, pad or spray techniques, at a rate of application not to exceed 37.2 metres per 3.79 litres (400 square feet per gallon). Surface texture and porosity will affect actual yield. **For best brush application** results, use a quality synthetic filament brush. **For roller application**, use a 6.4 mm to 9.5 mm (¼" to 3/8") nap cover for smooth surfaces, a 12.7 mm (½") nap cover for semi-rough surfaces and a 19.1 mm to 25.4 mm (¾" – 1") nap cover for rough surfaces. Do not jeopardize the success of your painting project by using poor quality applicator tools. Apply only when surface and air temperatures are between 10 °C and 32.2 °C (50 °F and 90 °F).

**Airless** – Tip size and atomization pressures will vary with the type of equipment, viscosity and temperature. An orifice of .017 - .019 will provide the most satisfactory spray pattern. Super Kote 5000 Acrylic Latex Satin Enamel may be thinned with clean water, up to 15%, for spray application.

### Clean up

Clean up with warm, soapy water followed by a clean water rinse.

### Environmental Health & Safety Information

**Use only in a well ventilated area.** Keep container closed when not in use. In case of spillage, absorb with inert material and dispose of in accordance with local regulations. Wash thoroughly after handling.

**KEEP OUT OF REACH OF CHILDREN  
PROTECT FROM FREEZING**

**Refer to Safety Data Sheet for  
additional health and safety information.**