



ULTRALAQ[®]

LOW HAPS WHITE PRE-CATALYZED N/C TOPCOAT 1M.80X

Features

- Passes KCMA Standards
- Meets AWI OP-5 Standards
- Excellent Chemical Resistance

General Description

Lenmar[®] UltraLaq[®] 1M.80X White Precatalyzed Nitrocellulose topcoats are designed for professional woodworkers who demand top quality performance and durability in a lacquer finish. This white precat lacquer offers superior resistance to moisture, an exceptional amount of solids for hiding, resists cold checking. No reduction is required, but depending on the type of spray equipment used, reduction with Lenmar[®] 1A.406 lacquer thinner might be necessary to achieve good atomization. This product should be used in conjunction with the UltraLaq[®] 1C.800 White Precatalyzed undercoater, or another approved Lenmar[®] undercoat.

Recommended For

Furniture, Kitchen Cabinets, Bathroom Vanities, Displays & Fixtures

Limitations

- Entire system not to exceed 5 mils dry.
- Not for use on floors.

Product Information

Colours — Standard:	Technical Data	White/Gloss
1M-802 Dull Rubbed	Vehicle Type	Nitrocellulose/Alkyd/Urea
1M-804 Satin	Pigment Type	N/A
1M-806 Semi-Gloss	Weight Solids	43% ±1.0%
1M-808 Gloss	Volume Solids	25% ± 1.0%
— Tint Bases:	Coverage per 3.79 L at 1 mil DFT	37.3 – 39.5 sq. m. (401 – 425 sq. ft.)
N/A	Recommended Film Thickness	– Wet 3 - 5 mils – Dry 0.9 – 1.25 mils
— Special Colours:	Coverage calculation does not include spray loss or equipment inefficiency. Also allow for wood species, surface preparation, surface defects and porosity of substrate to affect spread rates.	
N/A	Dry Time @ 23.8 °C (75 °F) @ 50% RH	– To Sand 25 – 35 Minutes – To Recoat 30 – 45 Minutes
Certifications & Qualifications:	High humidity and cool temperatures will result in longer dry and recoat times.	
The products supported by this data sheet contain a maximum of 680 grams per litre VOC /VOS excluding water & exempt solvents.	Dries By	Evaporation
This product is not compliant for field applications. This product is intended for Shop or OEM application only.	Viscosity	20 – 25 Seconds (#2 Zahn)
	Flash Point	2.2 °C (36 °F)
	Gloss / Sheen	Gloss/Semi-Gloss/Satin /Dull Rubbed
	Surface Temperature at Application	– Min. 20 °C (68 °F) – Max. 32.2 °C (90 °F)
	Thin With	Not Required
	Clean Up Thinner	1A.406 or 1A.519 Lacquer Thinner
	Weight Per 3.79 L	4.1 – 4.2 kg (9.1 – 9.3 lbs.)
	Storage Temperature	– Min. 10 °C (50 °F) – Max. 32.2 °C (90 °F)
	Volatile Organic Compounds (VOC)	
	608 Grams/Litre	
Technical Assistance:	Available through your local authorized independent dealer. For the location of the dealer nearest you, call 1-800-361-5898 or visit www.lenmar-coatings.ca	

UltraLaq® Low HAPS White Pre-catalyzed N/C Topcoat 1M.80X

WARNING! If you scrape, sand, or remove old paint, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by logging onto Health Canada @<https://www.canada.ca/en/health-canada/services/environmental-workplace-health/environmental-contaminants/lead/lead-information-package-some-commonly-asked-questions-about-lead-human-health.html>

Application

ENTIRE SYSTEM SHOULD NOT EXCEED MORE THAN 5 MILS DRY. LENMAR PRODUCTS ARE DESIGNED FOR INTERIOR USE, BY SPRAY APPLICATION ONLY.

Apply one coat of UltraLaq® 1C.800 premium precatalyzed white undercoater (or another recommended undercoater) in accordance with supplied guidelines. Select the desired sheen from the UltraLaq® 1M.80X Series, **shake well** and apply two full coats, 3–5 mils each. Allow to dry 30 - 60 minutes and scuff sand between each coat. Total system should be three coats, either 2 undercoats and one topcoat, or one undercoat and two topcoats.

ENTIRE SYSTEM SHOULD NOT EXCEED 5 MILS DRY.

Specifications

Moisture content of wood should be no higher than 9%. Wood must be free of surface contaminants. Sand wood with no finer than 120-grit sandpaper and remove all dust. Apply by spray only at a rate of 3–5 mils wet. Mix all product well before use. Apply UltraLaq® 1C.800, precatalyzed white undercoater (or another approved undercoater as a first coat) let dry and sand with 280-320 grit, non-stearated, silicon carbide sandpaper. Follow with two additional wet coats (3–5 mils) of UltraLaq® 1M.80X series topcoat in the desired sheen, scuff sanding between each coat. No reduction is required. However, the 1M.80X Series may be reduced or retarded with Acetone, T-Butyl Acetate, 1A.406 or 1A.114, if necessary, for specific application conditions. Do not reduce if doing so would violate any VOC regulations. Check with equipment manufacturer for correct settings to achieve proper atomization of material. Read label and SDS for additional information and warnings.

Clean Up

Clean up with 1A.406 or 1A.519 Lacquer Thinner.

Environmental Health & Safety Information

DANGER!

Causes skin irritation

Causes serious eye damage

May cause cancer

May damage fertility or the unborn child

May cause damage to organs

May cause damage to organs through prolonged or repeated exposure

Highly flammable liquid and vapor

Reactive flammable material

Prevention: Obtain special instructions before use. Do not handle until all safety precautions have been read and understood. Use personal protective equipment as required. Wash face, hands and any exposed skin thoroughly after handling. Do not breathe dust/fume/mist/vapors/spray. Do not eat, drink or smoke when using this product. Keep away from heat/sparks/open flames/hot surfaces, no smoking. Keep container tightly closed. Ground/bond container and receiving equipment. Use explosion-proof electrical/ventilating/ lighting/equipment. Use only non-sparking tools. Take precautionary measures against static discharge.

Response: If exposed or concerned get medical attention. If in eyes rinse cautiously with water for several minutes. Remove contact lenses, if present and easy to do. Continue rinsing. Immediately call a POISON CENTER or physician. If skin irritation occurs get medical attention. If on skin (or hair) take off immediately all contaminated clothing. Rinse skin with water. Wash contaminated clothing before reuse. In case of fire use CO₂, dry chemical, or foam for extinction.

Storage: Store locked up. Store in a well-ventilated place. Keep cool.

Disposal: Dispose of contents/container to an approved waste disposal plant.

This document presents hazards of the product referenced above. Refer to the individual Material Safety Data Sheet for hazards of the specific product you will be using.

KEEP OUT OF REACH OF CHILDREN

THIS PRODUCT IS INTENDED FOR SHOP OR OEM APPLICATION ONLY.

**READ ALL DIRECTIONS BEFORE USE.
UNDERSTAND ALL DANGERS WITH THIS
PRODUCT PRIOR TO USE.**

**Refer to Safety Data Sheet for
additional health and safety information.**