



# DURALAQ-WB<sup>®</sup>

## STRIPPABLE SPRAY BOOTH COATING

### 1W.48X

#### Features

- Easy Clean Up With Water
- Apply By Brush Or Spray
- Non-Flammable
- Peels Quickly & Cleanly
- White Reflects Light
- Tintable

#### General Description

Lenmar<sup>®</sup> DuraLaq-WB<sup>®</sup> Waterborne Strippable Spray Booth Coatings are designed to facilitate the removal of troublesome over-spray build-up from spray booth walls, ducts and baffles. They are quick drying. When applied to walls of the spray booth, these specialty coatings will remain not only flexible but, due to reflective surfaces, will also increase the brightness in the spray booth. DuraLaq-WB<sup>®</sup> Strippable Booth Coater will peel away easily, together with any overspray deposited, when cleaning or recoating is necessary. These coatings will reduce the down time from cleaning the spray room; they will also preserve the initial investment and keep the booth operating efficiently. Booth coatings may be applied directly to wood or glass surfaces as a mask allowing for easy clean-up and touch-up of painted surfaces.

#### Recommended For

On glass as a mask, spray booths.

#### Limitations

- Make sure your spray equipment is designed for use with waterborne products

#### Product Information

<b>Colors — Standard:</b> Milky Clear (1W.482) and White (1W.483)	<b>Technical Data</b> ◊ <b>Milky Clear</b>
<b>— Tint Bases:</b> N/A	Vehicle Type Vinyl Acrylic
<b>— Special Colors:</b> N/A	Pigment Type Titanium Dioxide
<b>Certifications &amp; Qualifications:</b> <b>VOC compliant in all regulated areas</b>  The products supported by this data sheet contain a maximum of 100 grams per liter VOC /VOS (0.83 lbs/gal.) excluding water & exempt solvents.	Weight Solids 51% ± 1.0%
	Volume Solids 48.4%
<b>Technical Assistance:</b> Available through your local authorized independent Lenmar dealer. For the location of the dealer nearest you, call 1-866-708-9180 or visit <a href="http://www.lenmar-coatings.com">www.lenmar-coatings.com</a>	Coverage per Gallon at Recommended Film Thickness 225 – 325 Sq. Ft.
	Recommended Film Thickness – Wet 5 – 7 mils – Dry 2.4 – 3.7 mils
	Coverage calculation does not include spray loss or equipment inefficiency. Also allow for wood species, surface preparation, surface defects and porosity of substrate to affect spread rates
	Dry Time @ 75 °F (23.8 °C) @ 50% RH – To Touch 15 Minutes – To Recoat 45 Minutes
	High humidity and cool temperatures will result in longer dry and recoat times.
	Dries By Coalescence
	Viscosity 70 – 80 KU
	Flash Point >200° F
	Gloss / Sheen Flat
	Surface Temperature at Application – Min. 68 °F – Max. 90 °F
Thin With Distilled Water	
Clean Up Thinner Use distilled water immediately & flush system with isopropyl alcohol	
Weight Per Gallon 9.2 – 9.4 lbs.	
Storage Temperature – Min. 50 °F – Max. 90 °F	
<b>Volatile Organic Compounds (VOC)</b>  82.8 Grams/Liter    0.69 Lbs./Gallon	

◊ Reported values are for Milky Clear. Contact dealer/distributor for values of other bases or colors.

## Duralaq-WB® Strippable Spray Booth Coating 1W.48X

**WARNING!** If you scrape, sand, or remove old paint, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Informational Hotline at 1-800-424-LEAD or log on to [www.epa.gov/lead](http://www.epa.gov/lead).

### Application

This high solids booth coating can be applied with a nylon brush straight from the container; for spray applications, reduce the material with distilled water, only as required to achieve good atomization. Make sure your spray equipment is designed for use with waterborne products. Apply a full wet coat of 5-7 mils for maximum protection. When applying less than the recommended wet film thickness it greatly reduces the effectiveness of this product.

### Specifications

Make sure surface is free of all contaminants prior to applying the booth coat. When spraying, reduce the coating with distilled water as required. Check with spray equipment manufacturer for proper settings. Flush your equipment immediately after use with warm water and do a final rinse with Isopropyl Alcohol to remove moisture in the line. Apply a minimum of 5 mils wet for maximum protection. Ensure 2 dry mils applied when application is complete. Read label and SDS for additional information and warnings.

### Clean up

Use distilled water immediately and flush system with Isopropyl Alcohol.

## Environmental Health & Safety Information

Not a hazardous substance or mixture according to the Globally Harmonized System (GHS)

Keep container closed when not in use. In case of spillage, absorb with inert material and dispose of in accordance with local regulations. Wash thoroughly after handling. Refer to Safety Data Sheet for additional health and safety information.

1.8 % of the mixture consists of ingredient(s) of unknown toxicity



**WARNING** Cancer and Reproductive Harm—  
[www.P65warnings.ca.gov](http://www.P65warnings.ca.gov)

This document represents hazards of the product referenced above. Refer to the individual Safety Data Sheet for hazards of the specific product you will be using.

**KEEP OUT OF REACH OF CHILDREN  
KEEP FROM FREEZING  
FOR PROFESSIONAL USE ONLY**

**READ ALL DIRECTIONS BEFORE USE.  
UNDERSTAND ALL DANGERS WITH THIS  
PRODUCT PRIOR TO USE.**

**Refer to Safety Data Sheet for additional  
health and safety information.**