



SUPER KOTE 5000[®]

ACRYLIC LATEX ENAMEL SEMI-GLOSS 32 LINE

Features

- Premium commercial acrylic latex designed for the professional painter
- Professional semi-gloss finish withstands washing and scrubbing
- No spatter and good flow & leveling provide fast production
- Soap and water cleanup

Recommended For

Interior drywall, plaster, wood, metal, and masonry in commercial, institutional and residential applications. Ideal for walls and trim where routine cleaning is needed.

General Description

Super Kote 5000[®] Acrylic Latex Semi-Gloss Enamel is designed for commercial projects—when getting the job done quickly is a priority. Suited for wall and trim applications in kitchens, bathrooms, and hallways where routine cleaning is needed. With low spatter and easy application, this premium-quality, vinyl-acrylic formula delivers dependable quality and may be washed repeatedly without film damage.

Limitations

- Apply only when surface and air temperatures are above 50 °F (10 °C).

Product Information

<p>Colors — Standard: White (1)</p> <p>— Tint Bases: Pastel Base (32), Tint Base (33), Deep Base (34), Accent Base (36) Tint with Universal colorants only</p> <p>— Special Colors: Contact your dealer.</p> <p>Certification & Qualifications:</p> <p>The products supported by this data sheet contain a maximum of 50 grams per liter VOC/VOS (0.42 lbs./gal.) excluding water & exempt solvents.</p> <table border="1"> <thead> <tr> <th>VOC REGION</th> <th>COMPLIANT</th> </tr> </thead> <tbody> <tr><td>FEDERAL</td><td>YES</td></tr> <tr><td>OTC</td><td>YES</td></tr> <tr><td>LADCO</td><td>YES</td></tr> <tr><td>OTCII</td><td>YES</td></tr> <tr><td>OTCII RI</td><td>YES</td></tr> <tr><td>CARB</td><td>YES</td></tr> <tr><td>CARB07</td><td>YES</td></tr> <tr><td>UTAH</td><td>YES</td></tr> <tr><td>AZMC</td><td>YES</td></tr> <tr><td>SCAQMD</td><td>NO</td></tr> </tbody> </table> <p>Technical Assistance: Available through your local authorized independent dealer. For the location of the dealer nearest you, call 1-866-708-9180, or visit www.coronadopaint.com</p>	VOC REGION	COMPLIANT	FEDERAL	YES	OTC	YES	LADCO	YES	OTCII	YES	OTCII RI	YES	CARB	YES	CARB07	YES	UTAH	YES	AZMC	YES	SCAQMD	NO	<p>Technical Data White</p> <table border="1"> <tr><td>Vehicle Type</td><td colspan="2">Vinyl Acetate/Acrylic</td></tr> <tr><td>Pigment Type</td><td colspan="2">Titanium Dioxide</td></tr> <tr><td>Volume Solids</td><td colspan="2">34 ± 1.0%</td></tr> <tr><td>Coverage per Gallon at Recommended Film Thickness</td><td colspan="2">300 – 400 Sq. Ft.</td></tr> <tr><td>Recommended Film Thickness</td><td>– Wet</td><td>4.0 – 5.3 mils</td></tr> <tr><td></td><td>– Dry</td><td>1.3 – 1.7 mils</td></tr> </table> <p>Depending on surface texture and porosity. Be sure to estimate the right amount of paint for the job. This will ensure color uniformity and minimize the disposal of excess paint.</p> <table border="1"> <tr><td>Dry Time @ 77 °F (25 °C) @ 50% RH</td><td>– Tack Free</td><td>30 Minutes</td></tr> <tr><td></td><td>– To Recoat</td><td>4 Hours</td></tr> </table> <p>High humidity and cool temperatures will result in longer dry, recoat and service times.</p> <table border="1"> <tr><td>Dries By</td><td colspan="2">Coalescence</td></tr> <tr><td>Viscosity</td><td colspan="2">95 – 100 KU</td></tr> <tr><td>Flash Point</td><td colspan="2">200 °F or greater (TT-P-141, Method 4293)</td></tr> <tr><td>Gloss / Sheen</td><td colspan="2">Semi-Gloss (45 - 55 @ 60°)</td></tr> <tr><td>Surface Temperature at Application</td><td>– Min.</td><td>50 °F</td></tr> <tr><td></td><td>– Max.</td><td>90 °F</td></tr> <tr><td>Thin With</td><td colspan="2">Clean Water</td></tr> <tr><td>Clean Up Thinner</td><td colspan="2">Warm, Soapy Water</td></tr> <tr><td>Weight Per Gallon</td><td colspan="2">10.3 lbs.</td></tr> <tr><td>Storage Temperature</td><td>– Min.</td><td>40 °F</td></tr> <tr><td></td><td>– Max.</td><td>95 °F</td></tr> </table> <p style="text-align: center;">Volatile Organic Compounds (VOC)</p> <p style="text-align: center;">45 Grams/Liter 0.42 Lbs./Gallon</p>	Vehicle Type	Vinyl Acetate/Acrylic		Pigment Type	Titanium Dioxide		Volume Solids	34 ± 1.0%		Coverage per Gallon at Recommended Film Thickness	300 – 400 Sq. Ft.		Recommended Film Thickness	– Wet	4.0 – 5.3 mils		– Dry	1.3 – 1.7 mils	Dry Time @ 77 °F (25 °C) @ 50% RH	– Tack Free	30 Minutes		– To Recoat	4 Hours	Dries By	Coalescence		Viscosity	95 – 100 KU		Flash Point	200 °F or greater (TT-P-141, Method 4293)		Gloss / Sheen	Semi-Gloss (45 - 55 @ 60°)		Surface Temperature at Application	– Min.	50 °F		– Max.	90 °F	Thin With	Clean Water		Clean Up Thinner	Warm, Soapy Water		Weight Per Gallon	10.3 lbs.		Storage Temperature	– Min.	40 °F		– Max.	95 °F
VOC REGION	COMPLIANT																																																																															
FEDERAL	YES																																																																															
OTC	YES																																																																															
LADCO	YES																																																																															
OTCII	YES																																																																															
OTCII RI	YES																																																																															
CARB	YES																																																																															
CARB07	YES																																																																															
UTAH	YES																																																																															
AZMC	YES																																																																															
SCAQMD	NO																																																																															
Vehicle Type	Vinyl Acetate/Acrylic																																																																															
Pigment Type	Titanium Dioxide																																																																															
Volume Solids	34 ± 1.0%																																																																															
Coverage per Gallon at Recommended Film Thickness	300 – 400 Sq. Ft.																																																																															
Recommended Film Thickness	– Wet	4.0 – 5.3 mils																																																																														
	– Dry	1.3 – 1.7 mils																																																																														
Dry Time @ 77 °F (25 °C) @ 50% RH	– Tack Free	30 Minutes																																																																														
	– To Recoat	4 Hours																																																																														
Dries By	Coalescence																																																																															
Viscosity	95 – 100 KU																																																																															
Flash Point	200 °F or greater (TT-P-141, Method 4293)																																																																															
Gloss / Sheen	Semi-Gloss (45 - 55 @ 60°)																																																																															
Surface Temperature at Application	– Min.	50 °F																																																																														
	– Max.	90 °F																																																																														
Thin With	Clean Water																																																																															
Clean Up Thinner	Warm, Soapy Water																																																																															
Weight Per Gallon	10.3 lbs.																																																																															
Storage Temperature	– Min.	40 °F																																																																														
	– Max.	95 °F																																																																														

◊ Reported values are for White.

Super Kote 5000® Acrylic Latex Enamel Semi-Gloss Finish 32 Line

Surface Preparation

Surfaces to be painted must be clean, dry, and free of dirt, dust, grease, oil, soap, wax, scaling paint, water soluble materials and mildew. Remove any peeling or scaling paint, and sand these areas to feather edges smooth with adjacent surfaces. Glossy areas should be dulled. Drywall surfaces must be free of sanding dust. Spot prime before and after filling nail holes, cracks, and other surface imperfections.

New plaster or masonry surfaces must be allowed to cure (30 days) before applying base coat. Cured plaster should be hard, have a slight sheen and maximum pH of 10; soft, porous or powdery plaster indicates improper cure.

Primers: New surfaces should be fully primed. Previously painted surfaces should be primed or spot primed as necessary. There are a number of specialty primers available in our family of brands that can be used on difficult substrates such as bleeding woods, hard glossy surfaces, or other substrates where paint adhesion or stain blocking is a problem. Your dealer can recommend the right problem solving primer necessary to meet your needs.

WARNING! If you scrape, sand, or remove old paint, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Informational Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead.

Application

Stir thoroughly. Apply by brush (synthetic filament), roller or spray. Length of roller nap depends upon the texture of the surface. Thinning is not usually required for brush or roller application. Apply a full, even coat. Do not apply directly over chalky surfaces or bleeding stains. Apply only when surface and air temperatures are above 50 °F (10 °C).

Spray, Airless: Fluid Pressure —1,500 to 2,000 PSI;
Tip —.015 - .019 Orifice

Clean Up

Clean up with warm, soapy water.

USE COMPLETELY OR DISPOSE OF PROPERLY. Dry, empty containers may be recycled in a can recycling program. **Local disposal requirements vary; consult your sanitation department or state-designated environmental agency on disposal options.**

Environmental Health & Safety Information

Use only with adequate ventilation. Do not breathe spray mist or sanding dust. Ensure fresh air entry during application and drying. Avoid contact with eyes and prolonged or repeated contact with skin. Avoid exposure to dust and spray mist by wearing a NIOSH approved respirator during application, sanding and clean up. Follow respirator manufacturer's directions for respirator use. Close container after each use. Wash thoroughly after handling.



WARNING: Cancer and Reproductive Harm—
www.P65warnings.ca.gov

WARNING: This product contains isothiazolinone compounds at levels of <0.1%. These substances are biocides commonly found in most paints and a variety of personal care products as a preservative. Certain individuals may be sensitive or allergic to these substances, even at low levels.

FIRST AID: In case of eye contact, flush immediately with plenty of water for at least 15 minutes; for skin, wash thoroughly with soap and water. If symptoms persist, seek medical attention. If you experience difficulty breathing, leave the area to obtain fresh air. If continued difficulty is experienced, get medical attention immediately.

IN CASE OF SPILL – Absorb with inert material and dispose of as specified under “Clean Up”.

**KEEP OUT OF REACH OF CHILDREN
PROTECT FROM FREEZING**

**Refer to Safety Data Sheet for
additional health and safety information.**