



# CRYLI COTE®

## 100% ACRYLIC EXTERIOR PAINT

### SATIN C410 LINE

#### Features

- 100% Acrylic Exterior Paint
- Superb Color Retention
- Excellent Durability
- Fast Dry
- Blister Resistant
- Self-priming on many surfaces

#### Recommended For

For exterior wood, masonry, hardboard and metal in commercial, institutional and residential applications. Use on exterior siding, foundations, fascia, shutters or retaining walls. Designed as a self-priming system on non-bleeding woods, smooth poured or pre-cast masonry and clean, rust free galvanized surfaces.

#### General Description

Cryli Cote® Satin Exterior Paint provides tenacious adhesion to a variety of substrates. It is blister resistant, exhibits excellent durability and superb color retention. It is an excellent choice for painting pre-finished siding new or previously painted surfaces in good condition. Contains an agent which inhibits growth of mildew on the surface of the paint film.

#### Limitations

- Do not apply when air and surface temperatures are below 40 °F (4.4 °C).
- Not for interior use.

#### Product Information

|   |  |   |              |                  |                  |               |           |   |                   |                            |  |             |     |               |                       |                                    |                               |           |             |                  |                  |                   |          |                     |                              |
|---|--|---|--------------|------------------|------------------|---------------|-----------|---|-------------------|----------------------------|--|-------------|-----|---------------|-----------------------|------------------------------------|-------------------------------|-----------|-------------|------------------|------------------|-------------------|----------|---------------------|------------------------------|
| <b>Colors — Standard:</b><br>White (1)  | <b>Technical Data</b> <span style="float: right;"><b>White</b></span>  |   |              |                  |                  |               |           |   |                   |                            |  |             |     |               |                       |                                    |                               |           |             |                  |                  |                   |          |                     |                              |
| <b>— Tint Bases:</b><br>Tint Base (33), Deep Base (34), Accent Base (36)<br><br>Tint with Universal colorants only  | <table border="1"> <tr> <td>Vehicle Type</td> <td>100% Acrylic</td> </tr> <tr> <td>Pigment Type</td> <td>Titanium Dioxide</td> </tr> <tr> <td>Volume Solids</td> <td>40 ± 1.0%</td> </tr> <tr> <td>Coverage per Gallon at Recommended Film Thickness</td> <td>350 – 450 Sq. Ft.</td> </tr> <tr> <td>Recommended Film Thickness</td> <td>– Wet 3.6 – 4.6 mils<br/>– Dry 1.4 – 1.8 mils</td> </tr> </table>  | Vehicle Type                            | 100% Acrylic | Pigment Type     | Titanium Dioxide | Volume Solids | 40 ± 1.0% | Coverage per Gallon at Recommended Film Thickness | 350 – 450 Sq. Ft. | Recommended Film Thickness | – Wet 3.6 – 4.6 mils<br>– Dry 1.4 – 1.8 mils |             |     |               |                       |                                    |                               |           |             |                  |                  |                   |          |                     |                              |
| Vehicle Type  | 100% Acrylic   |   |              |                  |                  |               |           |   |                   |                            |  |             |     |               |                       |                                    |                               |           |             |                  |                  |                   |          |                     |                              |
| Pigment Type  | Titanium Dioxide   |   |              |                  |                  |               |           |   |                   |                            |  |             |     |               |                       |                                    |                               |           |             |                  |                  |                   |          |                     |                              |
| Volume Solids   | 40 ± 1.0%  |   |              |                  |                  |               |           |   |                   |                            |  |             |     |               |                       |                                    |                               |           |             |                  |                  |                   |          |                     |                              |
| Coverage per Gallon at Recommended Film Thickness   | 350 – 450 Sq. Ft.  |   |              |                  |                  |               |           |   |                   |                            |  |             |     |               |                       |                                    |                               |           |             |                  |                  |                   |          |                     |                              |
| Recommended Film Thickness  | – Wet 3.6 – 4.6 mils<br>– Dry 1.4 – 1.8 mils   |   |              |                  |                  |               |           |   |                   |                            |  |             |     |               |                       |                                    |                               |           |             |                  |                  |                   |          |                     |                              |
| <b>— Special Colors:</b><br>Contact your dealer.  | Depending on surface texture and porosity. Be sure to estimate the right amount of paint for the job. This will ensure color uniformity and minimize the disposal of excess paint.   |   |              |                  |                  |               |           |   |                   |                            |  |             |     |               |                       |                                    |                               |           |             |                  |                  |                   |          |                     |                              |
| <b>Certifications &amp; Qualifications:</b><br><b>VOC compliant in all regulated areas</b><br><br>The products supported by this data sheet contain a maximum of 50 grams per liter VOC/VOS (.42 lbs. /gal.) excluding water & exempt solvents. | <table border="1"> <tr> <td>Dry Time @ 77 °F (25 °C) @ 50% RH</td> <td>– Tack Free</td> <td>30 – 60 Minutes</td> </tr> <tr> <td></td> <td>– To Recoat</td> <td>4 Hours</td> </tr> </table> <p>High humidity and cool temperatures will result in longer dry, recoat and service times.</p> <table border="1"> <tr> <td>Dries By</td> <td>Coalescence</td> </tr> <tr> <td>Viscosity</td> <td>100 – 105 KU</td> </tr> <tr> <td>Flash Point</td> <td>N/A</td> </tr> <tr> <td>Gloss / Sheen</td> <td>Satin (27 – 37 @ 85°)</td> </tr> <tr> <td>Surface Temperature at Application</td> <td>– Min. 40 °F<br/>– Max. 100 °F</td> </tr> <tr> <td>Thin With</td> <td>Clean Water</td> </tr> <tr> <td>Clean Up Thinner</td> <td>Warm Soapy Water</td> </tr> <tr> <td>Weight Per Gallon</td> <td>10.8 lbs</td> </tr> <tr> <td>Storage Temperature</td> <td>– Min. 40 °F<br/>– Max. 95 °F</td> </tr> </table> | Dry Time @ 77 °F (25 °C) @ 50% RH       | – Tack Free  | 30 – 60 Minutes  |                  | – To Recoat   | 4 Hours   | Dries By  | Coalescence       | Viscosity                  | 100 – 105 KU                                 | Flash Point | N/A | Gloss / Sheen | Satin (27 – 37 @ 85°) | Surface Temperature at Application | – Min. 40 °F<br>– Max. 100 °F | Thin With | Clean Water | Clean Up Thinner | Warm Soapy Water | Weight Per Gallon | 10.8 lbs | Storage Temperature | – Min. 40 °F<br>– Max. 95 °F |
| Dry Time @ 77 °F (25 °C) @ 50% RH   | – Tack Free  | 30 – 60 Minutes                         |              |                  |                  |               |           |   |                   |                            |  |             |     |               |                       |                                    |                               |           |             |                  |                  |                   |          |                     |                              |
|   | – To Recoat  | 4 Hours                                 |              |                  |                  |               |           |   |                   |                            |  |             |     |               |                       |                                    |                               |           |             |                  |                  |                   |          |                     |                              |
| Dries By  | Coalescence  |   |              |                  |                  |               |           |   |                   |                            |  |             |     |               |                       |                                    |                               |           |             |                  |                  |                   |          |                     |                              |
| Viscosity   | 100 – 105 KU   |   |              |                  |                  |               |           |   |                   |                            |  |             |     |               |                       |                                    |                               |           |             |                  |                  |                   |          |                     |                              |
| Flash Point   | N/A  |   |              |                  |                  |               |           |   |                   |                            |  |             |     |               |                       |                                    |                               |           |             |                  |                  |                   |          |                     |                              |
| Gloss / Sheen   | Satin (27 – 37 @ 85°)  |   |              |                  |                  |               |           |   |                   |                            |  |             |     |               |                       |                                    |                               |           |             |                  |                  |                   |          |                     |                              |
| Surface Temperature at Application  | – Min. 40 °F<br>– Max. 100 °F  |   |              |                  |                  |               |           |   |                   |                            |  |             |     |               |                       |                                    |                               |           |             |                  |                  |                   |          |                     |                              |
| Thin With   | Clean Water  |   |              |                  |                  |               |           |   |                   |                            |  |             |     |               |                       |                                    |                               |           |             |                  |                  |                   |          |                     |                              |
| Clean Up Thinner  | Warm Soapy Water   |   |              |                  |                  |               |           |   |                   |                            |  |             |     |               |                       |                                    |                               |           |             |                  |                  |                   |          |                     |                              |
| Weight Per Gallon   | 10.8 lbs   |   |              |                  |                  |               |           |   |                   |                            |  |             |     |               |                       |                                    |                               |           |             |                  |                  |                   |          |                     |                              |
| Storage Temperature   | – Min. 40 °F<br>– Max. 95 °F   |   |              |                  |                  |               |           |   |                   |                            |  |             |     |               |                       |                                    |                               |           |             |                  |                  |                   |          |                     |                              |
| <b>Technical Assistance:</b><br>Available through your local authorized independent dealer. For the location of the dealer nearest you, call 1-866-708-9180, or visit <a href="http://www.coronadopaint.com">www.coronadopaint.com</a>          | <table border="1"> <tr> <td colspan="2" style="text-align: center;"><b>Volatile Organic Compounds (VOC)</b></td> </tr> <tr> <td>45.5 Grams/Liter</td> <td>0.37 Lbs./Gallon</td> </tr> </table>   | <b>Volatile Organic Compounds (VOC)</b> |              | 45.5 Grams/Liter | 0.37 Lbs./Gallon |               |           |   |                   |                            |  |             |     |               |                       |                                    |                               |           |             |                  |                  |                   |          |                     |                              |
| <b>Volatile Organic Compounds (VOC)</b>   |  |   |              |                  |                  |               |           |   |                   |                            |  |             |     |               |                       |                                    |                               |           |             |                  |                  |                   |          |                     |                              |
| 45.5 Grams/Liter  | 0.37 Lbs./Gallon   |   |              |                  |                  |               |           |   |                   |                            |  |             |     |               |                       |                                    |                               |           |             |                  |                  |                   |          |                     |                              |

◇ Reported values are for White. Contact dealer for values of other bases or colors.

## Cryli Cote® 100% Acrylic Exterior Paint Satin C410 Line

### Surface Preparation

Surfaces must be clean, dry and free of grease, wax, and mildew. Remove any chalk and loose or scaling paint. If previously coated with cement-base waterproofing paints, clean by sandblasting. Glossy surfaces must be dulled. Un-weathered areas such as eaves, ceilings, and overhangs should be washed with a detergent solution and/or rinsed with a strong stream of water from a garden hose to remove contaminants that can interfere with proper adhesion. Stains from mildew must be removed by cleaning with an anti-mildew wash prior to coating the surface. **Caution:** Refer to the anti-mildew wash technical data and material safety data sheet for instructions on its proper use and handling. For metal surfaces, remove rust. Wipe down with Oil & Grease Emulsifier to remove surface oils.

All new masonry surfaces must be power washed or brushed thoroughly with stiff fiber bristles to remove loose particles. New masonry substrates must be allowed to cure for 30 days before priming or painting. Remove all form release agents and curing compounds.

**Primers:** Cryli Cote® is a self-priming system on non-bleeding woods, smooth poured or pre-cast masonry and clean, rust free galvanized surfaces. There are a number of specialty primers available in our family of brands that can be used on difficult substrates such as bleeding woods, hard glossy surfaces, or other substrates where paint adhesion or stain blocking is a problem. Your dealer can recommend the right problem solving primer necessary to meet your needs.

**WARNING!** If you scrape, sand, or remove old paint, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Informational Hotline at 1-800-424-LEAD or log on to [www.epa.gov/lead](http://www.epa.gov/lead).

**WARRANTY:** Manufacturer warrants that this product when used in accordance with the label instructions will not: 1. blister from properly prepared and primed surfaces, 2. peel from properly prepared and primed surfaces, and 3. wear down or weather to expose the previously painted surface. This warranty shall be effective for 20 years and is made to the original residential consumer paint purchaser. This warranty is non-transferable. If this product fails to perform as explained above when used according to label instructions within the warranty period, Manufacturer will, upon presentation of proof of purchase (original sales receipt), provide an equivalent or comparable product at no charge. Since we have no control over surface preparation or application, THIS LIMITED WARRANTY DOES NOT INCLUDE THE COST OF LABOR FOR APPLICATION OF PAINT. MANUFACTURER SHALL IN NO EVENT BE LIABLE FOR INDIRECT, SPECIAL, INCIDENTAL OR CONSEQUENTIAL DAMAGES. SOME STATES DO NOT ALLOW THE EXCLUSION OF INCIDENTAL OR CONSEQUENTIAL DAMAGES, SO THE LIMITATIONS OR EXCLUSIONS CONTAINED IN THE ABOVE WARRANTY MAY NOT APPLY TO YOU. This warranty gives you specific legal rights; you may also have other rights which vary state to state.

### Application

Stir product with a circular, lifting motion before you begin to paint. 100% Acrylic Exterior House Paint may be applied by brush, spray, pad or roller, at a rate of application not to exceed 450 square feet per gallon. Surface texture and porosity will affect actual yield. For best brush application results, use a quality synthetic filament brush. For roller application, use a 3/8" or 1/2" nap cover for smooth surfaces, a 3/4" nap cover for semi-rough surfaces and a 1" or 1 1/2" nap cover for rough surfaces. For spray application, thin with clean water, up to 10% reduction if necessary. Do not apply when surface or air temperatures are below 40 °F. Do not apply to hot surfaces or in direct sunlight. Do not apply if rain is threatening.

### Clean Up

Clean up with warm, soapy water followed by a clean water rinse.

USE COMPLETELY OR DISPOSE OF PROPERLY. Dry empty containers may be recycled in a can recycling program. **Local disposal requirements vary; consult your sanitation department or state-designated environmental agency on disposal options.**

### Environmental Health & Safety Information

#### WARNING!

**Possible birth defect hazard.** Contains, **Carbamic acid, 1H-benzimidazol-2-yl-, methyl ester**, which may cause birth defects based on animal data.

**Use only with adequate ventilation.** Do not breathe vapors, spray mist or sanding dust. Ensure fresh air entry during application and drying. Avoid contact with eyes and prolonged or repeated contact with skin. Avoid exposure to dust and spray mist by wearing a NIOSH approved respirator during application, sanding and clean up. Follow respirator manufacturer's directions for respirator use. Close container after each use. Wash thoroughly after handling.



**WARNING:** Cancer and Reproductive Harm—  
[www.P65warnings.ca.gov](http://www.P65warnings.ca.gov)

**WARNING:** This product contains isothiazolinone compounds at levels of <0.1%. These substances are biocides commonly found in most paints and a variety of personal care products as a preservative. Certain individuals may be sensitive or allergic to these substances, even at low levels.

**FIRST AID:** In case of eye contact, flush immediately with plenty of water for at least 15 minutes; for skin, wash thoroughly with soap and water. If symptoms persist, seek medical attention. If you experience difficulty breathing, leave the area to obtain fresh air. If continued difficulty is experienced, get medical attention immediately.

**IN CASE OF SPILL** – Absorb with inert material and dispose of as specified under "Clean up".

**KEEP OUT OF REACH OF CHILDREN  
PROTECT FROM FREEZING**

**Refer to Safety Data Sheet for  
additional health and safety information.**