



NOTABLE[®]

DRY ERASE PAINT

0500

Features

- Silicone Epoxy
- <150 g/L VOC
- Ready to use 7 days after application
- Applicable to most surfaces
- 10 year warranty

Recommended For

For professional use in interior commercial or residential spaces such as office buildings, classrooms and homes.

General Description

Notable[®] is a two-component dry erase paint. Notable[®] transforms virtually any surface into a writeable and erasable surface. **This is a two component product that requires all of the proper 0500 part "A" component be mixed with all of the proper 0500 part "B" component.**

Limitations

- Do not paint when temperature of air and surface is below 45 °F (7.2 °C)
- Do not mix with other paints, colorants, stains or glazes
- **Do not mix partial kits**

Product Information																																																																																								
<p>Colors — Standard: White (01), Clear (00)</p> <p>Available in 50, 100 and 200 sq. ft. kit sizes</p> <p>— Tint Bases: N/A</p> <p>— Special Colors: N/A</p> <p>Certifications & Qualifications:</p> <p>The products supported by this data sheet contain a maximum of 150 grams per liter VOC / VOS (1.25 lbs. /gal.) excluding water & exempt solvents.</p> <p>Qualifies for LEED[®] v4 Credit</p> <p>Qualifies for CHPS low emitting credit (Collaborative for High Performance Schools)</p> <p>CDPH v1 Emission Certified</p>	<table border="1"> <thead> <tr> <th>VOC REGION</th> <th>COMPLIANT</th> </tr> </thead> <tbody> <tr> <td>FEDERAL</td> <td>YES</td> </tr> <tr> <td>OTC</td> <td>YES</td> </tr> <tr> <td>OTCII</td> <td>YES</td> </tr> <tr> <td>CARB</td> <td>YES</td> </tr> <tr> <td>CARB07</td> <td>YES</td> </tr> <tr> <td>UTAH</td> <td>YES</td> </tr> <tr> <td>AZMC</td> <td>YES</td> </tr> <tr> <td>SCAQMD</td> <td>NO</td> </tr> </tbody> </table>	VOC REGION	COMPLIANT	FEDERAL	YES	OTC	YES	OTCII	YES	CARB	YES	CARB07	YES	UTAH	YES	AZMC	YES	SCAQMD	NO																																																																					
VOC REGION	COMPLIANT																																																																																							
FEDERAL	YES																																																																																							
OTC	YES																																																																																							
OTCII	YES																																																																																							
CARB	YES																																																																																							
CARB07	YES																																																																																							
UTAH	YES																																																																																							
AZMC	YES																																																																																							
SCAQMD	NO																																																																																							
<p>Technical Assistance</p> <p>Available through your local authorized independent Benjamin Moore retailer. For the location of the retailer nearest you, call 1-866-708-9180 or visit www.benjaminmoore.com</p>	<table border="1"> <thead> <tr> <th colspan="2">Technical Data</th> <th>White</th> </tr> </thead> <tbody> <tr> <td>Vehicle Type</td> <td colspan="2">Silicone Epoxy Hybrid</td> </tr> <tr> <td>Pigment Type</td> <td colspan="2">Titanium Dioxide</td> </tr> <tr> <td>Volume Solids</td> <td colspan="2">85.8%</td> </tr> <tr> <td>Coverage per Gallon kit at Recommended Film Thickness</td> <td colspan="2">200 Sq. Ft.</td> </tr> <tr> <td>Recommended Film Thickness</td> <td>– Wet</td> <td>4 mils</td> </tr> <tr> <td></td> <td>– Dry</td> <td>3.5 mils</td> </tr> <tr> <td colspan="3">Depending on surface texture and porosity. Be sure to estimate the right amount of paint for the job. This will ensure color uniformity and minimize the disposal of excess paint.</td> </tr> <tr> <td></td> <td>– To Touch</td> <td>4 Hours</td> </tr> <tr> <td>Dry Time @ 77 °F (25 °C) @ 50% RH</td> <td>– To Recoat</td> <td>Refer to Application on page 2</td> </tr> <tr> <td></td> <td>– Full Cure</td> <td>7 Days</td> </tr> <tr> <td colspan="3">High humidity and cool temperatures will result in longer dry, recoat and service times.</td> </tr> <tr> <td>Dries By</td> <td colspan="2">Chemical Cure</td> </tr> <tr> <td>Viscosity</td> <td colspan="2">White (Mixed) <55 KU</td> </tr> <tr> <td>Flash Point</td> <td colspan="2">239 °F</td> </tr> <tr> <td>Dry Heat Resistance</td> <td colspan="2">300 °F</td> </tr> <tr> <td>Gloss / Sheen</td> <td colspan="2">High Gloss (75+ @ 60°)</td> </tr> <tr> <td>Surface Temperature at Application</td> <td>– Min.</td> <td>45 °F</td> </tr> <tr> <td></td> <td>– Max</td> <td>90 °F</td> </tr> <tr> <td>Thin With</td> <td colspan="2">Do Not Thin</td> </tr> <tr> <td>Clean Up Thinner</td> <td colspan="2">Mineral Spirits</td> </tr> <tr> <td>Weight Per Gallon</td> <td colspan="2">11.6 lbs.</td> </tr> <tr> <td>Mixed Ratio (by volume)</td> <td colspan="2">Premeasured</td> </tr> <tr> <td>Induction time @ 77°F</td> <td colspan="2">Not Required</td> </tr> <tr> <td>Pot Life @ 77°F</td> <td colspan="2">4 Hours</td> </tr> <tr> <td>Storage Temperature</td> <td>– Min.</td> <td>40 °F</td> </tr> <tr> <td></td> <td>– Max</td> <td>90 °F</td> </tr> <tr> <td colspan="3" style="text-align: center;">Volatile Organic Compounds (VOC)</td> </tr> <tr> <td></td> <td>121 Grams/Liter</td> <td>1.0 Lbs./Gallon</td> </tr> </tbody> </table>	Technical Data		White	Vehicle Type	Silicone Epoxy Hybrid		Pigment Type	Titanium Dioxide		Volume Solids	85.8%		Coverage per Gallon kit at Recommended Film Thickness	200 Sq. Ft.		Recommended Film Thickness	– Wet	4 mils		– Dry	3.5 mils	Depending on surface texture and porosity. Be sure to estimate the right amount of paint for the job. This will ensure color uniformity and minimize the disposal of excess paint.				– To Touch	4 Hours	Dry Time @ 77 °F (25 °C) @ 50% RH	– To Recoat	Refer to Application on page 2		– Full Cure	7 Days	High humidity and cool temperatures will result in longer dry, recoat and service times.			Dries By	Chemical Cure		Viscosity	White (Mixed) <55 KU		Flash Point	239 °F		Dry Heat Resistance	300 °F		Gloss / Sheen	High Gloss (75+ @ 60°)		Surface Temperature at Application	– Min.	45 °F		– Max	90 °F	Thin With	Do Not Thin		Clean Up Thinner	Mineral Spirits		Weight Per Gallon	11.6 lbs.		Mixed Ratio (by volume)	Premeasured		Induction time @ 77°F	Not Required		Pot Life @ 77°F	4 Hours		Storage Temperature	– Min.	40 °F		– Max	90 °F	Volatile Organic Compounds (VOC)				121 Grams/Liter	1.0 Lbs./Gallon
Technical Data		White																																																																																						
Vehicle Type	Silicone Epoxy Hybrid																																																																																							
Pigment Type	Titanium Dioxide																																																																																							
Volume Solids	85.8%																																																																																							
Coverage per Gallon kit at Recommended Film Thickness	200 Sq. Ft.																																																																																							
Recommended Film Thickness	– Wet	4 mils																																																																																						
	– Dry	3.5 mils																																																																																						
Depending on surface texture and porosity. Be sure to estimate the right amount of paint for the job. This will ensure color uniformity and minimize the disposal of excess paint.																																																																																								
	– To Touch	4 Hours																																																																																						
Dry Time @ 77 °F (25 °C) @ 50% RH	– To Recoat	Refer to Application on page 2																																																																																						
	– Full Cure	7 Days																																																																																						
High humidity and cool temperatures will result in longer dry, recoat and service times.																																																																																								
Dries By	Chemical Cure																																																																																							
Viscosity	White (Mixed) <55 KU																																																																																							
Flash Point	239 °F																																																																																							
Dry Heat Resistance	300 °F																																																																																							
Gloss / Sheen	High Gloss (75+ @ 60°)																																																																																							
Surface Temperature at Application	– Min.	45 °F																																																																																						
	– Max	90 °F																																																																																						
Thin With	Do Not Thin																																																																																							
Clean Up Thinner	Mineral Spirits																																																																																							
Weight Per Gallon	11.6 lbs.																																																																																							
Mixed Ratio (by volume)	Premeasured																																																																																							
Induction time @ 77°F	Not Required																																																																																							
Pot Life @ 77°F	4 Hours																																																																																							
Storage Temperature	– Min.	40 °F																																																																																						
	– Max	90 °F																																																																																						
Volatile Organic Compounds (VOC)																																																																																								
	121 Grams/Liter	1.0 Lbs./Gallon																																																																																						

◊ Reported values are for White. Contact Benjamin Moore for values of other bases or colors

Notable® Dry Erase Paint 0500

Surface Preparation

Because Notable® is a high gloss paint and imperfections can be magnified, it is important to smooth your surface as best as possible. Fill any holes or cracks and sand any rough surfaces. Next, frame the area to be painted with painters tape (3M blue tape recommended). Use at least 4 inches of tape at the bottom to help capture any drips. Make sure the tape is sealed smoothly without wrinkles, especially where Notable® will meet the edges of the tape. Prime (if applicable) any areas where filler was used. Notable® performs best over non-flat paint finishes. If painting over a flat or matte finish, apply primer. Priming is also recommended if Notable® is being applied to new dry wall. When using Notable® White over a different surface color, apply a primer followed by an intermediate white base coat prior to using Notable®. Allow the primer/base coat to dry for 24 hours (Recommended primer: Benjamin Moore® Fresh Start® Multi-Purpose Latex Primer). Clean the surface of any loose dirt or debris.

WARNING! If you scrape, sand, or remove old paint, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead.

Application

Comply with printed application instructions.

Mix components according to printed application instructions. Do not use a plastic tray liner – aluminum foil can be used to line any tray of your choice. **Use the roller cover provided in your kit.** Notable® may be applied by brush to cut in the edges, if desired. The product should be applied 50 sq. ft. at a time. Start at the top left corner of your section and apply using up and down strokes. Use minimal pressure to avoid drips. Wait 5-10 minutes and then apply a second coat on the wet film. Any wet areas that need to be touched up must be done within 30 minutes. Wait 30 minutes to remove painters tape and pull off at a 45-degree angle. Notable® will be dry to touch in 4 hours, but has a cure time of 7 days. If full coverage is not achieved, allow a full 24 hours prior to applying another finish coat. **If the second coat is not applied within 72 hours, abrade the surface to ensure proper inter-coat adhesion.**

After 7 day cure period, it is safe to use any standard dry erase marker on the new surface (Expo® markers are recommended). Remove marks with any standard dry eraser. For harder to erase marks, we recommend using Expo® cleaner, conventional glass cleaner or similar. For best results, we do not recommend leaving dry erase markers on the surface for more than 30 days.

Spray Application:

Prior to spraying Notable® Dry Erase Paint, rinse equipment thoroughly with mineral spirits to remove any contaminants

Spray Type	Tip Size	Pressure
Siphon Feed	1.4mm – 1.7mm	40-65 PSI
Gravity Feed	1.3mm – 1.4mm	40-65 PSI
HVLP Siphon	1.3mm – 1.5mm	10 PSI Max.
HVLP Gravity	1.3mm – 1.5mm	10 PSI Max.

Clean up

Allow used roller cover to dry before disposing. Allow mixed product to fully harden before disposing. Dispose of all hardened, unused, or unwanted product in accordance with all applicable federal, state and local regulations. Local disposal requirements vary; consult your sanitation department or state-designated environmental agency on disposal options.

Environmental Health & Safety Information

Danger

Causes severe skin burns and eye damage

May cause an allergic skin reaction

Suspected of causing genetic defects

May damage fertility or the unborn child

Causes damage to organs

Causes damage to organs through prolonged or repeated exposure

Prevention

Wash face, hands and any exposed skin thoroughly after handling. Avoid breathing dust/fume/mist/vapors/spray. Contaminated work clothing should not be allowed out of the workplace. Wear protective gloves.

Response

If in eyes rinse cautiously with water for several minutes. Remove contact lenses, if present and easy to do. Continue rinsing. If eye irritation persists get medical attention. If on skin wash with plenty of soap and water. If skin irritation or rash occurs get medical attention. Wash contaminated clothing before reuse.

Disposal

Dispose of contents/container to an approved waste disposal plant.

IMPORTANT: Designed to be mixed with other components. Mixture will have hazards of all components. Before opening packages, read all warning labels. Follow all precautions.



WARNING Cancer and Reproductive Harm–
www.P65warnings.ca.gov

This document represents hazards of the product referenced above. Refer to the individual Safety Data Sheet for hazards of the specific product you will be using.

**KEEP OUT OF REACH OF CHILDREN
FOR PROFESSIONAL USE ONLY**

**Refer to Safety Data Sheet for additional
health and safety information.**