



NOTABLE® DRY ERASE PAINT 0500

Features

- Silicone Epoxy
- <150 g/L VOC
- Ready to use 7 days after application
- Applicable to most surfaces
- 10 year warranty

Recommended For

For professional use in interior commercial or residential spaces such as office buildings, classrooms and homes.

General Description

Notable® is a two-component dry erase paint. Notable® transforms virtually any surface into a writeable and erasable surface. **This is a two component product that requires all of the proper 0500 part "A" component be mixed with all of the proper 0500 part "B" component.**

Limitations

- Do not paint when temperature of air and surface is below 45 °F (7.2 °C)
- Do not mix with other paints, colorants, stains or glazes
- **Do not mix partial kits**

Product Information

Colors — Standard:

White (01), Clear (00)

Available in 50, 100 and 200 sq. ft. kit sizes

— Tint Bases:

N/A

— Special Colors:

N/A

Certifications & Qualifications:

The products supported by this data sheet contain a maximum of 150 grams per liter VOC / VOS (1.25 lbs. /gal.) excluding water & exempt solvents.

Eligible for LEED® v4 Credit

Qualifies for CHPS low emitting credit (Collaborative for High Performance Schools)

CDPH v1 Emission Certified

VOC REGION	COMPLIANT
FEDERAL	YES
OTC	YES
OTCII	YES
CARB	YES
CARB07	YES
UTAH	YES
AZMC	YES
SCAQMD	NO

Technical Assistance

Available through your local authorized independent Benjamin Moore retailer. For the location of the retailer nearest you, call 1-866-708-9180 or visit www.benjaminmoore.com

Technical Data◇

White

Generic Type Silicone Epoxy Hybrid

Pigment Type Titanium Dioxide

Volume Solids (mixed as recommended) 85.8%

Coverage Refer to kit size and recommended application method

Total Recommended – Wet 4 mils

Film Thickness – Dry 3.5 mils

Depending on surface texture and porosity. Be sure to estimate the right amount of paint for the job. This will ensure color uniformity and minimize the disposal of excess paint.

– To Touch 4 Hours

Dry Time @ 77 °F (25 °C) @ 50 RH – To Recoat Refer to Application on page 2

– Full Cure 7 Days

High humidity and cool temperatures will result in longer dry, recoat and service times.

Dries By Chemical Cure

Dry Heat Resistance 250 °F

Viscosity White (Mixed) <55 KU

Flash Point 239 °F

Gloss High Gloss (75+ @ 60°)

Surface Temperature – Min. 45 °F

at application – Max. 90 °F

Thin With Do Not Thin

Clean Up Thinner Mineral Spirits

Mixed Ratio (by volume) Premeasured

Induction time @ 77 °F (25 °C) Not Required

Pot Life @ 77 °F (25 °C) 4 Hours

Weight Per Gallon (mixed as recommended) 11.6 lbs.

Storage Temperature – Min. 4 °F

– Max. 90 °F

Volatile Organic Compounds (VOC)

121 Grams / Liter* 1.0 LBS / Gallon*
*mixed

◇ Reported values are for White. Contact retailer for values of other bases or colors.

Notable® Dry Erase Paint 0500

Surface Preparation

Because Notable® is a high gloss paint and imperfections can be magnified, it is important to smooth your surface as best as possible. Fill any holes or cracks and sand any rough surfaces. Next, frame the area to be painted with painters tape (3M blue tape recommended). Use at least 4 inches of tape at the bottom to help capture any drips. Make sure the tape is sealed smoothly without wrinkles, especially where Notable® will meet the edges of the tape. Prime (if applicable) any areas where filler was used. Notable® performs best over non-flat paint finishes. If painting over a flat or matte finish, apply primer. Priming is also recommended if Notable® is being applied to new dry wall. When using Notable® White over a different surface color, apply a primer followed by an intermediate white base coat prior to using Notable®. Allow the primer/base coat to dry for 24 hours (Recommended primer: Benjamin Moore® Fresh Start® Multi-Purpose Latex Primer). Clean the surface of any loose dirt or debris.

WARNING! If you scrape, sand, or remove old paint, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead

Primer/Finish Systems

Laminate & Engineered Wood Products:

White

Primer: Fresh Start® All Purpose Primer (046) or equivalent

Basecoat: Regal® Select Semi-Gloss Finish or equivalent

Finish: Notable® Dry Erase Paint, White

Clear

Primer: Not needed

Basecoat: Not needed

Finish: Notable® Dry Erase Paint, Clear

Bare Wood:

White

Primer: Fresh Start® All Purpose Primer (046) or equivalent

Basecoat: Regal® Select Semi-Gloss Finish or equivalent

Finish: Notable® Dry Erase Paint, White

Clear

Primer: Not needed

Basecoat: Lenmar® ClearCoat PRO Sealer 1PR.100 or equivalent

Finish: Notable® Dry Erase Paint, Clear

Drywall/Plaster (cured):

White (bare)

Primer: Fresh Start® All Purpose Primer (046) or equivalent

Basecoat: Regal® Select Semi-Gloss Finish or equivalent

Finish: Notable® Dry Erase Paint, White

Clear (previously painted)

Primer: Not needed

Basecoat: Not needed

Finish: Notable® Dry Erase Paint, Clear

Ferrous Metal (Steel and Iron):

White

Primer: Ultra Spec® HP Acrylic Metal Primer (HP04)

Basecoat: Regal® Select Semi-Gloss Finish or equivalent

Finish: Notable® Dry Erase Paint, White

Clear

Primer: Not needed

Basecoat: Not needed

Finish: Notable® Dry Erase Paint, Clear

Non-Ferrous Metal (Galvanized & Aluminum):

White

Primer: Not needed

Basecoat: Regal® Select Semi-Gloss Finish or equivalent

Finish: Notable® Dry Erase Paint, White

Clear

Primer: Not needed

Basecoat: Not needed

Finish: Notable® Dry Erase Paint, Clear

All new metal surfaces must be thoroughly cleaned with an Oil & Grease Emulsifier Corotech® V600 to remove contaminants. New shiny non-ferrous metal surfaces that will be subject to abrasion should be dulled with very fine sandpaper or a synthetic steel wool pad to promote adhesion.

Glass:

White

Primer: Insl-x® Stix® WB Bonding Primer

Basecoat: Regal® Select Semi-Gloss Finish or equivalent

Finish: Notable® Dry Erase Paint, White

Clear

Primer: Not needed

Basecoat: Not needed

Finish: Notable® Dry Erase Paint, Clear

Application

Comply with printed application instructions.

Mix components according to printed application instructions. Do not use a plastic tray liner – aluminum foil can be used to line any tray of your choice. **Use the roller cover provided in your kit.** Notable® may be applied by brush to cut in the edges, if desired. The product should be applied 50 sq. ft. at a time. Start at the top left corner of your section and apply using up and down strokes. Use minimal pressure to avoid drips. Wait 5-10 minutes and then apply a second coat on the wet film. Any wet areas that need to be touched up must be done within 30 minutes. Wait 30 minutes to remove painters tape and pull off at a 45-degree angle. Notable® will be dry to touch in 4 hours, but has a cure time of 7 days. If full coverage is not achieved, allow a full 24 hours prior to applying another finish coat.

After 7 day cure period, it is safe to use any standard dry erase marker on the new surface (Expo® markers are recommended). Remove marks with any standard dry eraser. For harder to erase marks, we recommend using Expo® cleaner, conventional glass cleaner or similar. For best results, we do not recommend leaving dry erase markers on the surface for more than 30 days.

Spray Application:

Prior to spraying Notable® Dry Erase Paint, rinse equipment thoroughly with mineral spirits to remove any contaminants

Spray Type	Tip Size	Pressure
Siphon Feed	1.4mm – 1.7mm	40-65 PSI
Gravity Feed	1.3mm – 1.4mm	40-65 PSI
HVLP Siphon	1.3mm – 1.5mm	10 PSI Max.
HVLP Gravity	1.3mm – 1.5mm	10 PSI Max.

Notable® Dry Erase Paint 0500

Clean up

Allow used roller cover to dry before disposing. Allow mixed product to fully harden before disposing. Dispose of all hardened, unused, or unwanted product in accordance with all applicable federal, state and local regulations. Local disposal requirements vary; consult your sanitation department or state-designated environmental agency on disposal options.

Environmental Health & Safety Information

Danger

Causes severe skin burns and eye damage

May cause an allergic skin reaction

Suspected of causing genetic defects

May damage fertility or the unborn child

Causes damage to organs

Causes damage to organs through prolonged or repeated exposure

Prevention

Wash face, hands and any exposed skin thoroughly after handling. Avoid breathing dust/fume/mist/vapors/spray. Contaminated work clothing should not be allowed out of the workplace. Wear protective gloves.

Response

If in eyes rinse cautiously with water for several minutes. Remove contact lenses, if present and easy to do. Continue rinsing. If eye irritation persists get medical attention. If on skin wash with plenty of soap and water. If skin irritation or rash occurs get medical attention. Wash contaminated clothing before reuse.

Disposal

Dispose of contents/container to an approved waste disposal plant.

IMPORTANT: Designed to be mixed with other components. Mixture will have hazards of all components. Before opening packages, read all warning labels. Follow all precautions.



WARNING Cancer and Reproductive Harm—
www.P65warnings.ca.gov

This document represents hazards of the product referenced above. Refer to the individual Safety Data Sheet for hazards of the specific product you will be using.

**KEEP OUT OF REACH OF CHILDREN
FOR PROFESSIONAL USE ONLY**

**Refer to Safety Data Sheet for additional health
and safety information.**