



SUPER KOTE 5000 EXTERIOR ACRYLIC SEMI-GLOSS 804 LINE

Features

- Acrylic Exterior Paint
- Water Clean-Up
- Fast Drying

General Description

Acrylic Semi-Gloss Exterior is formulated to provide long lasting weather, colour and gloss paint retention. The enamel sheen minimizes dirt pickup, so the film stays fresh looking longer. The breathing action of the paint film permits moisture vapour to escape, reducing peeling problems.

Recommended For

For exterior wood, hardboard, masonry and properly prepared metal surfaces in commercial, institutional and residential applications. It is self-priming on non-bleeding woods, masonry and clean, rust free galvanized surfaces. Also apply over primed ferrous metal and aluminum. Contains an agent which inhibits growth of mildew on the surface of the paint film.

Limitations

- Apply only when surface and air temperatures are above 10 °C (50°F).
- Do not apply to hot surfaces or in direct sunlight.
- Do not apply if rain is threatening.

Product Information

Colours — Standard:	Technical Data◇	White
White	Vehicle Type	Acrylic
	Pigment Type	Titanium Dioxide
	Volume Solids	30.2 ± 1.0%
— Tint Bases:	Coverage per 3.79 L at	27.9 - 37.2 m ²
804-33, Tint Base	Recommended Film Thickness	(300 - 400 Sq. Ft.)
804-34, Deep Base	Recommended Film Thickness	— Wet 4.0 to 5.4 mils
804-36, Accent Base	Thickness	— Dry 1.2 to 1.6 mils
— Special Colours:	Depending on surface texture and porosity. Be sure to estimate the right amount of paint for the job. This will ensure colour uniformity and minimize the disposal of excess paint.	
Contact your dealer.	Dry Time @ 25°C (77°F) @ 50% RH	— Tack Free 30 Minutes — To Recoat 4 Hours
Certifications & Qualifications:	High humidity and cool temperatures will result in longer dry, recoat and service times.	
The products supported by this data sheet contain a maximum of 100 grams per liter VOC/VOS (0.83 lbs. /gal.) excluding water & exempt solvents.	Dries By	Coalescence
This product is compliant under the Ozone Transport Commission regulations as a Non-Flat Coating.	Viscosity	95 – 100 KU
	Flash Point	93°C (200°F) or greater (TT-P-141, Method 4293)
	Gloss / Sheen	Semi-Gloss 40 - 50 Units @ 16°C (60°F)
	Surface Temperature at Application	— Min. 10°C (50°F) — Max. 32°C (90°F)
	Thin With	Clean Water
	Clean-Up Thinner	Warm Soapy Water
	Weight Per 3.79 L	4.54 kg (10.0 lbs.)
	Storage Temperature	— Min. 4.4°C (40°F) — Max. 32°C (90°F)
	Volatile Organic Compounds (VOC)	
	90 Grams/Litre	0.34 kg/3.79 L (0.75 Lbs./Gallon)

◇ Reported values are for White. Contact dealer for values of other bases or colours.

Super Kote 5000 Exterior Acrylic Semi-Gloss 804 Line

Surface Preparation

Surfaces must be clean and free of grease, wax, and mildew. Remove any chalk and loose or scaling paint. If previously coated with cement-base waterproofing paints, clean by sandblasting. Glossy surfaces must be dulled. Un-weathered areas such as eaves, ceilings, and overhangs should be washed with a detergent solution and/or rinsed with a strong stream of water from a garden hose to remove contaminants that can interfere with proper adhesion. Stains from mildew must be removed by cleaning with an anti-mildew wash prior to coating the surface. **Caution:** Refer to the anti-mildew wash technical data and material safety data sheet for instructions on its proper use and handling. For metal surfaces, remove rust. Wipe down with paint thinner to remove surface oils.

All new masonry surfaces must be power washed or brushed thoroughly with stiff fiber bristles to remove loose particles. New masonry substrates must be allowed to cure for 30 days before priming or painting.

Primers: New surfaces should be fully primed. Previously painted surfaces should be primed or spot primed as necessary. There are a number of specialty primers available in our family of brands that can be used on difficult substrates such as bleeding woods, hard glossy surfaces, or other substrates where paint adhesion or stain blocking is a problem. Your dealer can recommend the right problem solving primer necessary to meet your needs.

WARNING! If you scrape, sand, or remove old paint, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by logging onto Health Canada @ <https://www.canada.ca/en/health-canada/services/environmental-workplace-health/environmental-contaminants/lead/lead-information-package-some-commonly-asked-questions-about-lead-human-health.html>

Application

Stir thoroughly. Apply by brush (synthetic filament), roller or spray. Length of roller nap depends upon the texture of the surface. Thinning is not usually required for brush or roller application. Apply a full, even coat. Do not apply directly over chalky surfaces or bleeding stains. Apply only when surface and air temperatures are above 10°C (50°F).

Spray, Airless: Fluid Pressure—1,500 to 2,000 PSI;
Tip—.38-.48 mm (.015-.019 in.) Orifice

Clean-Up

Clean up with warm, soapy water.

Environmental Health & Safety Information

Use only in a well ventilated area. Keep container closed when not in use. In case of spillage, absorb with inert material and dispose of in accordance with local regulations. Wash thoroughly after handling.

**KEEP OUT OF REACH OF CHILDREN
PROTECT FROM FREEZING**

**Refer to Safety Data Sheet for
additional health and safety information.**