



SUPREME

HOUSE PAINT EXTERIOR ACRYLIC

FLAT 8 LINE

Features

- Acrylic Latex House Paint
- Fast Drying
- Low Odor
- Excellent Sealing
- Water Clean Up

General Description

This Acrylic Latex House Paint is designed for service over new or previously painted surfaces in good condition. It is formulated to cover most surfaces in one coat when applied at the rate of four hundred square feet per gallon. Acrylic Latex House Paint dries dust and bug free in thirty minutes. Provides a durable and protective finish on any properly primed and prepared exterior surface.

Recommended For

For properly prepared exterior wood, hardboard, masonry, metal and galvanized surfaces in commercial, institutional and residential applications. Use on exterior siding, foundations, fascia, shutters or retaining walls. Contains an agent which inhibits growth of mildew on the surface of the paint film.

Limitations

- Apply only when surface and air temperatures are above 50°F (10 °C).
- Do not apply if rain is expected within 12 hours

Product Information

<p>Colors — Standard: White</p> <p>— Tint Bases: 8-33, Tint Base 8-34, Deep Base 8-36, Accent Base</p> <p>— Special Colors: Contact your dealer.</p> <p>Certification: The products supported by this data sheet contain a maximum of 50 grams per liter VOC/VOS (0.42 lbs/gal.) excluding water & exempt solvents. This product is compliant under the Ozone Transport Commission regulations as a Flat Coating. This product is currently approved for use under MPI #10.</p> <p>Technical Assistance: Available through your local authorized independent dealer. For the location of the dealer nearest you, call 1-800-225-5554 or visit www.coronadopaint.com.</p>	<table border="1"> <thead> <tr> <th colspan="2">Technical Data◇</th> <th>White</th> </tr> </thead> <tbody> <tr> <td>Vehicle Type</td> <td></td> <td>Acrylic</td> </tr> <tr> <td>Pigment Type</td> <td></td> <td>Titanium Dioxide</td> </tr> <tr> <td>Volume Solids</td> <td></td> <td>32.0 ± 1.0%</td> </tr> <tr> <td>Coverage per Gallon at Recommended Film Thickness</td> <td></td> <td>300 - 400 Sq. Ft.</td> </tr> <tr> <td>Recommended Film Thickness</td> <td>– Wet</td> <td>4.0 to 5.3 mils</td> </tr> <tr> <td></td> <td>– Dry</td> <td>1.3 to 1.7 mils</td> </tr> <tr> <td colspan="3">Depending on surface texture and porosity. Be sure to estimate the right amount of paint for the job. This will ensure color uniformity and minimize the disposal of excess paint.</td> </tr> <tr> <td>Dry Time @ 77°F (25°C) @ 50% RH</td> <td>– Tack Free</td> <td>30 Minutes</td> </tr> <tr> <td></td> <td>– To Recoat</td> <td>4 Hours</td> </tr> <tr> <td colspan="3">High humidity and cool temperatures will result in longer dry, recoat and service times.</td> </tr> <tr> <td>Dries By</td> <td></td> <td>Coalescence</td> </tr> <tr> <td>Viscosity</td> <td></td> <td>92 – 97 KU</td> </tr> <tr> <td>Flash Point</td> <td></td> <td>200°F or greater (TT-P-141, Method 4293)</td> </tr> <tr> <td>Gloss / Sheen</td> <td></td> <td>Flat 2 - 4 Units@85°</td> </tr> <tr> <td>Surface Temperature at Application</td> <td>– Min.</td> <td>50°F</td> </tr> <tr> <td></td> <td>– Max.</td> <td>90°F</td> </tr> <tr> <td>Thin With</td> <td></td> <td>Clean Water</td> </tr> <tr> <td>Clean Up Thinner</td> <td></td> <td>Warm Soapy Water</td> </tr> <tr> <td>Weight Per Gallon</td> <td></td> <td>11.1 lbs.</td> </tr> <tr> <td>Storage Temperature</td> <td>– Min.</td> <td>40°F</td> </tr> <tr> <td></td> <td>– Max.</td> <td>95°F</td> </tr> <tr> <td colspan="3" style="text-align: center;">Volatile Organic Compounds (VOC)</td> </tr> <tr> <td></td> <td>46 Grams/Liter</td> <td>0.39 Lbs./Gallon</td> </tr> </tbody> </table>	Technical Data◇		White	Vehicle Type		Acrylic	Pigment Type		Titanium Dioxide	Volume Solids		32.0 ± 1.0%	Coverage per Gallon at Recommended Film Thickness		300 - 400 Sq. Ft.	Recommended Film Thickness	– Wet	4.0 to 5.3 mils		– Dry	1.3 to 1.7 mils	Depending on surface texture and porosity. Be sure to estimate the right amount of paint for the job. This will ensure color uniformity and minimize the disposal of excess paint.			Dry Time @ 77°F (25°C) @ 50% RH	– Tack Free	30 Minutes		– To Recoat	4 Hours	High humidity and cool temperatures will result in longer dry, recoat and service times.			Dries By		Coalescence	Viscosity		92 – 97 KU	Flash Point		200°F or greater (TT-P-141, Method 4293)	Gloss / Sheen		Flat 2 - 4 Units@85°	Surface Temperature at Application	– Min.	50°F		– Max.	90°F	Thin With		Clean Water	Clean Up Thinner		Warm Soapy Water	Weight Per Gallon		11.1 lbs.	Storage Temperature	– Min.	40°F		– Max.	95°F	Volatile Organic Compounds (VOC)				46 Grams/Liter	0.39 Lbs./Gallon
Technical Data◇		White																																																																							
Vehicle Type		Acrylic																																																																							
Pigment Type		Titanium Dioxide																																																																							
Volume Solids		32.0 ± 1.0%																																																																							
Coverage per Gallon at Recommended Film Thickness		300 - 400 Sq. Ft.																																																																							
Recommended Film Thickness	– Wet	4.0 to 5.3 mils																																																																							
	– Dry	1.3 to 1.7 mils																																																																							
Depending on surface texture and porosity. Be sure to estimate the right amount of paint for the job. This will ensure color uniformity and minimize the disposal of excess paint.																																																																									
Dry Time @ 77°F (25°C) @ 50% RH	– Tack Free	30 Minutes																																																																							
	– To Recoat	4 Hours																																																																							
High humidity and cool temperatures will result in longer dry, recoat and service times.																																																																									
Dries By		Coalescence																																																																							
Viscosity		92 – 97 KU																																																																							
Flash Point		200°F or greater (TT-P-141, Method 4293)																																																																							
Gloss / Sheen		Flat 2 - 4 Units@85°																																																																							
Surface Temperature at Application	– Min.	50°F																																																																							
	– Max.	90°F																																																																							
Thin With		Clean Water																																																																							
Clean Up Thinner		Warm Soapy Water																																																																							
Weight Per Gallon		11.1 lbs.																																																																							
Storage Temperature	– Min.	40°F																																																																							
	– Max.	95°F																																																																							
Volatile Organic Compounds (VOC)																																																																									
	46 Grams/Liter	0.39 Lbs./Gallon																																																																							

◇ Reported values are for White, Contact dealer for values of other bases or colors.

Supreme House Paint Exterior Acrylic Flat 8 Line

Surface Preparation

Surfaces must be clean and free of grease, wax, and mildew. Remove any chalk and loose or scaling paint. If previously coated with cement-base waterproofing paints, clean by sandblasting. Glossy surfaces must be dulled. Un-weathered areas such as eaves, ceilings, and overhangs should be washed with a detergent solution and/or rinsed with a strong stream of water from a garden hose to remove contaminants that can interfere with proper adhesion. Stains from mildew must be removed by cleaning with an anti-mildew wash prior to coating the surface. **Caution:** Refer to the anti-mildew wash technical data and material safety data sheet for instructions on its proper use and handling. For metal surfaces, remove rust. Wipe down with paint thinner to remove surface oils.

All new masonry surfaces must be power washed or brushed thoroughly with stiff fiber bristles to remove loose particles. New masonry substrates must be allowed to cure for 30 days before priming or painting.

Primers: New surfaces should be fully primed. Previously painted surfaces should be primed or spot primed as necessary. There are a number of specialty primers available in our family of brands that can be used on difficult substrates such as bleeding woods, hard glossy surfaces, or other substrates where paint adhesion or stain blocking is a problem. Your dealer can recommend the right problem solving primer necessary to meet your needs.

WARNING! If you scrape, sand, or remove old paint, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead.

Application

Stir thoroughly. Apply by brush (synthetic filament), roller or spray. Length of roller nap depends upon the texture of the surface. Thinning is not usually required for brush or roller application. Apply a full, even coat. Do not apply directly over chalky surfaces or bleeding stains. Apply only when surface and air temperatures are above 50 °F (10 °C).

Clean Up

Clean up with warm, soapy water.

USE COMPLETELY OR DISPOSE OF PROPERLY. Dry empty containers may be recycled in a can recycling program. **Local disposal requirements vary; consult your sanitation department or state-designated environmental agency on disposal options.**

Environmental Health & Safety Information

Use only with adequate ventilation. Do not breathe spray mist or sanding dust. Ensure fresh air entry during application and drying. Avoid contact with eyes and prolonged or repeated contact with skin. Avoid exposure to dust and spray mist by wearing a NIOSH approved respirator during application, sanding and clean up. Follow respirator manufacturer's directions for respirator use. Close container after each use. Wash thoroughly after handling.

WARNING: This product contains a chemical known to the state of California to cause cancer and birth defects, or other reproductive harm.

FIRST AID: In case of eye contact, flush immediately with plenty of water for at least 15 minutes; for skin, wash thoroughly with soap and water. If symptoms persist, seek medical attention. If you experience difficulty breathing, leave the area to obtain fresh air. If continued difficulty is experienced, get medical attention immediately.

IN CASE OF SPILL – Absorb with inert material and dispose of as specified under "Clean Up".

**KEEP OUT OF REACH OF CHILDREN
PROTECT FROM FREEZING**

**Refer to Safety Data Sheet for
additional health and safety information.**