



MAXUM[®] DECK & SIDING PRIMER 800

Features

- Prepares wood and promotes even color
- Can be top coated with paint or solid-colour stain
- Blocks Tannin Stains
- Suitable for new or previously painted wood

Recommended For

Maxum[®] Deck & Siding Primer is designed for use on new and previously painted exterior wood. It may be topcoated with either oil or acrylic house paints and solid colour stain. For use on exterior siding, trim, fascias, fences and asbestos shingles.

General Description

Maxum[®] 800 Deck & Siding Primer is designed for use on new and previously painted exterior wood. It is also recommended to block tannin, water, rust and other stains. It may be top coated with house paints or solid colour stain.

Limitations

- Do not apply when surface or air temperatures are below 4.4 °C (40 °F)
- Do not apply to hot surfaces or in direct sunlight
- Do not apply if rain is threatening

Product Information

Colours — Standard:	Technical Data◇	White
White (11)	Vehicle Type	Linseed Oil/Alkyd
	Pigment Type	Titanium Dioxide
	Volume Solids	54.7 ± 1.0%
	Coverage per 3.79 L at Recommended Film Thickness	27.87 – 37.16 sq m. (300 - 400 Sq. Ft.)
	Recommended Film Thickness	– Wet 4.6 mils – Dry 2.5 mils
	Depending on surface texture and porosity. Be sure to estimate the right amount of paint for the job. This will ensure colour uniformity and minimize the disposal of excess paint.	
	Dry Time @ 25 °C (77 °F) @ 50% RH	– Tack Free 4 Hours – To Recoat 16 Hours
	High humidity and cool temperatures will result in longer dry, recoat and service times.	
	Dries By	Oxidation
	Viscosity	85 – 90 KU
	Flash Point	105°F or greater (TT-P-141, Method 4293)
	Gloss / Sheen	Flat
	Surface Temperature at Application	– Min. 4.4 °C (40 °F) – Max. 32 °C (90 °F)
	Thin With	Do Not Thin
	Clean Up Thinner	Mineral Spirits
	Weight Per 3.79 L	11.0 lbs.
	Storage Temperature	– Min. 7.2 °C (45 °F) – Max. 35 °C (95 °F)
	Volatile Organic Compounds (VOC)	
	348 Grams/Litre 2.9 Lbs./3.79 L	
Colours — Standard: White (11)		
— Tint Bases: N/A		
— Special Colours: Contact your dealer.		
Certifications & Qualifications: The products supported by this data sheet contain a maximum of 350 grams per liter VOC / VOS (2.92 lbs/gal.) excluding water and exempt solvents. Master Painters Institute MPI # 5		
Technical Assistance: Available through your local authorized independent dealer. For the location of the dealer nearest you, call 1-800-361-5898 or visit www.coronadopaint.ca		

◇ Reported values are for White. Contact dealer for values of other bases or colours.

Maxum® Deck & Siding Primer 800

Surface Preparation

Surface to be painted must be clean and free of dirt, chalk, mildew, wax, grease, rust or loose flaking paint. Dirt and chalk should be removed by power washing or hand scrubbing with an abrasive cleaner and water, or an All Purpose Cleaner followed by a clean water rinse. Test for mildew by applying a solution of household bleach and water to any discoloured areas; if discoloration dissolves and rinses away, mildew is present and the entire area to be coated should be thoroughly washed and rinsed with a solution of one part household bleach and three parts water. Follow bleach manufacturer's instructions for safe handling and use of bleach solution. Protect plant life around the structure. Rinse and repeat operation if all discoloration is not removed. Wax should be removed by solvent cleaning. Grease and oil should be cleaned by using an Oil and Grease Emulsifier. Rust must be removed by blasting, hand sanding vigorously or by conscientious power tool cleaning. Remove loose, flaking paint by scraping. Feather sand rough edges to insure a smooth finish coat. Glossy surfaces must be dulled by lightly sanding. Remove sanding dust before paint application.

WARNING! If you scrape, sand, or remove old paint, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by logging onto Health Canada @ <https://www.canada.ca/en/health-canada/services/environmental-workplace-health/environmental-contaminants/lead/lead-information-package-some-commonly-asked-questions-about-lead-human-health.html>

Application

Stir product with a circular, lifting motion before you begin to paint. Maxum® Deck & Siding Primer may be applied by brush, spray, pad or roller, at a rate of application not to exceed 350 square feet per 3.79 L. Surface texture and porosity will affect actual yield. For best brush application results, use a quality synthetic filament brush. For roller application, use a 1/4" or 3/8" nap cover for smooth surfaces, 1/2" naps cover for semi-rough surfaces. Tip size should be .017 - .021. Always follow spray equipment manufacturers recommendations carefully. Do not apply when surface or air temperatures are below 4.4 °C (40 °F). Do not apply to hot surfaces or in direct sunlight. Do not apply if rain is threatening. When priming tannin-bleeding woods like cedar and redwood, it may be necessary to apply two coats to seal in the tannin. Do not thin.

Clean Up

Clean brushes and equipment with mineral spirits or follow state/local guidelines on solvent use.

Environmental Health & Safety Information

CAUTION

READ INSTRUCTIONS BEFORE USING

DANGER OF COMBUSTION

May cause allergic skin reaction.

Do not get on skin or clothing.

Keep away from flames or sparks.

Materials such as rags used with this product may begin to burn by themselves.

After use, put rags in water or lay flat to dry, then discard.

Use only in a well ventilated area. Keep container closed when not in use. In case of spillage, absorb with inert material and dispose of in accordance with local regulations. Wash thoroughly after handling.

**FOR BLOCKING STAINS
KEEP OUT OF REACH OF CHILDREN**

**Refer to Safety Data Sheet for
additional health and safety information.**