



CABINET COAT

TRIM & CABINET ENAMEL

SATIN FINISH CC-55XX

Features

- Urethane acrylic cabinet and trim finish
- Resists chipping, scuffing, food stains, grease & water
- Super adhesion
- Waterborne formula provides an ultra-smooth "factory-like" finish
- Durable satin finish

Recommended For

Cabinets, Metal, New & Previously Painted Wood, Furniture, Woodwork, Doors Trim.

General Description

Cabinet Coat is the ultimate finish for refurbishing dingy kitchen and bathroom cabinets, shelving, furniture, trim & crown molding and other interior applications that require an ultra-smooth, factory like finish with long lasting beauty. Its superior adhesion allows painting difficult surfaces, even polyurethane and varnish, without using a primer. Cabinet Coat offers excellent flow and leveling, superior stain resistance and an extremely durable satin finish that will look like new for years.

Limitations

- Do not apply when air, product or surface temperature is below 50 °F (10 °C) and above 90 °F (32 °C).
- Not for surfaces that will be immersed in liquids (sinks or tubs) or the surface of stoves or ovens.

Product Information																																																																							
<p>Colors — Standard: White (01)</p> <p>— Tint Bases: Base 1, 2, 3 & 4 Tint with Universal colorants only</p> <p>— Special Colors: Contact your dealer.</p> <p>Certifications & Qualifications: VOC compliant in all regulated areas</p> <p>The product supported by this data sheet contains a maximum of 50 grams per liter VOC/VOS (0.42 lbs./gal.) excluding water & exempt solvents. This product meets the qualifications for LEED (Leadership in Energy and Environmental Design) projects as a Non-Flat Coating. Master Painter Institute MPI # 140</p> <p>Technical Assistance: Available through your local authorized independent Insl-x dealer. For the location of the dealer nearest you, call 1-866-708-9180 or visit www.insl-x.com</p>	<table border="1"> <thead> <tr> <th colspan="2">Technical Data◇</th> <th>Base 1</th> </tr> </thead> <tbody> <tr> <td>Vehicle Type</td> <td colspan="2">Urethane Reinforced Acrylic</td> </tr> <tr> <td>Pigment Type</td> <td colspan="2">Titanium Dioxide</td> </tr> <tr> <td>Volume Solids</td> <td colspan="2">35.2 ± 1.0%</td> </tr> <tr> <td>Coverage per Gallon at Recommended Film Thickness</td> <td colspan="2">350 - 450 Sq. Ft.</td> </tr> <tr> <td rowspan="2">Recommended Film Thickness</td> <td>– Wet</td> <td>3.6 - 4.6 mils</td> </tr> <tr> <td>– Dry</td> <td>1.3 - 1.6 mils</td> </tr> <tr> <td colspan="3">Depending on surface texture and porosity. Be sure to estimate the right amount of paint for the job. This will ensure color uniformity and minimize the disposal of excess paint.</td> </tr> <tr> <td rowspan="3">Dry Time @ 77 °F (25 °C) @ 50% RH</td> <td>– Tack Free</td> <td>1 Hour</td> </tr> <tr> <td>– To Recoat</td> <td>6 Hours</td> </tr> <tr> <td>– Full Cure</td> <td>14 Days</td> </tr> <tr> <td colspan="3">High humidity and cool temperatures will result in longer dry, recoat and service times.</td> </tr> <tr> <td>Dries By</td> <td colspan="2">Coalescence</td> </tr> <tr> <td>Viscosity</td> <td colspan="2">90 – 95 KU</td> </tr> <tr> <td>Flash Point</td> <td colspan="2">200 °F or greater (TT-P-141, Method 4293)</td> </tr> <tr> <td>Gloss / Sheen</td> <td colspan="2">Satin (27 - 32 @ 60°)</td> </tr> <tr> <td rowspan="2">Surface Temperature at Application</td> <td>– Min.</td> <td>50 °F</td> </tr> <tr> <td>– Max.</td> <td>90 °F</td> </tr> <tr> <td>Thin With</td> <td colspan="2">Refer to page 2</td> </tr> <tr> <td>Clean Up Thinner</td> <td colspan="2">Warm Soapy Water</td> </tr> <tr> <td>Weight Per Gallon</td> <td colspan="2">10.9 lbs.</td> </tr> <tr> <td rowspan="2">Storage Temperature</td> <td>– Min.</td> <td>50 °F</td> </tr> <tr> <td>– Max.</td> <td>90 °F</td> </tr> <tr> <td colspan="3" style="text-align: center;">Volatile Organic Compounds (VOC)</td> </tr> <tr> <td>44.7 Grams/Liter</td> <td colspan="2">0.37 Lbs./Gallon</td> </tr> </tbody> </table>	Technical Data◇		Base 1	Vehicle Type	Urethane Reinforced Acrylic		Pigment Type	Titanium Dioxide		Volume Solids	35.2 ± 1.0%		Coverage per Gallon at Recommended Film Thickness	350 - 450 Sq. Ft.		Recommended Film Thickness	– Wet	3.6 - 4.6 mils	– Dry	1.3 - 1.6 mils	Depending on surface texture and porosity. Be sure to estimate the right amount of paint for the job. This will ensure color uniformity and minimize the disposal of excess paint.			Dry Time @ 77 °F (25 °C) @ 50% RH	– Tack Free	1 Hour	– To Recoat	6 Hours	– Full Cure	14 Days	High humidity and cool temperatures will result in longer dry, recoat and service times.			Dries By	Coalescence		Viscosity	90 – 95 KU		Flash Point	200 °F or greater (TT-P-141, Method 4293)		Gloss / Sheen	Satin (27 - 32 @ 60°)		Surface Temperature at Application	– Min.	50 °F	– Max.	90 °F	Thin With	Refer to page 2		Clean Up Thinner	Warm Soapy Water		Weight Per Gallon	10.9 lbs.		Storage Temperature	– Min.	50 °F	– Max.	90 °F	Volatile Organic Compounds (VOC)			44.7 Grams/Liter	0.37 Lbs./Gallon	
Technical Data◇		Base 1																																																																					
Vehicle Type	Urethane Reinforced Acrylic																																																																						
Pigment Type	Titanium Dioxide																																																																						
Volume Solids	35.2 ± 1.0%																																																																						
Coverage per Gallon at Recommended Film Thickness	350 - 450 Sq. Ft.																																																																						
Recommended Film Thickness	– Wet	3.6 - 4.6 mils																																																																					
	– Dry	1.3 - 1.6 mils																																																																					
Depending on surface texture and porosity. Be sure to estimate the right amount of paint for the job. This will ensure color uniformity and minimize the disposal of excess paint.																																																																							
Dry Time @ 77 °F (25 °C) @ 50% RH	– Tack Free	1 Hour																																																																					
	– To Recoat	6 Hours																																																																					
	– Full Cure	14 Days																																																																					
High humidity and cool temperatures will result in longer dry, recoat and service times.																																																																							
Dries By	Coalescence																																																																						
Viscosity	90 – 95 KU																																																																						
Flash Point	200 °F or greater (TT-P-141, Method 4293)																																																																						
Gloss / Sheen	Satin (27 - 32 @ 60°)																																																																						
Surface Temperature at Application	– Min.	50 °F																																																																					
	– Max.	90 °F																																																																					
Thin With	Refer to page 2																																																																						
Clean Up Thinner	Warm Soapy Water																																																																						
Weight Per Gallon	10.9 lbs.																																																																						
Storage Temperature	– Min.	50 °F																																																																					
	– Max.	90 °F																																																																					
Volatile Organic Compounds (VOC)																																																																							
44.7 Grams/Liter	0.37 Lbs./Gallon																																																																						

◇ Reported values are for Base 1. Contact your dealer for values of other bases or colors.

Cabinet Coat Trim & Cabinet Enamel Satin Finish CC-55XX

Surface Preparation

General – All surface areas to be painted should be clean, dry, sound and free of all dirt, grease, oils, waxes, mildew and any other surface contaminants. Dirt and chalk should be thoroughly removed by scrubbing with warm soapy water. Surface wax should be removed with a commercial wax stripper. Grease or Oil residue should be removed using Grease & Oil emulsifier. Remove all loose chipping, cracking and peeling from previously painted surfaces by hand scraping, sanding, wire brushing and/or by use of power tool cleaning methods such as electric sanders, grinders, etc. Remove any loose rust, mill scale, rust deposits from metal surfaces. Repair/replace any seriously damaged and/or delaminated surface areas. Lightly feather sand all rough paint edges to adjacent surface area. All glossy surface areas should be lightly sanded to effectively dull any existing sheen and create a more suitable surface for painting.

NOTE: Always clean before sanding to prevent driving contamination into the substrate or previous coatings!

Glossy Surfaces – Although Cabinet Coat is formulated to be applied to hard to coat surfaces without the need for sanding, it is recommended that proper surface preparation still be completed to enhance adhesion properties. Surfaces such as Melamine Laminate, Formica®, ceramic tile and glossy painted surfaces should be properly deglossed.

Previously Painted Surfaces: No primer is needed if surface is in good condition. Clean or sand as described above. Spot prime bare spots with an initial coat of Cabinet Coat.

Wood (non-bleeding), and engineered wood products:

Primer: Insl-x® Aqua Lock® Plus or Cabinet Coat

Finish: 1-2 coats of Cabinet Coat

Bleeding Type Woods (Redwood and Cedar):

Primer: Insl-x® Prime Lock™ Plus or 1-2 coats of Insl-x® Aqua Lock® Plus

Finish: 1-2 coats of Cabinet Coat

Melamine Laminate or Formica®: No primer needed. Lightly sand with fine sandpaper. Remove sanding dust with tack rag.

Ferrous Metal: Prime bare spots with acrylic metal primer.

WARNING! If you scrape, sand, or remove old paint, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead.

Application

Cabinet Coat applies easily with a high-quality brush or roller. If spraying is desired, the preferred method is HVLP. Stir product thoroughly before using. It is important to maintain a wet edge during all methods of paint application by brushing or rolling into previously applied coating area. Overworking Cabinet Coat can lead to brush marks or roller marks, as this product dries quickly. Apply when surface and ambient temperature are above 50°F and below 90°F. Avoid paint application outside when weather conditions are threatening, and late in the afternoon when there is a threat of moisture condensing on wet paint. Do not paint if surface temperature is within 5 degrees of the dew point.

Brush: High-quality Synthetic Bristle only.

Roller: High-quality Short Nap Cover (Less than ½")

Spray, HVLP: Thin with up to 8-10 oz per gallon of clean water.
1.8 Tip / 20 PSI

Spray, Airless: Fluid Pressure — 1,500 - 2,500 PSI;
Tip — .011 - .015 Orifice

Clean Up

Clean hands, brushes, rollers and other equipment with warm, soapy water immediately after use.

USE COMPLETELY OR DISPOSE OF PROPERLY. Dry empty containers may be recycled in a can recycling program. **Local disposal requirements vary; consult your sanitation department or state-designated environmental agency on disposal options.**

Environmental Health & Safety Information

Use only with adequate ventilation. Do not breathe spray mist or sanding dust. Ensure fresh air entry during application and drying. Avoid contact with eyes and prolonged or repeated contact with skin. Avoid exposure to dust and spray mist by wearing a NIOSH approved respirator during application, sanding and clean up. Follow respirator manufacturer's directions for respirator use. Close container after each use. Wash thoroughly after handling.



WARNING Cancer and Reproductive Harm—
www.P65warnings.ca.gov

FIRST AID: In case of eye contact, flush immediately with plenty of water for at least 15 minutes; for skin, wash thoroughly with soap and water. If symptoms persist, seek medical attention. If you experience difficulty breathing, leave the area to obtain fresh air. If continued difficulty is experienced, get medical attention immediately.

IN CASE OF SPILL – Absorb with inert material and dispose of as specified under "Clean Up".

**KEEP OUT OF REACH OF CHILDREN
PROTECT FROM FREEZING**

**Refer to Safety Data Sheet for
additional health and safety information.**