



# CABINET COAT

TRIM & CABINET ENAMEL  
SEMI-GLOSS CC66

## Features

- Urethane acrylic cabinet and trim finish
- Resists chipping, scuffing, food stains, grease & water
- Super adhesion
- Waterborne formula provides an ultra-smooth "factory-like" finish
- Durable semi-gloss finish

## Recommended For

New & previously painted wood cabinets, furniture, woodwork, doors & trim.

## General Description

Cabinet Coat is the ultimate finish for refurbishing kitchen and bathroom cabinets, shelving, furniture, trim & crown molding and other interior applications that require an ultra-smooth, factory like finish with long lasting beauty. Its superior adhesion allows painting difficult surfaces, even polyurethane and varnish, without using a primer. Cabinet Coat offers excellent flow and leveling, superior stain resistance and an extremely durable semi-gloss finish that will look like new for years.

## Limitations

- Do not apply when air, product or surface temperature is below 50 °F (10 °C) and above 90 °F (32 °C).
- Not for surfaces that will be immersed in liquids (sinks or tubs) or the surface of stoves or ovens.

## Product Information

### Colors — Standard:

White (01)

### — Tint Bases:

Base 1B, 2B, 3B & 4B.

Tint with Benjamin Moore® Gennex®, Color Preview® or Universal colorants

### — Special Colors:

Contact your dealer.

### Certifications & Qualifications:

#### VOC compliant in all regulated areas

The product supported by this data sheet contains a maximum of 50 grams per liter VOC/VOS (0.42 lbs./gal.) excluding water & exempt solvents.

### Technical Assistance:

Available through your local authorized independent Insl-X® dealer. For the location of the dealer nearest you, call 1-866-708-9180 or visit [www.benjaminmoore.com/INSLX](http://www.benjaminmoore.com/INSLX)

### Technical Data◇

### Base 1

Vehicle Type Urethane Reinforced Acrylic

Pigment Type Titanium Dioxide

Volume Solids 36 ± 2.0%

Coverage per Gallon at Recommended Film Thickness 350 – 450 Sq. Ft.

Recommended Film Thickness	– Wet	3.6 – 4.6 mils
	– Dry	1.3 – 1.6 mils

Depending on surface texture and porosity. Be sure to estimate the right amount of paint for the job. This will ensure color uniformity and minimize the disposal of excess paint.

Dry Time @ 77 °F (25 °C) @ 50% RH	– Tack Free	1 Hour
	– To Recoat	6 Hours
	– Full Cure	14 Days

High humidity and cool temperatures will result in longer dry, recoat and service times.

Dries By Coalescence

Viscosity 97 ± 4 KU

Flash Point 200 °F or greater (TT-P-141, Method 4293)

Gloss / Sheen Semi-Gloss (55 – 63 @ 60°)

Surface Temperature at Application	– Min.	50 °F
	– Max.	90 °F

Thin With Refer to page 2

Clean Up Thinner Warm Soapy Water

Weight Per Gallon 10.6 lbs.

Storage Temperature	– Min.	50 °F
	– Max.	90 °F

### Volatile Organic Compounds (VOC)

46.2 Grams/Liter 0.38 Lbs./Gallon

### Surface Preparation

**General** – All surface areas to be painted should be clean, dry, sound and free of all dirt, grease, oils, waxes, mildew and any other surface contaminants. Dirt and chalk should be thoroughly removed using Insl-X® Citrus Cleaner CL-0200 or warm soapy water. Grease or Oil residue should be removed using Insl-X® Heavy Duty Degreaser CL-0100. Remove all loose chipping, cracking and peeling from previously painted surfaces by hand scraping, sanding, wire brushing and/or by use of power tool cleaning methods such as electric sanders, grinders, etc. Remove any loose rust, mill scale, rust deposits from metal surfaces. Repair/replace any seriously damaged and/or delaminated surface areas. Lightly feather sand all rough paint edges to adjacent surface area. All glossy surface areas should be lightly sanded to effectively dull any existing sheen and create a more suitable surface for painting.

**NOTE:** Always clean before sanding to prevent driving contamination into the substrate or previous coatings!

**Glossy Surfaces** – Although Cabinet Coat is formulated to be applied to hard to coat surfaces without the need for sanding, for best results, it is recommended that proper surface preparation still be completed to enhance adhesion properties.

Surfaces such as Melamine Laminate, Formica®, ceramic tile and glossy painted surfaces should be properly deglossed for best results.

**Previously Painted Surfaces:** No primer is needed if surface is in good condition. Clean or sand as described above. Spot prime bare spots with an initial coat of Cabinet Coat.

**Bare Wood (non-bleeding), and engineered wood products:**

**Primer:** Insl-X® Aqua Lock® Plus or Cabinet Coat

**Bare Bleeding Type Woods (Redwood and Cedar):**

**Primer:** Insl-X® Prime Lock Plus or 1-2 coats of Insl-X® Aqua Lock® Plus

**Melamine Laminate or Formica®:** No primer needed. Lightly sand with fine sandpaper. Remove sanding dust with tack rag.

**Ferrous Metal:** Prime bare metal with acrylic metal primer.

**WARNING!** If you scrape, sand, or remove old paint, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to [www.epa.gov/lead](http://www.epa.gov/lead).

### Application

Cabinet Coat applies easily with a high-quality brush or roller. If spraying is desired, the preferred method is HVLP. Stir product thoroughly before using. It is important to maintain a wet edge during all methods of paint application by brushing or rolling into previously applied coating area. Overworking Cabinet Coat can lead to brush marks or roller marks, as this product dries quickly. Apply when surface and ambient temperature are above 50 °F and below 90 °F. Avoid paint application if there is a threat of moisture condensing on the wet paint.

**Brush:** High-quality Synthetic Bristle only.

**Roller:** High-quality Short Nap Cover (Less than ½").

**Spray, HVLP:** Thin with up to 8-10 oz per gallon of clean water.  
1.8 Tip / 20 PSI

**Spray, Airless:** Fluid Pressure — 1,500 - 2,500 PSI;  
Tip — .011 - .015 Orifice

### Clean Up

Clean hands, brushes, rollers and other equipment with warm, soapy water immediately after use.

USE COMPLETELY OR DISPOSE OF PROPERLY. Dry empty containers may be recycled in a can recycling program. **Local disposal requirements vary; consult your sanitation department or state-designated environmental agency on disposal options.**

### Environmental Health & Safety Information

**Use only with adequate ventilation.** Do not breathe spray mist or sanding dust. Ensure fresh air entry during application and drying. Avoid contact with eyes and prolonged or repeated contact with skin. Avoid exposure to dust and spray mist by wearing a NIOSH approved respirator during application, sanding and clean up. Follow respirator manufacturer's directions for respirator use. Close container after each use. Wash thoroughly after handling.



**WARNING:** Cancer and Reproductive Harm—

[www.P65Warnings.ca.gov](http://www.P65Warnings.ca.gov)

Refer to the product label & Safety Data Sheet for product specific information.

**WARNING:** This product contains isothiazolinone compounds at levels of <0.1%. These substances are biocides commonly found in most paints and a variety of personal care products as a preservative. Certain individuals may be sensitive or allergic to these substances, even at low levels.

**FIRST AID:** In case of eye contact, flush immediately with plenty of water for at least 15 minutes; for skin, wash thoroughly with soap and water. If symptoms persist, seek medical attention. If you experience difficulty breathing, leave the area to obtain fresh air. If continued difficulty is experienced, get medical attention immediately.

**IN CASE OF SPILL** – Absorb with inert material and dispose of as specified under "Clean Up".

**KEEP OUT OF REACH OF CHILDREN  
PROTECT FROM FREEZING**

**Refer to Safety Data Sheet for  
additional health and safety information.**