

HP | HIGH PERFORMANCE

General Description

HP3310 Acrylic DTM Enamel is a high-performance, direct-to-metal acrylic finish formulated for application to a wide variety of metals and other substrates. The coating performs very well in light to moderate industrial exposures and is ideal for commercial and facility applications. Additionally, the product is formulated to prevent flash rusting when applied to ferrous metals and provide long term corrosion protection. The waterborne formulation ensures easy application and easy clean-up.

- Highly moisture resistant
- Flash rust resistant
- Can be applied to a wide variety of substrates

Usage

HP3310 is for interior and exterior use on steel, galvanized steel, aluminum, masonry, concrete, wood, machinery, plaster, drywall, and properly prepared equipment and other fixtures.

Colours	White (01), Black (80)
Bases	7X, 8X, 9X
Colorant System	Gennex®

Technical Data

Vehicle		Acrylic
Pigment		Titanium Dioxide
Volume Solids		45 ± 2%
Spread Rate Per 3.79	θL	27.9 – 37.2 sq. m. (300 – 400 sq. ft.)
Recommended	Wet:	4.0 – 5.3 mils
Film Thickness	Dry:	1.8 – 2.4 mils
Depending on surface texture and porosity. Be sure		
to estimate the right amount of paint for the job.		
This will ensure colour uniformity and minimize the		
disposal of excess paint.		

Dry Time @ 25 °C	To Touch:	1 hour
(77 °F) @ 50% RH	To Recoat:	4 hours

High humidity and cool temperatures will result in longer dry, recoat and service times.

Surface Temperature	Min:	10 °C (50 °F)
During Application	Max:	37.7 °C (100 °F)
Viscosity		82 ± 4 KU
Flash Point		NA
Sheen / Gloss		45 – 55 @ 60°
Clean Up		Warm, soapy water
Thinner		Water
Weight Per 3.79 L		4.7 kg (10.5 lbs.)
Storage Temperature	Min:	7.2 °C (45 °F)
	Max:	35 °C (95 °F)
VOC		< 100 g/L

Surface Preparation

Prior to painting any surface, area must be clean, dry and free of all grease, dirt, dust, oil and wax. Clean all surfaces using HP6000 Oil & Grease Emulsifier. Remove all remaining loose paint, rust and mill scale via Hand Tool Cleaning (SSPC-SP 2) or Power Tool cleaning (SSPC-SP 3). Fill holes and cracks and sand smooth. Glossy surfaces must be fully deglossed. Moderate to heavily rusted areas must be thoroughly prepared and active rust should be properly removed.

WARNING! If you scrape, sand, or remove old paint, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by logging onto Health Canada @ https://www.canada.ca/en/healthcanada/services/environmental-workplacehealth/environmental-contaminants/lead/lead-

health/environmental-contaminants/lead/leadinformation-package-some-commonly-askedguestions-about-lead-human-health.html

Primer Systems

Ferrous Metal: Apply directly to properly prepared, ferrous metal surfaces. For additional rust protection, prime with HP1100 Acrylic Metal Primer.

Galvanized, Aluminum and Non-Ferrous Metals:

Clean oil from new galvanized metal by cleaning with HP6000 Oil & Grease Emulsifier. Apply directly to properly prepared, ferrous metal surfaces. For additional rust protection, prime with HP1100 Acrylic Metal Primer.

Wood: Sand surfaces. Prime bare spots and new wood with an acrylic primer/sealer/undercoater. Apply one or two coats of HP3410 as needed.

Drywall and Cured Plaster: Sand surfaces. Prime with an acrylic primer/sealer/undercoater.

Concrete/Masonry: All vertical masonry surfaces must be allowed to cure a minimum of 30 days before painting. Acid etch or abrasive blast all slick, glazed concrete or concrete with laitance. For acid etching, follow all manufacturer's directions and safety instructions. Smooth surfaces should be coated with a masonry sealer. For rough surfaces, prime with a block filler to produce a smoother finish followed by one or two coats of HP3310 as needed.

HP3310

DTM Acrylic Enamel Semi-Gloss

Compliance & Certifications

Eligible for LEED [®] v4	✓
CDPH Emissions Certified	\checkmark
Eligible for CHPS low emitting credit	1
(Collaborative for High Performance Schools)	•
MPI 15	3, 163

Limitations

- Not recommended for immersion service
- Do not apply if material, substrate or ambient temperature is below 50 °F (10 °C)

Technical Assistance

Available through your local authorized independent Benjamin Moore retailer.

call 1-800-361-5898 visit <u>www.benjaminmoore.ca</u>

Application

For best results, use a premium Benjamin Moore[®] custom-blended nylon/polyester brush, premium Benjamin Moore[®] roller, or a similar product. Apply paint generously from unpainted areas into wet area. This product can also be sprayed.

Spray, Airless:

Pressure / 1,500 – 2,500 PSI Tip / 0.013 – 0.017

NOTE: Do not allow material to remain in hoses, gun or spray equipment. Thoroughly flush all equipment with warm water. No reduction is necessary. Do not apply if material, substrate or ambient temperature is below 10 °C / 50 °F. Relative humidity should be below 90%.

Clean Up

Wash brushes, rollers, and other painting tools with soap and water immediately after use.

USE COMPLETELY OR DISPOSE OF PROPERLY. Dry, empty containers may be recycled in a can recycling program. Local disposal requirements vary; consult your sanitation department or state-designated environmental agency on disposal options.

CHEMICAL RESISTANCE GUIDE (NON-IMMERSION) *		
Fresh Water	Excellent	
Salt Water	Good	
Acids	Fair	
Alkalis	Fair	
Solvents	Not Recommended	
Fuel	Not Recommended	
Acidic Salt Solutions	Fair	
Alkaline Salt Solutions	Fair	
Neutral Salt Solutions	Good	

TEST DATA		
Flexibility (ASTM D1737)	Pass 1/8" Mandrel	
Dry Heat Resistance	93.3 °C / 200 °F	
Wet Heat Resistance	65.5 °C / 150 °F	
Adhesion (ASTM D3359)	Passes 5B	
Salt Fog Resistance (ASTM B117)	Rust Breakthrough: 10 Rating	
150 Hours (2 coats over HP1100)	Rust Area: 0.01%	
Abrasion Resistance		
(ASTM D4060) CS-17 wheel,	100 mg Loss	
1000 Cycles, 100 g Load		
Accelerated Weathering	90% Gloss Retention	
(ASTM G53) 500 Hours	< 0.25 DE Color Change	

Environmental Health & Safety Information

Use only in a well ventilated area. Keep container closed when not in use. In case of spillage, absorb with inert material and dispose of in accordance with local regulations. Wash thoroughly after handling.

FOR PROFESSIONAL USE ONLY PROTECT FROM FREEZING

Refer to Safety Data Sheet for additional health and safety information.