



COLOR-CHANGING CEILING PAINT

PC-1200

Features

- Spatter resistant
- Self-Priming
- Disappearing pink color-change technology
- For smooth or textured ceilings
- Easy clean-up

Recommended For

For new or previously painted wallboard, acoustical ceiling tile cured masonry, plaster, and other ceiling substrates.

General Description

Color-Changing Ceiling Paint is applied as a light pink color to indicate painted areas for preventing missed spots. It dries to a uniform, white finish in a flat sheen that helps minimize the appearance of surface imperfections. Once dry, moisture or humidity will not affect the color-change from pink to white.

Limitations

- Apply when surface and ambient temperature is above 50 °F (10 °C) and below 90 °F (32 °C).
- Not for high traffic areas or surfaces that require frequent cleaning

Product Information

<p>Colors — Standard: White</p> <p>— Tint Bases: Do not tint</p> <p>— Special Colors: Contact your retailer</p> <p>Certifications & Qualifications: VOC compliant in all regulated areas</p> <p>Technical Assistance: Available through your local authorized independent retailer. For the location of the retailer nearest you, call 1-866-708-9180 or see www.insl-x.com</p>	<table border="1"> <thead> <tr> <th colspan="2">Technical Data◇</th> <th>White</th> </tr> </thead> <tbody> <tr> <td>Vehicle Type</td> <td></td> <td>Acrylic</td> </tr> <tr> <td>Pigment Type</td> <td></td> <td>Titanium Dioxide</td> </tr> <tr> <td>Volume Solids</td> <td></td> <td>28 ± 1.0%</td> </tr> <tr> <td>Coverage per Gallon at Recommended Film Thickness</td> <td></td> <td>300 – 400 Sq. Ft.</td> </tr> <tr> <td>Recommended Film Thickness</td> <td>– Wet</td> <td>3.9 – 4.6 mils</td> </tr> <tr> <td></td> <td>– Dry</td> <td>1.1 – 1.3 mils</td> </tr> <tr> <td colspan="3">Depending on surface texture and porosity. Be sure to estimate the right amount of paint for the job. This will ensure color uniformity and minimize the disposal of excess paint.</td> </tr> <tr> <td>Dry Time @ 77 °F (25 °C) @ 50% RH</td> <td>– Tack Free</td> <td>1 Hour</td> </tr> <tr> <td></td> <td>– To Recoat</td> <td>2 Hours</td> </tr> <tr> <td colspan="3">High humidity and cool temperatures will result in longer dry, recoat and service times.</td> </tr> <tr> <td>Dries By</td> <td></td> <td>Coalescence</td> </tr> <tr> <td>Viscosity</td> <td></td> <td>99 – 103 KU</td> </tr> <tr> <td>Flash Point</td> <td></td> <td>None</td> </tr> <tr> <td>Gloss / Sheen</td> <td></td> <td>Flat (2 – 5 @ 85°)</td> </tr> <tr> <td>Surface Temperature at Application</td> <td>– Min.</td> <td>50 °F</td> </tr> <tr> <td></td> <td>– Max.</td> <td>90 °F</td> </tr> <tr> <td>Thin With</td> <td></td> <td>Do not Thin</td> </tr> <tr> <td>Clean Up Thinner</td> <td></td> <td>Warm Soapy Water</td> </tr> <tr> <td>Weight Per Gallon</td> <td></td> <td>11.2 lbs.</td> </tr> <tr> <td>Storage Temperature</td> <td>– Min.</td> <td>40 °F</td> </tr> <tr> <td></td> <td>– Max.</td> <td>90 °F</td> </tr> <tr> <td colspan="3" style="text-align: center;">Volatile Organic Compounds (VOC)</td> </tr> <tr> <td></td> <td>47.8 Grams/Liter</td> <td>0.39 Lbs./Gallon</td> </tr> </tbody> </table>	Technical Data◇		White	Vehicle Type		Acrylic	Pigment Type		Titanium Dioxide	Volume Solids		28 ± 1.0%	Coverage per Gallon at Recommended Film Thickness		300 – 400 Sq. Ft.	Recommended Film Thickness	– Wet	3.9 – 4.6 mils		– Dry	1.1 – 1.3 mils	Depending on surface texture and porosity. Be sure to estimate the right amount of paint for the job. This will ensure color uniformity and minimize the disposal of excess paint.			Dry Time @ 77 °F (25 °C) @ 50% RH	– Tack Free	1 Hour		– To Recoat	2 Hours	High humidity and cool temperatures will result in longer dry, recoat and service times.			Dries By		Coalescence	Viscosity		99 – 103 KU	Flash Point		None	Gloss / Sheen		Flat (2 – 5 @ 85°)	Surface Temperature at Application	– Min.	50 °F		– Max.	90 °F	Thin With		Do not Thin	Clean Up Thinner		Warm Soapy Water	Weight Per Gallon		11.2 lbs.	Storage Temperature	– Min.	40 °F		– Max.	90 °F	Volatile Organic Compounds (VOC)				47.8 Grams/Liter	0.39 Lbs./Gallon
Technical Data◇		White																																																																							
Vehicle Type		Acrylic																																																																							
Pigment Type		Titanium Dioxide																																																																							
Volume Solids		28 ± 1.0%																																																																							
Coverage per Gallon at Recommended Film Thickness		300 – 400 Sq. Ft.																																																																							
Recommended Film Thickness	– Wet	3.9 – 4.6 mils																																																																							
	– Dry	1.1 – 1.3 mils																																																																							
Depending on surface texture and porosity. Be sure to estimate the right amount of paint for the job. This will ensure color uniformity and minimize the disposal of excess paint.																																																																									
Dry Time @ 77 °F (25 °C) @ 50% RH	– Tack Free	1 Hour																																																																							
	– To Recoat	2 Hours																																																																							
High humidity and cool temperatures will result in longer dry, recoat and service times.																																																																									
Dries By		Coalescence																																																																							
Viscosity		99 – 103 KU																																																																							
Flash Point		None																																																																							
Gloss / Sheen		Flat (2 – 5 @ 85°)																																																																							
Surface Temperature at Application	– Min.	50 °F																																																																							
	– Max.	90 °F																																																																							
Thin With		Do not Thin																																																																							
Clean Up Thinner		Warm Soapy Water																																																																							
Weight Per Gallon		11.2 lbs.																																																																							
Storage Temperature	– Min.	40 °F																																																																							
	– Max.	90 °F																																																																							
Volatile Organic Compounds (VOC)																																																																									
	47.8 Grams/Liter	0.39 Lbs./Gallon																																																																							

◇ Reported values are for White.

Color-Changing Ceiling Paint PC-1200

Surface Preparation

Surfaces to be painted must be clean, dry, and free of dirt, dust, grease, oil, soap, wax, scaling paint, water soluble materials, and mildew. Remove any peeling or scaling paint and sand these areas to feather edges smooth with adjacent surfaces. Glossy areas should be dulled. Drywall surfaces must be free of sanding dust.

New plaster or masonry surfaces must be allowed to cure before applying base coat. Cured plaster should be hard, have a slight sheen and maximum PH of 10; soft, porous or powdery plaster indicates improper cure. Never sand a plaster surface; knife off any protrusions and prime plaster before and after applying patching compound. Poured or pre-cast concrete with a very smooth surface should be etched or abraded to promote adhesion, after removing all form release agents and curing compounds. Remove any powder or loose particles before priming. Wood substrates must be thoroughly dry. Caution: Smooth planed clapboards or siding must be sanded thoroughly to break the "mill glaze" allowing proper penetration and adhesion.

Difficult Substrates: Insl-x offers a number of specialty primers for use over difficult substrates such as stains, grease, crayon markings, hard glossy surfaces, galvanized metal, or other substrates where paint adhesion or stain suppression is a particular problem.

WARNING! If you scrape, sand or remove old paint, you may release lead dust. **LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE.** Wear a NIOSH-approved respirator to control lead exposure. Carefully clean up with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead

Application

Color-Changing Ceiling Paint applies easily with a quality brush, roller, airless, HVLP or conventional spray methods. Apply paint generously from unpainted area into wet area. Stir product thoroughly before using. When applying by brush, apply a smooth and generous coat application in an "M" or criss-cross motion avoiding any excessive re-spreading or reworking. If applying by airless sprayer, it is recommended to use a unit with a minimum of 1500 PSI of pressure with a 0.013 – 0.017 fluid spray tip. It is important to maintain a wet edge during all methods of paint application by brushing or rolling into previously applied coating area. Apply when surface and ambient temperature are above 50 °F and below 90 °F.

Clean Up

Remove all spatters immediately with soap and water. Wash all equipment with soap and water immediately after use.

USE COMPLETELY OR DISPOSE OF PROPERLY. Dry empty containers may be recycled in a can recycling program. **Local disposal requirements vary; consult your sanitation department or state-designated environmental agency on disposal options.**

Environmental Health & Safety Information

Use only with adequate ventilation. Do not breathe spray mist or sanding dust. Ensure fresh air entry during application and drying. Avoid contact with eyes and prolonged or repeated contact with skin. Avoid exposure to dust and spray mist by wearing a NIOSH approved respirator during application, sanding and clean up. Follow respirator manufacturer's directions for respirator use. Close container after each use. Wash thoroughly after handling.



WARNING: Cancer and Reproductive Harm—
www.P65warnings.ca.gov

FIRST AID: In case of eye contact, flush immediately with plenty of water for at least 15 minutes; for skin, wash thoroughly with soap and water. If symptoms persist, seek medical attention. If you experience difficulty breathing, leave the area to obtain fresh air. If continued difficulty is experienced, get medical attention immediately.

WARNING: This product contains isothiazolinone compounds at levels of <0.1%. These substances are biocides commonly found in most paints and a variety of personal care products as a preservative. Certain individuals may be sensitive or allergic to these substances, even at low levels.

IN CASE OF SPILL – Absorb with inert material and dispose of as specified under "Clean Up".

**KEEP OUT OF REACH OF CHILDREN
PROTECT FROM FREEZING**

**Refer to Safety Data Sheet for
additional health and safety information.**