



STIX[®]

**WATERBORNE BONDING PRIMER
SXA-110**

Features

- Strongly Bonds to Glossy Surfaces
- Unparalleled Adhesion to the Most Challenging Surfaces.
- Excellent Holdout
- Water Clean-up
- Cures as low as 1.7 °C (35 °F)

Recommended For

Interior and Exterior surfaces. Drywall, Plaster, Ceiling, Acoustical Tile, Wood Trim & Doors, Formica, Ceramic Tiles, Glossy Surfaces, PVC Plastic, Masonry Walls, Wood, Trim, Shutters, Masonry, Stucco, Concrete, Cement Block, Galvanized Metal, Aluminum, etc.

General Description

Stix[®] Waterborne Bonding Primer is a premium quality, waterborne, acrylic urethane primer/sealer with unparalleled adhesion to the most challenging surfaces, including PVC, Vinyl, Plastic, Glass, Tile, Glazed Block, Glossy Paints, Pre-Coated Siding, Fiberglass, and Galvanized Metals. Stix is also ideal for use on plaster, drywall, wood, and non-ferrous metals, where a low ambient or surface temperature would present a problem for conventional primers. Offers an extremely hard film when cured. Use it on interior and exterior surfaces and topcoat with almost any type of coating including Alkyd, Acrylic Latex, Urethane, Epoxy, and Lacquer Finishes. Stix levels to a smooth surface and cleans up with soap and water.

Limitations

- Apply when air, surface and product temperature are above 1.7 °C (35 °F)
- Do not apply in direct sunlight or on a hot surface. Avoid rain, moisture or high humidity for the first 24 hours of curing.
- Not intended for immersion service or continuous water contact. Not for below grade applications.
- Not recommended for use over polyethylene or polypropylene. Stix[®] must be top coated for exterior use.
- Not recommended over Kyna[®] (and similar finishes) unless tested and approved by the buyer.
- Not recommended as a whole house exterior primer over wood

Product Information

Colours — Standard: SXA-110, White	Technical Data ◊ White
— Tint Bases: N/A Can be Tinted With a Maximum of 60 ml Universal Colorant per 3.79 L	Vehicle Type Urethane Modified Acrylic
— Special Colours: Contact your dealer.	Pigment Type Titanium Dioxide
Certifications & Qualifications: VOC compliant in Canada All products supported by this data sheet contain a maximum of 100 grams per liter VOC/VOS (.83 lbs. /gal.) excluding water & exempt solvents. Qualifies for LEED [®] v4 Credit Qualifies for CHPS low emitting credit (Collaborative for High Performance Schools) CDPH v1 Emission Certified	Volume Solids 40.0 ± 1.0%
Technical Assistance: Available through your local authorized independent dealer. For the location of the dealer nearest you, call 1-800-361-5898 or visit www.Insl-x.ca	Coverage per 3.79 L at Recommended Film Thickness 27.9 – 37.2 sq. m. (300 – 400 sq. ft.)
	Recommended Film Thickness – Wet 4.0 - 5.5 mils – Dry 1.6 - 2.2 mils
	Depending on surface texture and porosity. Be sure to estimate the right amount of paint for the job. This will ensure colour uniformity and minimize the disposal of excess paint.
	Dry Time @ 25 °C (77 °F) @ 50% RH – Tack Free 30 Minutes – To Recoat 3 – 4 Hours – Full Cure 3 – 4 Days
	High humidity and cool temperatures will result in longer dry, recoat and service times.
	Dries By Coalescence
	Viscosity 70 – 80 KU
	Flash Point 93.2 °C (200 °F) or greater (TT-P-141, Method 4293)
	Gloss / Sheen Flat
	Surface Temperature at Application – Min. 1.7 °C (35 °F) – Max. 32.2 °C (90 °F)
	Thin With Do not Thin
	Clean Up Thinner Warm, Soapy Water
	Weight Per 3.79 L 5 kg (11.0 lbs.)
	Storage Temperature – Min. 7.2 °C (45 °F) – Max. 35 °C (95 °F)
	Volatile Organic Compounds (VOC) 87.6 Grams/Litre

◊ Reported values are for White. Contact dealer for values of other bases or colours.

Stix® Waterborne Bonding Primer SXA-110

Surface Preparation

General – All surface areas to be painted should be clean, dry, sound and free of all dirt, grease, oils, waxes, mildew and any other surface contaminants that can cause paint failure. Dirt and chalk should be thoroughly removed by scrubbing with warm soapy water. Surface wax should be removed with a commercial wax stripper. Grease residue should be removed with a grease and oil emulsifier. Remove all loose chipping, cracking and peeling from previously painted surfaces by hand scraping, sanding, wire brushing and/or by use of power tool cleaning methods such as electric sanders, grinders, etc. Remove any loose rust, mill scale, rust deposits from metal surfaces by hand or power tool cleaning according to SSPC Standards. Repair/replace any seriously damaged and/or delaminated surface areas. Use over most glossy surfaces without sanding.

Mildew – Surface areas affected by mildew should be thoroughly hand scrubbed with a soft to medium bristle scrub brush and a solution of 237 ml Tri-Sodium Phosphate or a nonammoniated detergent cleaner mixed with one part household bleach* and three parts warm water per 3.79 L solution. Allow solution to stand on the affected surface areas for approximately 10 – 20 minutes, then rinse thoroughly with clean water and allow 24 – 48 hours to dry.

*Follow bleach manufacturer's instructions for safe handling and use of bleach solution.

SPECIAL NOTE ON SURFACE PREPARATION:

Glossy Surfaces – Although Stix® is formulated to be applied to hard to coat surfaces without the need for sanding, it is recommended that proper surface preparation still be completed to enhance adhesion properties. Surfaces such as Formica®, ceramic tile and glossy painted surfaces should be properly de-glossed. Once applied, allow Stix® to cure for approximately 3 to 4 days to achieve maximum resistance to scrape off. However, Stix® may be top-coated with a quality latex or oil-based finish within 3 to 4 hours, depending on overall drying conditions.

WARNING! If you scrape, sand, or remove old paint, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by logging onto Health Canada @ <https://www.canada.ca/en/health-canada/services/environmental-workplace-health/environmental-contaminants/lead/lead-information-package-some-commonly-asked-questions-about-lead-human-health.html>

Application

Stix® may be applied by brush, roller, pad applicator, or airless spray. Use a high quality nylon brush or a 6.4 mm – 12.7 mm (¼" – ½") synthetic nap roller cover. Do not thin. Do not apply when surface, air, or product temperature is below 1.7°C (35°F). Do not paint in direct sun or on a hot surface. If possible, plan your painting to avoid rain, moisture, or high humidity for the first 24 hours of curing. Stop application a minimum of two hours before rain or dew is expected. Do not paint if surface temperature is within 5 degrees of the dew point. When top coating with two component paints, allow 24 hours dry time before painting. Always test questionable substrates such as plastics, composites, Kynars, and polyester surfaces by applying a small area for adhesion and topcoat compatibility before proceeding with the entire job.

Airless Spray: Tip range between .013 and .017. Total fluid output pressure at the tip should not be less than 2200 PSI. Preferred pressure is 2500 PSI.

Clean Up

Clean brushes, rollers and other equipment with warm, soapy water immediately after use. If dry, clean with lacquer thinner.

Environmental, Health & Safety Information

Use only in a well ventilated area. Keep container closed when not in use. In case of spillage, absorb with inert material and dispose of in accordance with local regulations. Wash thoroughly after handling.

**KEEP OUT OF REACH OF CHILDREN
PROTECT FROM FREEZING**

**Refer to Safety Data Sheet for
additional health and safety information.**