

#### **Features**

- · High solids
- Suitable for occupied areas
- Can be recoated in just 4 hours
- Suitable For Use In USDA Inspected Facilities

#### **Recommended For**

Carbon Steel, Iron, Aluminum, Galvanized, Other Non-Ferrous Metals, Glass, Lexan, Concrete, Drywall. Acrylic Metal Primer is designed for use in general metal finishing/fabrication, food/beverage processing, chemical processing, industrial maintenance/refurbishment, and other segments where a rust inhibitive water cleanup primer is necessary.

# ACRYLIC METAL PRIMER V110

#### **General Description**

Acrylic Metal Primer is a water-reducible, rust-inhibitive primer for steel, iron, and non-ferrous metal. It provides excellent adhesion to a range of hard-to-coat surfaces and can even be applied over tightly adhering rust. Designed for light-to-moderate industrial exposures, this product can be top coated with a wide variety of coatings.

#### Limitations

- Do not apply if material, substrate or ambient temperature is below 50 °F (10 °C). Relative humidity should be below 90%.
- Do not apply if within 5 degrees of dew point or if rain is expected within 12 hours of application.
- Not for immersion service.
- Not for use on Kynar unless tested and approved by user.

	Prod	uct Informat	ion		
Colors — Standard:			Technical Data◊		White
White (01), Red (20)			Vehicle Type	Waterbased Acrylic	
Can be tinted with up to 2 oz. of Benjamin Moore® Color Preview® colorants per gallon			Pigment Type	Titanium Dioxide	
			Volume Solids	40 ± 1.0%	
— Tint Bases:			Coverage per Gallon at		
N/A			Coverage per Gallon at Recommended Film Thickness Clean Metal 350 - 450 Sq. /Ft. Tight Rust 160 - 220 Sq./Ft.		
— Special Colors: Contact your retailer.			Tight Rust	– Wet	7.3 - 10.0 mils
				– Dry	3.0 - 4.0 mils
			Clean Metal — Wet 3.5 – 4.6 mils		
Certification & Qualifications :			— Dry 1.4 – 1.9 mils		
Suitable for use in USDA inspected facilities			Depending on surface texture and porosity.		
Meets Performance Requirements of	VOC REGION	COMPLIANT		– Tack Free	1 Hour
TT-P-1975 and MIL-P-28577	FEDERAL	YES	Dry Time @ 77 °F (25 °C) @ 50% RH	<ul><li>To Recoat</li></ul>	4 Hours
Meets SSPC Paint #23	ОТС	YES	(25 0) (@ 50 % 1111	<ul><li>Cure Time</li></ul>	7 – 10 Days
	OTCII CARB	YES YES	High humidity and cool	temperatures w	Il result in longer
	CARB CARB07	YES	dry, recoat and service to	nd service times.	
	UTAH	YES	Dries By		Coalescence
	AZMC	YES	Viscosity		85 – 90 KU
	SCAQMD	NO	SAG Rating:	Passes 9-10 mils wet (Leneta)	
Technical Assistance:		1	Flash Point	(TT-P-1	200 °F or greater 41, Method 4293)
Available through your local authorized independent Benjamin Moore retailer.			Gloss/Sheen		5 – 10 @ 60°
For the location of the retailer nearest you, call 1-866-708-9180 or visit			Surface Temperature	– Min.	50 °F
www.benjaminmoore.com			at Application	– Max.	90 °F
			Thin With		Clean Water
			Clean Up Thinner	Wa	arm, Soapy Water
			Weight Per Gallon		10.9 lbs.
				– Min.	40 °F
			Storage Temperature	– Max.	95 °F
			Volatile Orga 199 Grams/Li	nic Compounds iter 1.66 Lbs.	` '

 $<sup>\</sup>Diamond$  Reported values are for White. Contact retailer for values of other bases or colors.

#### **Surface Preparation**

The performance of this product is directly dependent upon the degree of surface preparation employed. All dirt, oils and accumulated salts must be removed prior to employing specific surface preparation methods. SSPC-SP 1 Solvent Cleaning using Corotech V600 Oil & Grease Emulsifier will best accomplish this task.

WARNING! If you scrape, sand, or remove old paint, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Informational Hotline at 1-800-424-LEAD or log on to <a href="https://www.epa.gov/lead">www.epa.gov/lead</a>.

**Ferrous metals:** All loose rust and mill scale should be removed prior to application of this product. This is best accomplished by abrasive blasting. A minimum of SSPC-SP 6 Commercial Blast is recommended for severe environmental exposures. Small areas may be cleaned in accordance with SSPC-SP 2 Hand Tool Cleaning or SSPC-SP 3 Power Tool Cleaning or SSPC-SP 13 Power Tool Cleaning to Bare Metal. Tightly adhering rust may be coated over provided the surface is intended for use in mild atmospheric exposures.

**Galvanized steel, aluminum and other non-ferrous metals:** Clean bare metal with Corotech V600 Oil & Grease Emulsifier.

**Concrete** should have form release agents and hardening/curing compounds removed prior to coating.

#### **Application**

Mix thoroughly before application. The use of a drill mixer at low speed will best accomplish this task. Should not require thinning, however small amounts of water may be used if necessary.

**Airless Spray:** Tip range between 15 and 19 thousandths. Total fluid output pressure at tip should not be less than 2400 psi.

**Air Spray (Pressure Pot):** DeVilbis MBC or JGA gun, with 704 or 765 air cap and Fluid Tip E.

**NOTE:** Do not allow material to remain in hoses, gun or spray equipment. Thoroughly flush all equipment with recommended thinner.

Brush: Synthetic Bristle. / Roller: High quality short nap cover.

**NOTE:** Do not apply if material, substrate or ambient temperature is below 45 °F (7.2 °C). Relative humidity should be below 90%. Do not apply if within 5 degrees of dew point or if rain is expected within 12 hours of application.

TEST DATA		
Flexibility (ASTM D1737)	Pass 1/8" Mandrel	
Dry Heat Resistance	200 °F	
Wet Heat Resistance	150 °F	
Adhesion (ASTM D3359)	Pass 5B	
Salt Spray (ASTM B117) (2 Coats w/1 Topcoat; 1000 Hours	Rust Breakthrough: 10 Rust Area: 0.01%	
Abrasion Resistance (ASTM D4060) CS-17 Wheel, 1000 Cycles, 1000 g Load	100 mg Loss	
Accelerated Weathering (ASTM G53) 500 Hours	90% Gloss Retention <0.25 DE Color Change (CMC)	

CHEMICAL RESISTANCE GUIDE (NON-IMMERSION)				
Fresh Water				
Salt Water				
Acids				
Alkalis	See Finish Coat Data Sheets for			
Solvents	Resistance Information.			
Fuel	Resistance information.			
Acidic Salt Solutions				
Alkaline Salt Solutions				
Neutral Salt Solutions				

SYSTEMS RECOMMENDATIONS
COMPATIBLE FINISHES
V200 Line, V201, V230 Line, V231 Line, V220 Line, V300 Line,
V330 Line, V400 Line, V410, V440 Line, V500 Line, V510 Line,
V520 Line, 540 Line, and Other Acrylics, Vinyl Acrylics & Alkyds
V110 Waterborne DTM Metal Primer can be used as a barrier
coat on top of older coatings prior to application of high
performance coatings with "hotter" solvents, such as 2
component epoxies and urethanes.
For substrates other than listed above, or for usage in severe
environmental conditions, please consult with Corotech®
Technical Service

#### Clean Up

Clean up with warm, soapy water followed by a clean water rinse.

### Environmental Health & Safety Information

#### Danger

May cause cancer

Causes damage to organs through prolonged or repeated exposure

**Prevention:** IF exposed or concerned: Get medical advice/attention.

Response: If exposed or concerned get medical attention.

Storage: Store locked up.

**Disposal:** Dispose of contents/container to an approved waste disposal plant.



**WARNING:** This product contains isothiazolinone compounds at levels of <0.1%. These substances are biocides commonly found in most paints and a variety of personal care products as a preservative. Certain individuals may be sensitive or allergic to these substances, even at low levels

This document represents hazards of the product referenced above. Refer to the individual Safety Data Sheet for hazards of the specific product you will be using.

## PROTECT FROM FREEZING FOR PROFESSIONAL USE ONLY

Refer to Safety Data Sheet for additional health and safety information.