Benjamin Moore<sup>®</sup>



#### Features

- High zinc content delivers cathodic protection
- Thermoplastic resin requires tie coat under certain finishes
- Can be top coated or left uncoated

#### **Recommended For**

Ferrous Metal & Weathered Galvanized. Corotech® Organic Zinc Rich Primer is designed for the General Metal Finishing / Fabrication market, industrial maintenance market, the marine / offshore market.

# ORGANIC ZINC RICH PRIMER V170

#### **General Description**

Organic Zinc Rich Primer is a heavy-duty corrosion inhibitor for interior or exterior ferrous metal and weathered galvanized metal. It is made from an organic thermoplastic resin and leaves a finished film that is 83% zinc. Ideal for touching up existing galvanized metal with no topcoat.

#### Limitations

- Not for immersion service.
- Do not apply Corotech<sup>®</sup> Organic Zinc Rich Primer if air or surface temperatures are below 35 °F (1 °C) or above 90 °F (32.2 °C), or in relative humidity greater than 90%, or if surface or air temperatures are within 5 degrees of the dew point.
- · Do not apply over previous finishes.

	Pro	oduct Informa	tion			
Colors — Standard:			Technical Data◊	Gray		
Gray (79)			Vehicle Type	Thermoplastic Rubber		
			Pigment Type	Zinc		
— Tint Bases:			Volume Solids	43 ± 1.0%		
N/A Do not tint			Coverage per Gallon at Recommended Film Th			
— Special Colors:			Recommended Film Thickness	– Wet – Dry	4.0 - 5.3 mils 1.7 - 2.3 mils	
Contact your retailer.			Depending on surface texture and porosity.			
Certification & Qualifications: The product supported by this data sheet contains a maximum of 500 grams per liter VOC / VOS (4.17 lbs. /gal.) excluding			Dry Time @ 77 °F (25 °C) @ 50% RH	<ul> <li>Tack Free</li> <li>To Recoat</li> <li>Full Cure</li> </ul>	30 Minutes 12-18 Hours* 72 Hours	
water & exempt solvents.			*Allow 12 hours before topcoating with waterborne finishes. Allow a full 18 hours when topcoating with			
Masters Painters Institute MPI # 18		COMPLIANT	solvent, epoxy and urethane-based finishes. High			
Cold Galvanizing Project Qualification Meets Composition Requirements of	FEDERAL OTC	YES	humidity and cool temperatures will result in longer dry, recoat and service times.			
TT-P-1046	OTC	YES	Dries By			
Meets Performance Requirements of	CARB	YES	· · · · · ·		100 – 115 KU	
TT-P-641 & DOD-P-21035 Meets Performance Requirements of Mil-P-26915 Type I, Class A	CARB07	NO	Viscosity		80 °F or greater	
	UTAH	YES	Flash Point	Flash Point (TT-P-141, J		
Meets SSPC Paint #5 & SSPC Paint # 20, Type II	AZMC	NO	Gloss / Sheen	(11-1-1	$0 - 5 @ 60^{\circ}$	
	SCAQMD	NO		N.C.		
		•	Surface Temperature at Application	– Min. – Max.	35 °F 90 °F	
<b>Technical Assistance:</b> Available through your local authorized independent Benjamin Moore retailer. For the location of the retailer nearest you, call 1-866-708-9180 or visit www.benjaminmoore.com			Thin With		Do Not Thin	
			Clean Up Thinner	Corot	ech <sup>®</sup> V703 Xylene	
			Weight Per Gallon	00101	20.3 lbs.	
				N.C.		
			Storage Temperature	– Min. – Max.	45 °F 95 °F	
				– Wax.	90 F	
			Volatile Orga	anic Compounds	s (VOC)	
			498.5 Grams/Liter 4.16 Lbs./Gallon			

 $\Diamond$  Reported values are for Gray. Contact retailer for values of other bases or colors.

#### Surface Preparation

The performance of this product is directly dependent upon the degree of surface preparation employed. All dirt, oils, accumulated salts, and other contaminants must be removed prior to employing specific surface preparation methods. Removal of all contaminants should be completed in accordance with SSPC-SP 1. Ferrous metal substrates should be free of all mill scale and rust. Aggregate blasting should be in accordance with SSPC-SP 10 Near White Blast for cleanliness. Conscientious power tool cleaning (SSPC-SP 3) may be employed; however, for best results, power tool cleaning to bare metal (SSPC-SP 10 Near White Blast for cleanliness. Conscientious power tool cleaning to bare metal (SSPC-SP 10 Near White Blast for cleanliness. Conscientious power tool cleaning in accordance with SSPC-SP 10 Near White Blast for cleanliness. Conscientious power tool cleaning (SSPC-SP 3) may be employed; however, for best results, power tool cleaning in accordance with SSPC-SP 10 Near White Blast for cleanliness. Conscientious power tool cleaning (SSPC-SP 3) may be employed; however, for best results, power tool cleaning (SSPC-SP 11) is strongly suggested. Weathered Galvanized substrates should have all rust removed by aggregate blasting in accordance with SSPC-SP 10 Near White Blast for cleanliness. Conscientious power tool cleaning (SSPC-SP 3) may be employed; however, for best results, power tool cleaning to bare metal (SSPC-SP 11) is strongly suggested.

### It is not recommended that this coating be applied over previous finishes.

WARNING! If you scrape, sand, or remove old paint, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Informational Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead.

#### Application

Mix the product thoroughly before application. The use of a drill mixer at low speed will best accomplish this task. Ensure that all zinc is mixed into solution with none remaining on the bottom of the can. Do not apply Corotech® Organic Zinc Rich Primer if air or surface temperatures are below 35 °F (1 °C) or above 90 °F (32.2 °C), or in relative humidity greater than 90%, or if surface or air temperatures are within 5 degrees of the dew point. Product should be allowed to dry tack free prior to air or surface temperatures being within 5 degrees of the dew point.

Airless Spray (Preferred Method): Tip range between .019 and .025. Total fluid output pressure at tip should not be less than 2100 psi.

Air Spray (Pressure Pot): Must have air agitator. Binks or equivalent equipment. (Gun: #18 or 62; Fluid Nozzle: #66; Air Nozzle: 66 PE).

**NOTE:** Do not allow material to remain in hoses, gun or spray equipment. Thoroughly flush all equipment with recommended thinner. **Brush:** Natural Bristle (for small areas only).

TEST DATA				
Dry Heat Resistance	200 °F (93 °C)			
Wet Heat Resistance	125 °F (52 °C)			
Adhesion (ASTM D3359)	Pass 5B			
Salt Fog Resistance (ASTM B117) One coat	500 Hours-Pass (Rating: 10 Rust Area: 0.00%)			
CHEMICAL RESISTANCE GUIDE (NON-IMMERSION)				
Fresh Water				
Salt Water	1			
Acids				
Alkalis				
Solvents	See Finish Coat Data Sheets for			
Fuel	Resistance Information.			
Acidic Salt Solutions				
Alkaline Salt Solutions				
Neutral Salt Solutions				
SYSTEMS RECOMMENDATIONS				
COMPATIBLE FINISHES				
V300 Line, V330 Line, V341/V342 Line, V400, V440, V500, V510, V540 and other high performance coatings				

#### Clean Up

Clean with Corotech® V703 Xylene.

### Environmental Health & Safety Information DANGER!

Causes skin irritation

Causes serious eye irritation

May cause cancer

Suspected of damaging fertility or the unborn child

May cause damage to organs through prolonged or repeated exposure

May be fatal if swallowed and enters airways

#### Flammable liquid and vapor

**Prevention:** Obtain special instructions before use. Do not handle until all safety precautions have been read and understood. Use personal protective equipment as required. Wash face, hands and any exposed skin thoroughly after handling. Wear eye/face protection. Do not breathe dust/fume/mist/vapors/spray. Keep away from heat/sparks/open flames/hot surfaces, no smoking. Keep container tightly closed. Ground/bond container and receiving equipment. Use explosion-proof electrical/ventilating/lighting/equipment. Use only non-sparking tools. Take precautionary measures against static discharge.

**Response:** If exposed or concerned, get medical attention. If in eyes rinse cautiously with water for several minutes. Remove contact lenses, if present and easy to do. Continue rinsing. If eye irritation persists get medical attention. If skin irritation occurs get medical attention. If on skin (or hair) take off immediately all contaminated clothing. Rinse skin with water. Wash contaminated clothing before reuse. If swallowed immediately call a POISON CENTER or physician. Do NOT induce vomiting. In case of fire use CO2, dry chemical, or foam for extinction.

Storage: Store locked up. Store in a well-ventilated place, keep cool.

**Disposal:** Dispose of contents/container to an approved waste disposal plant.

WARNING Cancer and Reproductive Harm– www.P65warnings.ca.gov

This document represents hazards of the product referenced above. Refer to the individual Safety Data Sheet for hazards of the specific product you will be using.

#### KEEP OUT OF REACH OF CHILDREN PROTECT FROM FREEZING FOR PROFESSIONAL USE ONLY

## Refer to Safety Data Sheet for additional health and safety information.

Benjamin Moore & Co., 101 Paragon Drive, Montvale, NJ 07645 Tel: 866-708-9180 Fax: 888-248-2143 <u>www.benjaminmoore.com</u> M72 V170 EN 100219 ©2017, 2019 Benjamin Moore & Co. Benjamin Moore and the triangle "M" symbol are registered trademarks licensed to Benjamin Moore & Co. All other marks are the property of their respective owner.