Benjamin Moore



Features

- Pre-catalyzed, waterborne acrylic epoxy
- Single pack no catalyst
- Tints to all colors
- Excellent for retail, commercial, healthcare, schools and more
- Low VOC and water cleanup

Recommended For

Properly Prepared and/or Primed Steel, Iron, Concrete, Non-Ferrous Metals, Wood & Drywall. Corotech® V342 Pre-Catalyzed WB Epoxy is designed for interior use in food and beverage processing, chemical processing, transportation, warehouses, industrial refurbishment, healthcare, schools, large commercial structures and other areas where a high performance epoxy is needed which concerns that accompany conventional solvent thinned epoxies.

PRE-CATALYZED WATERBORNE EPOXY EGGSHELL V342

General Description

This unique product provides epoxy toughness in a ready-touse waterborne formula for walls, ceilings and trim (not ideal for floors). Low VOC and water cleanup make this product ideal for use in occupied areas. The cured film is scrubbable, resists water and common cleaning chemicals, and stands up to abrasion and marring. Excellent adhesion to many surfaces, including existing paint, drywall, primed masonry and primed metal.

Limitations

- Do not apply if material, substrate or ambient temperature is below 50 °F (10 °C) Relative humidity should be below 90%.
- Not recommended for floors.
- Interior Use Only

	Prod	luct Informat				
Colors — Standard:			Technical Data◊	Pastel Base		
White (01)			Vehicle Type	Pre-Catalyzed WB Epoxy		
		Pigment Type	Titanium Dioxide			
— Tint Bases:			Volume Solids	38 ± 1.0%		
Pastel Base (85), Tint Base (86), Deep Base (87), Clear Base (88).		Coverage per Gallon at Recommended Film Thickness 350 – 400 Sq. Ft.				
Tint with Universal Colorants Only			Recommended Film Thickness	– Wet – Drv	4.0 - 4.6 mils 1.5 - 1.7 mils	
— Special Colors: Contact your retailer.			Depending on surface texture and porosity. Be sure to estimate the right amount of paint for the job. This will ensure color uniformity and minimize the disposal of excess paint.			
Certification & Qualifications :			Dry Time @ 77 °F (25 °C) @ 50% RH	 – Tack Free – To Recoat – Full Cure 	1 Hour 2 Hours 72 Hours	
The products supported by this data sheet contain a maximum of 100 grams per liter VOC / VOS (0.83 lbs. /gal.) excluding water &	VOC REGION FEDERAL	COMPLIANT YES	High humidity and cool temperatures will result in longer dry, recoat and service times.			
exempt solvents.	OTC	YES	Dries By	Oxidation / Chemical Reaction		
Masters Painters Institute MPI #151 CDPH v1 Emission Certified Qualifies for CHPS low emitting credit (Collaborative for High Performance Schools)	OTCII	YES	Viscosity		95 – 100 KU	
	CARB CARB07 UTAH	YES YES YES	Flash Point	Greater than 200 °F (TT-P-141, Method 4293)		
	AZMC	YES	Gloss/Sheen	Eggshell	(10 - 15 @ 60°)	
	SCAQMD	NO	Surface Temperature at Application	– Min. – Max.	50 °F 90 °F	
Technical Assistance: Available through your local authorized independent Benjamin Moore retailer. For the location of the retailer nearest you, call 1-866-708-9180 or visit www.benjaminmoore.com			Thin With		Water	
			Clean Up Thinner	War	m, Soapy Water	
			Weight Per Gallon		10.8 lbs.	
			Storage Temperature	– Min. – Max.	45 °F 95 °F	
			Volatile Orga	nic Compounds		
			73 Grams/Lite			

◊ Reported values are for Pastel Base. Contact retailer for values of other bases or colors.

Surface Preparation

All surfaces must be sound, dry, clean and free of oil, grease, dirt, mildew, mill scale, form release agents, curing compounds, loose and flaking paint and other surface contaminants. Clean with Corotech[®] V600 Oil & Grease Emulsifier or V610 Citrus Based Cleaner. Remove all loose and peeling paint by wire brushing, scraping or sanding. Fill holes and cracks and sand smooth. Dull glossy surfaces by sanding. Moderate to heavily rusted surfaces must be thoroughly cleaned and properly primed.

NEW SURFACES: Concrete and Masonry: All vertical masonry surfaces must be allowed to cure a minimum of 30 days before painting. Acid etch or abrasive blast all slick, glazed concrete or concrete with laitance. For acid etching, follow all manufacturer's directions and safety instructions. We recommend Corotech® V620 Concrete Etch. Rinse thoroughly and allow to dry. Prime with one coat of InsI-x® Aqua Lock® Plus Primer Sealer.

Steel and Ferrous Metals: The use of Corotech® V110 Acrylic Metal Primer or V175 Waterborne Bonding Primer is recommended. All primers provide maximum performance over near white metal blasted surfaces (SSPCSP 10). There are however, situations and cost considerations that may prevent this type of surface preparation from being done. Corotech® Industrial Coatings have been designed to provide protection over less than ideal surfaces. The recommended standard is a commercial blast (SSPC-SP 6). The steel profile after the blast should be 1-2 mils and be jagged in nature. Surfaces must be free of grit dust. The coating should be applied as soon as possible after the blast in order to prevent flash rusting or surface contamination. Hand tool cleaning (SSPC-SP 2) or power tool cleaning (SSPC-SP 3) can be used if blasting is not possible. In areas where adequate surface preparation is not possible the use of V155 100% Solid Epoxy Pre-Primer is recommended. In highly corrosive areas where additional rust inhibitive qualities are required, prime with one coat of V170 Organic Zinc-Rich Primer prior to applying epoxy coatings.

Galvanized and Non-Ferrous Metals: Remove all oils from surface with Corotech® V600 Oil & Grease emulsifier. Solvent clean all surfaces [SSPC-SP 1]. Apply one coat of Corotech® V110 Acrylic Metal Primer or V175 Waterborne Bonding Primer.

Wood: Sand surfaces. Primer with $Insl-x^{\otimes}$ Prime Lock Plus Alkyd Primer or Aqua Lock[®] Plus Acrylic Primer Sealer.

Drywall: Insure drywall is dust & chalk free. Prime with an acrylic drywall primer.

Previously Painted Surfaces: Can be applied over most existing industrial finishes in good condition.

WARNING! If you scrape, sand, or remove old paint, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Informational Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead.

Application

Airless Spray (Preferred Method): Tip range between .015 and .019. Total fluid output pressure at tip should not be less than 2400 psi.

Air Spray (Pressure Pot): DeVilbis MBC or JGA gun, with 704 or 765 air cap and Fluid Tip E.

Brush: Synthetic Bristle only. / Roller: Synthetic Cover. 3/8" - 3/4" nap.

NOTE: Do not allow material to remain in hoses, gun or spray equipment. Thoroughly flush all equipment with warm water. No reduction is necessary. Do not apply if material, substrate or ambient temperature is below 50 °F (10 °C). Relative humidity should be below 90%.

TEST DATA		
Flexibility (ASTM D1737)	Pass 1/8" Mandrel	
Sag Resistance	6+ mils	
Scrub Resistance	600+ cycles	
Dry Heat Resistance	200°F	
Wet Heat Resistance	150°F	
Adhesion (ASTM D3359)	Pass 5B	
Pencil Hardness (2 week cure)	6B	
Block Resistance	Passes	
Accelerated Weathering (ASTM G53) 500 Hrs	90% Gloss Retention < 0.25 DE Color Change	
Abrasion Resistance (ASTM D4060) CS-10 Wheel, 1000g load	100 mg Loss	
Salt Spray (ASTM B117) 2 coats over V110 primer (1000 Hours)	Rust Breakthrough: 10 Rust Area: 0.01%	

SYSTEMS RECOMMENDATIONS		
PRIMERS		
Ferrous Metal (Blasted)	V110 Line, V150 Line, V155-00 or V160 Line	
Ferrous Metal (Marginally Prepared)	V155-00 or V160 Line	
Non-Ferrous Metal	V110 Line or V175-00	
Concrete	V110 Line, V114-01, V155-00, V160 Line, V163-01, V400-00 Clear or Aqua Lock™ Primer Sealer	
Drywall	Use Aqua Lock™ Primer Sealer or a good quality acrylic drywall primer	
Wood	Use Prime Lock™ Alkyd Primer or Aqua Lock Acrylic Primer Sealer	
Aged coatings	Use Direct (Check Compatibility) or use V110 Line as a barrier Coat	
COMPATIBLE INTERMEDIATES		
V160 Line, V163-01		
For substrates other than listed above, or for usage in severe environmental conditions, please consult with Corotech [®] Technical		

Clean Up

Clean with warm, soapy water.


Environmental Health & Safety Information

Service

Not a dangerous substance or mixture according to the Globally Harmonized System (GHS)

Keep container closed when not in use. In case of spillage, absorb with inert material and dispose of in accordance with local regulations. Wash thoroughly after handling. Refer to Safety Data Sheet for additional health and safety information.

May cause allergic skin reaction



This document represents hazards of the product referenced above. Refer to the individual Safety Data Sheet for hazards of the specific product you will be using.

KEEP OUT OF REACH OF CHILDREN KEEP FROM FREEZING

Refer to Safety Data Sheet for additional health and safety information.

Benjamin Moore & Co., 101 Paragon Drive, Montvale, NJ 07645 Tel: 866-708-9180 Fax: 888-248-2143 <u>www.benjaminmoore.com</u> M72 V342 EN 080318 ©2017, 2018 Benjamin Moore & Co. Benjamin Moore and the triangle "M" symbol are registered trademarks licensed to Benjamin Moore & Co. All other marks are the property of their respective owner. This product is not endorsed by or a division of CHPS. This product is provided by Benjamin Moore, not CHPS. All rights reserved