



GLOSS AND HARDNESS CATALYST V705

Features

- Speeds Drying
- Produces a higher gloss

General Description

Alkyd Gloss and Hardness Catalyst speeds drying while producing a higher gloss and more corrosion resistance, as well as a harder enamel finish. Other benefits include increased solvent and chemical resistance.

Recommended For

Corotech® Gloss & Hardness Alkyd Catalyst can be used with the following Corotech® Alkyds:

V200, V201, V220, V225, V230, and V231

Limitations

Product Information																																		
<p>Certifications & Qualifications: OEM/SHOP USE ONLY</p> <p>The product supported by this data sheet contains a maximum of 615 grams per liter VOC / VOS (5.13 lbs. /gal.) excluding water & exempt solvents.</p>	<p align="center">Technical Data</p> <table border="1"> <tr> <td>Generic Type</td> <td>Isocyanate</td> </tr> <tr> <td>Pigment Type</td> <td>N/A</td> </tr> <tr> <td>Volume Solids (mixed as recommended)</td> <td>69.1% ± 1.0% mixed</td> </tr> <tr> <td colspan="2">*If top coat is not applied within 72 hours abrade the surface to ensure proper inter-coat adhesion. Maximum abrasion and chemical resistance are achieved at full cure; care should be taken to prevent damage to the coating during the curing process. High humidity and cool temperatures will result in longer dry, recoat and cure times.</td> </tr> <tr> <td>Dries By</td> <td>N/A</td> </tr> <tr> <td>Dry Heat Resistance</td> <td>N/A</td> </tr> <tr> <td>Viscosity @ 77°F (mixed as recommended)</td> <td>N/A</td> </tr> <tr> <td>Flash Point (Mixed)</td> <td>91 ° F (TT-P-141, Method 4293)</td> </tr> <tr> <td>Gloss/Sheen</td> <td>N/A</td> </tr> <tr> <td>Thin With</td> <td>N/A</td> </tr> <tr> <td>Clean Up Thinner</td> <td>Xylene</td> </tr> <tr> <td>Mixed Ratio (by volume)</td> <td>See Application Section</td> </tr> <tr> <td>Induction time @ 77 °F</td> <td>None</td> </tr> <tr> <td>Pot Life @ 70 °F</td> <td>2 – 3 Hours</td> </tr> <tr> <td>Weight Per Gallon (mixed as recommended)</td> <td>9.0 lbs.</td> </tr> <tr> <td rowspan="2">Storage Temperature</td> <td>– Min. 40 °F</td> </tr> <tr> <td>– Max. 95 °F</td> </tr> </table>	Generic Type	Isocyanate	Pigment Type	N/A	Volume Solids (mixed as recommended)	69.1% ± 1.0% mixed	*If top coat is not applied within 72 hours abrade the surface to ensure proper inter-coat adhesion. Maximum abrasion and chemical resistance are achieved at full cure; care should be taken to prevent damage to the coating during the curing process. High humidity and cool temperatures will result in longer dry, recoat and cure times.		Dries By	N/A	Dry Heat Resistance	N/A	Viscosity @ 77°F (mixed as recommended)	N/A	Flash Point (Mixed)	91 ° F (TT-P-141, Method 4293)	Gloss/Sheen	N/A	Thin With	N/A	Clean Up Thinner	Xylene	Mixed Ratio (by volume)	See Application Section	Induction time @ 77 °F	None	Pot Life @ 70 °F	2 – 3 Hours	Weight Per Gallon (mixed as recommended)	9.0 lbs.	Storage Temperature	– Min. 40 °F	– Max. 95 °F
	Generic Type	Isocyanate																																
Pigment Type	N/A																																	
Volume Solids (mixed as recommended)	69.1% ± 1.0% mixed																																	
*If top coat is not applied within 72 hours abrade the surface to ensure proper inter-coat adhesion. Maximum abrasion and chemical resistance are achieved at full cure; care should be taken to prevent damage to the coating during the curing process. High humidity and cool temperatures will result in longer dry, recoat and cure times.																																		
Dries By	N/A																																	
Dry Heat Resistance	N/A																																	
Viscosity @ 77°F (mixed as recommended)	N/A																																	
Flash Point (Mixed)	91 ° F (TT-P-141, Method 4293)																																	
Gloss/Sheen	N/A																																	
Thin With	N/A																																	
Clean Up Thinner	Xylene																																	
Mixed Ratio (by volume)	See Application Section																																	
Induction time @ 77 °F	None																																	
Pot Life @ 70 °F	2 – 3 Hours																																	
Weight Per Gallon (mixed as recommended)	9.0 lbs.																																	
Storage Temperature	– Min. 40 °F																																	
	– Max. 95 °F																																	
<p>Technical Assistance</p> <p>Available through your local authorized independent Benjamin Moore retailer. For the location of the retailer nearest you, call 1-866-708-9180 or visit www.benjaminmoore.com</p>	<p align="center">Volatile Organic Compounds (VOC)</p> <p align="center">615 Grams / Liter 5.13 LBS / Gallon</p>																																	

Gloss And Hardness Catalyst V705

WARNING! If you scrape, sand, or remove old paint, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead.

Application

Mix the product thoroughly before adding to the alkyd enamel. Add a maximum of 1 pint per gallon of paint. When working with Isocyanates it is recommended that you wear an appropriate, properly fitted respirator approved by NIOSH/MSHA; an airline respirator (TC19C NIOSH/MSHA) is recommended.

Environmental Health & Safety Information

DANGER!

Harmful if inhaled

Causes skin irritation

Causes serious eye irritation

May cause allergy or asthma symptoms or breathing difficulties if inhaled

May cause an allergic skin reaction

Suspected of causing cancer

May cause respiratory irritation

May cause damage to organs through prolonged or repeated exposure

May be fatal if swallowed and enters airways

Flammable liquid and vapor

Prevention: Obtain special instructions before use. Do not handle until all safety precautions have been read and understood. Use personal protective equipment as required. Use only outdoors or in a well-ventilated area. Wash face, hands and any exposed skin thoroughly after handling. In case of inadequate ventilation wear respiratory protection. Contaminated work clothing should not be allowed out of the workplace. Do not breathe dust/fume/ mist/ vapors/spray. Keep away from heat/sparks/open flames/hot surfaces, no smoking. Keep container tightly closed. Ground/bond container and receiving equipment. Use explosion-proof electrical/ventilating/lighting/equipment. Use only non-sparking tools. Take precautionary measures against static discharge. Keep cool. Wear protective gloves/protective clothing/eye protection/face protection.

Response: If exposed or concerned get medical attention. If in eyes rinse cautiously with water for several minutes. Remove contact lenses, if present and easy to do. Continue rinsing. If eye irritation persists get medical attention. If skin irritation or rash occurs get medical attention. If on skin (or hair) take off immediately all contaminated clothing. Rinse skin with water. Wash contaminated clothing before reuse. If inhaled remove victim to fresh air and keep at rest in a position comfortable for breathing. If experiencing respiratory symptoms: Call a POISON CENTER or physician. If swallowed immediately call a POISON CENTER or physician. Do NOT induce vomiting. In case of fire use CO₂, dry chemical, or foam for extinction.

Storage: Store locked up. Store in a well-ventilated place. Keep container tightly closed.

Disposal

Dispose of contents/container to an approved waste disposal plant.

IMPORTANT: Designed to be mixed with other components. Mixture will have hazards of all components. Before opening packages, read all warning labels. Follow all precautions.



WARNING Cancer and Reproductive Harm—
www.P65warnings.ca.gov

KEEP OUT OF REACH OF CHILDREN

**Refer to Safety Data Sheet for
additional health and safety information.**