



ARBORCOAT®

EXTERIOR OIL FINISH TRANSLUCENT C326

Features

- Provides protection and color without obscuring the grain or texture of the wood
- Provides mildew resistant coating
- Scuff resistant
- Formulated to penetrate, protect, and beautify wooden decking and furniture
- A water repellent coating
- May be applied to either soft or hard woods.

General Description

A premium quality translucent deck and siding stain that penetrates deeper into the wood to provide superior durability. Trans-Oxide pigments are ground into this weather tested resin to provide ultimate sun protection, abrasion and mildew resistance. It may be used over substrates previously stained with a transparent stain in good condition.

Recommended For

Residential or commercial applications where a premium quality finish is desired. For exterior use on wood decking, fencing, siding, and furniture. Ideal for hardwoods like mahogany, teak, ipe and softwoods like cedar, pine and redwood.

Limitations

- Do not apply when air and surface temperatures are below 40 °F (4.4 °C)
- New pressure treated lumber must be allowed to dry out or have a moisture content below 12%.
- Do not apply at a rate less than 200 sq ft per Gallon.

Product Information

<p>Colors — Standard: Natural (10), Redwood (20), Teak (30), Cedar (40), Mahogany (60) and Silver Gray (70)</p> <p>Do not tint</p>	<table border="1"> <thead> <tr> <th colspan="2">Technical Data◇</th> <th>Natural</th> </tr> </thead> <tbody> <tr> <td>Vehicle Type</td> <td colspan="2">Alkyd / Tung Oil</td> </tr> <tr> <td>Pigment Type</td> <td colspan="2">Trans-Oxide</td> </tr> <tr> <td>Volume Solids</td> <td colspan="2">57%</td> </tr> <tr> <td>Coverage per Gallon at</td> <td colspan="2">200 – 350 sq. ft.</td> </tr> <tr> <td>Recommended Film Thickness</td> <td colspan="2">(18.6 – 32.5 sq. m.)</td> </tr> <tr> <td rowspan="2">Recommended Film Thickness</td> <td>– Wet</td> <td>Penetrating Minimal</td> </tr> <tr> <td>– Dry</td> <td>Penetrating Minimal</td> </tr> <tr> <td colspan="3">Depending on surface texture and porosity. Be sure to estimate the right amount of stain for the job. This will ensure color uniformity and minimize the disposal of excess material.</td> </tr> <tr> <td rowspan="3">Dry Time @ 77 °F (25 °C) @ 50% RH</td> <td>– To Touch</td> <td>6 - 8 Hours</td> </tr> <tr> <td>– To Recoat</td> <td>24 - 48 Hours</td> </tr> <tr> <td>– Return to Service</td> <td>5 – 7 Days</td> </tr> <tr> <td colspan="3">High humidity and cool temperatures will result in longer dry, recoat and service times. Allow 48 hours dry time before subjecting decks to normal foot traffic.</td> </tr> <tr> <td>Dries By</td> <td colspan="2">Evaporation, Oxidation</td> </tr> <tr> <td>Viscosity</td> <td colspan="2">53 ± 2 KU</td> </tr> <tr> <td>Flash Point</td> <td colspan="2">Combustible @ 107 °F</td> </tr> <tr> <td>Gloss / Sheen</td> <td colspan="2">Flat</td> </tr> <tr> <td rowspan="2">Surface Temperature at Application</td> <td>– Min.</td> <td>40 °F (4.4 °C)</td> </tr> <tr> <td>– Max</td> <td>90 °F (32 °C)</td> </tr> <tr> <td>Thin With</td> <td colspan="2">Do Not Thin</td> </tr> <tr> <td>Clean Up Thinner</td> <td colspan="2">Mineral Spirits</td> </tr> <tr> <td>Weight Per Gallon</td> <td colspan="2">8.2 lbs.</td> </tr> <tr> <td rowspan="2">Storage Temperature</td> <td>– Min.</td> <td>40 °F (4.4 °C)</td> </tr> <tr> <td>– Max</td> <td>90 °F (32 °C)</td> </tr> <tr> <td colspan="3" style="text-align: center;">Volatile Organic Compounds (VOC)</td> </tr> <tr> <td colspan="2">245 Grams/Liter</td> <td>2.04 Lbs./Gallon</td> </tr> </tbody> </table>	Technical Data◇		Natural	Vehicle Type	Alkyd / Tung Oil		Pigment Type	Trans-Oxide		Volume Solids	57%		Coverage per Gallon at	200 – 350 sq. ft.		Recommended Film Thickness	(18.6 – 32.5 sq. m.)		Recommended Film Thickness	– Wet	Penetrating Minimal	– Dry	Penetrating Minimal	Depending on surface texture and porosity. Be sure to estimate the right amount of stain for the job. This will ensure color uniformity and minimize the disposal of excess material.			Dry Time @ 77 °F (25 °C) @ 50% RH	– To Touch	6 - 8 Hours	– To Recoat	24 - 48 Hours	– Return to Service	5 – 7 Days	High humidity and cool temperatures will result in longer dry, recoat and service times. Allow 48 hours dry time before subjecting decks to normal foot traffic.			Dries By	Evaporation, Oxidation		Viscosity	53 ± 2 KU		Flash Point	Combustible @ 107 °F		Gloss / Sheen	Flat		Surface Temperature at Application	– Min.	40 °F (4.4 °C)	– Max	90 °F (32 °C)	Thin With	Do Not Thin		Clean Up Thinner	Mineral Spirits		Weight Per Gallon	8.2 lbs.		Storage Temperature	– Min.	40 °F (4.4 °C)	– Max	90 °F (32 °C)	Volatile Organic Compounds (VOC)			245 Grams/Liter		2.04 Lbs./Gallon
Technical Data◇		Natural																																																																								
Vehicle Type	Alkyd / Tung Oil																																																																									
Pigment Type	Trans-Oxide																																																																									
Volume Solids	57%																																																																									
Coverage per Gallon at	200 – 350 sq. ft.																																																																									
Recommended Film Thickness	(18.6 – 32.5 sq. m.)																																																																									
Recommended Film Thickness	– Wet	Penetrating Minimal																																																																								
	– Dry	Penetrating Minimal																																																																								
Depending on surface texture and porosity. Be sure to estimate the right amount of stain for the job. This will ensure color uniformity and minimize the disposal of excess material.																																																																										
Dry Time @ 77 °F (25 °C) @ 50% RH	– To Touch	6 - 8 Hours																																																																								
	– To Recoat	24 - 48 Hours																																																																								
	– Return to Service	5 – 7 Days																																																																								
High humidity and cool temperatures will result in longer dry, recoat and service times. Allow 48 hours dry time before subjecting decks to normal foot traffic.																																																																										
Dries By	Evaporation, Oxidation																																																																									
Viscosity	53 ± 2 KU																																																																									
Flash Point	Combustible @ 107 °F																																																																									
Gloss / Sheen	Flat																																																																									
Surface Temperature at Application	– Min.	40 °F (4.4 °C)																																																																								
	– Max	90 °F (32 °C)																																																																								
Thin With	Do Not Thin																																																																									
Clean Up Thinner	Mineral Spirits																																																																									
Weight Per Gallon	8.2 lbs.																																																																									
Storage Temperature	– Min.	40 °F (4.4 °C)																																																																								
	– Max	90 °F (32 °C)																																																																								
Volatile Organic Compounds (VOC)																																																																										
245 Grams/Liter		2.04 Lbs./Gallon																																																																								
<p>— Tint Bases: N/A</p>																																																																										
<p>— Special Colors: Contact your Benjamin Moore representative</p>																																																																										
<p>Certifications & Qualifications: Master Painter Institute MPI # 13 & 33</p> <table border="1"> <thead> <tr> <th>VOC REGION</th> <th>COMPLIANT</th> </tr> </thead> <tbody> <tr> <td>FEDERAL</td> <td>YES</td> </tr> <tr> <td>OTC</td> <td>YES</td> </tr> <tr> <td>OTCII</td> <td>YES</td> </tr> <tr> <td>CARB</td> <td>YES</td> </tr> <tr> <td>CARB07</td> <td>YES</td> </tr> <tr> <td>UTAH</td> <td>YES</td> </tr> <tr> <td>AZMC</td> <td>YES</td> </tr> <tr> <td>SCAQMD</td> <td>NO</td> </tr> </tbody> </table>	VOC REGION	COMPLIANT	FEDERAL	YES	OTC	YES	OTCII	YES	CARB	YES	CARB07	YES	UTAH	YES	AZMC	YES	SCAQMD	NO																																																								
VOC REGION	COMPLIANT																																																																									
FEDERAL	YES																																																																									
OTC	YES																																																																									
OTCII	YES																																																																									
CARB	YES																																																																									
CARB07	YES																																																																									
UTAH	YES																																																																									
AZMC	YES																																																																									
SCAQMD	NO																																																																									
<p>Technical Assistance Available through your local authorized independent Benjamin Moore retailer. For the location of the retailer nearest you, call 1-866-708-9180 or visit www.benjaminmoore.com</p>																																																																										

◇ Reported values are for Natural. Contact Benjamin Moore for values of other bases or colors.

Surface Preparation

Optimal performance is achieved when the product is applied to a clean, dry and absorbent wood substrate. This product must be able to penetrate.

New Wood: Smooth planed wood siding, trim, or deck boards must be sanded thoroughly or treated with Benjamin Moore® Brighten, Brightener & Neutralizer (317) to break the "mill glaze" and allow proper penetration and adhesion. After prep is complete, test for penetration by applying a few drops of water to the dry substrate. If the water does not quickly penetrate, repeat prep or consult your Benjamin Moore® retailer.

Weathered Wood: Prior to staining, weathered wood must be treated with Benjamin Moore® Restore, for Gray & Weathered Wood (N316), following label directions, until a sound surface is obtained (loose or damaged wood fibers removed).

Previously Stained Surfaces: This product can also be applied to surfaces previously stained with a transparent or semi transparent stain that is weathered but is not flaking or peeling. Remove contaminants or chalky residue from weathered stained surfaces by washing with Benjamin Moore® Clean, (N318) and allow to dry thoroughly.

If the existing stain is flaking or peeling it should be removed prior to staining. Existing paint, stain or sealer can be removed by sanding with an On Floor machine or using Benjamin Moore® Remove, Finish Remover (315).

Un-weathered areas such as eaves, ceilings, overhangs or protected wall areas must be washed with Benjamin Moore® Clean, (N318) and rinsed with a strong stream from a garden hose to remove surface salts that can interfere with proper adhesion.

Mildew: Stains from mildew must be removed by cleaning with Benjamin Moore® Clean (N318) prior to coating the surface.

Caution: Refer to the 315, N316, 317 and N318 technical data and material safety data sheets for instructions on their proper use and handling.

WARNING! If you scrape, sand or remove old paint, you may release lead dust. **LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE.** Wear a NIOSH-approved respirator to control lead exposure. Carefully clean up with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead

Application

Prior to finishing, ensure having enough product to complete an entire section. Stir thoroughly before and occasionally during use. Brushing is the preferred method of application. When applied by roller or spray, back brushing is recommended to ensure a uniform distribution. Apply as received in the container.

Do not over apply, excessive or uneven application will prolong the dry time and may result in sheen irregularity. To minimize lapping, always maintain a wet edge. On horizontal siding apply the stain on a section of 2 or 3 boards completely across the house. Lower the ladder and continue in the same manner until the side is completed. Vertical siding is coated using the same principle from top to bottom. Never stop staining in mid-wall; continue until a natural break is reached, such as a window. On decks apply stain only a few boards at a time keeping the leading edge "wet."

Refrain from applying this finish in direct hot sun. Do not apply when air and surface temperatures are below 40 °F (4.4 °C), nor over damp surfaces or during threatening weather.

If needed, a second thin coat of stain can be applied. Wait for the first coat to dry 24-48 hours before applying the second coat. Please note that multiple coats will affect the opacity of the final finish and obscure more of the natural color of the wood

Spray Application, Airless: Fluid Pressure — 1,000 to 2,000 PSI;
Tip — .011–.013 Orifice

Thinning/Clean Up

DANGER – Rags, steel wool or waste soaked with the product may spontaneously catch fire if improperly discarded. Immediately after use, place rags, steel wool or waste in a sealed water-filled metal container.

USE COMPLETELY OR DISPOSE OF PROPERLY. This product contains organic solvents which may cause adverse effects to the environment if handled improperly. Emptied containers may retain product residue. Follow label warnings even after container is emptied. Residual vapors may explode on ignition.

Disposal of wastes containing either organic solvents or free-liquids in landfills is prohibited. **Local disposal requirements vary; consult your sanitation department or state-designated environmental agency for local disposal options.**

Environmental, Health & Safety Information

DANGER!

COMBUSTIBLE LIQUID AND VAPOR

VAPOR HARMFUL

Contains: 4-Chlorobenzotrifluoride, Petroleum distillates and Methyl ethyl ketoxime

HARMFUL OR FATAL IF SWALLOWED. ASPIRATION HAZARD. CAUSES IRRITATION TO EYES, SKIN AND RESPIRATORY TRACT. MAY CAUSE ALLERGIC SKIN REACTION.

NOTICE: Repeated or prolonged exposure to organic solvents may lead to permanent brain and nervous system damage. Intentional misuse by deliberately concentrating and inhaling vapors may be harmful or fatal.

Keep away from heat and flame. **Use only with adequate ventilation.** Do not breathe vapors, spray mist or sanding dust. Avoid contact with eyes and prolonged or repeated contact with skin. To avoid breathing vapors or spray mist open windows and doors or use other means to ensure fresh air entry during application and drying. If you experience eye watering, headache or dizziness or if air monitoring demonstrates vapor levels are above the applicable limits, wear an appropriate, properly fitted respirator (NIOSH approved) during and after application. Follow respirator manufacturer's directions for respirator use. Aspiration Hazard. Small amounts aspirated into the respiratory system may cause mild to severe pulmonary injury. Close container after each use. Wash thoroughly after handling.



WARNING Cancer and Reproductive Harm—
www.P65warnings.ca.gov

FIRST AID: If affected by inhalation of vapors or spray mist, remove to fresh air. In case of eye contact, flush immediately with plenty of water for at least 15 minutes and get medical attention immediately; for skin, wash thoroughly with soap and water. If symptoms persist, seek medical attention. If swallowed, do not induce vomiting. Get medical attention immediately.

IN CASE OF: FIRE – Use foam, CO₂, dry chemical, or water fog.
SPILL – Absorb with inert material and dispose of as specified under "Clean Up".

KEEP OUT OF REACH OF CHILDREN

Refer to Safety Data Sheet for additional health and safety information.