



LATEX DRY FALL FLAT 395

Features

- Overspray settles as dry powder (10 ft.)
- Minimal surface preparation
- Super hiding
- Fast dry for quick recoat

Recommended For

- For commercial and residential applications
- For spray application to interior ceilings, walls and structural members in commercial and institutional buildings. Overspray dries to dust before reaching the floor. May be applied to galvanized metal.

General Description

This fast dry interior latex is designed to provide superior hiding and allow for minimal surface preparation. The dry fall qualities of this product cause the overspray to settle as a dry powder in approximately 10 feet of fall.

Limitations

- Apply when surface and air temperatures are between 50 °F (10 °C) and 90 °F (32.2 °C)
- Spray application only
- Not for high corrosion areas
- Not for high abuse areas
- Not for areas with very high humidity
- Air movement, temperature and humidity will affect the dry fall

Product Information

Colors — Standard:

White (01), Black (80)

— Tint Bases:

Benjamin Moore® Gennex® bases 1X, 2X, 3X & 4X

— Special Colors:

Contact your Benjamin Moore® retailer.

Certifications & Qualifications:

VOC compliant in all regulated areas

- Qualifies for LEED® v4 Credit
- Qualifies for CHPS low emitting credit (Collaborative for High Performance Schools)
- CDPH v1 Emission Certified
- Class A (0-25) over non-combustible surfaces when tested in accordance with ASTM E-84
- Master Painters Institute MPI # 118

Technical Assistance

Available through your local authorized independent Benjamin Moore retailer. For the location of the retailer nearest you, call 1-866-708-9180 or visit www.benjaminmoore.com

Technical Data◇

White

Vehicle Type	Acrylic	
Pigment Type	Titanium Dioxide	
Volume Solids	41 ± 1.0%	
Coverage per Gallon at Recommended Film Thickness	250 – 425 sq. ft. (23.2-39.5 sq. m.)	
Recommended Film Thickness	– Wet	3.4 – 6.1 mils
	– Dry	1.4 – 2.6 mils
Depending on surface texture and porosity. Be sure to estimate the right amount of paint for the job. This will ensure color uniformity and minimize the disposal of excess paint.		
Dry Time @ 77 °F (25 °C) @ 50% RH	– To Touch	30 Minutes
	– To Recoat	1 Hour
High humidity and cool temperatures will result in longer dry, recoat and service times.		
Dries By	Coalescence	
Viscosity	85 ± 5 KU	
Flash Point	None	
Gloss / Sheen	Flat (0 – 6 @ 85°)	
Surface Temperature at Application	– Min.	50 °F
	– Max.	90 °F
Thin With	Clean Water	
Clean Up Thinner	Clean Water	
Weight Per Gallon	12.9 lbs	
Storage Temperature	– Min.	40 °F
	– Max.	95 °F

Volatile Organic Compounds (VOC)

37.9 Grams/Liter 0.31 Lbs./Gallon

◇ Reported values are for White.

Surface Preparation

Previously Painted or Primed Surfaces: Ensure that the surface is clean, dry, and free from oil, grease, dirt, salts, and any other contaminants. All blistered and loose paint must be removed. All bare surfaces should be appropriately primed. Consult your retailer. Glossy surfaces should be roughened before recoating.

Factory Primed or Finished Interior Metal Roof Deck: These surfaces may be hard, slick and contain silicone or other ingredients to prevent blocking. The surface can pose adhesion and fish-eye problems especially for acrylic coatings. Always apply a test patch to confirm suitability before completing the entire project. Allow paint to dry at least 3 days before testing adhesion. Be sure decking manufacturer certifies the deck is paintable.

Concrete and Masonry: Remove all loose particles, laitance, oil, grease, form release agents, and any other contaminants. New concrete and masonry must be allowed to cure for a minimum of 30 days. Before painting, roughen the surface by abrasive blasting, acid etching, or scarifying.

Wood: Ensure the wood is clean and dry. Sand all rough areas to a smooth appearance. Seal all knots, sap streaks, and pitch stains with an appropriate stain-sealing primer.

WARNING! If you scrape, sand, or remove old paint, you may release lead dust. **LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE.** Wear a NIOSH approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Informational Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead.

Application

This product is best applied with airless spray equipment. Mix product thoroughly stirring before use. For best results, test dry fall distance and follow surface preparation instructions prior to applying product. Changes in application equipment, pressures and/or tip sizes may be required as a result of changes in ambient temperatures or conditions. Dry fall characteristics are dependent on the degree of air movement and will be adversely affected at temperatures below 70°F (21°C) and relative humidity greater than 50%. Reduction will adversely affect the dry fall characteristics of the product. Overspray may adhere to hot surfaces; protection of some equipment may be required.

Spray, Airless: Fluid Pressure — 1,800 to 3,000 PSI;
Tip — .013 - .019 Orifice

Thinning/Clean Up

Clean all equipment immediately after use with clean, fresh water. Spray equipment should be given a final rinse with mineral spirits to prevent rusting or follow state/local guidelines on solvent use or follow state/local guidelines on solvent use.

USE COMPLETELY OR DISPOSE OF PROPERLY. Dry, empty containers may be recycled in a can recycling program. **Local disposal requirements vary; consult your sanitation department or state-designated environmental agency on disposal options.**

Environmental Health & Safety Information

Use only with adequate ventilation. Do not breathe spray mist or sanding dust. Ensure fresh air entry during application and drying. Avoid contact with eyes and prolonged or repeated contact with skin. Avoid exposure to dust and spray mist by wearing a NIOSH approved respirator during application, sanding and clean up. Follow respirator manufacturer's directions for respirator use. Close container after each use. Wash thoroughly after handling.



WARNING Cancer and Reproductive Harm—
www.P65warnings.ca.gov

WARNING: This product contains isothiazolinone compounds at levels of <0.1%. These substances are biocides commonly found in most paints and a variety of personal care products as a preservative. Certain individuals may be sensitive or allergic to these substances, even at low levels.

FIRST AID: In case of eye contact, flush immediately with plenty of water for at least 15 minutes; for skin, wash thoroughly with soap and water. If symptoms persist, seek medical attention. If you experience difficulty breathing, leave the area to obtain fresh air. If continued difficulty is experienced, get medical attention immediately.

IN CASE OF SPILL – Absorb with inert material and dispose of as specified under "Clean Up".

**KEEP OUT OF REACH OF CHILDREN
PROTECT FROM FREEZING**

**Refer to Safety Data Sheet for additional
health and safety information.**