



STAYS CLEAR®

ACRYLIC POLYURETHANE GLOSS

W422

Features

- Does not yellow like solvent based varnishes & polyurethanes.
- Tintable to many decorative shades.
- Quick dry and re-coat.
- Soap and water clean up.

Recommended For

- For commercial and residential applications
- Applicable for new or previously painted, stained, or varnished interior wood surfaces including floors.

General Description

A premium quality product that combines the attributes of acrylic and polyurethane resins to produce a durable clear finish that dries quickly. Provides excellent resistance to damage caused by abrasion, household chemicals and water, alcohol or food stains. For use on new or previously painted, stained or varnished interior wood surfaces, including floors.

Limitations

- Do not apply when air and surface temperatures are below 50 °F (10 °C)

Product Information																																									
<p>Colors — Standard: Clear (00)</p> <p>(May be tinted with up to 2.0 fl. oz. Benjamin Moore® Color Preview® or Gennex® colorants per gallon)</p> <p>— Tint Bases: Not available</p> <p>— Special Colors: Not available</p> <p>Certifications & Qualifications: VOC compliant in all regulated areas</p> <p>Qualifies for LEED® v4 Credit Qualifies for CHPS low emitting credit (Collaborative for High Performance Schools) CDPH v1 Emission Certified</p> <p>Technical Assistance Available through your local authorized independent Benjamin Moore retailer. For the location of the retailer nearest you, call 1-866-708-9180 or visit www.benjaminmoore.com</p>	<table border="1"> <thead> <tr> <th>Technical Data</th> <th>Gloss</th> </tr> </thead> <tbody> <tr> <td>Vehicle Type</td> <td>Acrylic Polyurethane</td> </tr> <tr> <td>Pigment Type</td> <td>None</td> </tr> <tr> <td>Volume Solids</td> <td>26.4%</td> </tr> <tr> <td>Coverage per Gallon at Recommended Film Thickness</td> <td>350 – 450 Sq. Ft.</td> </tr> <tr> <td>Recommended Film Thickness</td> <td>– Wet 3.8 – 4.9 mils – Dry 1.0 – 1.3 mils</td> </tr> <tr> <td colspan="2">Depending on surface texture and porosity. Be sure to estimate the right amount of paint for the job. This will ensure color uniformity and minimize the disposal of excess paint.</td> </tr> <tr> <td>Dry Time @ 77 °F (25 °C) @ 50% RH</td> <td>– To Touch 1 hour – To Recoat 2 – 3 hours</td> </tr> <tr> <td colspan="2">Painted surfaces can be washed after two weeks. High humidity and cool temperatures will result in longer dry, recoat and service times. Allow final coat to harden 24 hours before subjecting to normal floor traffic.</td> </tr> <tr> <td>Dries By</td> <td>Evaporation, Coalescence</td> </tr> <tr> <td>Viscosity</td> <td>72 ± 2 KU</td> </tr> <tr> <td>Flash Point</td> <td>None</td> </tr> <tr> <td>Gloss / Sheen</td> <td>Gloss (75+ @ 60°)</td> </tr> <tr> <td>Surface Temperature at Application</td> <td>– Min. 50 °F – Max 90 °F</td> </tr> <tr> <td>Thin With</td> <td>Do not thin</td> </tr> <tr> <td>Clean Up Thinner</td> <td>Clean Water</td> </tr> <tr> <td>Weight Per Gallon</td> <td>8.6 lbs</td> </tr> <tr> <td>Storage Temperature</td> <td>– Min. 40 °F – Max 90 °F</td> </tr> <tr> <td colspan="2" style="text-align: center;">Volatile Organic Compounds (VOC)</td> </tr> <tr> <td colspan="2" style="text-align: center;">250 Grams/Liter 2.08 lbs./Gallon</td> </tr> </tbody> </table>	Technical Data	Gloss	Vehicle Type	Acrylic Polyurethane	Pigment Type	None	Volume Solids	26.4%	Coverage per Gallon at Recommended Film Thickness	350 – 450 Sq. Ft.	Recommended Film Thickness	– Wet 3.8 – 4.9 mils – Dry 1.0 – 1.3 mils	Depending on surface texture and porosity. Be sure to estimate the right amount of paint for the job. This will ensure color uniformity and minimize the disposal of excess paint.		Dry Time @ 77 °F (25 °C) @ 50% RH	– To Touch 1 hour – To Recoat 2 – 3 hours	Painted surfaces can be washed after two weeks. High humidity and cool temperatures will result in longer dry, recoat and service times. Allow final coat to harden 24 hours before subjecting to normal floor traffic.		Dries By	Evaporation, Coalescence	Viscosity	72 ± 2 KU	Flash Point	None	Gloss / Sheen	Gloss (75+ @ 60°)	Surface Temperature at Application	– Min. 50 °F – Max 90 °F	Thin With	Do not thin	Clean Up Thinner	Clean Water	Weight Per Gallon	8.6 lbs	Storage Temperature	– Min. 40 °F – Max 90 °F	Volatile Organic Compounds (VOC)		250 Grams/Liter 2.08 lbs./Gallon	
Technical Data	Gloss																																								
Vehicle Type	Acrylic Polyurethane																																								
Pigment Type	None																																								
Volume Solids	26.4%																																								
Coverage per Gallon at Recommended Film Thickness	350 – 450 Sq. Ft.																																								
Recommended Film Thickness	– Wet 3.8 – 4.9 mils – Dry 1.0 – 1.3 mils																																								
Depending on surface texture and porosity. Be sure to estimate the right amount of paint for the job. This will ensure color uniformity and minimize the disposal of excess paint.																																									
Dry Time @ 77 °F (25 °C) @ 50% RH	– To Touch 1 hour – To Recoat 2 – 3 hours																																								
Painted surfaces can be washed after two weeks. High humidity and cool temperatures will result in longer dry, recoat and service times. Allow final coat to harden 24 hours before subjecting to normal floor traffic.																																									
Dries By	Evaporation, Coalescence																																								
Viscosity	72 ± 2 KU																																								
Flash Point	None																																								
Gloss / Sheen	Gloss (75+ @ 60°)																																								
Surface Temperature at Application	– Min. 50 °F – Max 90 °F																																								
Thin With	Do not thin																																								
Clean Up Thinner	Clean Water																																								
Weight Per Gallon	8.6 lbs																																								
Storage Temperature	– Min. 40 °F – Max 90 °F																																								
Volatile Organic Compounds (VOC)																																									
250 Grams/Liter 2.08 lbs./Gallon																																									

Stays Clear® Acrylic Polyurethane Gloss W422

Surface Preparation

Surfaces to be finished must be free from wax, dirt, grease, dust, and other contaminants. Glossy surfaces must be dulled with sandpaper or synthetic steel wool. **Do not use steel wool loose fibers will cause rusting in the finish coat.** Open grained woods such as oak or mahogany that will be subject to water or liquid spills should be filled with an interior wood grain filler according to label instructions.

Note: The application of this or any clear acrylic finish over fresh alkyl coatings may cause yellowing of the basecoat.

WARNING! If you scrape, sand or remove old paint, you may release lead dust. **LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE.** Wear a NIOSH-approved respirator to control lead exposure. Carefully clean up with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead.

Primer/Finish Systems

Raw Wood: New interior wood must be sanded smooth. Use fine sandpaper following the grain of the wood to achieve a smooth finish. Stays Clear® may be used as both the sealer and finish on raw wood. Allow sufficient dry time before sanding lightly and applying topcoats.

Sealer: 1 coat Stays Clear® Acrylic Polyurethane

Finish: 1-2 or more coats Stays Clear® Acrylic Polyurethane

Old Finishes: Do not apply over sealers containing silicones, wax, or stearate. Remove old finishes which are chipping, peeling, or in otherwise poor condition. Remove any and all old finishes containing wax or stearate. Other finishes in good condition must be sanded lightly with fine sandpaper until smooth. Surfaces requiring complete restoration must have the finish removed by either power sanding or use of paint and varnish remover, then treated as new surface.

One-Day Finishing (Floors): Apply in thin, even coats following grain of wood. For 3 coat/1-day application, allow at least 3 hours dry time between coats. Sand lightly with fine sandpaper between applications. If sandpaper gums when sanding, insufficient drying time has been allowed between coats. Optimal conditions are 60 °F to 80° F and 30% to 60% relative humidity. After final coat has been applied, avoid heavy traffic on floors during the initial 24 hours. In addition, care should be taken during first week after application, especially when replacing furniture.

Application

Stir thoroughly before and occasionally during use to ensure a uniform sheen.

Brush: Apply as received in the container with a good quality synthetic brush or painting pad. Apply along grain of the wood in thin, even, uniform coats. Keep a wet-edge during application and avoid working back into partially dry areas.

Roller: Large smooth surfaces can be coated using a short-nap roller in thin, even, uniform coats. Keep a wet-edge during application and avoid working back into partially dry areas.

Spray, Airless: Fluid Pressure —1,500 to 2,000 PSI;

Tip —.011 - .015 Orifice;

Allow a minimum of 2-3 hours dry; then sand lightly, rubbing with the grain, before recoating. For optimal performance a minimum of two coats are required for furniture or trim. Floors require 3 or more coats. Allow final coat to harden for 24 hours before subjecting to normal floor traffic.

Thinning/Cleanup

Do not thin; thinning will reduce the sealing ability of this product. Do not add other paints or solvents. Wash painting tools in warm soapy water immediately after use. Spray equipment should be given a final rinse with mineral spirits to prevent rusting.

USE COMPLETELY OR DISPOSE OF PROPERLY. Dry empty containers may be recycled in a can recycling program. Local disposal requirements vary; consult your sanitation department or state-designated environmental agency on disposal options.

Environmental, Health & Safety Information

Use only with adequate ventilation. Do not breathe spray mist or sanding dust. Ensure fresh air entry during application and drying. Avoid contact with eyes and prolonged or repeated contact with skin. Avoid exposure to dust and spray mist by wearing a NIOSH approved respirator during application, sanding and clean up. Follow respirator manufacturer's directions for respirator use. Close container after each use. Wash thoroughly after handling.



WARNING Cancer and Reproductive Harm—
www.P65warnings.ca.gov

FIRST AID: In case of eye contact, flush immediately with plenty of water for at least 15 minutes; for skin, wash thoroughly with soap and water. If symptoms persist, seek medical attention. If you experience difficulty breathing, leave the area to obtain fresh air. If continued difficulty is experienced, get medical attention immediately.

IN CASE OF SPILL – Absorb with inert material and dispose of as specified under "Clean Up".

**KEEP OUT OF REACH OF CHILDREN
PROTECT FROM FREEZING
For Wood Substrates Only**

**Refer to Safety Data Sheet for additional
health and safety information.**