

## Features

- Exceptional film durability
- Exceptional hiding power
- Long lasting gloss
- Resistant to color fading, blistering, and alkali
- May be applied at temperatures down to 40 °F (4.4 °C)

# **Recommended For**

Recommended for wood, hardboard, vinyl, aluminum and fiber cement sidings; unglazed brick, concrete, stucco, cinder block, and primed metal.

- Easy to apply
- Rapid dry for quick recoating
- Provides mildew resistant coating
- Low VOC in any color.

# ULTRA SPEC<sup>®</sup> EXT GLOSS FINISH N449

## **General Description**

A professional quality 100% acrylic exterior gloss finish which features excellent hiding, film durability and color retention. Fast-dry formula allows for quick re-coating as well as low temperature application.

## Limitations

- Do not apply when air and surface temperatures are below 40 °F (4.4 °C).
- Do not paint vinyl siding or trim darker than the original color
- Not for interior use

Product Information				
Colors — Standard:	Technical Data◊		Pastel Base	
White (01)	Vehicle Type		100% Acrylic	
(May be tinted with up to 2.0 fl. oz. of Benjamin Moore $^{\otimes}$ Gennex $^{\otimes}$ colorants per gallon.)	Pigment Type	Titanium Dioxide		
	Volume Solids	37.8 ± 2%		
Tint Bases: Benjamin Moore <sup>®</sup> Gennex <sup>®</sup> bases 1X, 2X, 3X & 4X	Coverage per Gallon at Recommended Film Thickness 350 – 450 Sq. Ft.			
Benjamin Moore* Gennex* bases 1X, 2X, 3X & 4X	Recommended Film Thickness	– Wet – Dry	4.0 mils 1.5 mils	
— Special Colors: Contact your Benjamin Moore representative	Depending on surface texture and porosity. Be sure to estimate the right amount of paint for the job. This will ensure color uniformity and minimize the disposal of excess paint.			
Certifications & Qualifications: VOC compliant in all regulated areas Water vapor permeance (breathability) ASTM D1693: 48.98 perms Master Painters Institute MPI # 11	Dry Time @ 77 °F (25 °C) @ 50% RH	<ul> <li>– To Touch</li> <li>– To Recoat</li> </ul>	1 Hour 4 Hours	
	Painted surfaces can be washed after two weeks. High humidity and cool temperatures will result in longer dry, recoat and service times.			
	Dries By	Evaporation, Coalescence		
	Viscosity	96 ± 2 KU		
	Flash Point	None		
	Gloss / Sheen	Gloss (35-45 @ 60°)		
	Surface Temperature at Application	– Min.	40 °F	
		– Max.	100 °F	
	Thin With		See Chart	
<b>Technical Assistance</b> Available through your local authorized independent Benjamin Moore retailer.	Clean Up Thinner		Clean Water	
For the location of the retailer nearest you, call 1-866-708-9180 or visit www.benjaminmoore.com	Weight Per Gallon		10.3 lbs	
	Storage Temperature	– Min.	40 °F	
		– Max.	90 °F	
	Volatile Organic Compounds (VOC)			
	46 Grams/Liter .38 Lbs./Gallon			

◊ Reported values are for Pastel Base. Contact Benjamin Moore for values of other bases or colors.

## **Surface Preparation**

Surfaces must be clean, dry and free of oil, grease, wax, rust, mildew, chalk and loose or scaling paint. Cement based water proofing paints should be removed. Glossy surfaces must be dulled. Un-weathered areas such as eaves, porch ceilings, overhangs and protected wall areas should be washed with a Benjamin Moore® Clean (N318) and rinsed with a strong stream of water from a garden hose or power washer to remove contaminants that can interfere with proper adhesion. Stains from mildew must be removed by cleaning with Benjamin Moore® Clean (N318) prior to coating the surface. Caution: Refer to the (N318) Clean technical data and material safety data sheets for instructions on its proper use and handling.

All new masonry surfaces must be power washed or brushed thoroughly with stiff fiber bristles to remove loose particles. New masonry substrates must be allowed to cure for 30 days before priming or painting. Poured or pre-cast concrete with a very smooth surface should be etched or abraded to promote adhesion, after removing all form release agents and curing compounds.

Difficult Substrates: Benjamin Moore offers a number of specialty primers for use over difficult substrates such as bleeding woods, grease stains, crayon markings, hard glossy surfaces, or other substrates where paint adhesion or stain suppression is a particular problem. Your Benjamin Moore® retailer or Architectural Representative can recommend the right problem-solving primer for your special needs.

WARNING! If you scrape sand or remove old paint, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH-approved respirator to control lead exposure. Carefully clean up with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead.

## **Primer/ Finish Systems**

New surfaces should be fully primed, and previously painted surfaces may be primed or spot primed as necessary. For best hiding results, tint the primer to the approximate shade of the finish coat, especially when a significant color change is desired. Special Note: Certain custom colors require a Deep Color Base Primer tinted to a special prescription formula to achieve the desired color. Consult your retailer.

#### Wood and engineered wood products:

Primer: Ultra Spec® EXT latex Primer (N558), Fresh Start® Multi-Purpose Latex Primer (N023) or Fresh Start<sup>®</sup> Exterior Wood Primer (094) Finish: 1 or 2 coats Ultra Spec® EXT Gloss Finish (N449)

#### Bleeding Type Woods, (Redwood and Cedar):

Primer: Fresh Start® Exterior Wood Primer (094) or 1-2 coats of Fresh Start® High-Hiding All Purpose Primer (046) may be used Finish: 1 or 2 coats Ultra Spec® EXT Gloss Finish (N449)

### Hardboard Siding, Bare or Factory Primed:

Primer: Ultra Spec® EXT latex Primer (N558) Finish: 1 or 2 coats Ultra Spec® EXT Gloss Finish (N449)

## Vinyl Siding & Vinyl Composite

Note: Do not paint vinyl siding or trim darker than the original color. Primer: Fresh Start® Multi-Purpose Latex Primer (N023) Finish: 1 or 2 coats Ultra Spec<sup>®</sup> EXT Gloss Finish (N449)

#### **Rough or Pitted Masonry:**

Primer: Ultra Spec® Masonry Interior/Exterior Hi-Build Block Filler (571) Finish: 1 or 2 coats Ultra Spec® EXT Gloss Finish (N449)

#### Poured or Pre-cast Concrete and Fiber Cement Siding:

Primer: Ultra Spec® Masonry Interior / Exterior 100% Acrylic Masonry Sealer (608) or Fresh Start® Multi-Purpose Latex Primer (N023) Finish: 1 or 2 coats Ultra Spec® EXT Gloss Finish (N449)

## Ferrous Metal (Steel and Iron):

Primer: Ultra Spec® HP Acrylic Metal Primer (HP04) or Super Spec HP® Alkyl Metal Primer (P06)

Finish: 1 or 2 coats Ultra Spec® EXT Gloss Finish (N449)

Non-Ferrous Metal (Galvanized & Aluminum): All new metal surfaces must be thoroughly cleaned with Corotech® Oil & Grease Emulsifier (V600) to remove contaminants. New shiny non-ferrous metal surfaces that will be subject to abrasion should be dulled with very fine sandpaper or a synthetic steel wool pad to promote adhesion Primer: Ultra Spec® HP Acrylic Metal Primer (HP04) Finish: 1 or 2 coats Ultra Spec® EXT Gloss Finish (N449)

Repaint, All Substrates: Prime bare areas with the primer recommended for the substrate above.

## Application

Stir thoroughly before and during use. Apply one or two coats. Paint Application: For best results, use a premium Benjamin Moore® customblended nylon/polyester brush, premium Benjamin Moore® roller, or a similar product. Apply paint generously from unpainted area into wet area. This product can also be sprayed.

Conditioning with Benjamin Moore <sup>®</sup> 518 Extender may be necessary under certain conditions to adjust open time or spray characteristics. The chart below is for general guidance			
	Mild conditions	Severe Conditions	
	Humid (RH> 50%)	Dry (RH<50%), in direct	
	with no direct sunlight	sunlight, or windy	
	& with little to no wind	conditions	
Brush: Nylon / Polyester		Add 518 Extender or	
Roller: Premium		water:	
Quality	No thinning	Max of 8 fl. oz. to a gallon	
<b>Spray</b> : Airless Pressure: 1500 -2500 psi Tip: .011-0.015	necessary	of paint Never add other paints or solvents.	

# Thinning/Clean up

Clean Up: Clean up with warm soapy water. Spray equipment should be given a final rinse with mineral spirits to prevent rusting.

USE COMPLETELY OR DISPOSE OF PROPERLY. Dry empty containers may be recycled in a can recycling program. Local disposal requirements vary; consult your sanitation department or statedesignated environmental agency on disposal options.

## Environmental, Health & Safety Information

Use only with adequate ventilation. Do not breathe spray mist or sanding dust. Ensure fresh air entry during application and drying. Avoid contact with eyes and prolonged or repeated contact with skin. Wear an appropriate, properly fitted respirator (NIOSH approved) during application, sanding, and clean-up. Follow respirator manufacturer's directions for respirator use. Close container after each use. Wash thoroughly after handling.



FIRST AID: In case of eye contact, flush immediately with plenty of water for at least 15 minutes; for skin, wash thoroughly with soap and water. If symptoms persist, seek medical attention. If you experience difficulty breathing, leave the area to obtain fresh air. If continued difficulty is experienced, get medical attention immediately.

IN CASE OF SPILL - Absorb with inert material and dispose of as specified under "Clean up".

# **KEEP OUT OF REACH OF CHILDREN** PROTECT FROM FREEZING

# **Refer to Safety Data Sheet for additional** health and safety information

Benjamin Moore & Co., 101 Paragon Drive, Montvale, NJ 07645 Tel: (201) 573-9600 Fax: (201) 573-9046 www.benjaminmoore.com M72 N449 US 080718 Benjamin Moore, Fresh Start, Gennex, Regal, Revive, Super Spec HP, Ultra Spec and the triangle "M" symbol are registered trademarks, licensed to Benjamin Moore & Co. © 2011, 2018 Benjamin Moore & Co All rights reserved