



ULTRA SPEC[®] SCUFF-X[®] INTERIOR MATTE FINISH K484

Features

- Innovative and proprietary scuff-resistance formula
- Superior durability
- Washable
- Quick dry
- Great touch-up
- Easy application
- Spatter resistant
- Eligible for LEED[®] v4 credit

Recommended For

Ideal for high-traffic areas in commercial and institutional spaces such as school hallways, hospital waiting areas, hotels lobbies, gym locker rooms and bathrooms, retail fitting rooms, cafeterias, bathrooms and stairwells. For use on primed or previously painted drywall, plaster, wood, metal and wallpapered surfaces.

General Description

A high-performance, one-component latex paint specifically engineered to deliver outstanding performance and protection for the toughest high-traffic areas in busy commercial spaces. This breakthrough product offers superior durability and scuff-resistance than traditional high-performance two-component coatings, without the pre-mixing, short pot-life and application difficulties related to similar products. It will retain its high-quality appearance longer with minimal maintenance and re-painting required. The matte finish is great for hiding surface imperfections, while providing walls a beautiful and sophisticated look.

Limitations

- Do not apply when air and surface temperatures are below 10 °C (50 °F)
- Not recommended for floors
- Interior use only

Product Information

<p>Colours — Standard: White (01)</p> <p>— Tint Bases: Benjamin Moore[®] Gennex[®] bases 1X, 2X, 3X & 4X</p> <p>— Special Colours: Contact your Benjamin Moore representative</p> <p>Certifications & Qualifications: VOC compliant in all regulated areas</p> <p>Eligible for LEED[®] v4 Credit Qualifies for CHPS low emitting credit (Collaborative for High Performance Schools) CDPH v1 Emission Certified Class A (0-25) over non-combustible surfaces when tested in accordance with ASTM E-84</p> <p>Customer Information Centre: 1-800-361-5898, info@benjaminmoore.ca, www.benjaminmoore.ca</p>	<table border="1"> <thead> <tr> <th>Technical Data[◇]</th> <th>Pastel Base</th> </tr> </thead> <tbody> <tr> <td>Vehicle Type</td> <td>Proprietary Acrylic Copolymer</td> </tr> <tr> <td>Pigment Type</td> <td>Titanium Dioxide</td> </tr> <tr> <td>Volume Solids</td> <td>39 ± 2%</td> </tr> <tr> <td>Coverage per 3.79 L at</td> <td>32.5 – 37.2 sq. metres</td> </tr> <tr> <td>Recommended Film Thickness</td> <td>(350 – 400 sq. ft.)</td> </tr> <tr> <td>Recommended Film Thickness</td> <td>– Wet 4.0 – 4.5 mils – Dry 1.6 – 1.8 mils</td> </tr> <tr> <td colspan="2">Depending on surface texture and porosity. Be sure to estimate the right amount of paint for the job. This will ensure colour uniformity and minimize the disposal of excess paint</td> </tr> <tr> <td>Dry Time @ 25 °C (77 °F) @ 50% RH</td> <td>– To Touch 1 Hour – To Recoat 2 – 3 Hours</td> </tr> <tr> <td colspan="2">Painted surfaces can be washed after two weeks. High humidity and cool temperatures will result in longer dry, recoat and service times</td> </tr> <tr> <td>Dries By</td> <td>Coalescence</td> </tr> <tr> <td>Viscosity</td> <td>97 ± 3 KU</td> </tr> <tr> <td>Flash Point</td> <td>N/A</td> </tr> <tr> <td>Gloss / Sheen</td> <td>Matte (8 – 13 @ 85°) (9.5 @ 60°)</td> </tr> <tr> <td>Surface Temperature at Application</td> <td>– Min. 10 °C (50 °F) – Max. 32.2 °C (90 °F)</td> </tr> <tr> <td>Thin With</td> <td>See Chart</td> </tr> <tr> <td>Clean Up Thinner</td> <td>Clean Water</td> </tr> <tr> <td>Weight Per 3.79 L</td> <td>4.9 kg (10.7 lbs)</td> </tr> <tr> <td>Storage Temperature</td> <td>– Min. 4.4 °C (40 °F) – Max. 32.2 °C (90 °F)</td> </tr> <tr> <td colspan="2" style="text-align: center;">Volatile Organic Compounds (VOC)</td> </tr> <tr> <td colspan="2" style="text-align: center;">90 Grams/Litre</td> </tr> </tbody> </table>	Technical Data [◇]	Pastel Base	Vehicle Type	Proprietary Acrylic Copolymer	Pigment Type	Titanium Dioxide	Volume Solids	39 ± 2%	Coverage per 3.79 L at	32.5 – 37.2 sq. metres	Recommended Film Thickness	(350 – 400 sq. ft.)	Recommended Film Thickness	– Wet 4.0 – 4.5 mils – Dry 1.6 – 1.8 mils	Depending on surface texture and porosity. Be sure to estimate the right amount of paint for the job. This will ensure colour uniformity and minimize the disposal of excess paint		Dry Time @ 25 °C (77 °F) @ 50% RH	– To Touch 1 Hour – To Recoat 2 – 3 Hours	Painted surfaces can be washed after two weeks. High humidity and cool temperatures will result in longer dry, recoat and service times		Dries By	Coalescence	Viscosity	97 ± 3 KU	Flash Point	N/A	Gloss / Sheen	Matte (8 – 13 @ 85°) (9.5 @ 60°)	Surface Temperature at Application	– Min. 10 °C (50 °F) – Max. 32.2 °C (90 °F)	Thin With	See Chart	Clean Up Thinner	Clean Water	Weight Per 3.79 L	4.9 kg (10.7 lbs)	Storage Temperature	– Min. 4.4 °C (40 °F) – Max. 32.2 °C (90 °F)	Volatile Organic Compounds (VOC)		90 Grams/Litre	
Technical Data [◇]	Pastel Base																																										
Vehicle Type	Proprietary Acrylic Copolymer																																										
Pigment Type	Titanium Dioxide																																										
Volume Solids	39 ± 2%																																										
Coverage per 3.79 L at	32.5 – 37.2 sq. metres																																										
Recommended Film Thickness	(350 – 400 sq. ft.)																																										
Recommended Film Thickness	– Wet 4.0 – 4.5 mils – Dry 1.6 – 1.8 mils																																										
Depending on surface texture and porosity. Be sure to estimate the right amount of paint for the job. This will ensure colour uniformity and minimize the disposal of excess paint																																											
Dry Time @ 25 °C (77 °F) @ 50% RH	– To Touch 1 Hour – To Recoat 2 – 3 Hours																																										
Painted surfaces can be washed after two weeks. High humidity and cool temperatures will result in longer dry, recoat and service times																																											
Dries By	Coalescence																																										
Viscosity	97 ± 3 KU																																										
Flash Point	N/A																																										
Gloss / Sheen	Matte (8 – 13 @ 85°) (9.5 @ 60°)																																										
Surface Temperature at Application	– Min. 10 °C (50 °F) – Max. 32.2 °C (90 °F)																																										
Thin With	See Chart																																										
Clean Up Thinner	Clean Water																																										
Weight Per 3.79 L	4.9 kg (10.7 lbs)																																										
Storage Temperature	– Min. 4.4 °C (40 °F) – Max. 32.2 °C (90 °F)																																										
Volatile Organic Compounds (VOC)																																											
90 Grams/Litre																																											

[◇]Reported values are for Pastel Base. Contact Benjamin Moore for values of other bases or colour.

Surface Preparation

Surfaces to be painted must be clean, dry, and free of dirt, dust, grease, oil, soap, wax, scaling paint, water soluble materials, and mildew. Remove any peeling or scaling paint and sand these areas to feather edges smooth with adjacent surfaces. Glossy areas should be dulled. Drywall surfaces must be free of sanding dust.

New plaster or masonry surfaces must be allowed to cure 30 days before applying base coat. Cured plaster should be hard, have a slight sheen and maximum PH of 10; soft, porous or powdery plaster indicates improper cure. Never sand a plaster surface; knife off any protrusions and prime plaster before and after applying patching compound. Poured or pre-cast concrete with a very smooth surface should be etched or abraded to promote adhesion, after removing all form release agents and curing compounds. Remove any powder or loose particles before priming. Wood substrates must be thoroughly dry.

Difficult Substrates: Benjamin Moore® offers a variety of specialty primers for use over difficult substrates such as bleeding woods, grease stains, crayon markings, hard glossy surfaces, galvanized metal or other substrates where paint adhesion or stain suppression is a particular problem. Your Benjamin Moore® retailer can recommend the right problem-solving primer for your special needs.

WARNING! If you scrape, sand, or remove old paint, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by logging onto Health Canada @ <https://www.canada.ca/en/health-canada/services/environmental-workplace-health/environmental-contaminants/lead/lead-information-package-some-commonly-asked-questions-about-lead-human-health.html>

Primer/Finish Systems

New surfaces should be fully primed, and previously painted surfaces may be primed or spot primed as necessary. For best hiding results, tint the primer to the approximate shade of the finish coat, especially when a significant colour change is desired. **Special Note:** Certain custom colours require a Deep Colour Base Primer tinted to a special prescription formula to achieve the desired colour. Consult your retailer.

Wood, and engineered wood products:

Primer: Ultra Spec® 500 Interior Latex Primer (K534) or Fresh Start® Multi-Purpose Latex Primer (F023)
Finish: 1 or 2 coats Ultra Spec® SCUFF-X® Interior Matte Finish (K484)

Bleeding Type Woods, (Redwood and Cedar):

Primer: Fresh Start® Multi-Purpose Oil Based Primer (F024) or 1-2 coats of Fresh Start® High-Hiding All Purpose Primer (K046) may be used
Finish: 1 or 2 coats Ultra Spec® SCUFF-X® Interior Matte Finish (K484)

Drywall:

Primer: Ultra Spec® 500 Interior Latex Primer (K534)
Finish: 1 or 2 coats Ultra Spec® SCUFF-X® Interior Matte Finish (K484)

Plaster:

Primer: Fresh Start® High-Hiding All Purpose Primer (K046) or Fresh Start® Multi-Purpose Latex Primer (F023)
Finish: 1 or 2 coats Ultra Spec® SCUFF-X® Interior Matte Finish (K484)

Rough or Pitted Masonry:

Primer: Ultra Spec® Masonry Interior/Exterior Hi-Build Block Filler (K571)
Finish: 1 or 2 coats Ultra Spec® SCUFF-X® Interior Matte Finish (K484)

Smooth Poured or Precast Concrete:

Primer: Fresh Start® Multi-Purpose Latex Primer (F023)
Finish: 1 or 2 coats Ultra Spec® SCUFF-X® Interior Matte Finish (K484)

Ferrous Metal (Steel and Iron):

Primer: Ultra Spec® HP Acrylic Metal Primer (FP04) or Super Spec HP® Alkyd Metal Primer (KP06)
Finish: 1 or 2 coats Ultra Spec® SCUFF-X® Interior Matte Finish (K484)

Non-Ferrous Metal (Galvanized & Aluminum): All new metal surfaces must be thoroughly cleaned with Corotech® Oil & Grease Emulsifier (V600) to remove contaminants. New shiny non-ferrous metal surfaces that will be subject to abrasion should be dulled with very fine sandpaper or a synthetic steel wool pad to promote adhesion

Primer: Ultra Spec® HP Acrylic Metal Primer (FP04)
Finish: 1 or 2 coats Ultra Spec® SCUFF-X® Interior Matte Finish (K484)

Wallpapered Surfaces: Remove wallpaper when possible, followed by thoroughly cleaning the surfaces removing all glue residue. Once the surface has fully dried, sand the surfaces to be painted with 150-180 grit paper. Vinyl wallpapered surfaces tightly adhered may be primed with Fresh Start® High-Hiding All Purpose Primer (K046) prior to filling the seams and top coating with Ultra Spec® SCUFF-X®

Repaint, All Substrates: Prime bare areas with the primer recommended for the substrate above.

Application

Stir thoroughly before use. Apply one or two coats. For best results, use a Benjamin Moore® Professional custom-blended nylon/polyester brush, Benjamin Moore® Professional roller, or a similar product. This product can also be sprayed.

Conditioning with Benjamin Moore® K518 Extender may be necessary under certain conditions to adjust open time or spray characteristics. The chart below is for general guidance

	Mild conditions	Severe conditions
	Humid (RH> 50%) with no direct sunlight & with little to no wind	Dry (RH<50%), in direct sunlight, or windy conditions
Brush: Nylon / Polyester	No thinning necessary	Add K518 Extender or water: Max of 236 ml to 3.79 L of paint Never add other paints or solvents.
Roller: Premium Quality 10 mm (3/8") roller cover		
Spray: Airless Pressure: 1,800-3,000 psi Tip: 0.015-0.017		

Thinning/Clean Up

Thinning is unnecessary, but if required to obtain desired application properties, a small amount of clean water may be added. Never add other paints or solvents.

Clean Up: Use soap and water. Spray equipment should be given a final rinse with mineral spirits to prevent corrosion.

Maintenance: SCUFF-X® needs to fully cure for 2 weeks following application, before applying any cleaning chemicals and liquids. Minimal scuffing and stains can be easily removed by using soap and water. For tougher stains, stronger cleaners may be used with a sponge or rag. Before using a new cleaner for the first time, test its effect on the finish by applying in an inconspicuous area to make sure there's no damage to the paint film.

Environmental Health & Safety Information

Not a hazardous substance or mixture according to the Globally Harmonized System (GHS)

WARNING: This product contains isothiazolinone compounds at levels of <0.1%. These substances are biocides commonly found in most paints and a variety of personal care products as a preservative. Certain individuals may be sensitive or allergic to these substances, even at low levels.

Keep container closed when not in use. In case of spillage, absorb with inert material and dispose of in accordance with local regulations. Wash thoroughly after handling. Refer to Safety Data Sheet for additional health and safety information.

This document represents hazards of the product referenced above. Refer to the individual Safety Data Sheet for hazards of the specific product you will be using

**KEEP OUT OF REACH OF CHILDREN
 PROTECT FROM FREEZING**

Refer to Safety Data Sheet for additional health and safety information.