



SUPER KOTE 5000[®] HIGH BUILD PRO FLAT 762

Features

- Commercial vinyl acrylic designed for the professional painter
- Excellent touch-up
- Low spatter and fast-dry formula provide fast production
- Soap and water cleanup

General Description

Super Kote 5000[®] High Build Pro Flat is a high build interior flat with excellent touch up properties. For use on all new construction and touch up work. The flat sheen hides surface imperfections.

Recommended For

Interior drywall, plaster, properly primed wood, metal, masonry and stucco in commercial, institutional and residential applications. An ideal flat coating to be used for rental property, general maintenance and apartment buildings.

Limitations

- Apply only when surface and air temperatures are above 50°F (10°C).

Product Information

<p>Colors — Standard: White (762-1)</p> <hr/> <p>— Tint Bases: N/A</p> <hr/> <p>— Special Colors: Contact your dealer.</p> <hr/> <p>Certifications & Qualifications: The products supported by this data sheet contain a maximum of 100 grams per liter VOC/VOS (0.83 lbs. /gal.) excluding water & exempt solvents. This product is compliant under the Ozone Transport Commission regulations as a Flat Coating.</p> <hr/> <p>Technical Assistance: Available through your local authorized independent dealer. For the location of the dealer nearest you, call 1-866-708-9180 or visit www.coronadopaint.com</p>	<table border="1"> <thead> <tr> <th colspan="2">Technical Data[◇]</th> <th>White</th> </tr> </thead> <tbody> <tr> <td>Vehicle Type</td> <td></td> <td>Vinyl Acrylic</td> </tr> <tr> <td>Pigment Type</td> <td></td> <td>Titanium Dioxide</td> </tr> <tr> <td>Volume Solids</td> <td></td> <td>33.5 ± 1.0%</td> </tr> <tr> <td>Coverage per Gallon at Recommended Film Thickness</td> <td></td> <td>350 - 400 Sq. Ft.</td> </tr> <tr> <td>Recommended Film Thickness</td> <td>– Wet</td> <td>4.0 mils</td> </tr> <tr> <td></td> <td>– Dry</td> <td>1.3 mils</td> </tr> <tr> <td colspan="3">Depending on surface texture and porosity. Be sure to estimate the right amount of paint for the job. This will ensure color uniformity and minimize the disposal of excess paint.</td> </tr> <tr> <td>Dry Time @ 77°F (25°C) @ 50% RH</td> <td>– Tack Free</td> <td>30 Minutes</td> </tr> <tr> <td></td> <td>– To Recoat</td> <td>4 Hours</td> </tr> <tr> <td colspan="3">High humidity and cool temperatures will result in longer dry, recoat and service times.</td> </tr> <tr> <td>Dries By</td> <td></td> <td>Coalescence</td> </tr> <tr> <td>Viscosity</td> <td></td> <td>110 – 115 KU</td> </tr> <tr> <td>Flash Point</td> <td></td> <td>200°F or greater (TT-P-141, Method 4293)</td> </tr> <tr> <td>Gloss / Sheen</td> <td></td> <td>Flat 1 - 5 Units @85°</td> </tr> <tr> <td>Surface Temperature at Application</td> <td>– Min.</td> <td>50° F (10° C)</td> </tr> <tr> <td></td> <td>– Max.</td> <td>90° F (32° C)</td> </tr> <tr> <td>Thin With</td> <td></td> <td>Clean Water</td> </tr> <tr> <td>Clean Up Thinner</td> <td></td> <td>Warm, Soapy Water</td> </tr> <tr> <td>Weight Per Gallon</td> <td></td> <td>11.5 lbs.</td> </tr> <tr> <td>Storage Temperature</td> <td>– Min.</td> <td>40° F</td> </tr> <tr> <td></td> <td>– Max.</td> <td>95° F</td> </tr> <tr> <td colspan="3">Volatile Organic Compounds (VOC)</td> </tr> <tr> <td colspan="3">< 100 Grams/Liter < 0.83 Lbs./Gallon</td> </tr> </tbody> </table>	Technical Data [◇]		White	Vehicle Type		Vinyl Acrylic	Pigment Type		Titanium Dioxide	Volume Solids		33.5 ± 1.0%	Coverage per Gallon at Recommended Film Thickness		350 - 400 Sq. Ft.	Recommended Film Thickness	– Wet	4.0 mils		– Dry	1.3 mils	Depending on surface texture and porosity. Be sure to estimate the right amount of paint for the job. This will ensure color uniformity and minimize the disposal of excess paint.			Dry Time @ 77°F (25°C) @ 50% RH	– Tack Free	30 Minutes		– To Recoat	4 Hours	High humidity and cool temperatures will result in longer dry, recoat and service times.			Dries By		Coalescence	Viscosity		110 – 115 KU	Flash Point		200°F or greater (TT-P-141, Method 4293)	Gloss / Sheen		Flat 1 - 5 Units @85°	Surface Temperature at Application	– Min.	50° F (10° C)		– Max.	90° F (32° C)	Thin With		Clean Water	Clean Up Thinner		Warm, Soapy Water	Weight Per Gallon		11.5 lbs.	Storage Temperature	– Min.	40° F		– Max.	95° F	Volatile Organic Compounds (VOC)			< 100 Grams/Liter < 0.83 Lbs./Gallon		
Technical Data [◇]		White																																																																							
Vehicle Type		Vinyl Acrylic																																																																							
Pigment Type		Titanium Dioxide																																																																							
Volume Solids		33.5 ± 1.0%																																																																							
Coverage per Gallon at Recommended Film Thickness		350 - 400 Sq. Ft.																																																																							
Recommended Film Thickness	– Wet	4.0 mils																																																																							
	– Dry	1.3 mils																																																																							
Depending on surface texture and porosity. Be sure to estimate the right amount of paint for the job. This will ensure color uniformity and minimize the disposal of excess paint.																																																																									
Dry Time @ 77°F (25°C) @ 50% RH	– Tack Free	30 Minutes																																																																							
	– To Recoat	4 Hours																																																																							
High humidity and cool temperatures will result in longer dry, recoat and service times.																																																																									
Dries By		Coalescence																																																																							
Viscosity		110 – 115 KU																																																																							
Flash Point		200°F or greater (TT-P-141, Method 4293)																																																																							
Gloss / Sheen		Flat 1 - 5 Units @85°																																																																							
Surface Temperature at Application	– Min.	50° F (10° C)																																																																							
	– Max.	90° F (32° C)																																																																							
Thin With		Clean Water																																																																							
Clean Up Thinner		Warm, Soapy Water																																																																							
Weight Per Gallon		11.5 lbs.																																																																							
Storage Temperature	– Min.	40° F																																																																							
	– Max.	95° F																																																																							
Volatile Organic Compounds (VOC)																																																																									
< 100 Grams/Liter < 0.83 Lbs./Gallon																																																																									

◇ Reported values are for White.

Super Kote 5000® High Build Pro Flat 762

Surface Preparation

Surfaces to be painted must be clean, dry, and free of dirt, dust, grease, oil, soap, wax, scaling paint, water soluble materials and mildew. Remove any peeling or scaling paint, and sand these areas to feather edges smooth with adjacent surfaces. Glossy areas should be dulled. Drywall surfaces must be free of sanding dust. Spot prime before and after filling nail holes, cracks, and other surface imperfections.

New plaster or masonry surfaces must be allowed to cure (30 days) before applying base coat. Cured plaster should be hard, have a slight sheen and maximum pH of 10; soft, porous or powdery plaster indicates improper cure.

Primers: New surfaces should be fully primed. Previously painted surfaces should be primed or spot primed as necessary. There are a number of specialty primers available in our family of brands that can be used on difficult substrates such as bleeding woods, hard glossy surfaces, or other substrates where paint adhesion or stain blocking is a problem. Your dealer can recommend the right problem solving primer necessary to meet your needs.

WARNING! If you scrape, sand, or remove old paint, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Informational Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead.

Application

Stir thoroughly. Apply by brush (synthetic filament), roller or spray. Length of roller nap depends upon the texture of the surface. Thinning is not usually required for brush or roller application. Apply a full, even coat. Do not apply directly over chalky surfaces or bleeding stains. Apply only when surface and air temperatures are above 50° F (10° C).

Spray, Airless: Fluid Pressure—1,500 to 2,000 PSI;
Tip—.017 - .021 Orifice

Clean Up

Clean up with warm, soapy water.

USE COMPLETELY OR DISPOSE OF PROPERLY. Dry empty containers may be recycled in a can recycling program. **Local disposal requirements vary; consult your sanitation department or state-designated environmental agency on disposal options.**

Environmental Health & Safety Information

Cancer Hazard. Contains Crystalline Silica which can cause cancer when in respirable form (spray mist or sanding dust).

Use only with adequate ventilation. Do not breathe spray mist or sanding dust. Ensure fresh air entry during application and drying. Avoid contact with eyes and prolonged or repeated contact with skin. Avoid exposure to dust and spray mist by wearing a NIOSH approved respirator during application, sanding and clean up. Follow respirator manufacturer's directions for respirator use. Close container after each use. Wash thoroughly after handling.



WARNING: Cancer and Reproductive Harm—
www.P65warnings.ca.gov

FIRST AID: In case of eye contact, flush immediately with plenty of water for at least 15 minutes; for skin, wash thoroughly with soap and water. If symptoms persist, seek medical attention. If you experience difficulty breathing, leave the area to obtain fresh air. If continued difficulty is experienced, get medical attention immediately.

IN CASE OF SPILL – Absorb with inert material and dispose of as specified under “CleanUp”.

**KEEP OUT OF REACH OF CHILDREN
PROTECT FROM FREEZING**

**Refer to Safety Data Sheet for
additional health and safety information.**