

PVA

PRIMER / FINISH 100-11

Features

- Uniform Flat Finish
- Good Touch Up
- Good Dry Hide
- Resists Spattering

Recommended For

New interior drywall for walls and ceilings, and thoroughly cured plaster. It is ideal for new residential and commercial construction, as well as rental properties.

General Description

An easy to apply fast-drying vinyl acrylic primer/finish for use on properly prepared interior drywall and thoroughly cured plaster.

Limitations

- Apply when surface temperature is above 50 °F (10 °C).
- Not for use in high-abuse areas that are frequently washed or scrubbed.

Product Information

<p>Colors — Standard: White (11)</p> <p>Up to 2 fl. oz. of Benjamin Moore Gennex[®], Color Preview[®] or Universal colorant may be added per gallon.</p> <hr/> <p style="text-align: center;">— Tint Bases:</p> <p>N/A</p> <hr/> <p style="text-align: center;">— Special Colors:</p> <p>Contact your dealer.</p> <hr/> <p>Certifications & Qualifications: VOC compliant in all regulated areas</p> <p>Qualifies for LEED[®] v4 Credit Qualifies for CHPS low emitting credit (Collaborative for High Performance Schools) CDPH v1 Emission Certified</p> <hr/> <p>Technical Assistance: Available through your local authorized independent dealer. For the location of the dealer nearest you, call 1-866-708-9180, or visit www.coronadopaint.com</p>	<table style="width: 100%; border-collapse: collapse;"> <thead> <tr> <th style="text-align: left; border-bottom: 1px solid black;">Technical Data[◇]</th> <th style="text-align: right; border-bottom: 1px solid black;">White</th> </tr> </thead> <tbody> <tr> <td>Vehicle Type</td> <td style="text-align: right;">Vinyl Acrylic</td> </tr> <tr> <td>Pigment Type</td> <td style="text-align: right;">Titanium Dioxide</td> </tr> <tr> <td>Volume Solids</td> <td style="text-align: right;">30 ± 1.0%</td> </tr> <tr> <td>Coverage per Gallon at Recommended Film Thickness</td> <td style="text-align: right;">300 – 400 Sq. Ft.</td> </tr> <tr> <td>Recommended Film Thickness</td> <td style="text-align: right;"> <table style="width: 100%; border-collapse: collapse;"> <tr> <td style="border-bottom: 1px solid black;">– Wet</td> <td style="text-align: right; border-bottom: 1px solid black;">4.0 – 5.3 mils</td> </tr> <tr> <td>– Dry</td> <td style="text-align: right;">1.2 – 1.6 mils</td> </tr> </table> </td> </tr> <tr> <td colspan="2">Depending on surface texture and porosity. Be sure to estimate the right amount of paint for the job. This will ensure color uniformity and minimize the disposal of excess paint.</td> </tr> <tr> <td>Dry Time @ 77 °F (25 °C) @ 50% RH</td> <td style="text-align: right;"> <table style="width: 100%; border-collapse: collapse;"> <tr> <td style="border-bottom: 1px solid black;">– Tack Free</td> <td style="text-align: right; border-bottom: 1px solid black;">30 Minutes</td> </tr> <tr> <td>– To Recoat</td> <td style="text-align: right;">4 Hours</td> </tr> </table> </td> </tr> <tr> <td colspan="2">High humidity and cool temperatures will result in longer dry, recoat and service times.</td> </tr> <tr> <td>Dries By</td> <td style="text-align: right;">Evaporation, Coalescence</td> </tr> <tr> <td>Viscosity</td> <td style="text-align: right;">112 ± 3 KU</td> </tr> <tr> <td>Flash Point</td> <td style="text-align: right;">N/A</td> </tr> <tr> <td>Gloss / Sheen</td> <td style="text-align: right;">Flat (1 – 3.0 @ 85°)</td> </tr> <tr> <td>Surface Temperature at Application</td> <td style="text-align: right;"> <table style="width: 100%; border-collapse: collapse;"> <tr> <td style="border-bottom: 1px solid black;">– Min.</td> <td style="text-align: right; border-bottom: 1px solid black;">50 °F</td> </tr> <tr> <td>– Max.</td> <td style="text-align: right;">90 °F</td> </tr> </table> </td> </tr> <tr> <td>Thin With</td> <td style="text-align: right;">Clean Water</td> </tr> <tr> <td>Clean Up Thinner</td> <td style="text-align: right;">Clean Water</td> </tr> <tr> <td>Weight Per Gallon</td> <td style="text-align: right;">10.9 lbs.</td> </tr> <tr> <td>Storage Temperature</td> <td style="text-align: right;"> <table style="width: 100%; border-collapse: collapse;"> <tr> <td style="border-bottom: 1px solid black;">– Min.</td> <td style="text-align: right; border-bottom: 1px solid black;">40 °F</td> </tr> <tr> <td>– Max.</td> <td style="text-align: right;">95 °F</td> </tr> </table> </td> </tr> <tr> <td colspan="2" style="text-align: center; padding: 10px;"> <p>Volatile Organic Compounds (VOC)</p> <p>19.3 g/L / 0.16 lbs./gallon</p> </td> </tr> </tbody> </table>	Technical Data [◇]	White	Vehicle Type	Vinyl Acrylic	Pigment Type	Titanium Dioxide	Volume Solids	30 ± 1.0%	Coverage per Gallon at Recommended Film Thickness	300 – 400 Sq. Ft.	Recommended Film Thickness	<table style="width: 100%; border-collapse: collapse;"> <tr> <td style="border-bottom: 1px solid black;">– Wet</td> <td style="text-align: right; border-bottom: 1px solid black;">4.0 – 5.3 mils</td> </tr> <tr> <td>– Dry</td> <td style="text-align: right;">1.2 – 1.6 mils</td> </tr> </table>	– Wet	4.0 – 5.3 mils	– Dry	1.2 – 1.6 mils	Depending on surface texture and porosity. Be sure to estimate the right amount of paint for the job. This will ensure color uniformity and minimize the disposal of excess paint.		Dry Time @ 77 °F (25 °C) @ 50% RH	<table style="width: 100%; border-collapse: collapse;"> <tr> <td style="border-bottom: 1px solid black;">– Tack Free</td> <td style="text-align: right; border-bottom: 1px solid black;">30 Minutes</td> </tr> <tr> <td>– To Recoat</td> <td style="text-align: right;">4 Hours</td> </tr> </table>	– Tack Free	30 Minutes	– To Recoat	4 Hours	High humidity and cool temperatures will result in longer dry, recoat and service times.		Dries By	Evaporation, Coalescence	Viscosity	112 ± 3 KU	Flash Point	N/A	Gloss / Sheen	Flat (1 – 3.0 @ 85°)	Surface Temperature at Application	<table style="width: 100%; border-collapse: collapse;"> <tr> <td style="border-bottom: 1px solid black;">– Min.</td> <td style="text-align: right; border-bottom: 1px solid black;">50 °F</td> </tr> <tr> <td>– Max.</td> <td style="text-align: right;">90 °F</td> </tr> </table>	– Min.	50 °F	– Max.	90 °F	Thin With	Clean Water	Clean Up Thinner	Clean Water	Weight Per Gallon	10.9 lbs.	Storage Temperature	<table style="width: 100%; border-collapse: collapse;"> <tr> <td style="border-bottom: 1px solid black;">– Min.</td> <td style="text-align: right; border-bottom: 1px solid black;">40 °F</td> </tr> <tr> <td>– Max.</td> <td style="text-align: right;">95 °F</td> </tr> </table>	– Min.	40 °F	– Max.	95 °F	<p>Volatile Organic Compounds (VOC)</p> <p>19.3 g/L / 0.16 lbs./gallon</p>	
Technical Data [◇]	White																																																						
Vehicle Type	Vinyl Acrylic																																																						
Pigment Type	Titanium Dioxide																																																						
Volume Solids	30 ± 1.0%																																																						
Coverage per Gallon at Recommended Film Thickness	300 – 400 Sq. Ft.																																																						
Recommended Film Thickness	<table style="width: 100%; border-collapse: collapse;"> <tr> <td style="border-bottom: 1px solid black;">– Wet</td> <td style="text-align: right; border-bottom: 1px solid black;">4.0 – 5.3 mils</td> </tr> <tr> <td>– Dry</td> <td style="text-align: right;">1.2 – 1.6 mils</td> </tr> </table>	– Wet	4.0 – 5.3 mils	– Dry	1.2 – 1.6 mils																																																		
– Wet	4.0 – 5.3 mils																																																						
– Dry	1.2 – 1.6 mils																																																						
Depending on surface texture and porosity. Be sure to estimate the right amount of paint for the job. This will ensure color uniformity and minimize the disposal of excess paint.																																																							
Dry Time @ 77 °F (25 °C) @ 50% RH	<table style="width: 100%; border-collapse: collapse;"> <tr> <td style="border-bottom: 1px solid black;">– Tack Free</td> <td style="text-align: right; border-bottom: 1px solid black;">30 Minutes</td> </tr> <tr> <td>– To Recoat</td> <td style="text-align: right;">4 Hours</td> </tr> </table>	– Tack Free	30 Minutes	– To Recoat	4 Hours																																																		
– Tack Free	30 Minutes																																																						
– To Recoat	4 Hours																																																						
High humidity and cool temperatures will result in longer dry, recoat and service times.																																																							
Dries By	Evaporation, Coalescence																																																						
Viscosity	112 ± 3 KU																																																						
Flash Point	N/A																																																						
Gloss / Sheen	Flat (1 – 3.0 @ 85°)																																																						
Surface Temperature at Application	<table style="width: 100%; border-collapse: collapse;"> <tr> <td style="border-bottom: 1px solid black;">– Min.</td> <td style="text-align: right; border-bottom: 1px solid black;">50 °F</td> </tr> <tr> <td>– Max.</td> <td style="text-align: right;">90 °F</td> </tr> </table>	– Min.	50 °F	– Max.	90 °F																																																		
– Min.	50 °F																																																						
– Max.	90 °F																																																						
Thin With	Clean Water																																																						
Clean Up Thinner	Clean Water																																																						
Weight Per Gallon	10.9 lbs.																																																						
Storage Temperature	<table style="width: 100%; border-collapse: collapse;"> <tr> <td style="border-bottom: 1px solid black;">– Min.</td> <td style="text-align: right; border-bottom: 1px solid black;">40 °F</td> </tr> <tr> <td>– Max.</td> <td style="text-align: right;">95 °F</td> </tr> </table>	– Min.	40 °F	– Max.	95 °F																																																		
– Min.	40 °F																																																						
– Max.	95 °F																																																						
<p>Volatile Organic Compounds (VOC)</p> <p>19.3 g/L / 0.16 lbs./gallon</p>																																																							

Surface Preparation

Surfaces to be painted must be clean, dry, and free of dirt, dust, grease, oil, soap, wax, peeling or flaking paint, water soluble materials and mildew. Remove any peeling or flaking paint, and sand these areas to feather edges smooth with adjacent surfaces. Spot Prime before and after filling nail holes, cracks, and other surface imperfections. Glossy areas should be dulled. Drywall surfaces must be free of sanding dust.

New plaster or masonry surfaces must be allowed to cure (30 days) before applying base coat. Cured plaster should be hard, have a slight sheen and pH less than 9; soft, porous or powdery plaster indicates improper cure.

Previously painted surfaces should be primed or spot primed as necessary. There are a number of specialty primers available in our family of brands that can be used on difficult substrates such as bleeding woods, hard glossy surfaces, or other substrates where paint adhesion or stain blocking is a problem. Your dealer can recommend the right problem solving primer necessary to meet your needs.

WARNING! If you scrape, sand, or remove old paint, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead.

Application

Stir product with a circular, lifting motion before you begin to paint. Coronado® PVA Primer / Finish may be applied by brush, roller, pad or spray, at a rate of application not to exceed 400 square feet per gallon. Surface texture and porosity will affect actual yield. For best brush application results, use a quality synthetic filament brush. For roller application use a 3/8" nap cover for smooth surfaces, a 1/2" nap cover for semi-rough surfaces, and a 3/4" nap cover for rough surfaces. May be reduced with clean water up to 15% for spray application.

For use as a primer, apply one coat allowing 4 hours to dry before applying 1-2 finish coats. For use as a primer and finish, apply 2 coats allowing 4 hours to dry between each coat.

Airless Spray

Fluid Pressure — 1,500 to 3,000 PSI
Tip — .013-.017 Orifice

Clean Up

Clean up with warm, soapy water.

USE COMPLETELY OR DISPOSE OF PROPERLY. Dry, empty containers may be recycled in a can recycling program. **Local disposal requirements vary; consult your sanitation department or state-designated environmental agency on disposal options.**

Environmental Health & Safety Information

Use only with adequate ventilation. Do not breathe spray mist or sanding dust. Ensure fresh air entry during application and drying. Avoid contact with eyes and prolonged or repeated contact with skin. Avoid exposure to dust and spray mist by wearing a NIOSH approved respirator during application, sanding and clean up. Follow respirator manufacturer's directions for respirator use. Close container after each use. Wash thoroughly after handling



WARNING Cancer and Reproductive Harm—
www.P65warnings.ca.gov

WARNING: This product contains isothiazolinone compounds at levels of <0.1%. These substances are biocides commonly found in most paints and a variety of personal care products as a preservative. Certain individuals may be sensitive or allergic to these substances, even at low levels.

FIRST AID: In case of eye contact, flush immediately with plenty of water for at least 15 minutes; for skin, wash thoroughly with soap and water. If symptoms persist, seek medical attention. If you experience difficulty breathing, leave the area to obtain fresh air. If continued difficulty is experienced, get medical attention immediately.

IN CASE OF SPILL – Absorb with inert material and dispose of as specified under "Clean Up".

**KEEP OUT OF REACH OF CHILDREN
PROTECT FROM FREEZING**

**Refer to Safety Data Sheet for
additional health and safety information.**