



SUPER KOTE 5000

ACRYLIC LATEX FLAT

28 LINE

Features

- Premium commercial acrylic latex designed for the professional painter
- No spatter and fast-dry formula provide fast production
- Professional finish withstands washing
- Soap and water cleanup

Recommended For

Interior drywall, plaster, wood, metal, masonry and stucco in commercial, institutional and residential applications. It may be washed repeatedly without film damage. Perfect for offices, bedrooms, living rooms or wherever a flat sheen is desirable. Can be used on interior wall and ceiling surfaces in underground parking garages not directly exposed to the elements.

General Description

Super Kote 5000 is designed for commercial projects—when getting the job done quickly is a priority. With low spatter and easy application, this premium-quality, vinyl-acrylic formula delivers dependable quality and productivity.

Limitations

- Apply only when surface and air temperatures are above 10 °C (50 °F).

Product Information

<p>Colours — Standard: White (1), Black (2)</p> <p>— Tint Bases: Pastel Base (32) Tint with Universal colorants only</p> <p>— Special Colours: Contact your dealer.</p> <p>Certifications & Qualifications: VOC compliant in Canada</p> <p>The products supported by this data sheet contain a maximum of 50 grams per litre VOC/VOS (0.42 lbs/gal.) excluding water & exempt solvents.</p> <p>This product has been approved by CFIA (Canadian Food Inspection Agency) for use in Food Processing Facilities.</p> <p>This product meets the qualifications for LEED (Leadership in Energy and Environmental Design) projects as a flat coating.</p> <p>Master Painters Institute MPI # 53</p> <p>Technical Assistance: Available through your local authorized independent dealer. For the location of the retailer nearest you, call 1-877-711-6830 or visit www.benjaminmoore.ca/coronado</p>	<p>Technical Data White</p> <table border="1"> <tr> <td>Vehicle Type</td> <td colspan="2">Vinyl Acrylic</td> </tr> <tr> <td>Pigment Type</td> <td colspan="2">Titanium Dioxide</td> </tr> <tr> <td>Volume Solids</td> <td colspan="2">32.1 ± 1.0%</td> </tr> <tr> <td>Coverage per 3.79 L at Recommended Film Thickness</td> <td colspan="2">27.8 – 37.1 sq. m. (300 – 400 sq. ft.)</td> </tr> <tr> <td rowspan="2">Recommended Film Thickness</td> <td>– Wet</td> <td>4.0 – 5.3 mils</td> </tr> <tr> <td>– Dry</td> <td>1.3 – 1.7 mils</td> </tr> <tr> <td colspan="3">Depending on surface texture and porosity. Be sure to estimate the right amount of paint for the job. This will ensure colours uniformity and minimize the disposal of excess paint.</td> </tr> <tr> <td rowspan="2">Dry Time @ 25 °C (77 °F) @ 50% RH</td> <td>– Tack Free</td> <td>30 Minutes</td> </tr> <tr> <td>– To Recoat</td> <td>4 Hours</td> </tr> <tr> <td colspan="3">High humidity and cool temperatures will result in longer dry, recoat and service times.</td> </tr> <tr> <td>Dries By</td> <td colspan="2">Coalescence</td> </tr> <tr> <td>Viscosity</td> <td colspan="2">105 – 110 KU</td> </tr> <tr> <td>Flash Point</td> <td colspan="2">93.2 °C (200 °F) or greater (TT-P-141, Method 4293)</td> </tr> <tr> <td>Gloss / Sheen</td> <td colspan="2">Flat (1 – 2 @ 85°)</td> </tr> <tr> <td rowspan="2">Surface Temperature at Application</td> <td>– Min.</td> <td>10 °C (50 °F)</td> </tr> <tr> <td>– Max.</td> <td>32.2 °C (90 °F)</td> </tr> <tr> <td>Thin With</td> <td colspan="2">Clean Water</td> </tr> <tr> <td>Clean Up Thinner</td> <td colspan="2">Warm, Soapy Water</td> </tr> <tr> <td>Weight Per 3.79 L</td> <td colspan="2">5.3 kg (11.6 lbs.)</td> </tr> <tr> <td rowspan="2">Storage Temperature</td> <td>– Min.</td> <td>4.4 °C (40 °F)</td> </tr> <tr> <td>– Max.</td> <td>35 °C (95 °F)</td> </tr> <tr> <td colspan="3" style="text-align: center;">Volatile Organic Compounds (VOC)</td> </tr> <tr> <td colspan="3" style="text-align: center;">47.4 Grams/Litre</td> </tr> </table>	Vehicle Type	Vinyl Acrylic		Pigment Type	Titanium Dioxide		Volume Solids	32.1 ± 1.0%		Coverage per 3.79 L at Recommended Film Thickness	27.8 – 37.1 sq. m. (300 – 400 sq. ft.)		Recommended Film Thickness	– Wet	4.0 – 5.3 mils	– Dry	1.3 – 1.7 mils	Depending on surface texture and porosity. Be sure to estimate the right amount of paint for the job. This will ensure colours uniformity and minimize the disposal of excess paint.			Dry Time @ 25 °C (77 °F) @ 50% RH	– Tack Free	30 Minutes	– To Recoat	4 Hours	High humidity and cool temperatures will result in longer dry, recoat and service times.			Dries By	Coalescence		Viscosity	105 – 110 KU		Flash Point	93.2 °C (200 °F) or greater (TT-P-141, Method 4293)		Gloss / Sheen	Flat (1 – 2 @ 85°)		Surface Temperature at Application	– Min.	10 °C (50 °F)	– Max.	32.2 °C (90 °F)	Thin With	Clean Water		Clean Up Thinner	Warm, Soapy Water		Weight Per 3.79 L	5.3 kg (11.6 lbs.)		Storage Temperature	– Min.	4.4 °C (40 °F)	– Max.	35 °C (95 °F)	Volatile Organic Compounds (VOC)			47.4 Grams/Litre		
Vehicle Type	Vinyl Acrylic																																																																	
Pigment Type	Titanium Dioxide																																																																	
Volume Solids	32.1 ± 1.0%																																																																	
Coverage per 3.79 L at Recommended Film Thickness	27.8 – 37.1 sq. m. (300 – 400 sq. ft.)																																																																	
Recommended Film Thickness	– Wet	4.0 – 5.3 mils																																																																
	– Dry	1.3 – 1.7 mils																																																																
Depending on surface texture and porosity. Be sure to estimate the right amount of paint for the job. This will ensure colours uniformity and minimize the disposal of excess paint.																																																																		
Dry Time @ 25 °C (77 °F) @ 50% RH	– Tack Free	30 Minutes																																																																
	– To Recoat	4 Hours																																																																
High humidity and cool temperatures will result in longer dry, recoat and service times.																																																																		
Dries By	Coalescence																																																																	
Viscosity	105 – 110 KU																																																																	
Flash Point	93.2 °C (200 °F) or greater (TT-P-141, Method 4293)																																																																	
Gloss / Sheen	Flat (1 – 2 @ 85°)																																																																	
Surface Temperature at Application	– Min.	10 °C (50 °F)																																																																
	– Max.	32.2 °C (90 °F)																																																																
Thin With	Clean Water																																																																	
Clean Up Thinner	Warm, Soapy Water																																																																	
Weight Per 3.79 L	5.3 kg (11.6 lbs.)																																																																	
Storage Temperature	– Min.	4.4 °C (40 °F)																																																																
	– Max.	35 °C (95 °F)																																																																
Volatile Organic Compounds (VOC)																																																																		
47.4 Grams/Litre																																																																		

◇ Reported values are for White. Contact dealer for values of other bases or colours.

Super Kote 5000 Acrylic Latex Flat 28 Line

Surface Preparation

Surfaces to be painted must be clean, dry, and free of dirt, dust, grease, oil, soap, wax, scaling paint, water soluble materials and mildew. Remove any peeling or scaling paint, and sand these areas to feather edges smooth with adjacent surfaces. Glossy areas should be dulled. Drywall surfaces must be free of sanding dust. Spot prime before and after filling nail holes, cracks, and other surface imperfections.

New plaster or masonry surfaces must be allowed to cure (30 days) before applying base coat. Cured plaster should be hard, have a slight sheen and maximum pH of 10; soft, porous or powdery plaster indicates improper cure.

Primers: New surfaces should be fully primed. Previously painted surfaces should be primed or spot primed as necessary. There are a number of specialty primers available in our family of brands that can be used on difficult substrates such as bleeding woods, hard glossy surfaces, or other substrates where paint adhesion or stain blocking is a problem. Your dealer can recommend the right problem solving primer necessary to meet your needs.

WARNING! If you scrape, sand, or remove old paint, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by logging onto Health Canada @ <https://www.canada.ca/en/health-canada/services/environmental-workplace-health/environmental-contaminants/lead/lead-information-package-some-commonly-asked-questions-about-lead-human-health.html>

Application

Stir thoroughly. Apply by brush (synthetic filament), roller or spray. Length of roller nap depends upon the texture of the surface. Thinning is not usually required for brush or roller application. Apply a full, even coat. Do not apply directly over chalky surfaces or bleeding stains. Apply only when surface and air temperatures are above 10 °C (50 °F).

Spray, Airless: Fluid Pressure—1,500 to 2,000 PSI;
Tip—.017 - .021 Orifice

Clean up

Clean up with warm, soapy water.

Environmental Health & Safety Information

Use only in a well ventilated area. Keep container closed when not in use. In case of spillage, absorb with inert material and dispose of in accordance with local regulations. Wash thoroughly after handling.

WARNING: This product contains isothiazolinone compounds at levels of <0.1%. These substances are biocides commonly found in most paints and a variety of personal care products as a preservative. Certain individuals may be sensitive or allergic to these substances, even at low levels.

**KEEP OUT OF REACH OF CHILDREN
PROTECT FROM FREEZING**

**Refer to Safety Data Sheet for
additional health and safety information.**