



# SUPER KOTE™ 3000 LATEX ENAMEL FLAT 72 LINE

## Features

- Latex Flat Paint
- Low Odour
- Fast Drying
- Excellent Touch Up
- Hides Imperfections

## Recommended For

Professional grade paint for commercial and residential use on drywall, plaster, wood and masonry. Provides excellent touch up and hides imperfections in new construction and repaint work.

## General Description

Super Kote™ 3000 Latex Flat is designed to provide good dry hide appearance when applied to properly prepared interior surfaces. It resists spattering and exhibits good touch-up characteristics. The flat sheen hides surface imperfections. This product is an excellent choice for new construction as well as remedial work.

## Limitations

- Apply only when surface and air temperatures are above 10 °C (50 °F).
- Not for use in high abuse areas.

## Product Information

Colours — Standard:	Technical Data◇	White
White	Vehicle Type	Vinyl Acrylic
	Pigment Type	Titanium Dioxide
	Volume Solids	28.3 ± 1.0%
	Coverage per 3.79 L at	32.5 – 41.8 sq. m.
	Recommended Film Thickness	(350 – 450 sq. ft.)
	Recommended Film Thickness	– Wet 3.6 to 4.6 mils
		– Dry 1.0 to 1.3 mils
	Depending on surface texture and porosity. Be sure to estimate the right amount of paint for the job. This will ensure colour uniformity and minimize the disposal of excess paint.	
	Dry Time @ 25 °C	– Tack Free 30 Minutes
	(77 °F) @ 50% RH	– To Recoat 4 Hours
	High humidity and cool temperatures will result in longer dry, recoat and service times.	
	Dries By	Coalescence
	Viscosity	108 – 113 KU
	Flash Point	93.2 °C (200 °F) or greater (TT-P-141, Method 4293)
	Gloss / Sheen	Flat 0 - 3 units @ 29.4 °C (85 °F)
	Surface Temperature at Application	– Min. 10 °C (50 °F)
		– Max. 32.2 °C (90 °F)
	Thin With	Clean Water
	Clean Up Thinner	Warm, Soapy Water
	Weight Per 3.79 L	4.9 kg (10.9 lbs.)
	Storage Temperature	– Min. 4.4 °C (40 °F)
		– Max. 35 °C (95 °F)
	<b>Volatile Organic Compounds (VOC)</b>	
	44 Grams/Litre	0.17 kg (0.37 Lbs.)/3,79 L
<b>Colours — Standard:</b>		
White		
<b>— Tint Bases:</b>		
72-32, Pastel Base		
72-33, Tint Base		
<b>— Special Colours:</b>		
Contact your dealer.		
<b>Certification:</b>		
The products supported by this data sheet contain a maximum of 50 grams per litre VOC/VOS (0.41 lbs/gal.) excluding water & exempt solvents.		
This product is compliant as a Flat Coating.		
This product meets the qualifications for LEED (Leadership in Energy and Environmental Design) projects as a flat coating.		
<b>Technical Assistance:</b>		
Available through your local authorized independent dealer. For the location of the dealer nearest you, call 1-800-225-5554 or visit <a href="http://www.coronadopaint.ca">www.coronadopaint.ca</a> .		

◇ Reported values are for White. Contact dealer for values of other bases or colours.

## Super Kote™ 3000 Latex Enamel Flat 72 Line

### Surface Preparation

Surfaces to be painted must be clean, dry, and free of dirt, dust, grease, oil, soap, wax, peeling or flaking paint, water soluble materials and mildew. Remove any peeling or flaking paint, and sand these areas to feather edges smooth with adjacent surfaces. Glossy areas should be dulled. Drywall surfaces must be free of sanding dust. Spot prime before and after filling nail holes, cracks, and other surface imperfections.

New plaster or masonry surfaces must be allowed to cure (30 days) before applying base coat. Cured plaster should be hard, have a slight sheen and maximum pH of 10; soft, porous or powdery plaster indicates improper cure.

**Primers:** New surfaces should be fully primed. Previously painted surfaces should be primed or spot primed as necessary. There are a number of specialty primers available in our family of brands that can be used on difficult substrates such as bleeding woods, hard glossy surfaces, or other substrates where paint adhesion or stain blocking is a problem. Your dealer can recommend the right problem solving primer necessary to meet your needs.

**WARNING!** If you scrape, sand, or remove old paint, you may release lead dust. **LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE.** Wear a NIOSH approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by logging onto Health Canada @ [http://www.hc-sc.gc.ca/ewh-semt/contaminants/lead-plomb/asked\\_questions-questions\\_posees-eng.php](http://www.hc-sc.gc.ca/ewh-semt/contaminants/lead-plomb/asked_questions-questions_posees-eng.php)

### Application

Stir product thoroughly with a circular, lifting motion ensuring even mixing throughout.

**Roller** – 9.5 mm to 31.8 mm (3/8" to 1 1/4") nap, depending on surface texture

**Brush** – Nylon or polyester filament

**Airless Spray** – Tip size and atomization pressure will vary with type of equipment, viscosity and temperature. A tip size of .017 – .021 will provide the most satisfactory spray pattern. If necessary product may be thinned up to 15% with clean water for spray application.

### Clean Up

Clean up with warm, soapy water.

### Environmental Health & Safety Information

**Use only in a well ventilated area.** Keep container closed when not in use. In case of spillage, absorb with inert material and dispose of in accordance with local regulations. Wash thoroughly after handling.

**KEEP OUT OF REACH OF CHILDREN  
PROTECT FROM FREEZING**

**Refer to Safety Data Sheet for  
additional health and safety information.**