



SUPER KOTE™ 3000

LATEX ENAMEL SEMI-GLOSS

74 LINE

Features

- Latex Semi-Gloss Paint
- Washable
- Low Odor
- Semi-Gloss Sheen
- Fast Drying
- Water Clean Up

General Description

A professional grade Vinyl Acrylic Semi-Gloss Enamel that exhibits good washing characteristics. May be applied on walls and trim in kitchens, hallways, bathrooms, or other areas where routine maintenance is required. This product dries quickly, resists spattering and has low odor during application.

Recommended For

Professional grade paint for commercial and residential use on drywall, plaster, wood, metal and masonry. Provides excellent touch up and hides imperfections in new construction and repaint work.

Limitations

- Apply only when surface and air temperatures are above 50°F (10 °C).

Product Information																																																																									
<p>Colors — Standard:</p> <p>White</p> <p>— Tint Bases:</p> <p>74-32, Pastel Base 74-33, Tint Base</p> <p>— Special Colors:</p> <p>Contact your dealer.</p> <p>Certification:</p> <p>The products supported by this data sheet contain a maximum of 100 grams per liter VOC/VOS (0.83 lbs/gal.) excluding water & exempt solvents.</p> <p>This product is compliant under the Ozone Transport Commission regulations as a Non-Flat Coating.</p> <p>This product is currently approved for use under MPI #54</p> <p>This product meets the qualifications for LEED (Leadership in Energy and Environmental Design) projects as a non-flat coating.</p> <p>Technical Assistance:</p> <p>Available through your local authorized independent dealer. For the location of the dealer nearest you, call 1-800-225-5554 or visit www.coronadopaint.com.</p>	<table border="1"> <thead> <tr> <th colspan="2">Technical Data◇</th> <th>White</th> </tr> </thead> <tbody> <tr> <td>Vehicle Type</td> <td></td> <td>Vinyl Acrylic</td> </tr> <tr> <td>Pigment Type</td> <td></td> <td>Titanium Dioxide</td> </tr> <tr> <td>Volume Solids</td> <td></td> <td>31.0 ± 1.0%</td> </tr> <tr> <td>Coverage per Gallon at Recommended Film Thickness</td> <td></td> <td>300 – 400 Sq. Ft.</td> </tr> <tr> <td>Recommended Film Thickness</td> <td>– Wet</td> <td>4.0 to 5.3 mils</td> </tr> <tr> <td></td> <td>– Dry</td> <td>1.3 to 1.7 mils</td> </tr> <tr> <td colspan="3">Depending on surface texture and porosity. Be sure to estimate the right amount of paint for the job. This will ensure color uniformity and minimize the disposal of excess paint.</td> </tr> <tr> <td>Dry Time @ 77°F (25°C) @ 50% RH</td> <td>– Tack Free</td> <td>30 Minutes</td> </tr> <tr> <td></td> <td>– To Recoat</td> <td>4 Hours</td> </tr> <tr> <td colspan="3">High humidity and cool temperatures will result in longer dry, recoat and service times.</td> </tr> <tr> <td>Dries By</td> <td></td> <td>Coalescence</td> </tr> <tr> <td>Viscosity</td> <td></td> <td>90 – 95 KU</td> </tr> <tr> <td>Flash Point</td> <td></td> <td>N/A</td> </tr> <tr> <td>Gloss / Sheen</td> <td></td> <td>Semi-Gloss 45 - 55 units @60°</td> </tr> <tr> <td>Surface Temperature at Application</td> <td>– Min.</td> <td>50°F</td> </tr> <tr> <td></td> <td>– Max.</td> <td>90°F</td> </tr> <tr> <td>Thin With</td> <td></td> <td>Clean Water</td> </tr> <tr> <td>Clean Up Thinner</td> <td></td> <td>Warm Soapy Water</td> </tr> <tr> <td>Weight Per Gallon</td> <td></td> <td>10.2 lbs.</td> </tr> <tr> <td>Storage Temperature</td> <td>– Min.</td> <td>40°F</td> </tr> <tr> <td></td> <td>– Max.</td> <td>95°F</td> </tr> <tr> <td colspan="3">Volatile Organic Compounds (VOC)</td> </tr> <tr> <td></td> <td>98 Grams/Liter</td> <td>0.82 Lbs./Gallon</td> </tr> </tbody> </table>	Technical Data◇		White	Vehicle Type		Vinyl Acrylic	Pigment Type		Titanium Dioxide	Volume Solids		31.0 ± 1.0%	Coverage per Gallon at Recommended Film Thickness		300 – 400 Sq. Ft.	Recommended Film Thickness	– Wet	4.0 to 5.3 mils		– Dry	1.3 to 1.7 mils	Depending on surface texture and porosity. Be sure to estimate the right amount of paint for the job. This will ensure color uniformity and minimize the disposal of excess paint.			Dry Time @ 77°F (25°C) @ 50% RH	– Tack Free	30 Minutes		– To Recoat	4 Hours	High humidity and cool temperatures will result in longer dry, recoat and service times.			Dries By		Coalescence	Viscosity		90 – 95 KU	Flash Point		N/A	Gloss / Sheen		Semi-Gloss 45 - 55 units @60°	Surface Temperature at Application	– Min.	50°F		– Max.	90°F	Thin With		Clean Water	Clean Up Thinner		Warm Soapy Water	Weight Per Gallon		10.2 lbs.	Storage Temperature	– Min.	40°F		– Max.	95°F	Volatile Organic Compounds (VOC)				98 Grams/Liter	0.82 Lbs./Gallon
Technical Data◇		White																																																																							
Vehicle Type		Vinyl Acrylic																																																																							
Pigment Type		Titanium Dioxide																																																																							
Volume Solids		31.0 ± 1.0%																																																																							
Coverage per Gallon at Recommended Film Thickness		300 – 400 Sq. Ft.																																																																							
Recommended Film Thickness	– Wet	4.0 to 5.3 mils																																																																							
	– Dry	1.3 to 1.7 mils																																																																							
Depending on surface texture and porosity. Be sure to estimate the right amount of paint for the job. This will ensure color uniformity and minimize the disposal of excess paint.																																																																									
Dry Time @ 77°F (25°C) @ 50% RH	– Tack Free	30 Minutes																																																																							
	– To Recoat	4 Hours																																																																							
High humidity and cool temperatures will result in longer dry, recoat and service times.																																																																									
Dries By		Coalescence																																																																							
Viscosity		90 – 95 KU																																																																							
Flash Point		N/A																																																																							
Gloss / Sheen		Semi-Gloss 45 - 55 units @60°																																																																							
Surface Temperature at Application	– Min.	50°F																																																																							
	– Max.	90°F																																																																							
Thin With		Clean Water																																																																							
Clean Up Thinner		Warm Soapy Water																																																																							
Weight Per Gallon		10.2 lbs.																																																																							
Storage Temperature	– Min.	40°F																																																																							
	– Max.	95°F																																																																							
Volatile Organic Compounds (VOC)																																																																									
	98 Grams/Liter	0.82 Lbs./Gallon																																																																							

◇ Reported values are for White. Contact dealer for values of other bases or colors.

Surface Preparation

Surfaces to be painted must be clean, dry, and free of dirt, dust, grease, oil, soap, wax, peeling or flaking paint, water soluble materials and mildew. Remove any peeling or flaking paint, and sand these areas to feather edges smooth with adjacent surfaces. Glossy areas should be dulled. Drywall surfaces must be free of sanding dust. Spot prime before and after filling nail holes, cracks, and other surface imperfections.

New plaster or masonry surfaces must be allowed to cure (30 days) before applying base coat. Cured plaster should be hard, have a slight sheen and maximum pH of 10; soft, porous or powdery plaster indicates improper cure.

Primers: New surfaces should be fully primed. Previously painted surfaces should be primed or spot primed as necessary. There are a number of specialty primers available in our family of brands that can be used on difficult substrates such as bleeding woods, hard glossy surfaces, or other substrates where paint adhesion or stain blocking is a problem. Your dealer can recommend the right problem solving primer necessary to meet your needs.

WARNING! If you scrape, sand or remove old paint, you may release lead dust. **LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH-approved respirator to control lead exposure. Carefully clean up with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead.**

Application

Stir product thoroughly with a circular, lifting motion ensuring even mixing throughout.

Roller – 3/8" to 1 ¼ " nap, depending on surface texture

Brush – Nylon or polyester filament

Airless Spray – Tip size and atomization pressure will vary with type of equipment, viscosity and temperature. A tip size of .017 – .021 will provide the most satisfactory spray pattern. If necessary product may be thinned up to 15% with clean water for spray application.

Clean Up

Clean up with warm, soapy water.

USE COMPLETELY OR DISPOSE OF PROPERLY. Dry, empty containers may be recycled in a can recycling program. **Local disposal requirements vary; consult your sanitation department or state-designated environmental agency on disposal options.**

Environmental Health & Safety Information

Use only with adequate ventilation. Do not breathe spray mist or sanding dust. Ensure fresh air entry during application and drying. Avoid contact with eyes and prolonged or repeated contact with skin. Avoid exposure to dust and spray mist by wearing a NIOSH approved respirator during application, sanding and clean up. Follow respirator manufacturer's directions for respirator use. Close container after each use. Wash thoroughly after handling.

WARNING: This product contains a chemical known to the state of California to cause cancer and birth defects, or other reproductive harm.

FIRST AID: In case of eye contact, flush immediately with plenty of water for at least 15 minutes; for skin, wash thoroughly with soap and water. If symptoms persist, seek medical attention. If you experience difficulty breathing, leave the area to obtain fresh air. If continued difficulty is experienced, get medical attention immediately.

IN CASE OF SPILL – Absorb with inert material and dispose of as specified under "Clean Up".

**KEEP OUT OF REACH OF CHILDREN
PROTECT FROM FREEZING**

**Refer to Safety Data Sheet for
additional health and safety information.**